MIL-C-915/20D
5 April 1973
SUPERSEDING
MIL-C-915/20C
1 August 1972

MILITARY SPECIFICATION SHEET

CABLE, ELECTRICAL, 600 VOLTS, TYPE TRF

This specification sheet is approved for use by all Departments and Agencies of the Department of Defense.

The complete requirements for procuring the cable described herein shall consist of this document and the latest issue of Specification MIL-C-915.

REQUIREMENTS:

Qualification not required.

Construction

First - Copper conductor, uncoated, (see Details for size).
Second - Separator.
Third - Synthetic rubber insulation (see Details for wall thickness) with or without a tape, at the manufacturer's option.
Fourth - Reinforcement.
Fifth - Polychloroprene jacket bonded to the underlying insulation.

Details

Type and size	Conductor size Navy standard	Insulation thickness nominal (inch)	Conductor resistance per 1000 ft. maximum (ohms)	Overall diameter maximum (inch)
TRF-105	105(259)	0.075	0.108	0.76
TRF-133	133(259)	.075	.0856	.81
TRF-168	168(427)	.075	.0681	.86

EXAMINATION AND TESTS

	Requirements:
Basic electrical:	
(D) Conductor resistance - Ohms/1000 ft. at 25°C., maximum	(See Details)
Voltage withstand - Conductor to ground, volts, rms, minimum . . .	1200
Group A:	
Visual and dimensional	
Group B:	
Cold bending, cable - At minus 30° + 2°C., two turns around mandrel with diameter twice that of specimen.	No damage
Physical (unaged)	
Insulation (conductor)	
Tensile strength - psi, minimum	600
Elongation - Percent, minimum	225
Jacket (cable)	
Tensile strength - psi, minimum	1800
Elongation - Percent, minimum.	300
Set - Inch, maximum	3/8

(D) Denotes changes

FSC 6145

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:07Z
Check the source to verify that this is the current version before use.

	Requirements:
Group C:	
Flammability - Inches, maximum	2
Physicals (aged)	
Insulation (conductor)	
Air pressure heat	
Tensile strength - Percent of unaged, minimum	50
Elongation - Percent of unaged, minimum	50
Jacket (cable)	
Air pressure heat	
Tensile strength - Percent of unaged, minimum	60
Elongation - Percent of unaged, minimum	60
Hot oil immersion	
Tensile strength - Percent of unaged, minimum	50
Elongation - Percent of unaged, minimum	50

UNIT ORDERING LENGTHS:
All sizes 1000 feet (Nominal)

Custodians:
Army - MI
Navy - SH
Air Force - 80
Review activities:
Army - EL, MI, AV
Navy - EC
Air Force - 80
User activities:
Army - ME, MU, WC
Navy - CG

Preparing activity:
Navy - SH
(Project 6145-0648-21)

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:07Z
Check the source to verify that this is the current version before use.