MILITARY SPECIFICATION SHEET

CABLE, ELECTRICAL, 600 VOLTS, TYPE TRF

This specification sheet is approved for use by all Departments and Agencies of the Department of Defense.

The complete requirements for acquiring the cable described herein shall consist of this document and the latest issue of MIL-C-915.

REQUIREMENTS:

Qualification not required.

Construction (non-watertight)

First - Copper conductor, class H stranding, uncoated, (see table I for size).
Second - Separator.
Third - Synthetic rubber insulation (see table I for wall thickness) with or without a tape, at the manufacturer's option.
Fourth - Reinforcement.
Fifth - Polychloroprene jacket bonded to the underlying insulation.

TABLE I. Details.

| Type and size | Conductor size AWG | Insulation thickness nominal (inch) | Conductor resistance per 1000 feet maximum (ohms) | Overall diameter maximum (inch) |
|---|---|---|---|---|
| TRF-105 | 0(class H) | 0.075 | 0.107 | 0.76 |
| TRF-133 | 00(class H) | .075 | .0847 | .81 |
| TRF-168 | 000(class H) | .075 | .0675 | .86 |

FSC 6145

DISTRIBUTION STATEMENT A Approved for public release; distribution unlimited



Source: https://assist.dla.mil -- Downloaded: 202610-16T12:07Z
Check the source to verify that this is the current version before use.

EXAMINATION AND TESTS:

| | Requirements |
|---|---|
| **Basic electrical:** | |
| Conductor resistance - ohms/1000 feet at 25°C, maximum.. | (see table I) |
| Voltage withstand - conductor to water, volts, root mean square, minimum..... | 1200 |
| Insulation resistance - megohms/1000 feet, minimum | |
| Conductor to water..... | 100 |
| **Group A:** | |
| Visual and dimensional..... | No failure |
| **Group B:** | |
| Cold bending, cable - at minus 30 ± 2°C, two turns around mandrel with diameter twice that of specimen.... | No damage |
| Physicals (unaged) | |
| Insulation (conductor) | |
| Tensile strength - $lbf/in^2$, minimum..... | 600 |
| Elongation - percent, minimum..... | 125 |
| Jacket (cable) | |
| Tensile strength - $lbf/in^2$, minimum..... | 1800 |
| Elongation - percent, minimum..... | 300 |
| Set - inch, maximum..... | 3/8 |
| **Group C:** | |
| Flammability - inches, maximum..... | 2 |
| Physicals (aged) | |
| Insulation (conductor) | |
| Air pressure heat | |
| Tensile strength - percent of unaged, minimum..... | 50 |
| Elongation - percent of unaged, minimum.. | 50 |
| Jacket (cable) | |
| Air pressure heat | |
| Tensile strength - percent of unaged, minimum..... | 60 |
| Elongation - percent of unaged, minimum.. | 60 |
| Hot oil immersion | |
| Tensile strength - percent of unaged..... | 50 |
| Elongation - percent of unaged, minimum.. | 50 |



Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:07Z
Check the source to verify that this is the current version before use.

UNIT ORDERING LENGTHS:
All sizes 1000 feet (nominal).

Revision letters are not used to denote changes due to the extensiveness of the changes.

Custodians:
Army - MI
Navy - SH
Air Force - 85

Review activities:
Army - CR, ER
Navy - EC
Air Force - 99
DLA - IS

User activities:
Army - AL, AR, ME
Navy - CG

Preparing activity:
Navy - SH
(Project 6145-0885-18)



Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:07Z
Check the source to verify that this is the current version before use.