INCH POUND

MIL-C-915/20F
29 September 1989
SUPERSEDING
MIL-C-915/20E
18 June 1985

MILITARY SPECIFICATION SHEET

WIRE, ELECTRICAL, 600 VOLTS, FOR WELDING ELECTRIC CIRCUIT USE ONLY, TYPE TRF

This specification sheet is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specification sheet and the issue of the following specification listed in that issue of the Department of Defense Index of Specifications and Standards (DoDISS) specified in the solicitation: MIL-C-915.

REQUIREMENTS:

Qualification not required.

Construction (non-watertight)

First - Copper conductor, class H stranding, uncoated, (see table I for size).
Second - Separator.
Third - Synthetic rubber insulation (see table I for wall thickness) with or without a tape, at the manufacturer's option.
Fourth - Reinforcement.
Fifth - Polychloroprene jacket bonded to the underlying insulation.

AMSC N/A FSC 6145
DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 202610-16T12:07Z
Check the source to verify that this is the current version before use.

TABLE I. Details.

Type and size	Conductor size AWG	Insulation thickness nominal (inch)	Conductor resistance per 1000 feet maximum (ohms)	Overall diameter maximum (inch)
TRF-105	0(class H)	0.075	0.107	0.76
TRF-133	00(class H)	.075	.0847	.81
TRF-168	000(class H)	.075	.0675	.86

EXAMINATION AND TESTS:

	Requirements
Basic electrical:	
Conductor resistance - ohms/1000 feet at 25°C, maximum.	(see table I)
Voltage withstand - conductor to water, volts, root mean square, minimum.....	1200
Insulation resistance - megohms/1000 feet, minimum Conductor to water.....	100
Group A:	
Visual and dimensional.....	No failure
Group B:	
Cold bending, cable - at minus 30 ± 2°C, two turns around mandrel with diameter twice that of specimen...	No damage
Physicals (unaged)	
Insulation (conductor)	
Tensile strength - lbf/in², minimum.....	600
Elongation - percent, minimum.....	125
Jacket (cable)	
Tensile strength - lbf/in², minimum.....	1800
Elongation - percent, minimum.....	300
Set - inch, maximum.....	3/8
Group C:	
Flammability - inches, maximum.....	2
Physicals (aged)	
Insulation (conductor)	
Air pressure heat	
Tensile strength - percent of unaged, minimum.....	50
Elongation - percent of unaged, minimum.	50

Source: https://assist.dla.mil -- Downloaded: 20260-16T12:07Z
Check the source to verify that this is the current version before use.

EXAMINATION AND TESTS - Continued

	Requirements
Jacket (cable)	
Air pressure heat	
Tensile strength - percent of unaged, minimum	60
Elongation - percent of unaged, minimum	60
Hot oil immersion	
Tensile strength - percent of unaged	50
Elongation - percent of unaged, minimum	50

UNIT ORDERING LENGTHS:

All sizes 1000 feet (nominal).

NOTE: Not for Air Force use.

Revision letters are not used to denote changes due to the extensiveness of the changes.

Custodians:
Army - MI
Navy - SH

Review activities:
Army - CR, ER
Navy - EC
DLA - IS

User activities:
Army - AL, AR, ME
Navy - CG

Preparing activity:
Navy - SH
(Project 6145-1127-08)

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:07Z
Check the source to verify that this is the current version before use.