INCH POUND

MIL-C-915/21F
29 September 1989
SUPERSEDING
MIL-C-915/21E
18 June 1985

MILITARY SPECIFICATION SHEET

WIRE, ELECTRICAL, 125 VOLTS FOR WELDING ELECTRODE CIRCUIT USE ONLY, TYPE TRXF

This specification sheet is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this secification sheet and the issue of the following specification listed in that issue of the Department of Defense Index of Specifications and Standards (DoDISS) specified in the solicitation: MIL-C-915.

REQUIREMENTS:

Qualification not required.

Construction (non-watertight)

First - Copper conductor, uncoated, class M stranding (see table I for size).
Second - Separator.
Fifth - Polychloroprene jacket (see table I for dimensions).

TABLE I. Details.

Type and size	Conductor size AWG	Overall diameter maximum (inch)	Conductor resistance per 1000 feet maximum (ohms)
TRXF-84	1(class M)	0.60	0.137
TRXF-105	0(class M)	.68	.108
TRXF-133	00(class M)	.75	.0867

AMSC N/A FSC 6145

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:08Z
Check the source to verify that this is the current version before use.

EXAMINATION AND TESTS:

	Requirements
Basic electrical:	
Conductor resistance - ohms/1000 feet at 25°C, maximum	(see table I)
Voltage withstand - conductor to ground, volts, root mean square, minimum	1200
Insulation resistance - megohms/1000 feet, minimum	
Conductor to water	5
Group A:	
Visual and dimensional	No failure
Group B:	
Cold bending, cable - at minus 30 ± 2°C, two turns around mandrel with diameter twice that of specimen	No damage
Physicals (unaged)	
Jacket (cable)	
Tensile strength - lbf/in², minimum	1800
Elongation - percent, minimum	300
Set - inch, maximum	3/8
Group C:	
Flammability - inches, maximum	2
Physicals (aged)	
Jacket (cable)	
Air pressure heat	
Tensile strength - percent of unaged, minimum	50
Elongation - percent of unaged, minimum	50
Hot oil immersion	
Tensile strength - percent of unaged, minimum	60
Elongation - percent of unaged, minimum	60

UNIT ORDERING LENGTH:

All sizes 1000 feet (nominal).

NOTE: Not for Air Force use.

Source: https://assist.dla.mil -- Downloaded: 202610-16T12:08Z
Check the source to verify that this is the current version before use.

Revision letters are not used to denote changes due to the extensiveness of the changes.

Custodians:
Army - MI
Navy - SH

Preparing activity:
Navy - SH
(Project 6145-1127-09)

Review activities:
Army - CR, ER
Navy - EC
DLA - IS

User activities:
Army - AL, AR, ME
Navy - CG

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:08Z
Check the source to verify that this is the current version before use.