MIL-C-915/24B
1 August 1972
SUPERSEDING
MIL-C-00915/24A(SHIPS)
20 March 1972
MIL-C-915/24
15 March 1968

MILITARY SPECIFICATION SHEET

CABLE, ELECTRICAL, 300 VOLTS, TYPE TTOP

(B) This specification is approved for use by all Departments and Agencies of the Department of Defense.

The complete requirements for procuring the cable described herein shall consist of this document and the latest issue of Specification MIL-C-915.

REQUIREMENTS:

Qualification required

Construction

(B) (B)

First - Copper conductor, Navy Standard size 1(10), uncoated (see note 1).
Second - Polyvinyl chloride insulation (80°C.). Nominal wall thickness 0.020 inch. Telephone Identification Code, applied by Method 3.
Third - Two conductors shall be cabled together to form pairs, with a lay suitable to meet test requirements specified herein.
Fourth - The specified number of pairs (see Details) shall be cabled together in one or more layers, all in a left-hand direction. The length of lay shall be determined to permit the completed cable to meet the twisting and bending endurance tests. Fibrous fillers as necessary to form a round cable. Cabling sequence shall be consecutive, starting with pair No. 1, from center outward. A single pair shall not be used as a central core for the cable.
Fifth - Binder tape applied helically with overlap.
Sixth - Standard thermoplastic jacket (Gray) (see Details for thickness). Cable surface marking required.

(B) Note 1: At the manufacturer's option, conductors may consist of eight strands, each having a nominal diameter of 0.010-inch, around one strand having a nominal diameter of 0.0142-inch.

Details

Type and size	Number of pairs	Cable Jacket thickness nominal (inch)	Overall diameter maximum (inch)
TTOP-3	3	0.060	0.480
TTOP-5	5	.060	.590
TTOP-10	10	.060	.700
TTOP-15	15	.060	.830

EXAMINATION AND TESTS

	Requirements:
Basic electrical:	
Conductor resistance - Ohms/1000 ft. at 25°C., maximum	11.44
Voltage withstand - Volts, rms, minimum	
Conductor to conductor	2000
Insulation resistance - Megohms/1000 ft., minimum	100

(B) Denotes changes

FSC 6145

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:08Z
Check the source to verify that this is the current version before use.

	Requirements:
Group A:	
Visual and dimensional	
Group B:	
Physicals (unaged)	
Insulation (conductor)	
Tensile strength - psi, minimum	1800
Elongation - Percent, minimum	125
Jacket (cable)	
Tensile strength - psi, minimum	1800
Elongation - Percent, minimum	225
(B) Twisting and bending endurance - Note 2	
At 75° ± 2°C., cycles, minimum	6000
At minus 30° ± 2°C., cycles, minimum	2000

Note 2: Roller diameters for bending endurance test shall be as follows:

Cable type and size	Roller diameter (inches, maximum)
TTOP-3	1.4
TTOP-5	1.8
TTOP-10	2.1
TTOP-15	3.0

Group C:	
Flammability - inches, maximum	2
Physicals (aged)	
Insulation (conductor)	
Air oven	
Elongation - Percent of unaged, minimum	80
Jacket (cable)	
Hot oil immersion	
Tensile strength - psi, minimum.	1400
Elongation - Percent, minimum.	50
Permanence of printing (jacket) - Cycles, minimum.	250

QUALIFICATION INSPECTION

Qualification inspection shall include basic electrical, plus all of Groups A, B, and C.

UNIT ORDERING LENGTHS:

Size	Feet (Nominal)
3, 5, and 10	2500
15	1500

(B) Custodians:
Army - MI
Navy - SH
Air Force - 80

(B) Review activities:
Army - EL, MI, AV
Navy - EC
Air Force - 80

(B) User activities:
Army - ME, MU, WC
Navy - CG

Preparing activity:
Navy - SH
(Project 6145-0609-18)

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:08Z
Check the source to verify that this is the current version before use.