MIL-C-915/40D
18 February 1974
SUPERSEDING 1/
MIL-C-915/40C
20 August 1973

MILITARY SPECIFICATION SHEET

CABLE, ELECTRICAL, 600 VOLTS, TYPES DPS, FPS, TPS AND 7PS

This specification sheet is approved for use by all Departments and Agencies of the Department of Defense.

The complete requirements for procuring the cable described herein shall consist of this document and the latest issue of Specification MIL-C-915.

REQUIREMENTS:

Qualification required.

(D) Construction (Watertight)

First - Copper conductor, nickel coated (see Details for size).
Second - Extruded silicone rubber insulation (see Details for dimensions).
Third - Glass braid (see details for dimensions) Standard Identification Code, applied by Method 4.
(D) Fourth - The specified number of conductors (see details) cabled together with a lay not greater than 18 times the pitch diameter. Either non-fibrous or a combination of non-fibrous and asbestos fillers shall be used to form a firm, round assembly. (Non-fibrous filler shall be silicone).
Fifth - Binder tape, applied helically with overlap.
Sixth - Silicone rubber jacket. (see Details for thickness).
Seventh - Braided metal armor.
Eighth - Paint.

Details

Cable type and size	Conductors				Cable Jacket thick. min. (inch)	Overall dia. max. (inch)	Cold bending mandrel dia. maximum (inches)	Condr. res. per 1000 ft. at 25°C. max. (ohms)
	No.	Size Navy Stand.	Dia. over insul. min. (inch)	Dia. over braid max. (inch)				
DPS-3	2	3(7)	0.100	0.125	0.030	0.455	6.0	4.92
DPS-4	2	4(7)	.116	.141	.030	.489	6.0	3.09
DPS-6	2	6(7)	.143	.170	.040	.585	7.5	2.14
DPS-9	2	9(7)	.158	.185	.040	.628	7.5	1.55
DPS-14	2	14(7)	.200	.230	.050	.730	8.0	0.968
TPS-3	3	3(7)	.100	.125	.030	.475	6.5	4.92
TPS-4	3	4(7)	.116	.141	.040	.553	7.0	3.09
TPS-6	3	6(7)	.143	.170	.040	.620	7.5	2.14
TPS-9	3	9(7)	.158	.185	.040	.657	7.5	1.55
TPS-14	3	14(7)	.200	.230	.050	.751	9.5	0.968
TPS-23	3	23(7)	.257	.291	.050	.866	10.5	.587
TPS-30	3	30(19)	.304	.342	.060	.976	12.0	.433
FPS-14	4	14(7)	.200	.230	.050	.815	10.0	.968
7PS-6	7	6(7)	.143	.170	.050	.775	9.5	2.14

1/ Requirements formerly covered on MIL-C-23206/3.

(D) Denotes changes.

FSC 6145

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:10Z
Check the source to verify that this is the current version before use.

EXAMINATION AND TESTS:

Basic electrical:

	Requirements:
Conductor resistance - Ohms/1000 ft. at 25°C., max.	(See details)
Voltage withstand - Volts, rms, minimum	3000
Insulation resistance - Megohms/1000 ft., minimum	500

Group A:
Visual and dimensional
(D) Watertightness (see MIL-C-915, table of limits for water leakage)

Group B:

Cold bending, cable - (See details for mandrel diameter)	No damage
Gas flame, 1 hour at 230/130 volts, rms	No failure
Physicals (unaged)	
Insulation	
Tensile strength - psi, minimum	750
Elongation - Percent, minimum	125
Jacket	
Tensile strength - psi, minimum	800
Elongation - Percent, minimum	250
Durometer (Type A) hardness, minimum (on specimen of jacket) (ASTM-D 2240)	60

Group C:

Physicals - Cable aging (260° ± 10°C.)	
Jacket	
Tensile strength - psi, minimum	600
Elongation - Percent, minimum	150

QUALIFICATION INSPECTION:
Qualification inspection shall include basic electrical plus all of Groups A, B and C plus the following:

Cold working (minus 20° ± 2°C.)	No damage
Gas flame (3 hours) at 230/130 volts, rms	No failure
Armor	Conformance to material, construction, coverage
Specific gravity of extruded silicone insulation, maximum	1.55
(D) Cable aging and compatibility (125° ± 5°C.)	

UNIT ORDERING LENGTHS:
All types and sizes. . . . . 100 feet, minimum.

Custodians:
Army - MI
Navy - SH
Air Force - 80

Review activities:
Army - EL, MI, AV
Navy - EC
Air Force - 80

User activities:
Army - ME, MU, WC
Navy - CG

Preparing activity:
Navy - SH
(Project 6145-0661-72)

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:10Z
Check the source to verify that this is the current version before use.