MIL-C-915/43B
6 May 1974
SUPERSEDING 1/
MIL-C-915/43A
1 August 1972

MILITARY SPECIFICATION SHEET

CABLE, ELECTRICAL, 300 VOLTS, TYPE MU

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The complete requirements for procuring the cable described herein shall consist of this document and the latest issue of Specification MIL-C-915.

REQUIREMENTS:

Qualification required.

Construction

First - Copper conductor, ASTM B-286 Size 20-7, tin-coated. Maximum diameter 0.039 inch.
Second - Polyvinyl chloride insulation, 105°C., white. Minimum thickness 0.008 inch.
Third - Clear polyamide jacket on each conductor, type III grade E, or type IV of MIL-M-20693. Nominal thickness 0.003 inch. Standard Identification Code, applied by method 1.
Fourth - The required number of singles (see details) cabled with a lay not greater than 24 times the pitch diameter of the layer. Cabling sequence shall be consecutive, starting with No. 1, from the center outward.
Fifth - Binder tape applied helically with overlap.
(B) Sixth - Standard thermoplastic jacket (gray). Thickness 0.030 inch minimum. Cable surface marking required.

Details

Type and size	Number of condrs.	Overall diameter	
		Min. (inch)	Max. (inch)
MU-14	14	0.365	0.400

EXAMINATION AND TESTS:

	Requirements:
Basic electrical:	
Conductor resistance - Ohms/1000 ft. at 25°C., max.	10.93
Voltage withstand - Volts, rms, minimum	
Conductor to conductor	2000
Insulation resistance - Megohms/1000 ft., min.	500

1/ Requirements previously covered on MIL-C-24145/3.

(B) Denotes change.

FSC 6145

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:10Z
Check the source to verify that this is the current version before use.

	Requirements:
Group A:	
Visual and dimensional	
Group B:	
Cold bending, cable - At 0° ± 2°C. (6 inch max. diameter mandrel) . .	No damage
Physicals (unaged)	
Insulation (conductor)	
Tensile strength - psi, minimum.	1800
Elongation - Percent, minimum.	100
Jacket (cable)	
Tensile strength - psi, minimum.	1800
Elongation - Percent, minimum.	225
Group C:	
Physicals (aged)	
Insulation (conductor)	
Air oven	
Elongation - Percent of unaged, minimum	90
Jacket (cable)	
Hot oil immersion	
Tensile strength - psi, minimum	1400
Elongation - Percent, minimum	50
Permanence of printing (conductor) - Cycles, minimum.	50
Permanence of printing (jacket) - Cycles, minimum	250

QUALIFICATION INSPECTION:

Qualification inspection shall include basic electrical plus all of Groups A, B and C.

UNIT ORDERING LENGTHS: 2500 feet (nominal).

Custodians:
Army - MI
Navy - SH
Air Force - 80

Review activities:
Army - EL, MI, AV
Navy - EC
Air Force - 80

User activities:
Army - ME, MU, WC
Navy - CG

Preparing activity:
Navy - SH
(Project 6145-0667)

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:10Z
Check the source to verify that this is the current version before use.