MIL-C-915/44A
1 August 1972
SUPERSEDING[1/]
MIL-C-915/44(SHIPS)
20 March 1972

MILITARY SPECIFICATION SHEET

CABLE, ELECTRICAL, TYPE 1SWU

(A) This specification is approved for use by all Departments and Agencies of the Department of Defense.

The complete requirements for procuring the cable described herein shall consist of this document and the latest issue of Specification MIL-C-915.

REQUIREMENTS:

Qualification required.

Construction (Watertight)

First - Copper conductor, ASTM B-286 size 22-7, uncoated. Maximum diameter 0.033 inch.
(A) Second - Polyethylene insulation, natural, type II, class L, grade 3 of L-P-390. Nominal thickness 0.045 inch.
Third - Braided shield of AWG No. 36 uncoated copper. Braid angle of 30 to 35 degrees; minimum coverage of 85 percent.
(A) Fourth - Shield insulation of one polyester tape, type G of MIL-I-631, plus a jacket of clear polyamide, type III, grade E or type IV of MIL-M-20693. Nominal thickness of 0.003 inch. Standard Identification Code, applied by method 2.
- Alternate shield insulation of two polyester tapes, type G of MIL-I-631, sealed. Standard Identification Code, applied by method 2, on inner tape.
(A) Fifth - The required number of singles (see details) cabled with a lay not greater than 24 times the pitch diameter of the layer. Cabling sequence shall be consecutive, starting with No. 1, from center outward. Non-fibrous fillers shall be employed.
Sixth - Binder tape applied helically with overlap.
(A) Seventh - Standard thermoplastic (gray). (See details for thickness.) Cable surface marking required.

(A) Details

Type and size	Number of condrs.	Cable jacket thick. min. (inch)	Overall diameter	
			Min. (inch)	Max. (inch)
1SWU-2	2	0.030	0.430	0.455
1SWU-14	14	.040	.825	.870
1SWU-20	20	.040	.970	1.030
1SWU-30	30	.050	1.135	1.200

EXAMINATION AND TESTS:

Basic electrical:

	Requirements:
(A) Conductor resistance - At 25°C., ohms/1000 ft., maximum.	17.2
Voltage withstand - Volts, rms, minimum	
Conductor to shield	3000
Shield to shield.	500

1/ Requirements formerly covered on MIL-C-24145/4.

(A) Denotes changes.

FSC 6145

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:10Z
Check the source to verify that this is the current version before use.

	Requirements:
Group A:	
Visual and dimensional	
(A) Hydrostatic (open end) - Leakage at 300 psi, 2 hrs., cu. inch, maximum.	1.0
Capacitance - 1 kHz, pF/ft., maximum.	28
Characteristic impedance - At 1 MHz, ohms	61±3
Thermoplastic flow at 95° ± 3° C.	No failure
Group B:	
(A) Drip - At 75° ± 1°C.,	Zero
Physicals (unaged)	
Insulation (conductor)	
Tensile strength - psi, minimum	1400
Elongation - Percent, minimum	300
Jacket (cable)	
Tensile strength - psi, minimum	1800
Elongation - Percent, minimum	225
Group C:	
Physicals (aged)	
Insulation (conductor)	
Air oven	
Elongation - Percent of unaged, minimum.	60
Jacket (cable)	
Hot oil immersion	
Tensile strength - psi, minimum.	1400
Elongation - Percent, minimum.	50
Permance of printing (jacket) - Cycles, minimum.	250
Cable filler removability	

QUALIFICATION INSPECTION

Qualification inspection shall include basic electrical plus all of Groups A, B and C plus the following:

(A) Cable aging and compatability (95° ± 3°C.).	No failure

UNIT ORDERING LENGTHS:

All sizes 1000 feet (nominal)

Custodians:
Army - MI
Navy - SH
Air Force - 80

Preparing activity:
Navy - SH
(Project 6145-0609-37)

Review activities:
Army - EL, MI, AV
Navy - EC
Air Force - 80

User activities:
Army - ME, MU, WC
Navy - CG

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:10Z
Check the source to verify that this is the current version before use.