MIL-C-915/45B
5 April 1973
SUPERSEDING 1/
MIL-C-915/45A
1 August 1972

MILITARY SPECIFICATION SHEET

CABLE, ELECTRICAL, TYPE 2SU

This specification sheet is approved for use by all Departments and Agencies of the Department of Defense.

The complete requirements for procuring the cable described herein shall consist of this document and the latest issue of Specification MIL-C-915.

REQUIREMENTS:

Qualification required.

Construction

First - Copper conductor, ASTM B-286 size 22-7, uncoated. Maximum diameter 0.033 inch.
Second - Polyethylene insulation, type II, class L, grade 4 of L-P-390. Nominal thickness 0.010 inch. Colored insulation, one black, and one white conductor for each pair.
Third - Clear polyamide jacket on each conductor, type III, grade E, or type IV of MIL-M-20693. Nominal thickness 0.003 inch.
Fourth - Two conductors (one black and one white) cabled together with a nominal lay of 2.5 inches to form each pair.
Fifth - Binder tape over each pair, at manufacturer's option, applied helically with overlap.
(B) Sixth - Braided shield of AWG No. 34 or No. 36 tin coated copper strands. Braid angle 30 to 35 degrees; minimum coverage, of 85 percent.
Seventh - Shield insulation of one polyester tape, type G of MIL-I-631, plus a jacket of clear polyamide, type III, grade E or type IV of MIL-M-20693. Nominal thickness of 0.003 inch. Standard Identification Code, applied by method 2.
- Alternate shield insulation of two polyester tapes, type G of MIL-I-631, sealed. Standard Identification Code, applied by method 2, on inner tape.
Eighth - The required number of pairs (see details) cabled with a lay not greater than 24 times the pitch diameter of the layer. Cabling sequence shall be consecutive, starting with pair No. 1, from center outward. Fibrous fillers as necessary to form a round cable.
Ninth - Binder tape applied helically with overlap.
Tenth - Standard thermoplastic jacket (gray). (See details for thickness.) Cable surface marking required.

Details

Type and size	Number of pairs	Cable jacket thick. min. (inch)	Overall diameter	
			Min. (inch)	Max. (inch)
2SU-3	3	0.040	0.480	0.520
2SU-7	7	.040	.610	.660
2SU-10	10	.040	.770	.830
2SU-14	14	.050	.860	.930
2SU-19	19	.050	.970	1.040
2SU-24	24	.050	1.120	1.210
2SU-30	30	.050	1.190	1.280
2SU-37	37	.050	1.290	1.380
2SU-44	44	.050	1.460	1.550
2SU-61	61	.060	1.660	1.740

1/ Requirements formerly covered on MIL-C-24145/5.
(B) Denotes changes

FSC 6145

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:11Z
Check the source to verify that this is the current version before use.

EXAMINATION AND TESTS:

	Requirements:
Basic electrical:	
Conductor resistance - At 25°C., ohms/1000 ft., maximum.	17.37
Voltage withstand - Volts, rms, minimum	
Conductor to conductor.	2000
Conductor to shield	1000
Shield to Shield.	500
Group A:	
Visual and dimensional	
Capacitance	
Mutual capacitance - At 1 mHz, pF/ft., maximum.	30
Capacitance unbalance - Percent, maximum.	8
Characteristic impedence - At 1 mHz, ohms.	75±5
Group B:	
Attenuation - At 3 mHz, db/100 ft., maximum.	3
Physicals (unaged)	
Insulation (conductor)	
Tensile strength - psi, minimum.	1400
Elongation - Percent, minimum.	300
Jacket (cable)	
Tensile strength - psi, minimum.	1800
Elongation - Percent, minimum.	225
Group C:	
Physicals (aged)	
Insulation (conductor)	
Air oven	
Elongation - Percent of unaged, minimum	60
Jacket (cable)	
Hot oil immersion	
Tensile strength - psi, minimum	1400
Elongation - Percent, minimum	50
Permanence of printing (jacket) - Cycles, minimum.	250

QUALIFICATION INSPECTION:
Qualification inspection shall include basic electrical plus all of Groups A, B and C.

UNIT ORDERING LENGTHS:

Size	Feet (nominal)
3 through 30	1000
37 through 61	500

Custodians:
Army - MI
Navy - SH
Air Force - 80

Review activities:
Army - EL, MI, AV
Navy - EC
Air Force - 80

User activities:
Army - ME, MU, WC
Navy - CG

Preparing activity:
Navy - SH
(Project 6145-0648-11)

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:11Z
Check the source to verify that this is the current version before use.