MIL-C-915/53B
5 April 1973
SUPERSEDING 1/
MIL-C-915/53A
1 August 1972

MILITARY SPECIFICATION SHEET

CABLE, ELECTRICAL, TYPE 3U

This specification sheet is approved for use by all Departments and Agencies of the Department of Defense.

The complete requirements for procuring the cable described herein shall consist of this document and the latest issue of Specification MIL-C-915.

REQUIREMENTS:

Qualification required.

Construction

(B)

First - Copper conductor AWG No. 18 (7 X 0.0152 inch), uncoated. Maximum diameter 0.050-inch.
Second - Polyethylene insulation, type II, class L, grade 4 of L-P-390. Nominal thickness 0.020-inch. Colored insulation - one conductor black, one conductor white and one conductor red for each triad.
Third - Insulation jacket of clear polyamide, type III grade E or type IV of MIL-M-20693. Nominal thickness 0.003-inch. Diameter over jacket 0.092 inch nominal.
Fourth - One black, one white and one red conductor cabled together with a nominal lay of 3-1/2 inches to form a triad.
Fifth - Marker braid on each triad. Standard Identification Code, applied by Method 4. Diameter over braided triad 0.215 inch nominal.
Sixth - The specified number of triads (see details) cabled together with a lay not greater than 24 times the pitch diameter of the layer. Cabling sequence shall be consecutive, starting with triad number 1, from center outward. Fibrous fillers as necessary to form a firm, round assembly.
Seventh - Binder tape of polyester, type G of MIL-I-631, applied helically with overlap.
Eighth - Standard thermoplastic jacket (gray). (See details for thickness.) Cable surface marking required.

Details

Type and size	Number of triads	Cable jacket thick. min. (inch)	Overall diameter	
			Min. (inch)	Max. (inch)
3U-3	3	0.040	0.580	0.620
3U-7	7	.040	.760	.810
3U-12	12	.050	1.030	1.090

1/ Requirements formerly covered on MIL-C-24145/13.

(B) Denotes changes

FSC 6145

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:12Z
Check the source to verify that this is the current version before use.

EXAMINATION AND TESTS:

	Requirements:
Basic electrical:	
Conductor resistance - At 25°C., ohms/1000 ft., maximum	6.80
Voltage withstand - Volts, rms, minimum,	
Conductor to conductor	2000
Group A:	
Visual and dimensional	
Capacitance	
Mutual capacitance - At 1 kHz, pF/ft., maximum	30
Capacitance unbalance - Percent, maximum	5
Group B:	
Physicals (unaged)	
Insulation	
Tensile strength - psi, minimum	1400
Elongation - Percent, minimum	300
Jacket (cable)	
Tensile strength - psi, minimum	1800
Elongation - Percent, minimum	225
Group C:	
Physicals (aged)	
Insulation	
Air oven	
Elongation - Percent of unaged, minimum	60
Jacket (cable)	
Hot oil immersion	
Tensile strength - psi, minimum	1400
Elongation - Percent, minimum	50
Permanence of printing (jacket) - Cycles, minimum	250

QUALIFICATION INSPECTION

Qualification inspection shall include basic electrical plus all of groups A, B, and C.

UNIT ORDERING LENGTHS:
All sizes: 1000 feet (nominal)

Custodians:
Army - MI
Navy - SH
Air Force - 80
Review activities:
Army - EL, MI, AV
Navy - EC
Air Force - 80
User activities:
Army - ME, MU, WC
Navy - CG

Preparing activity:
Navy - SH
(Project 6145-0648-14)

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:12Z
Check the source to verify that this is the current version before use.