MIL-C-915/55A
1 August 1972
SUPERSEDING 1/
MIL-C-915/55(SHIPS)
20 March 1972

MILITARY SPECIFICATION SHEET

CABLE, ELECTRICAL, TYPE 1S75MU

(A) This specification is approved for use by all Departments and Agencies of the Department of Defense.

The complete requirements for procuring the cable described herein shall consist of this document and the latest issue of Specification MIL-C-915.

REQUIREMENTS:

Qualification required.

Construction

First - Copper conductor, ASTM B-286 size 22-7, tin coated. Maximum diameter 0.033 inch.

(A) Second - Polyethylene insulation, natural, type II, class L, grade 3 of L-P-390. Nominal thickness 0.070 inch.

Third - Braided shield of AWG No. 34, tin coated copper. Braid angle of 30 to 35 degrees, minimum coverage of 85 percent.

(A) Fourth - Shield insulation of one polyester tape, type G of MIL-I-631, plus a jacket of clear polyamide, type III, grade E or type IV of MIL-M-20693. Nominal thickness of 0.003 inch. Standard Identification Code, applied by method 2.

- Alternate shield insulation of two polyester tapes, type G of MIL-I-631, sealed. Standard Identification Code, applied by method 2, on inner tape.

(A) Fifth - The eight singles cabled with a lay not greater than 8 inches around a center filler. Cabling sequence shall be consecutive, starting with No. 1.

(A) Sixth - Binder tape applied helically with overlap.

Seventh - Standard thermoplastic jacket (gray). Minimum thickness 0.050 inch. Cable surface marking required.

(A)

Details

Type and size	Number of condrs.	Diameter over completed conductor nominal (inch)	Cable overall diameter	
			Min. (inch)	Max. (inches)
1S75MU-8	8	0.228	0.950	1.030

EXAMINATION AND TESTS:

Basic electrical:	Requirements:
(A) Conductor resistance - At 25°C., ohms/1000 ft., maximum.	17.37
Voltage withstand - Volts, rms, minimum	
Conductor to shield	7000
Shield to shield.	500

1/ Requirements formerly covered on MIL-C-24145/15.

(A) Denotes changes.

FSC 6145

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:12Z
Check the source to verify that this is the current version before use.

	Requirements:
Group A:	
Visual and dimensional	
Characteristic impedance - Ohms at 1 MHz	75 ± 3
Group B:	
Attenuation - At 400 MHz, db/100 ft., maximum.	9.0
(A) Cold bending, cable - At 0° ± 2°C., (mandrel 13 inch max. diameter).	No damage
Physicals (unaged)	
Insulation (conductor)	
Tensile strength - psi, minimum.	1400
Elongation - Percent, minimum.	300
Jacket (cable)	
Tensile strength - psi, minimum.	1800
Elongation - Percent, minimum.	225
Group C:	
Physicals (aged)	
Insulation (conductor)	
Air oven	
Elongation - Percent of unaged, minimum	60
Jacket (cable)	
Hot oil immersion	
Tensile strength - psi, minimum	1400
Elongation - Percent, minimum	50
(A) Permanence of printing (jacket) - Cycles, minimum.	250

QUALIFICATION INSPECTION:

(A) Qualification inspection shall include basic electrical plus all of Groups A, B and C.

UNIT ORDERING LENGTHS: 1000 feet (nominal)

Custodians:
Army - MI
Navy - SH
Air Force - 80

Review activities:
Army - EL, MI, AV
Navy - EC
Air Force - 80

User activities:
Army - ME, MU, WC
Navy - CG

Preparing activity:
Navy - SH
(Project 6145-0609-41)

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:12Z
Check the source to verify that this is the current version before use.