MIL-C-915/22D
5 April 1973
SUPERSEDING
MIL-C-915/22C
1 August 1972

MILITARY SPECIFICATION SHEET

CABLE, ELECTRICAL, 300 VOLTS, TYPE TSP

This specification sheet is approved for use by all Departments and Agencies of the Department of Defense.

The complete requirements for procuring the cable described herein shall consist of this document and the latest issue of Specification MIL-C-915.

REQUIREMENTS:

Qualification required.

Construction (Watertight)

First - Copper conductor, Navy standard size 3/5(7), tin-coated.
Second - Polyvinyl chloride insulation (80°C.). Nominal wall thickness 0.015 inch. Telephone identification code, applied by Method 3.
Third - Two conductors cabled together to form a pair with a lay not greater than 2-1/2 inches.
Fourth - The specified number of pairs (see Details) cabled with a lay not greater than 10 inches in the outer layer. Non-fibrous fillers shall be employed. Cabling sequence shall be consecutive, starting with pair No. 1, from center outward.
Fifth - Binder tape applied helically with overlap.
Sixth - Standard thermoplastic jacket (gray). Nominal wall thickness 0.080 inch. Cable surface marking required.

Details

Type and size	Number of pairs	Overall diameter maximum (inches)
TSP-11	11	0.735
TSP-31	31	1.062

EXAMINATION AND TESTS

	Requirements:
Basic electrical:	
Conductor resistance - Ohms/1000 ft. at 25°C., maximum	17.06
Voltage withstand - Volts, rms, minimum	
(D) Conductor to conductor	2000
(D) Conductor to ground	1000
Insulation resistance - Megohms/1000 ft., minimum	100
Group A:	
Visual and dimensional	
Watertightness - See MIL-C-915, table for limits of water leakage	

(D) Denotes changes

FSC 6145

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:08Z
Check the source to verify that this is the current version before use.

	Requirements:
Group B:	
Physicals (unaged)	
Insulation (conductor)	
Tensile strength - psi, minimum	1800
Elongation - Percent, minimum	125
Jacket (cable)	
Tensile strength - psi, minimum	1800
Elongation - Percent, minimum	225
Group C:	
Flammability - Inches, maximum	2
Physicals (aged)	
Insulation (conductor)	
Air Oven	
Elongation - Percent of unaged, minimum	80
Jacket (cable)	
Hot oil immersion	
Tensile strength - psi, minimum	1400
Elongation - Percent, minimum	50
Permanence of printing (jacket) - Cycles, minimum	250
Cable filler removability	

QUALIFICATION INSPECTION

Qualification inspection shall include basic electrical, all of Groups A, B, and C plus the following:

Cable aging and compatibility (95° + 3°C.)	No failure

UNIT ORDERING LENGTHS:

Size	Feet (Nominal)
11	2500
31	1000

Custodians:
Army - MI
Navy - SH
Air Force - 80
Review activities:
Army - EL, MI, AV
Navy - EC
Air Force - 80
User activities:
Army - ME, MU, WC
Navy - CG

Preparing activity:
Navy - SH
(Project 6145-0648-6)

☆U.S. GOVERNMENT PRINTING OFFICE:1973-714-545/5236

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:08Z
Check the source to verify that this is the current version before use.