MIL-C-915/47A
1 August 1972
SUPERSEDING[1/]
MIL-C-915/47(SHIPS)
20 March 1972

MILITARY SPECIFICATION SHEET

CABLE, ELECTRICAL, TYPE 1SWF

(A) This specification is approved for use by all Departments and Agencies of the Department of Defense.

The complete requirements for procuring the cable described herein shall consist of this document and the latest issue of Specification MIL-C-915.

REQUIREMENTS:
Qualification required.

Construction (Watertight)

First - Copper conductor, ASTM B-286 size 22-7, uncoated. Maximum diameter 0.033 inch.

(A) Second - Polyethylene insulation, natural, type II, class L, grade 3 of L-P-390. Nominal thickness 0.045 inch.

Third - Braided shield of AWG No. 36 uncoated copper. Braid angle of 30 to 35 degrees; minimum coverage of 85 percent.

(A) Fourth - Shield insulation of one polyester tape, type G of MIL-I-631, plus a jacket of clear polyamide, type III, grade E or type IV of MIL-M-20693. Nominal thickness of 0.003 inch. Standard Identification Code, applied by Method 2.

- Alternate shield insulation of two polyester tapes, type G of MIL-I-631, sealed. Standard Identification Code, applied by Method 2, on inner tape.

Fifth - Two conductors (one black and one white) cabled with a lay not greater than 3 inches. Non-fibrous fillers shall be used.

Sixth - Binder tape applied helically with overlap.

(A) Seventh - Arctic type polychloroprene jacket (black). Cable jacket thickness 0.100 inch maximum. Cable surface marking required.

Details

(A)

Type and size	Number of conductors	Overall diameter	
		Minimum (inch)	Maximum (inch)
1SWF-2	2	0.600	0.625

EXAMINATION AND TESTS:

	Requirements:
Basic electrical:	
(A) Conductor resistance - At 25°C., ohms/1000 ft., maximum	17.03
Voltage withstand - Volts, rms, minimum	
Conductor to shield	3000
Shield to shield	500

1/ Requirements formerly covered on MIL-C-24145/7.

(A) Denotes changes

FSC 6145

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:11Z
Check the source to verify that this is the current version before use.

	Requirements:
Group A:	
Visual and dimensional	
(A) Hydrostatic (open end) - Leakage 1000 psi, cu. in., 6 hrs., test each shipping length	Zero
Capacitance - At 1 kHz, pF/ft., maximum	28
Characteristic impedance - At 1 MHz, ohms	61 ± 3
Group B:	
Cold working (minus 54° ± 2°C.)	No damage
(A) Drip - At 75° ± 1°C.,	Zero
(A) Physicals (unaged)	
Insulation (conductor)	
Tensile strength - psi, minimum	1400
Elongation - Percent, minimum	300
Jacket (cable)	
Tensile strength - psi, minimum	1800
Elongation - Percent, minimum	300
Set - Inch, maximum	3/8
Group C:	
Physicals (aged)	
Insulation (conductor)	
Air oven	
(A) Elongation - Percent of unaged, minimum.	60
Permanence of printing (jacket) - Cycles, minimum	250
Cable filler removability	

QUALIFICATION INSPECTION:

Qualification inspection shall include basic electrical, all of Groups A, B and C plus the following:

(A) Cable aging and compatibility (95° ± 3°C.)	No failure
(A) Cold working (minus 54° ± 2°C.)	No failure

UNIT ORDERING LENGTHS:

All sizes: 1000 feet (nominal)

(A) Custodians:
Army - MI
Navy - SH
Air Force - 80

(A) Review activities:
Army - EL, MI, AV
Navy - EC
Air Force - 80

(A) User activities:
Army - ME, MU, WC
Navy - CG

Preparing activity:
Navy - SH
(Project 6145-0609-52)

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:11Z
Check the source to verify that this is the current version before use.