MIL-S-44212A(GL)
INTERIM AMENDMENT 1
1 May 1995

MILITARY SPECIFICATION

SWEATSHIRT, HOODED, PHYSICAL FITNESS UNIFORM (PFU)

This interim amendment is approved for use within the Department of the Army, and all Departments and Agencies of the Department of Defense, with MIL-S-44212A(GL), dated 23 February 1989.

PAGE 2

Para 2.1.1, under "Specifications" "Military", delete "MIL-T-43548 - Thread, Polyester Core: Cotton-, Rayon-, or Polyester-Covered", and add under "Specifications" "Federal", "A-A-50199 - Thread, Polyester Core: Cotton- or Polyester Covered".

PAGE 4

Para. 3.3.1, Line 3. After "rayon" add "or polyester".

Para. 3.3.1, Line 7. After "rayon" add "or polyester".

Para. 3.3.1, Line 18. Opposite "Weight, ounces per square yard", delete "8.2 $\pm$ 0.5" and substitute "8.45 $\pm$ .75".

Paragraph 3.3.1, Line 19. Opposite "Wales per inch", delete "21" and substitute "19".

PAGE 5

Para. 3.3.2, line 3. After "rayon" add "or polyester".

Para. 3.3.2, line 7. After "rayon" add "or polyester".

AMSC N/A FSC 8415

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T00:39Z
Check the source to verify that this is the current version before use.

PAGE 5

Para. 3.3.2, line 11. Opposite "Weight, ounces per square yard", delete "8.5 ± 0.5" and substitute "8.875 ± .875".

Para. 3.3.4, line 1. Delete "Gray 446" and substitute "Gray 466".

Para. 3.3.4.1, Colorfastness. Delete the paragraph in its entirety and substitute the following:

"3.3.4.1 Colorfastness. The finished cloth shall show fastness to laundering (after 3 cycles), and perspiration equal to or better than the standard sample or equal to or better than a rating of "good". The finished cloth shall show fastness to light (after 40 standard fading hours) equal to or better than a rating of "good". The finished cloth shall show fastness to crocking equal to or better than the standard sample or shall have an AATCC Chromatic Transferance Scale Rating of not lower than 3.5 when tested as specified in 4.4.1.2."

Para. 3.3.6, line 2. Delete "MIL-T-43548" and substitute "A-A-50199".

PAGE 6

Para. 3.3.7, line 3. After "tab", add "(7/8 inch minimum)"

Para. 3.3.8, Drawcord. Delete the paragraph in its entirety and substitute the following:

"3.3.8 Drawcord. The drawcord shall be 1/4 inch diameter, 100 percent continuous filament texturized polyester yarn, hot knifed (or tips impregnated with cellulose acetate for a minimum of 1/2 inch) into lengths of 45-65 inches. The polyester shall be made with 150 denier 2-ply yarn consisting of 16 carriers having 6 ends per carrier and have a minimum breaking strength of 150 pounds. The drawcord shall be regular weave with no core. The drawcord shall be Light Gray DoD Standard Shade AV, C.A. 66064 and shall show "good" colorfastness to laundering".

PAGE 7

Para. 3.5.1.2, line 1. In the heading, after "Types", add "406,". At the end of the paragraph, add the following:

"Type 301 stitching may be used in repairing type 406 stitching.".

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T00:39Z
Check the source to verify that this is the current version before use.

PAGE 7

Para. 3.5.2, lines 5 and 6. Delete "15 launderings when tested as specified in 4.4.1.1" and substitute "5 launderings and dryings when tested as specified in 4.4.2."

PAGE 12

Para. 3.7, TABLE I, Manufacturing Operations Requirements, Operation 8.c., line 2. Insert "and stitch" before "to".

PAGE 17

Para. 4.2.1.2, Component testing. Delete paragraph number "4.2.1.2" and substitute "4.4.1.2".

Para. 4.2.1.2, TABLE III, Cloth component tests. Under "Characteristic", line 5, delete "after 80" and substitute "after 40".

Para. 4.2.1.2, TABLE III, Cloth component tests, lines 11 and 12. Delete "Screen printing on jersey knit 3.5.7 5614 2/ colorfastness to laundering"

Para. 4.2.1.2, TABLE III, Cloth component tests, Footnote 1/, line 1. After "rayon" add "or polyester".

Para. 4.2.1.2, TABLE III, Cloth component tests, Footnote 2/. Delete in its entirety.

Para. 4.4.2, line 5. Delete "1.5" and "6.5" and substitute "1.0" and "4.0" respectively.

PAGE 18

Para. 4.4.2, TABLE IV, End item visual defects. Under "Defects" for "Slide fastener", add the following new defect:

"Pull tab below specified length Major"

PAGE 20

Para. 4.4.3, line 6. Delete "4.0" and substitute "2.5".

PAGE 20

Para. 4.4.4, line 2. Delete "105" and substitute "150".

PAGE 21

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T00:39Z
Check the source to verify that this is the current version before use.

Para. 4.4.4, line 5. Delete "4.4.1" and substitute "4.4.1.2".

Para. 4.4.4, Packaging examination. Delete this heading and substitute "4.4.5 Packaging examination."

PAGE 23

Para. 5.4.1, line 9. Delete "Quality" and substitute "Quantity".

PAGE 24

Para. 6.5.1, line 3. After "rayon" add "or polyester".

Para. 6.5.2, line 4. After "rayon" add "or polyester".

Custodian:

Army - GL

Review activity:

Army - MD

Preparing activity:

DLA - CT

(Project No. 8415-A037)

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T00:39Z
Check the source to verify that this is the current version before use.