INCH-POUND

MIL-T-44222A
1 March 1991
SUPERSEDING
MIL-T-44222
3 April 1986

MILITARY SPECIFICATION

TENT LINER SECTIONS; INSULATED (TEMPER)

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers insulated tent liner sections and covers for use with the tent, expandable, modular, personnel.

1.2 Classification. Tent liner sections shall be of the following types as specified (see 6.2).

Type I - End section
Type II - Intermediate section
Type III - Intermediate door section

2. APPLICABLE DOCUMENTS

2.1 Government documents.

2.1.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those listed in the issue of the Department of Defense Index of Specifications and Standards (DODISS) and supplement thereto, cited in the solicitation (see 6.2).

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be used in improving this document should be addressed to: U.S. Army Natick Research, Development, and Engineering Center, Natick, MA 01760-5017 by using the Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 8340

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T00:42Z
Check the source to verify that this is the current version before use.

SPECIFICATIONS

FEDERAL

DDD-L-20	-	Label: for Clothing, Equipage, and Tentage, (General Use)
PPP-B-601	-	Boxes, Wood, Cleated-Plywood
PPP-B-636	-	Boxes, Shipping, Fiberboard

STANDARDS

FEDERAL

FED-STD-751	-	Stitches, Seams and Stitchings

MILITARY

MIL-STD-105	-	Sampling Procedures and Tables for Inspection by Attributes
MIL-STD-129	-	Marking for Shipment and Storage
MIL-STD-147	-	Palletized Unit Loads
MIL-STD-731	-	Quality of Wood Members for Containers and Pallets

(Unless otherwise indicated, copies of federal and military specifications, standards, and handbooks are available from the Standardization Documents Order Desk, Building 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.)

2.1.2 Other Government documents, drawings, and publications. The following other Government documents, drawings, and publications form a part of this document to the extent specified herein. Unless otherwise specified, the issues are those cited in the solicitation.

DRAWINGS

U.S. ARMY NATICK RESEARCH, DEVELOPMENT, AND ENGINEERING CENTER

5-4-3359	-	Tent Cover
5-4-4127	-	End Section Liner (Insulated)
5-4-4128	-	End Liner (Insulated)
5-4-4129	-	Door Section Liner (Insulated)
5-4-4130	-	Intermediate Door Section Liner (Insulated)
5-4-4131	-	Intermediate Section Liner (Insulated)
5-4-4132	-	Flap Assemblies
5-4-4133	-	Vent Sleeve

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T00:42Z
Check the source to verify that this is the current version before use.

5-4-4134	-	Lanyard Assemblies
5-4-4135	-	Toggle Lanyard
5-4-4136	-	Light Support Assembly
5-4-4137	-	Hook, Chain, "S"

(Copies of drawings are available from the U.S. Army Natick Research, Development, and Engineering Center, ATTN: STRNC-UX, Natick, MA 01760-5017.)

PUBLICATION

U.S. DEPARTMENT OF THE ARMY FIELD MANUAL

FM 10-16 - General Repair of Tents, Canvas and Webbing

(Copies of documents required by contractors in connection with specific acquisition functions may be obtained from the contracting activity or as directed by the contracting activity.)

2.2 Non-Government publications. The following documents form a part of this document to the extent specified herein. Unless otherwise specified, the issues of the documents which are DOD adopted are those listed in the issue of the DODISS cited in the solicitation. Unless otherwise specified, the issues of documents not listed in the DODISS are the issues of the documents cited in the solicitation (see 6.2).

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

D 3951 - Standard Practice for Commercial Packaging

(Copies may be obtained from the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103-1187.)

(Non-Government standards and other publications are normally available from the organizations that prepare or distribute the documents. These documents also may be available in or through libraries or other informational services.)

2.3 Order of precedence. In the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 First article. When specified (see 6.2), a sample shall be subjected to first article inspection (see 6.3), in accordance with 4.3.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T00:42Z
Check the source to verify that this is the current version before use.

3.2 Materials and components. Materials and components shall be as specified on the applicable drawings. Materials not definetely specified shall be of the quality normally used by the contractor provided that the completed item complies with all the provisions of this specification. It is encouraged that recycled material be used when practical as long as it meets the requirements of this specification.

3.3. Construction. Construction shall conform to the drawings listed in section 2 and be as specified herein.

3.3.1 Stitching machine.

3.3.1.1 Types of stitching. All stitch types shall conform to FED-STD-751 as follows:

For all stitching except binding	- Type 301, 5 to 7 stitches per inch
For binding or stitching indicated by "Z" on drawings	- Type 401, 5 to 7 stitches per inch - Chain portion of stitching shall not appear on the outside of cover or pile fastener tape

3.3.1.2 Thread breaks. Thread breaks in stitching shall be overstitched not less than 1 inch at each break on stitch type 301 and not less than 1-1/2 inches at each break on type 401 stitching. Thread breaks on type 401 stitching may be overstitched with stitch type 301. Thread breaks noted during inspection shall be repaired by overstitching the existing stitching starting from a distance of 1 inch before the break, across the defective area, to a distance of 1 inch beyond the break. The ends of repair stitching are not required to be backstitched.

3.3.1.3 Stitching ends. Stitching at the ends shall be overstitched not less than 1 inch on stitch type 301 except where ends are turned under in a hem, held down by other stitching. Where 301 stitching is performed automatically on stitch patterns such as box, box with cross-stitch, "W" stitching, or straight line tacking, at least three tying, overlapping, or back stitches shall be used to secure the ends of stitching.

3.3.1.4 Skipped stitches. Two or more skipped stitches occurring consecutively in stitch type 301 shall be overstitched not less than 1 inch on each side of the skip. Any skipped stitch on stitch type 401 shall be overstitched not less than 1-1/2 inches on each side of the skip. Skipped stitches on type 401 stitching may be overstitched with stitch type 301.

3.3.1.5 Lubrication of thread. The addition of any lubricant to the polyester thread prior to or during the sewing operation is prohibited (see 4.4.2).

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T00:42Z
Check the source to verify that this is the current version before use.

3.3.2 Setting of grommets. Holes punched to receive grommets shall be smaller than the outside diameter of the grommet barrels so that the barrel must be forced through the hole. The grommets shall be securely clinched without cutting the material (see 4.4.2).

3.3.3 Splicing of ground cloth. If required, the ground cloth shall be spliced as shown on Drawing 5-4-4128.

3.3.4 Repairs. All necessary repairs shall be effected in accordance with the Department of the Army Field Manual FM 10-16, except that hand-sewn patches other than as specified herein, will not be acceptable.

3.4. Marking. All markings and labels shall conform to DDD-L-20.

3.4.1 Indentification label. Identification labels shall conform to type VI, class 6 and shall be 3-1/2 inches by 5-1/2 inches minimum with a blank space of at least 1-1/4 inches provided at the bottom of the label for the Department of Defense inspector's stamp. Identification labels shall be stitched to the liner in the location shown on the drawing.

3.4.2 Special markings. The letters "US" on the liner and nomenclature on the cover shall conform to type IV, class 9 in the size characters and in the locations shown on the drawings. Class 9 markings shall be clearly legible after subjection to accelerated weathering.

3.5 Workmanship. Cloth components shall be clean and free of holes, cuts, tears, or cloth defects such as multiple floats or broken or missing yarns. Webbing and tape shall not have frayed or scalloped edges and rope components shall be free of cuts or breaks. Thread tension shall be maintained with seams properly sewed so that no runoffs, twists, pleats, or open seams shall result. All thread ends shall be trimmed to 1/2 inch or less. Metal components shall be free of burrs, sharp edges, and corroded areas and shall not be broken or malformed.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements (examinations and tests) as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in this specification where such inspections are deemed necessary to ensure supplies and services conform to prescribed requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T00:42Z
Check the source to verify that this is the current version before use.

4.1.1 Responsibility for compliance. All items shall meet all requirements of sections 3 and 5. The inspection set forth in this specification shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in the specification shall not relieve the contractor of the responsibility of ensuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling inspection, as part of manufacturing operations, is an acceptable practice to ascertain conformance to requirements, however, this does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to accept defective material.

4.1.2 Responsibility for dimensional requirements. Unless otherwise specified in the contract or purchase order, the contractor is responsible for ensuring that all specified dimensions have been met. When dimensions cannot be examined on the end item, inspection shall be made at any point, or at all points in the manufacturing process necessary to ensure compliance with all dimensional requirements.

4.2 Classification of inspections. The inspection requirements specified herein are classified as follows:

a. First article inspection (see 4.3)
b. Quality conformance inspection (see 4.4)

4.3 First article inspection. When a first article is required (see 3.1 and 6.2), it shall be examined for the defects specified in 4.4.3 and 4.4.4. Any nonconformance shall be cause for rejection of the first article.

4.4 Quality conformance inspection. Unless otherwise specified, sampling for inspection shall be performed in accordance with MIL-STD-105.

4.4.1 Component and material inspection. In accordance with 4.1, components and materials shall be inspected in accordance with all the requirements of referenced documents unless otherwise excluded, amended, modified, or qualified in this specification or applicable purchase document.

4.4.2 In-process inspection. Inspections shall be made at any point or during any phase of the manufacturing operation to determine that the following are as specified:

a. There shall be no lubrication of polyester thread prior to or or during sewing operations for compliance with 3.3.1.5.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T00:42Z
Check the source to verify that this is the current version before use.

Whenever nonconformance is noted, correction shall be made to the items affected and to the process. Items which cannot be corrected shall be removed from production.

b. Holes punched to receive grommets are in compliance with 3.3.2.

4.4.3 End item visual examination. The end items shall be examined for the defects listed in table I. The lot size shall be expressed in units of tent liner sections and covers. The sample unit shall be one complete tent liner section and cover. The inspection level shall be II and the acceptable quality level (AQL), expressed in terms of defects per hundred units, shall be 10 for major defects, 25 for major and minor A combined defects, and 100 for total (major, minor A and minor B combined) defects.

TABLE I. End item visual defects

Examine	Defect	Classification		
		Major	Minor A	Minor B
Cloth, quilted	Any hole, cut, tear, or open place:			
	a. On the outside surface	101		
	b. On the inside surface:			
	- up to 1/4 inch in any direction		201	
	- more than 1/4 in any direction	102		
	Loose yarn, snagged yarn, misweave, slub, float, missing or broken yarn, or woven-in waste:			
	- up to 1/4 inch			301
	- more than 1/4 inch		202	
	Knot, clearly noticeable at a distance of 3 feet or more			302
	Stitch pattern not as specified on drawing		203	
	Color not as specified	103		
	Abrasion resulting in a weak place or any weak place	104		
	Broken or missing yarn, multiple floats, clearly visible at normal inspection distance of approximately 3 feet		204	
Cloth, coated, cover	Cut, tear, or hole (including exposed drill hole) greater than 1/8 inch in length or diameter	105		

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T00:42Z
Check the source to verify that this is the current version before use.

TABLE I. End item visual defects (cont'd)

Examine	Defect	Classification Major	Minor A	Minor B
Cloth, coated, cover (cont'd)	Cut, tear, or hole (including exposed drill hole) 1/8 inch or less in length or diameter		205	
Webbing and tape	Any hole, cut, tear, or smash	106		
	Abrasion mark, resulting in a weak area	107		
	Slub (more than twice the size of normal yarns)		206	
	Knot, extending above the surface		207	
	Spot, stain, or streak clearly visible at normal inspection distance (approximately 3 feet)		208	
	Mispick, double pick (two or more across full width)	108		
	Edge slack, scalloped, or otherwise poorly constructed exceeding 1/4 inch in length	109		
	Cut end of webbing or tape not fused as specified (when required)	110		
Webbing, tie tapes	Edge frayed or scalloped			303
Hardware and metal components	Broken	111		
	Malformed:			
	- fails to perform intended function	112		
	- but will perform intended function		209	
	Corroded area			304
	Burr or sharp edge which may cause injury in handling or damage to fabric	113		
Grommets	Improperly set, two or more teeth exposed (except where grommet is set as specified but is in an area of uneven thickness which prevents uniform clinching)			305
	Clinched loosely, allowing grommet to rotate in hole		210	
	Clinched excessively tight, cutting fabric:			
	- on liner	114		
	- on cover		211	
	Insecurely clinched (i.e., grommet or washer may become disengaged)	115		

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T00:42Z
Check the source to verify that this is the current version before use.

TABLE I. End item visual defects (cont'd)

Examine	Defect	Classification Major	Minor A	Minor B
Seams and stitching	Open seam on stitch type 301:			
	- for more than 1/4 inch but not more than 1 inch		212	
	- for more than 1 inch	116		
	Open seam on stitch type 401:			
	- one row of stitching open for 1 inch or less			306
	- one row of stitching open for more than 1 inch		213	
	Both rows of stitching open (not necessarily at the same location):			
	- on intermediate door section	117		
	- on end section or on cover	118		
NOTE:	A seam shall be classified as open when one or more stitches joining a seam are broken, or when one or more skipped or run-off stitches occur. On double stitched seams, a seam shall be classified as open when either one or both sides of a seam are open.			
	Raw edges caught in stitching:			
	- more than 1 inch but not more than 3 inches			307
	- more than 3 inches		214	
	Thread breaks:			
	- overstitched less than specified			308
	- secured with less than three tying, overlapping back stitches when automatic stitching is performed			309
NOTE:	Thread breaks and skipped stitches not overstitched shall be classified as open seams.			
Seams	Pleated:			
	- on liner		215	
	- on cover			310
Seam type	Wrong seam type	119		

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T00:42Z
Check the source to verify that this is the current version before use.

TABLE I. End item visual defects (cont'd)

Examine	Defect	Classification Major	Minor A	Minor B
Stitch type	Wrong stitch type	120		
Stitch tension	Loose, resulting in an exposed bobbin or top thread for more than 6 inches		216	
	Tight, as evidenced by puckering on fabric for more than 6 inches		217	
Stitches per inch	Less than minimum specified (except on panel joining seams):			
	- one stitch		218	
	- two or more stitches			311
	Less than minimum specified on panel joining seams		219	
	More than maximum specified:			
	- one stitch			312
	- two or more stitches		220	
	NOTE: Variations in the number of stitches per inch, caused by the operator speeding up the machine and pulling the fabric in order to sew over heavy places or heavy seams or in turning corners, shall be classified as follows: a. Within the minor "B" defect classification - no defect b. Within the minor "A" defect classification - minor "B" defect			
Stitching gage	Not as specified		221	
Stitching margin	Larger than specified:			
	- for more than 2 inches but not more than 4 inches			313
	- for more than 4 inches		222	
	Less than specified:			
	- for more than 2 inches but not more than 4 inches			314
	- for more than 4 inches		223	
Stitching	Chain portion of stitching shows on outside of cover or on pile fastener tape		224	

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T00:42Z
Check the source to verify that this is the current version before use.

TABLE I. End item visual defects (cont'd)

Examine	Defect	Classification Major	Minor A	Minor B
Mends, darns or patches	Repairs not in accordance with Department of the Army Field Manual FM 10-16, or not authorized by the contracting officer (see 3.3.4)	121		
Components and assembly	Any component part omitted, not assembled as specified, or not fabricated of applicable referenced material	122		
Hems	Constructed with partial turnunder when double turnunder is required		225	
	Twisted or pleated			315
Reinforcements	Improperly applied, causing excessive fullness on reinforcements or reinforced parts	123		
Cloth splicing	Spliced pieces (ground cloth only) not joined as shown on Drawing 5-4-4128		226	
	Spliced in other than ground cloth	124		
Slide fastener	Slider jams or fails to interlock chain	125		
	Any tape improperly assembled causing failure of chain to effect a smooth and secure closure	126		
Marking and labels	Omitted, incorrect, illegible, or misplaced		227	
Cleanness	Spots or stains		228	
	Thread ends not trimmed to 1/2 inch or less (except in slide fastener area)			316
	Thread ends not trimmed to 1/2 inch or less in slide fastener area		229	

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T00:42Z
Check the source to verify that this is the current version before use.

4.4.4 End item dimensional examination. The end items shall be examined for conformance to the dimensions specified in table II. Any dimension not within the specified tolerance shall be classified as a defect. The lot size shall be expressed in units of tent liner sections and covers. The sample unit shall be one complete tent liner section and cover. The inspection level shall be I and the AQL, expressed in terms of defects per hundred units, shall be 2.5 for major defects, 10 for major and minor A combined defects, and 100 for total (major, minor A, and minor B combined) defects.

TABLE II. End item dimensional defects

Examine	Defect	Classification Major	Minor A	Minor B
Overall Dimensions of end, door, and intermediate sections, and covers	Smaller than specified dimensions less applicable minus tolerances indicated on drawings	201		
	Larger than specified dimensions and applicable plus tolerance indicated on drawings			301
Location dimensions (unless otherwise specified)	Not within specified tolerance: - not exceeding twice the applicable tolerance			302
	- exceeding twice the applicable tolerance		201	
Webbing, tie tapes	Finished length less than specified by more than 1 inch			303
Grommets	Set beyond specified location by more than 1/2 inch			304
Reinforcements	Finished dimensions less than specified by more than 1/2 inch			305

4.4.5 Packaging examination. The fully packaged end items shall be examined for the defects listed below. The lot size shall be expressed in units of shipping containers. The sample unit shall be one shipping container fully packaged. The inspection level shall be S-2 and the AQL, expressed in terms of defects per hundred units, shall be 2.5.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T00:42Z
Check the source to verify that this is the current version before use.

Examine	Defect
Marking (exterior and interior)	Omitted; incorrect; illegible; of improper size, location, sequence, or method of application
Materials	Any component missing, damaged, or not as specified
Workmanship	Inadequate application of components, such as: incomplete sealing or closure of flap, improper taping, loose strapping or inadequate stapling Bulged or distorted container
Content	Number per container is more or less than required

4.4.6 Palletization examination. The fully packaged and palletized end items shall be examined for the defects listed below. The lot size shall be expressed in units of palletized unit loads. The sample unit shall be one palletized unit load, fully packaged. The inspection level shall be S-1 and AQL, expressed in terms of defects per hundred units, shall be 6.5.

Examine	Defect
Finished dimensions	Length, width, or height exceeds specified maximum requirement
Palletization	Pallet pattern not as specified Interlocking of loads not as specified Load not bonded as specified
Weight	Exceeds maximum load limits
Marking	Omitted; incorrect; illegible; of improper size, location, sequence, or method of application

5. PACKAGING.

5.1 Preservation. Preservation shall be level A, or Commercial as specified (see 6.2).

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T00:42Z
Check the source to verify that this is the current version before use.

5.1.1 Level A preservation.

5.1.1.1 End section liner. The liner, with all fasteners closed, shall be folded by first laying it flat in a trapezoidal shape with end wall facing up. The triangular ends will then be folded in at the eave line and straight across the bottom. Then the liner shall be folded by bringing the eave line together and butting in the center. The liner shall be folded in half by bringing one end over to the other end. The final fold shall then be accomplished by bringing the top edge down to the bottom edge. The dimensions of the liner, when folded, shall approximate 4 feet by 3 feet. Each folded liner shall be placed within its protective carrying cover.

5.1.1.2 Intermediate section liner (with door or blank). The liner, with all fasteners closed, shall be laid flat and folded in half along the length. Then the liner shall be folded by bringing the ends together and butting them in the center. Then, again, the ends shall be butted together at the center. The final fold shall then be accomplished by folding in half, one end over the other end. Each folded liner shall be placed within its protective cover.

5.1.2 Commercial preservation. Each liner shall be preserved in accordance with ASTM D 3951.

5.2 Packing. Packing shall be level A, B, or Commercial as specified (see 6.2).

5.2.1 Level A packing. Each liner, preserved as specified in 5.1.1, shall be packed in a close fitting wood box conforming to overseas type, style optional, grade A of PPP-B-601. Inside dimensions of each shipping container shall approximate 48 inches in length, 36 inches in width, and 12 inches in depth for intermediate section liners and 18 inches in depth for the end section liners. Approximate dimensions are furnished as a guide only. Each shipping container shall be closed in accordance with the appendix of PPP-B-601.

5.2.2 Level B packing. Each liner preserved as specified in 5.1.1, shall be packed in a snug fitting fiberboard container conforming to class weather-resistant, grade V13c, style FTC of PPP-B-636. Inside dimensions of each shipping container shall approximate 48 inches in length, 36 inches in width, and 12 inches in depth for intermediate section liners and 18 inches in depth for the end section liners. Approximate dimensions are furnished as a guide only. The container shall be closed and reinforced in accordance with the appendix of PPP-B-636.

5.2.3 Commercial packing. Each liner preserved as specified in 5.1, shall be packed in accordance with ASTM D 3951.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T00:42Z
Check the source to verify that this is the current version before use.

5.3 Palletization. When specified (see 6.2), tent liners, packed as specified in 5.1.1, 5.2.2 and 5.2.3, shall be palletized on a 4-way entry pallet in accordance with load type Ia of MIL-STD-147. Pallet types shall be type I (4-way entry), type IV, or type V in accordance with MIL-STD-147. Pallets shall be fabricated from wood groups I, II, III, or IV of MIL-STD-731. Each prepared load shall be bonded with primary and secondary straps in accordance with the bonding means C and D or film bonding means F or G. Pallet patterns shall be in accordance with the appendix of MIL-STD-147. Interlocking of loads shall be effected by reversing the pattern of each course.

5.4 Marking. In addition to any special marking required by the contract or purchase order, shipping containers shall be marked in accordance with MIL-STD-129 or ASTM D 3951 as applicable.

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory.)

6.1 Intended use. The insulated tent liner sections are designed for use with various components of the tent, extendable, modular, personnel (TEMPER).

6.2 Acquisition requirements. Acquisition documents must specify the following:

a. Title, number, and date of this specification.
b. Type, required (see 1.2).
c. Issue of DODISS to be cited in the solicitation, and if required, the specific issue of individual documents referenced (see 2.1.1 and 2.2).
d. When a first article is required (see 3.1, 4.3, and 6.3).
e. Levels of preservation and packing (see 5.1 and 5.2).
f. When palletization is required (see 5.3).

6.3 First article. When a first article is required, it shall be inspected and approved under the appropriate provisions of Federal Acquisition Regulation (FAR) 52.209. The first article should be a preproduction sample. The contracting officer should specify the appropriate type of first article and the number of units to be furnished. The contracting officer should also include specific instructions in acquisition documents regarding arrangements for selection, inspection, and approval of the first article.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T00:42Z
Check the source to verify that this is the current version before use.

6.4 Subject term (key word) listing.

Camp
Canvas
Shelter

6.5 Changes from previous issue. Marginal notations are not used in this revision to identify changes with respect to the previous issue due to the extensiveness of the changes.

Custodians:

Army - GL
Navy - NU

Preparing activity:

Army - GL

(Project 8340-0541)

Review activities:

Army - MD
DLA - CT

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T00:42Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS

1. The preparing activity must complete blocks 1, 2, 3, and 8. In block 1, both the document number and revision letter should be given.
2. The submitter of this form must complete blocks 4, 5, 6, and 7.
3. The preparing activity must provide a reply within 30 days from receipt of the form.

NOTE: This form may not be used to request copies of documents, nor to request waivers, or clarification of requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

I RECOMMEND A CHANGE:	1. DOCUMENT NUMBER	2. DOCUMENT DATE (YYMMDD)
	MIL-T-44222A	1991 March 1

3. DOCUMENT TITLE
TENT LINER SECTIONS; INSULATED (TEMPER)

4. NATURE OF CHANGE *(Identify paragraph number and include proposed rewrite, if possible. Attach extra sheets as needed.)*

5. REASON FOR RECOMMENDATION

6. SUBMITTER

a. NAME (Last, First, Middle Initial)	b. ORGANIZATION
c. ADDRESS (Include Zip Code)	d. TELEPHONE (Include Area Code) (1) Commercial (2) AUTOVON (If applicable)
	7. DATE SUBMITTED (YYMMDD)

8. PREPARING ACTIVITY

a. NAME	b. TELEPHONE (Include Area Code)
U.S. Army Natick RD&E Center	(1) Commercial: 508-651-4531 (2) AUTOVON: 256-4531
c. ADDRESS (Include Zip Code) Commander, U.S. Army Natick RD&E Center ATTN: STRNC-UXT Natick, MA 01760-5017	IF YOU DO NOT RECEIVE A REPLY WITHIN 45 DAYS, CONTACT: Defense Quality and Standardization Office 5203 Leesburg Pike, Suite 1403, Falls Church, VA 22041-3466 Telephone (703) 756-2340 AUTOVON 289-2340

DD Form 1426, OCT 89 NATICK OP, APR 90 Previous editions are obsolete. 198/290

Source: https://assist.dla.mil -- Downloaded: 2020-10-22T00:42Z
Check the ASSIST database prior to any use to ensure document is the correct revision before use.