MIL-C-63106A(AR)
AMENDMENT 1
6 April 1984

MILITARY SPECIFICATION

COUNTERMEASURE, CHAFF: M-1

This Amendment forms a part of Military Specification MIL-C-63106A(AR), dated 14 June 1983 and is approved for use by the US Army Armament, Munitions and Chemical Command and is available for use by all Departments and Agencies of the Department of Defense.

PAGE 1

2.1, Government documents: Under Specification, Military Add:

"MIL-STD-410 - Nondestructive Testing Personnel.
MIL-STD-453 - Inspection Radiographic.
MIL-C-81467 - Chaff, Countermeasure RR-129/LAE-29A".

PAGE 2

Add new paragraph 3.7:

"3.7 Radiographic examination. Chaff samples shall not exhibit any indication of loose, deformed, diffused components, voids, discontinuities or intermingling of adjacent bands i.e. there shall be a sharpline of demarcation between adjacent bands. Minimum optical density of each radiograph in the area being inspected shall not be less than 1.25 and shall be within a density range that will permit proper identification of defects. (A radiographic standard shall be established prior to lot acceptance testing)."

PAGE 4

TABLE I, Under Countermeasure Chaff, M1 (Dwg. 9311402), Examination of Defects, add: "Radiographic examination, 3.9, 4.5.5".

FSC 5865

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:13Z
Check the source to verify that this is the current version before use.

PAGE 9

4.4.2.4, Add:

Major 104: Chaff material measurement and coatings, 0.40%, 3.2, (a).

NOTE (a): See MIL-C-81467, Para. 3.2.

PAGE 11

4.4.2.6, Add: Major 104: Radiographic examination, 0.40%, 3.2, 4.5.5.

PAGE 17

Add new paragraph 4.5.5 and 4.5.5.1:

"4.5.5 Radiographic examination. Radiographic equipment procedures and evaluation shall be in accordance with MIL-STD-453. Radiographic personnel shall be qualified in accordance with MIL-STD-410. Prior to functional testing, the chaff samples shall be examined in accordance with MIL-STD-453 procedure. Two exposures shall be made of each chaff, each forming a 90 degree angle with the other and with the longitudinal axis of the chaff. Examination of the radiographic shall be made to determine compliance with the applicable requirement (see 3.9). Any chaff deemed unacceptable shall be cause for lot rejection. (Non-Destructive)

4.5.5.1 Radiograph sensitivity. The penetrameter used in the application specified in MIL-STD-453 shall be designed and constructed to insure a 2.0 percent sensitivity or better. The penetrameter shall be made of plastic having a density equal to the chaff. One penetrameter shall be used on each film exposed. The film density measurement shall be made with a photo electric densitometer calibrated to National Bureau of Standards (Photographic Step Tablet)".

Custodian:
Army-AR

Preparing activity:
Army-AR

(Project 5865-A043)

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:13Z
Check the source to verify that this is the current version before use.