INCH-POUND
MIL-I-24092/3A
21 September 1993
SUPERSEDING
MIL-I-24092/3
4 May 1989

MILITARY SPECIFICATION SHEET

INSULATING VARNISH, SOLVENT CONTAINING, BAKING, SEMI-RIGID, FOR DIP PROCESSING, GRADE CBH, CLASS 130 TO 200 THERMAL CLASS

This specification is approved for use by all departments and agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specification sheet and the issue of the following specification listed in that issue of the Department of Defense Index of Specifications and Standards (DODISS) specified in the solicitation: MIL-I-24092.

REQUIREMENTS:

1. Grade - CBH. Clear, solvent containing baking varnish that cures to a semi-rigid insulating film.

2. Class - 130 to 200 The cured varnish shall meet the requirements of the specified thermal class when determined in accordance with MIL-I-24092.

3. Composition - I or II. Composition I, which consists of aromatic solvent, is normally suitable for most varnish treating facilities. However, composition II shall be specified for those varnish treating facilities which are located in areas requiring controlled emission of aromatic hydrocarbons.

4. The varnish shall meet the qualification and quality conformance requirements specified in tables I and II herein when tested in accordance with MIL-I-24092.

AMSC N/A
FSC 5970
DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 202610-19T19:00Z
Check the source to verify that this is the current version before use.

TABLE I. Qualification requirements, grade CBH.

Characteristics (tests)	Units	Requirements
Storage life	Months, minimum	12
Nonvolatiles	Percent, minimum	40
Flash point	°C, minimum	26
Drying time at 150°C	Minutes, maximum	120
Viscosity at 20 r/min	Centipoise	200 to 1200
Build, as received	Mil, minimum	1.0
Dielectric strength:		
96/23/50	Volts per mil, minimum	2000
96/23/96	Minimum	1500
24/23/water	Minimum	1500
Bond strength:		
at 23°C	Pounds force, minimum	10
at 150°C	Pounds force, minimum	3
Thermal endurance (M2, K2) only:		
Class 130	Temperature index, °C, minimum	130
Class 155	Temperature index, °C, minimum	155
Class 180	Temperature index, °C, minimum	180
Class 200	Temperature index, °C, minimum	200
Salt water proofness	Hours, minimum	100
Hydrolytic stability	Maximum	To be determined
Chemical resistance:		
Hydraulic fluid	Percent decrease in bond strength, maximum	50
Lubrication oil		50
Cleaning fluid		50
Distilled water		50
Detergent solution		50

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T19:00Z
Check the source to verify that this is the current version before use.

TABLE II. Quality conformance requirements, grade CBH

Characteristics (tests)	Units	Requirements
Nonvolatiles	Percent of qualification value	±10
Drying time at 150°C	Minutes, maximum	130
Viscosity at 20 r/min	Centipoise, percent of qualification value	±20
Build as received	Mil, minimum	0.9
Specific gravity	Percent of as-received value	±10
Bond strength at 23°C	Pounds force, minimum	20

NOTE:

Part or Identifying Number (PIN). Part number shall be M24092/3-(dash number indicating thermal class) For example, M24092/3-155 describes a material meeting the requirements of this specification and having class 155 thermal endurance. The pin shall be the same format as specified in MIL-I-24092.

Custodians:
Army - ER
Navy - SH
Air Force - 11

Review activities:
Army - MI, AR
Navy - EC, YD, OS
Air Force - 99
DLA - GS, DS

User activities:
Army - ME
Navy - MC, AS

Preparing activity:
Navy - SH
(Project 5970-1076)

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T19:00Z
Check the source to verify that this is the current version before use.