MILITARY SPECIFICATION

CATHETER, PERITONEAL DIALYSIS, PLASTIC, DISPOSABLE, WITH Y-CONNECTOR AND ROLLER CLAMP, 11 INCH, 11 FR

This specification is mandatory for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 This specification covers a sterile, disposable, plastic peritoneal dialysis catheter with metal disc retainer, a connector tube, and metal stylet. The connector tube includes a Y-joint with a resealable injection site and a clamp. By means of the connector tube this catheter shall be suitable for attachment to the peritoneal dialysis administration set.

2. APPLICABLE DOCUMENTS

2.1 The following documents of the issue in effect on date of invitation for bids or request for proposals form a part of this specification to the extent specified herein:

SPECIFICATIONS

Federal

MMM-A-250	Adhesive, Water-Resistant, (for Sealing Fiberboard Boxes).
PPP-B-566	Boxes, Folding, Paperboard.
PPP-B-585	Boxes, Wood, Wirebound.
PPP-B-601	Boxes, Wood, Cleated-Plywood.
PPP-B-621	Boxes, Wood, Nailed and Lock-Corner.
PPP-B-636	Box, Fiberboard.
PPP-T-76	Tape, Pressure-Sensitive Adhesive Paper, (for Carton Sealing).

Military

MIL-S-36586	Sterilization Strip Test, Bacterial Spore.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:59Z
Check the source to verify that this is the current version before use.

STANDARDS

Military

MIL-STD-105 Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129 Marking for Shipment and Storage.

DRAWING

DEFENSE PERSONNEL SUPPORT CENTER (DPSC)

24224 CATHETER, PERITONEAL DIALYSIS, Disposable with Y-connector

(Copies of specifications, standards, and drawing required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposals shall apply:

U.S. PHARMACOPEIAL CONVENTION, INC.

Pharmacopeia of the United States (U.S.P.)

(Application for copies should be addressed to the Mack Publishing Company, Easton, Pa. 18042).

U.S. DEPARTMENT OF HEALTH, EDUCATION AND WELFARE

Federal, Food, Drug and Cosmetic Act (FDA) and Regulations Promulgated thereunder.

(Applications for copies should be addressed to the Food and Drug Administration, Washington, D. C. 20204).

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:59Z
Check the source to verify that this is the current version before use.

3. REQUIREMENTS

3.1 Materials.

3.1.1 Metal. The stylet shall be fabricated of AISI type 304 stainless steel. The retaining disc shall be made of a suitable aluminum alloy.

3.1.2 Plastics and rubber. The plastics and rubber shall be of high quality and suitable in all respects for the intended purpose. All plastic and rubber parts shall be sterilizable, free from pyrogens, inert, and safe (non-toxic) when tested as specified in 4.4.4, 4.4.5, and 4.4.6. Those plastic and rubber parts coming in contact with solutions being administered shall contain no more than 5 parts per million (ppm) total of lead, barium, and cadmium as specified in 3.6.

3.2 Style, design and dimensions. The peritoneal dialysis catheter shall consist of a catheter with an aluminum disc retainer, stylet, and a connector tube. The connector tube shall consist of two pieces of polyvinyl chloride tubing which are joined at the center by a Y-joint. The remaining arm of the Y-joint shall function as an injection site. The proximal end of the connector tube shall have a straight, plastisol, female connector. A similar L-shaped connector shall be present at the distal end of the connector tube. Between the Y-joint and the straight connector there shall be a roller clamp. The style, design, and dimensions of the catheter and its accessories shall be in conformance with Defense Personnel Support Center (DPSC) Drawing No. 24224.

3.2.1 Catheter. The catheter shall be fabricated of nylon. There shall be at the distal end four rows of perforations, each row containing 25 perforations. The catheter shall be free from loose particles. The length of the catheter shall be such that the trocar point of the stylet shall just protrude when the catheter is seated against the handle of the stylet.

3.2.2 Retainer. The retainer shall be a one-inch diameter aluminum disc. There shall be a 1/8-inch hole in the center of the disc to accommodate the catheter. Around the hole at four points, 90° apart, there shall be radial slits in the disc for a distance of 5/32 inch. This creates four tangs. The central portion of the disc shall also have a slight convexity. This design allows the retainer disc, convexity up, to be slipped in one direction only over the catheter. The spring action of the four tangs biting into the catheter prevents reverse motion of the disc toward the proximal end of the catheter.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:59Z
Check the source to verify that this is the current version before use.

3.2.3 Stylet. The stylet shall have a trocar point and be made of austenitic stainless steel. The proximal end shall have a molded nylon handle in order to provide control in manipulating the stylet.

3.2.4 Connector tube. The connector tube shall consist of two six-inch lengths of clear polyvinyl chloride tubing joined at the center by a Y-joint. The Y-joint shall be made of high-impact polystyrene. The free arm of the Y-joint shall function as an injection site and have a resealable rubber cap. There shall be two permanently affixed plastisol type of polyvinyl chloride plastic female connectors present. The connector at the proximal end shall be straight; that at the distal end shall be L-shaped.

3.2.4.1 Rubber stopper. Rubber stopper shall be fabricated from material as specified in 3.1.2. The stopper shall be capable of resealing subsequent to puncture with a non-siliconized 18 gage needle cannula. When tested for resealing as specified in 4.4.8, there shall be no falling drop within ten seconds.

3.3 Compatibility. The materials of which the catheter set are made shall not react with, nor be acted upon by, the liquids with which they will be in contact during normal use and operation. Furthermore, there shall not be any materials incorporated in the set which will cause any harmful or deleterious effect on the patient when the set is used for the intended purpose.

3.4 Leakage and separation of set. The connector tube shall be tested for leakage and separation of connectors at 30 pounds per square inch gage (psig) for 15 minutes as specified in 4.4.1. Connector tubes which show leakage or separation of the connectors or Y-joint shall be rejected.

3.5 Security of assembly.

3.5.1 The female connectors or Y-joint shall not separate or loosen from the connector tubes when subjected to a load of two pounds for 15 minutes as specified in 4.4.2.1.

3.5.2 The L-connector shall not separate or loosen from the catheter when the latter has been inserted to a depth of one-half inch into the L-connector and then a load of one pound applied for 15 minutes as specified in 4.4.2.2.

3.5.3 The straight connector shall not separate or loosen from a male Luer adapter of the dimensions specified in Figures 1 and 2 of ANSI Standard Z70.1 when a one-pound load is applied for 15 minutes as specified in 4.4.2.3.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:59Z
Check the source to verify that this is the current version before use.

3.6 Extractable metals. There shall be no more than 5 ppm total of lead, barium, and cadmium in the plastic components when extracted and tested as specified in 4.4.3.

3.7 Sterility, freedom from pyrogens, and safety. All equipment shall be sterile, pyrogen-free, and safe (non-toxic) when tested as specified in 4.4.4, 4.4.5, and 4.4.6, respectively.

3.8 Animal implantation test. The plastic catheter only shall be tested, and shall show no gross or microscopic evidence of toxicity or adverse tissue reaction, when tested as specified in 4.4.7.

3.9 Certificates of sterility, freedom from pyrogens, safety and animal implantation tests. A certificate listing all lot or control numbers shall state that representative samples from each lot or control have been tested and found to be sterile and free from pyrogens, and have passed the animal implantation test. This certificate shall include the specific tests performed and the tests results. The record of the animal implantation test and its results shall be certified by the pathologist who performed or supervised performance of the animal implantation test. For destination inspection, certificates shall be submitted by the contractor directly to Defense Personnel Support Center, Directorate of Medical Materiel, Technical Operations Division, 2800 South 20th Street, Philadelphia, Pa. 19101, Attention: Quality Assurance Branch, and one copy of each shall be forwarded with each shipment to the consignee. For source inspection, certificates shall be furnished to the procuring activity via the government inspector.

3.10 Workmanship. Workmanship shall be first class throughout. The catheter set shall be free from defects which detract from its appearance or impair its serviceability. The catheter and connector tube shall show smooth outer and inner surfaces and be free from burrs, chips, soils, slivers, or other foreign matter. The surface of the stylet also shall be smooth and free from burrs, chips, soils, slivers, or other foreign matter.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:59Z
Check the source to verify that this is the current version before use.

4.1.1 Inspection. Inspection, as used in this specification is defined as both examination (such as visual or auditory investigation without the use of special laboratory appliances or procedures) and testing (determination by technical means of physical and chemical properties) of the item.

4.2 Sampling.

4.2.1 For examination. Sampling for examination shall be conducted in accordance with MIL-STD-105. The inspection levels and acceptable quality levels shall be as indicated in Table I. The unit of product for examination purposes shall be one catheter complete with accessories.

Table I. Sampling for Examination

Type of defect	Inspection level	AQL (percent defective)*
Major	I	1.0
Minor	I	2.0

*If acceptance number is not exceeded, lot shall be acceptable. If rejection number is equaled or exceeded, inspection at level II may be performed to determine final acceptance or rejection.

4.2.2 Sampling for tests. Sampling for tests shall be conducted in accordance with MIL-STD-105 and as indicated in Table II. Where feasible, the same sample shall be used for the determination of two or more test characteristics.

Table II. Sampling for Tests

Component	Characteristic	Requirement	Test procedure	Inspection level	AQL (percent defective)
Connector tube	Leakage & separation of set	3.4	4.4.1	S-2	*
Rubber stopper	Reseal test	3.2.4.1	4.4.8	S-2	*
Connector tube	Security of assembly	3.5.1	4.4.2.1	S-2	*
L-connector to catheter	Security of assembly	3.5.2	4.4.2.2	S-2	*

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:59Z
Check the source to verify that this is the current version before use.

Table II. Sampling for Tests (Con't)

Component	Characteristic	Requirement	Test procedure	Inspection level	AQL (percent defective)
Straight connector	Security of assembly	3.5.3	4.4.2.3	S-2	*
Connector tube and catheter	Extractable metals	3.6	4.4.3	S-1	*
Unit of product	Sterility	3.7	4.4.4	S-3	*
Unit of product	Freedom from pyrogens	3.7	4.4.5	S-1	*
Unit of product	Safety	3.7	4.4.6	S-1	*
Catheter	Animal implantation	3.8	4.4.7	S-2	*

*Acceptance number shall be zero for all sample sizes.

4.3 Examination. The catheter complete with accessories shall be examined to determine compliance with specification requirements. Examination shall be conducted in accordance with MIL-STD-105 and the following classification of defects. Examination shall include but shall not be limited to the defects listed in Table III.

Table III. Classification of Defects

Categories	Defects
Major	
101	Presence of foreign materials, loose particles.
102	Split in catheter.
103	Absence of required perforations in catheter.
104	Defective connectors.
105	Stylet of improper length.
106	Stylet does not fit well in catheter.
107	Defective Y-joint.
Minor	
201	Stylet not free of burrs.
202	Retainer does not fit and grip catheter securely.
203	Faces at trocar point do not meet to form keen apices.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:59Z
Check the source to verify that this is the current version before use.

4.4 Tests. Tests shall be conducted to determine compliance with specification requirements.

4.4.1 Leakage and separation of set. The connector tube shall be attached at one end to a plug gage of the type shown in figure 5 of ANSI Standard Z70.1 (except that the gage shall have been provided with a fluid path) and a water pressure source having a pressure gage. The water is allowed to flow and displace all air. The other end is then clamped shut and the water pressure is allowed to increase. A pressure of 30 psig shall be applied for 15 minutes.

4.4.2 Security of assembly.

4.4.2.1 The bond of the connectors and the Y-joint to the two connecting tubes shall be tested by clamping or lashing one connector and gradually applying a two-pound load to the other connector. The two pound load shall be withstood for 15 minutes without evidence of separation of the connectors or Y-joint from the two connecting tubes. The L-connector is secured at the elbow to avoid distortion under load.

4.4.2.2 The bond of the L-connector to the catheter shall be tested in an identical manner as described in 4.4.2.1 except that a fresh proximal end of the catheter shall be used by cutting off and discarding the proximal one inch of the catheter. The catheter shall be inserted into the L-connector to a depth of one-half inch and a one-pound load gradually applied and maintained for 15 minutes.

4.4.2.3 The attachment of the straight connector to a male Luer adapter shall be subjected to a one-pound load for 15 minutes. The male Luer adapter shall be held in the same line as the straight connector and connector tubing. The male Luer adapter shall have the dimensions of Figures 1 and 2 of ANSI Standard Z70.1.

4.4.3 Extractable metals. A 2-gram composite sample shall be obtained from each catheter set to be tested. It shall be made up in the following approximate proportions of the components involved:

L-connector	7%
Straight connector	7%
Y-joint	7%
Tubing	29%
Catheter	50%
	100%

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:59Z
Check the source to verify that this is the current version before use.

The material shall be cut into small slivers, and so that no thickness exceeds 3 mm, and eluted for 72 hours at 50 degrees Centigrade (°C), 24 hours at 70° C, or 60 minutes at 121° C in two menstrua: 0.9% sodium chloride and cotton seed oil. Each gram of the material shall be covered with 5 ml of the menstruum. The usual amount shall be 10 grams of plastic covered by 50 ml of menstruum. The menstrua are collected, agitated after elution, and then submitted to spectrographic analysis for lead, barium, and cadmium. The metals are reported in parts per million in the eluate. Thus 1.0 ppm in the eluate is equivalent to extracting 1.0 mg from 200 g test material dispensed in 1,000 ml elution menstruum.

4.4.4 Sterility. Testing for sterility on exterior and interior surfaces shall be in accordance with the method specified in the U.S.P. Procedural Details for Sterility Tests of Class B, Type II, Inoculated Products, and for Parenteral Devices. As an alternate, testing for sterility shall be in accordance with the method specified in the U.S.P. Procedural Details for Sterility Tests, Class B, Type II, Inoculated Carrier, and Parenteral Devices, except that the inoculated carrier shall contain sterilization test strips carrying spores of Bacillus subtilis var. globigii and Bacillus stearothermophilus, Type B of MIL-S-36586.

4.4.5 Freedom from pyrogens. Samples of the catheter set shall be tested for freedom from pyrogens in accordance with the U.S.P. for Transfusion and Infusion Assemblies.

4.4.6 Safety (non-toxicity) test. The catheter sets shall be tested for safety in accordance with the U.S.P. for Transfusion and Infusion Assemblies.

4.4.7 Animal implantation test. Samples of the catheter only shall be tested in accordance with the method given in the current edition of the U.S.P. for Implantation Test, except for the following changes: Last paragraph, second line, after "72 hours" add "and not to exceed 144 hours." Last paragraph, third and fourth sentences delete in entirety and substitute: "The tissues surrounding the implants shall be examined, both grossly and microscopically, by a pathologist certified by the American Board of Pathology or the American College of Veterinary Pathologists."

4.4.8 Reseal test (rubber stopper). This test shall be applied to those samples previously subjected to the leakage test (4.4.1). The finished tubes shall be connected to a full, suitably vented, one liter bottle of water, saline solution, or dextrose solution. The bottle shall be hung in a normal manner so that the liquid level in the bottle shall be three feet above the injection site. The tube shall be completely filled with liquid and sealed at the male needle adapter. The "Y" shall be placed in a horizontal position and shall be punctured thru the stopper with an 18 gage non-siliconized needle and the needle immediately withdrawn.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:59Z
Check the source to verify that this is the current version before use.

5. PREPARATION FOR DELIVERY

5.1 Packaging.

5.1.1 Unit of issue. One each catheter, as specified, constitutes one unit of issue.

5.1.2 Packaging quantities. The number of units of issue indicated in Table IV shall be packaged in each unit, intermediate, and exterior container, as applicable, for the required level of protection specified in the procurement document.

Table IV. Packaging Quantities

Unit package	Intermediate package	Exterior container
1 unit	10 units	120 units

5.1.2.1 Packing variation permitted. If the required number of units in the entire shipment is less than the number of units specified to be overpacked in an exterior container, such units may be packed in an exterior container of suitable size and design, acceptable to a common carrier, which shall insure safe delivery to destination.

5.1.3 Level A.

5.1.3.1 Unit package. Each unit shall be mounted on a card to prevent binding of the tubing and to prevent movement of the stylet and the aluminum disk. The unit shall be further packaged in a sealed peel back type container with one transparent face, capable of maintaining sterility of contents until manually opened.

5.1.3.2 Intermediate package. Intermediate package shall be a box of appropriate size and design constructed in accordance with PPP-B-636, type CF, class weather-resistant. Boxes shall be closed by taping the top and bottom flaps with 2 inch wide tape conforming to PPP-T-76. Closing of bottom flap with adhesive conforming to MMM-A-250 or metal stitches is permitted.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:59Z
Check the source to verify that this is the current version before use.

5.1.4 Level C. Units shall be packaged in standard commercial containers of the size and kind commonly used, which will afford the degree of protection required for shipment and use of the product for its intended purpose.

5.2 Packing.

5.2.1 Level A.

5.2.1.1 Exterior container. Exterior container shall be designed for a type 2 load and constructed in accordance with PPP-B-585, class 3, style 3; PPP-B-601, overseas type; PPP-B-621, class 2; or PPP-B-636, class weather-resistant, grade V3. Closure and strapping shall be as specified in the appendix of the applicable box specification.

5.2.2 Level B.

5.2.2.1 Exterior container. Exterior container shall be designed for a type 2 load and constructed in accordance with PPP-B-585, class 1, style 3; PPP-B-601, domestic type; PPP-B-621, class 1; or PPP-B-636, class domestic. Closure shall be as specified in the appendix of the applicable box specification.

5.2.3 Level C. The subject commodity shall be packed in substantial commercial containers of the type, size, and kind commonly used for the purpose, so constructed as to insure acceptance and safe delivery by common or other carriers, at the lowest rate, to point of delivery called for in the contract or purchase order.

5.3 Marking.

5.3.1 Unit package. Labeling shall meet the requirements of the Federal Food, Drugs, and Cosmetic Act and in addition markings shall be in accordance with MIL-STD-129. The method of sterilization (G-Gas, R-Radiation, S-Steam, D-Dry Heat Sterilization) shall be shown following the level of packaging and date of packaging. Example "A-4/70-G." Final sterilization shall be on or after indicated packaging date. Instruction for use shall be provided with each unit package. Marking shall also include the lot (control) number and the following legends or similar statement:

"STERILITY GUARANTEED UNLESS PACKAGE IS DAMAGED OR OPENED"

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:59Z
Check the source to verify that this is the current version before use.

5.3.2 Intermediate package. Each intermediate package shall be marked in accordance with MIL-STD-129. Contract or purchase order number, lot (control) number and name of contractor shall be shown. In addition, method of sterilization markings as specified in 5.3.1 shall be shown.

5.3.3 Exterior container. Exterior container shall be marked in accordance with MIL-STD-129. The lot (control) number and method of sterilization markings as specified in 5.3.1 shall be shown.

Note: Each lot number shall be traceable to a specific sterilizer charge.

6. NOTES

6.1 Ordering data. Procurement documents should specify the following:

(a) Title, number, and date of this specification.
(b) Selection of applicable levels of packaging and packing (see 5.1 and 5.2)
(c) Applicable Federal stock number.

6.2 This specification is applicable to the following Federal Supply Catalog items:

6515-458-8410	CATHETER, PERITONEAL DIALYSIS, Disposable, with Y-connector and Roller Clamp, 11 inch, 11 Fr.

To be used with:

6515-799-7768	ADMINISTRATION SET, PERITONEAL DIALYSIS, Plastic

Custodians:
Army - MD
Navy - MS
Air Force - 03

Preparing activity:
Defense Supply Agency - DM

Project No. 6515-1454

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:59Z
Check the source to verify that this is the current version before use.

Review activities:
Army - MD
Navy - MS
Air Force - 03

Review information is current as of the date of this document. For future coordination of changes to this document, draft circulation should be based on the information in the current DODISS.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:59Z
Check the source to verify that this is the current version before use.

SPECIFICATION ANALYSIS SHEET

Form Approved
Budget Bureau No. 22-R255

INSTRUCTIONS: This sheet is to be filled out by personnel, either Government or contractor, involved in the use of the specification in procurement of products for ultimate use by the Department of Defense. This sheet is provided for obtaining information on the use of this specification which will insure that suitable products can be procured with a minimum amount of delay and at the least cost. Comments and the return of this form will be appreciated. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments and suggestions submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or serve to amend contractual requirements.

SPECIFICATION

MIL-C-36670 FSN:

ORGANIZATION

CITY AND STATE | CONTRACT NUMBER

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE SPECIFICATION CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY SPECIFICATION REQUIREMENT CONSIDERED TOO RIGID

3. IS THE SPECIFICATION RESTRICTIVE?

☐ YES ☐ NO *(If "yes", in what way?)*

4. REMARKS *(Attach any pertinent data which may be of use in improving this specification. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity)*

SUBMITTED BY *(Printed or typed name and activity - Optional)* | DATE

DD FORM 1 JAN 66 1426 REPLACES EDITION OF 1 OCT 64, WHICH MAY BE USED.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:59Z
Check the source to verify that this is the current version before use.

CAUTION

NOTICE TO BIDDERS/OFFERORS

DO NOT CONDITION OR BASE YOUR BID/OFFER ON ANY CURRENT PROCUREMENT ON THE INFORMATION SUBMITTED ON THIS FORM SINCE ANY CHANGES OR DELETIONS IN THE SPECIFICATIONS MAY RENDER YOUR BID/OFFER NON-RESPONSIVE IN WHICH CASE IT CANNOT BE CONSIDERED FOR AWARD.

Fold

DEFENSE PERSONNEL SUPPORT CENTER
2800 SOUTH 20TH STREET
PHILADELPHIA, PA. 19101

DEFENSE SUPPLY AGENCY
OFFICIAL BUSINESS

POSTAGE AND FEES PAID
DEFENSE SUPPLY AGENCY

HEADQUARTERS, DEFENSE PERSONNEL SUPPORT CENTER
ATTN: DIRECTORATE OF MEDICAL MATERIEL, CODE ATT
2800 SOUTH 20TH STREET
PHILADELPHIA, PA. 19101

Fold

DPSC FORM 2418
MAR 68

EDITION AUG 66, WILL BE USED UNTIL EXHAUSTED

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:59Z
Check the source to verify that this is the current version before use.