MILITARY SPECIFICATION

SYRINGE, ANTERIOR CHAMBER IRRIGATING, GLASS NOZZLE

This specification is mandatory for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers a Dougherty syringe, with glass nozzle, for irrigation of the anterior chamber of the eye.

2. APPLICABLE DOCUMENTS

2.1 The following documents, of the issue in effect on date of invitation for bids or request for proposals, form a part of this specification to the extent specified herein:

SPECIFICATIONS

Federal

MMM-A-250	Adhesive, Water-Resistant (for sealing Fiberboard Boxes).
PPP-B-566	Boxes, Folding, Paperboard.
PPP-B-585	Boxes, Wood, Wirebound.
PPP-B-601	Boxes, Wood, Cleated-Plywood.
PPP-B-621	Boxes, Wood, Nailed and Lock-Corner.
PPP-B-636	Box, Fiberboard.
PPP-B-676	Boxes, Set-Up.
PPP-T-76	Tape, Pressure-Sensitive Adhesive Paper, (for Carton Sealing).

STANDARDS

Federal

FED-STD-601	Rubber: Sampling and Testing.
FED-STD-626	Glassware: Methods for Sampling and Testing.

FSC 6515

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:59Z
Check the source to verify that this is the current version before use.

Military

MIL-STD-105 Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129 Marking for Shipment and Storage.

DRAWING

Defense Personnel Support Center (DPSC)

20315 Syringe, Anterior Chamber Irrigating, Glass Nozzle

(Copies of specifications, standards, and drawing required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

3. REQUIREMENTS

3.1 Material.

3.1.1 Nozzle. Nozzle shall be fabricated from clear borosilicate glass of the best quality. Glass shall be heat and chemical resistant. The distal tip of nozzle shall be colored blue.

3.1.2 Bulb. The bulb shall be fabricated from natural latex or synthetic rubber, of the best quality, suitable for the purpose intended.

3.2 Style, design and dimensions. Shall be a syringe of the Dougherty design, with a curved, glass nozzle. The bulb portion of the syringe shall have a capacity of one fluid ounce. Syringe shall be suitable for use in irrigation of the anterior chamber of the eye. Syringe assembly shall be in accordance with DPSC Drawing 20315, for type I or type II bulb design.

3.3 Resistance to aging. The rubber bulb shall not soften, embrittle, become sticky or tacky, or lack resilience when tested as specified in 4.4.1.

3.4 Annealing. The glass nozzle (cannula) shall be examined for strain as specified in 4.4.2. A moderate amount of evenly distributed longitudinal strain shall be acceptable. Any ring strain or severe longitudinal strain shall be cause for rejection.

3.5 Boiling test. The glass nozzle shall not exibit chipping or cracking when subjected to the boiling test described in 4.4.3.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:59Z
Check the source to verify that this is the current version before use.

3.6 Thermal shock. The glass nozzle shall not crack or break when subjected to the thermal shock test as specified in 4.4.4.

3.7 Identification marking. The syringe shall be clearly and legibly marked with the manufacturer's name or registered trademark.

3.8 Workmanship. Workmanship shall be first class throughout. Syringes shall be free from defects which detract from their appearance or may impair their serviceability.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Inspection. Inspection, as used in this specification, is defined as both examination (such as visual or auditory investigation without the use of special laboratory appliances or procedures) and testing (determination by technical means of physical and chemical properties) of the item.

4.2 Sampling.

4.2.1 For examination. Sampling for examination shall be conducted in accordance with MIL-STD-105, and as indicated in Table I. Unit of product for examination purposes shall be one syringe.

Table I. Sampling Criteria for Examination

Type Defect	Inspection Level	AQL (percent defective)
Major	II	1.0
Minor	II	4.0

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:59Z
Check the source to verify that this is the current version before use.

4.2.2 For tests. Sampling for tests shall be conducted in accordance with MIL-STD-105, and as indicated in Table II. Unit of product for test purposes shall be one syringe.

Table II. Sampling Criteria for Tests

Component	Characteristic	Rqmt.	Test procedure	Insp. level	AQL (percent defective)
Bulb	Accelerated aging test	3.3	4.4.1	S-2	*
Nozzle (cannula)	Annealing test	3.4	4.4.2	S-2	*
	Boiling test	3.5	4.4.3	S-2	*
	Thermal shock test	3.6	4.4.4	S-2	*
Syringe	Dimensions	3.2	- - -	S-2	2.5

* Acceptance number shall be zero for all sample sizes.

4.3 Examination. The syringes shall be examined to determine compliance with all the requirements contained in this specification. Examination shall be conducted as specified in Tables I and III. Inspection, however, shall not be restricted to defects listed in Table III. Any syringes in the sample containing one or more defects shall be rejected and if the number of defective syringes in any sample exceeds the acceptance number for the sample, the lot represented by the sample shall be rejected.

Table III. Classification of Defects

Categories	Defects
Critical	None defined.
Major	
101	Nozzle not assembled to bulb.
102	Nozzle tip not free from burrs and sharp edges.
103	Lumen of nozzle not free from obstructing particles.
104	Outside surface of nozzle not smooth or free from surface imperfections.
105	Rubber bulb not free from pits, cracks or holes.
106	Bulb not flexible (cannot be easily squeezed by one hand).
Minor	
201	Syringe not identified as specified in 3.7.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:59Z
Check the source to verify that this is the current version before use.

4.4 Tests. Tests shall be conducted, as necessary, to determine compliance with specification requirements.

4.4.1 Accelerated aging test. Syringes shall be subjected to the accelerated aging test described in method 7111 of Federal Test Method Standard No. 601, except that the rubber bulb shall be tested intact and the tensile strength and ultimate elongation tests will not be performed.

4.4.2 Annealing test. Glass parts shall be examined for strain with a polariscope that is constructed as described in method 420 of Federal Test Method Standard 626.

4.4.3 Boiling test. The glass nozzle taken for test shall be completely immersed in distilled water in a closed vessel having a small steam vent, and boiled continuously for 6 hours, boiling distilled water being added occasionally to compensate for evaporation losses. The nozzles shall be suspended in water so that they will not come in contact with the walls of the containers. The appearance of the nozzles shall be noted.

4.4.4 Thermal shock test. The glass nozzle selected as specified shall be immersed in tap water at 18.5 degrees centigrade (°C) ± 2.5 °C (65 degrees Fahrenheit [°F] ± 5° F), allowed to remain 10 minutes, then transferred suddenly into boiling water. This operation shall be repeated five times, and the nozzle examined for cracking or breaking.

5. PREPARATION FOR DELIVERY

5.1 Packaging.

5.1.1 Unit of issue. One syringe, as specified, constitutes one unit of issue.

5.1.2 Packaging quantities. The number of units of issue indicated in the following table shall be packaged in each unit, intermediate, and exterior container, as applicable, for the required level of protection specified in the procurement document.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:59Z
Check the source to verify that this is the current version before use.

Table IV. Packaging Quantities

Unit package	Intermediate package	Exterior container
1 unit	12 units	144 units

5.1.2.1 Packing variation permitted. If the required number of units in the entire shipment is less than the number of units specified to be overpacked in an exterior container, such units may be packed in an exterior container of suitable size and design, acceptable to a common carriers, which shall insure safe delivery to destination.

5.1.3 Level A.

5.1.3.1 Unit package. Each unit shall be packaged in a carton of appropriate size constructed in accordance with PPP-B-566 or PPP-B-676, except that commercial colors shall be acceptable. As an alternate, a clear plastic box of appropriate size and design may be used. Container shall be designed with suitable interior fittings or shall contain sufficient cushioning material to insure against shifting of, or damage to the contents. Closure shall be adequate to prevent spilling of contents under normal handling.

5.1.3.2 Intermediate package. Intermediate package shall be a box of appropriate size and design constructed in accordance with PPP-B-636, type CF, class weather-resistant. Boxes shall be closed by taping the top and bottom flaps with 2 inch wide tape conforming to PPP-T-76. Closing of bottom flap with adhesive conforming to MMM-A-250 or metal stitches is permitted.

5.1.4 Level C. Units shall be packaged in standard commercial containers of the size and kind commonly used, which will afford the degree of protection required for shipment and use of the product for its intended purpose.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:59Z
Check the source to verify that this is the current version before use.

5.2 Packing.

5.2.1 Level A.

5.2.1.1 Exterior container. Exterior container shall be designed for a type 2 load and constructed in accordance with PPP-B-585, class 3, style 3; PPP-B-601, overseas type; PPP-B-621, class 2; or PPP-B-636, class weather-resistant, grade V3. Closure and strapping shall be as specified in the appendix of the applicable box specification.

5.2.2 Level B.

5.2.2.1 Exterior container. Exterior container shall be designed for a type 2 load and constructed in accordance with PPP-B-585, class 1, style 3; PPP-B-601, domestic type; PPP-B-621, class 1; or PPP-B-636, class domestic. Closure shall be as specified in the appendix of the applicable box specification.

5.2.3 Level C. The subject commodity shall be packed in substantial commercial containers of the type, size, and kind commonly used for the purpose, so constructed as to insure acceptance and safe delivery by common or other carriers, at the lowest rate, to point of delivery called for in the contract or purchase order.

5.3 Marking.

5.3.1 Interior packages. Each unit package and each intermediate package shall be marked in accordance with MIL-STD-129. When labels are utilized, waterproofing shall be required only when applicable carton is fabricated of water-resistant material. Contract or purchase order number and name of contractor shall be shown.

5.3.2 Exterior container. Exterior container shall be marked in accordance with MIL-STD-129.

6. NOTES

6.1 Intended use. The syringes described herein shall be used to irrigate the anterior chamber of the eye.

6.2 This specification is intended to cover anterior chamber irrigating syringes which are normally procured to meet Military requirements. It does not include all types, sizes, etc., as indicated by the title, nor all types which are commercially available.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:59Z
Check the source to verify that this is the current version before use.

6.3 This specification covers Federal Stock Number 6515-342-8600 SYRINGE, ANTERIOR CHAMBER IRRIGATING, Glass Nozzle, appearing in the Federal Supply Catalog.

6.4 Supersession. This specification includes requirements of Purchase Description No. 4, dated 23 October 1968.

Custodians:
Army - MD
Navy - MS
Air Force - 03

Preparing activity:
Defense Supply Agency - DH

Project No. 6515-1466

Review activities:
Army - MD
Navy - MS
Air Force - 03

Review information is current as of the date of this document. For future coordination of changes to this document, draft circulation should be based on the information in the current DODISS.

☆U.S. GOVERNMENT PRINTING OFFICE: 1970-393-098/86203

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:59Z
Check the source to verify that this is the current version before use.

SPECIFICATION ANALYSIS SHEET

Form Approved
Budget Bureau No. 22-R255

INSTRUCTIONS: This sheet is to be filled out by personnel, either Government or contractor, involved in the use of the specification in procurement of products for ultimate use by the Department of Defense. This sheet is provided for obtaining information on the use of this specification which will insure that suitable products can be procured with a minimum amount of delay and at the least cost. Comments and the return of this form will be appreciated. Fold on lines on reverse side, staple in corner; and send to preparing activity. Comments and suggestions submitted on this form do not constitute or imply authorization to waive any portion of the referenced document (s) or serve to amend contractual requirements.

SPECIFICATION

MIL-8-36663 FSN:

ORGANIZATION

CITY AND STATE | CONTRACT NUMBER

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE SPECIFICATION CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY SPECIFICATION REQUIREMENT CONSIDERED TOO RIGID

3. IS THE SPECIFICATION RESTRICTIVE?

☐ YES ☐ NO *(If "yes", in what way?)*

4. REMARKS *(Attach any pertinent data which may be of use in improving this specification. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity)*

SUBMITTED BY *(Printed or typed name and activity - Optional)* | DATE

DD FORM 1 JAN 68 1426 REPLACES EDITION OF 1 OCT 64, WHICH MAY BE USED.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:59Z
Check the source to verify that this is the current version before use.

CAUTION

NOTICE TO BIDDERS/OFFERORS

DO NOT CONDITION OR BASE YOUR BID/OFFER ON ANY CURRENT PROCUREMENT ON THE INFORMATION SUBMITTED ON THIS FORM SINCE ANY CHANGES OR DELETIONS IN THE SPECIFICATIONS MAY RENDER YOUR BID/OFFER NON-RESPONSIVE IN WHICH CASE IT CANNOT BE CONSIDERED FOR AWARD.

Fold

DEFENSE PERSONNEL SUPPORT CENTER
2800 SOUTH 20TH STREET
PHILADELPHIA, PA. 19101

DEFENSE SUPPLY AGENCY
OFFICIAL BUSINESS

POSTAGE AND FEES PAID
DEFENSE SUPPLY AGENCY

HEADQUARTERS, DEFENSE PERSONNEL SUPPORT CENTER
ATTN: DIRECTORATE OF MEDICAL MATERIEL, CODE ATT
2800 SOUTH 20TH STREET
PHILADELPHIA, PA. 19101

Fold

DPSC FORM 2418
MAR 68

EDITION AUG 66, WILL BE USED UNTIL EXHAUSTED

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:59Z
Check the source to verify that this is the current version before use.