MILITARY SPECIFICATION

PRIMER, STAB: PA505 PARTS FOR, AND LOADING, ASSEMBLING AND PACKING

This Amendment forms a part of Military Specification MIL-P-63198 (AR), dated 14 October 1977, and is approved for use by the US Army Armament, Munitions and Chemical Command, and is available for use by all Departments and Agencies of the Department of Defense.

PAGE 14

4.5.2: Delete paragraph 4.5.2 in its entirety and substitute

"4.5.2 Determination of moisture content of lead azide. A tared dried aluminum dish 2 inches in diameter shall be covered with a sheet of polytetrafluoroethylene (PTFE) 2-1/2 inches square and sufficiently flat to form a tight cover. An accurately weighed portion of approximately 2 grams shall be transferred to the moisture dish while both the cover and dish are on the balance pan. The dish and contents shall be transferred to an oven and dried at 95 +/- 5 degrees C for 2 hours. The cover shall be placed in a desiccator during the drying period. After drying, the dish shall be quickly transferred to the desiccator and allowed to cool to room temperature. The PTFE cover shall be placed on the dish and the assembly weighed. The loss in weight shall be calculated to percentage of moisture in the lead azide has follows:

$$\text{Percentage of moisture} = \frac{100(A - B)}{A}$$

Where:

A = weight of specimen before drying
B = weight of specimen after drying

4.5.2.1 Determination of moisture content of lead azide, alternate method. The procedure is the same as paragraph 4.5.2 with the following exception. The sample shall be dried in a vacuum oven at a temperature of 95 +/- 5 degrees C and a pressure of 80 +/- 10 mm mercury for 45 minutes."

AMSC N/A

FSC 1375

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:23Z
Check the source to verify that this is the current version before use.

4.5.3: Delete paragraph 4.5.3 in its entirety and substitute:

"4.5.3 Determination of moisture content of primer mixture. Transfer weighed portion of approximately 1 gram of the primer mixture to a tared aluminum weighing dish provided with a polytetrafluroethylene (PTFE) cover while both the dish and cover are on the balance pan. Place the dish and contents with the cover removed in an oven maintained at 60 +/- 5 degrees C for 2 hours. The cover shall be placed in a desiccator during the drying period. After drying, transfer the dish and contents quickly to a desiccator and cool to room temperature. Replace the PTFE cover and weigh. Calculate the loss in weight of the dish, the cover, and the contents to percent moisture in the sample.

4.5.3.1 Determination of moisture content of primer mixture, alternate method. The procedure is the same as paragraph 4.5.3. with the following exception. The sample shall be dried in a vacuum oven at a temperature of 60 +/- 5 degrees C and a pressure 80 +/- 10 mm of mercury for 45 minutes."

Custodian:
Army-AR

Preparing activity
Army-AR

(Project 1375-A480)

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:23Z
Check the source to verify that this is the current version before use.