NOT MEASUREMENT SENSITIVE

A-A-59298
17 August 1998
SUPERSEDING
MIL-T-23142B
18 August 1977

COMMERCIAL ITEM DESCRIPTION

TAPE, PRESSURE SENSITIVE ADHESIVE

The General Services Administration has authorized the use of this commercial item description by all federal agencies.

1. SCOPE. This commercial item description (CID) covers the requirements for one type of pressure-sensitive tape to use as a separator to prevent galvanic attack between dissimilar metals.

2. SALIENT CHARACTERISTICS.

2.1 Material. The adhesive material shall be pressure sensitive, water insoluble, homogenous, and coated in a smooth and evenly distributed layer on one side of the backing. The adhesive shall require no solvent, heat, or any other preparation prior to application.

2.2 Breaking strength. The tape shall have a breaking strength of 15 pounds per inch width minimum when tested in accordance with FED-STD-191, Method No. 5102.

2.3 Adhesion. Adhesion of the tape to magnesium shall be 20 ounces per inch width minimum. Adhesion after exposure to petroleum base oils and di-ester fluids shall be 14 ounces per inch width minimum with 0.125 inch edge lifting permitted.

2.4 Finished tape. The tape shall be smoothly and uniformly wound in rolls, with the adhesive side in, on cores having an inside diameter of 3.000, +0.0625, -0.0000 inches. The core shall be rigid enough to prevent distortion of the roll under normal handling. The tape shall be one continuous strip and contain no bare spots or lumps.

Beneficial comments, recommendations, additions, deletions, clarification, etc. and any data which may improve this document should be sent to: Commander, Naval Air Warfare Center Aircraft Division, Code 414100B120-3, Highway 547, Lakehurst, NJ 08733-5100.

FSC 7510

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:09Z
Check the source to verify that this is the current version before use.

2.4.1 Width, length, and thickness. Unless otherwise specified (see 5.2), the width of the tape shall be one inch. The length of the tape in the rolls shall be a minimum of 72 yards. Thickness of the tape shall be 0.004 inch minimum.

3. QUALITY ASSURANCE PROVISIONS

3.1 Product conformance. The tape provided shall meet the salient characteristics of this CID, conform to the manufacturer's own drawings, specifications, standards, and quality assurance practices, and be the same product offered for sale in the commercial marketplace. The government reserves the right to require proof of such conformance.

3.2 Magnesium test panel. The panel shall be at least two inches wide by four inches long and 0.0625 inch thick conforming to SAE-AMS-M-3171, type I, composition AZ31B-H24 with chrome pickle treatment. The panel shall be cleaned with mineral spirits conforming to A-A-2904, type I or II, Grade A.

3.3 Tape application. A tape specimen one by eight inches shall be applied to the test panel described in 3.2 so that a one by four inch area is covered. The tape shall be applied by rolling the tape applicator back and forth once in the lengthwise direction.

3.4 Adhesion to magnesium. The free end of the tape applied in accordance with 3.3 shall be doubled back 180 degrees, and one inch of the applied tape shall be peeled back at the folded end to allow panel attachment to a tensile test machine. The free end of the tape shall be pulled by the tensile machine at a rate of 12 inches per minute, and the adhesion values recorded after the first inch and then again after the next inch is peeled back.

3.4.1 Adhesion after immersion. Two more tape samples shall be applied in accordance with 3.3. Using two separate containers, fill one with di-ethylhexysebacate and the other with a petroleum base oil conforming to TT-S-735, type VI (ASTM Oil No. 3) such that the test panels will be completely submerged. Place the two containers in an oven maintained at 155 ±2 °F for four hours. After this immersion period, the panels shall be removed and excess fluid blotted. The tape specimens shall then be subjected to the adhesion test of 3.4.

3.5 Market acceptability. The following market acceptability criteria are necessary to document the quality of the product to be provided under this CID.

3.5.1 Manufacturer's experience. The company producing the pressure sensitive tape must have been manufacturing a product meeting the requirements of this CID for at least six months.

3.5.2 Conformance inspection. The company must have offered the tape to a government lab for inspection (see 5.3).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:09Z
Check the source to verify that this is the current version before use.

4. PACKAGING

4.1 Packaging, packing, and marking. Packaging, packing, and marking shall be as specified in the contract or order.

5. NOTES

5.1 Source of documents. Federal Government activities may obtain copies of FED-STD-191, A-A-2904, TT-S-735, and SAE-AMS-M-3171 from established distribution points within their agencies; Department of Defense activities may obtain these documents from the Standardization Documents Order Desk, 700 Robbins Avenue, Building 4D, Philadelphia, PA 19111-5094. Other activities may obtain copies of FED-STD-191, A-A-2904, and TT-T-735, from the General Services Administration, Federal Supply Service, Specification Section, Suite 8100, 479 L'Enfant Plaza, SW, Washington, D.C. 20407; other activities may order SAE-AMS-M-3171 from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

5.2 Ordering data. Requests, requisitions, schedules, and contracts or orders should contain the following:

a. Width if other than one inch (see 2.4.1).
b. Length of tape in roll if other than 72 yards (see 2.4.1).
c. Packaging, packing, and marking (see 4.1).

5.3 Government laboratory. Manufacturers wanting to have their tape inspected may do so by contacting Commander, Naval Air Warfare Center Aircraft Division, Code 4.3.4.1, 22347 Cedar Point Road, Unit 6, Building 2188, Materials Lab, Patuxent River, MD 20670-1161.

CONCLUDING MATERIAL

MILITARY INTERESTS:

Custodians:
Army – GL
Air Force – 99

Review activities:
Army – CR4, MI
Air Force - 69

CIVIL AGENCY COORDINATING ACTIVITY:

GSA-FSS-2FYE

Preparing activity:
Navy – AS

Project 7510-0416

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:09Z
Check the source to verify that this is the current version before use.