MIL-E-0022200/1F(SH)
AMENDMENT 1
14 August 1985

MILITARY SPECIFICATION

ELECTRODES, WELDING, MINERAL COVERED, IRON-POWDER, LOW-HYDROGEN MEDIUM AND HIGH TENSILE STEEL, AS WELDED OR STRESS-RELIEVED WELD APPLICATION

This amendment forms a part of Military Specification MIL-E-22200/1F, dated 13 July 1981, and is approved for use by the Naval Sea Systems Command, Department of the Navy and is available for use by all Departments and Agencies of the Department of Defense.

PAGE 6

Table IV., under "MIL-7018" opposite from "Manganese": Delete "0.40 - 1.25" and substitute "0.40 - 1.60".

PAGE 17

Table XII., under "Maximum root opening (R)" opposite from "3/32": Delete "1/2" and substitute "1/4".

Preparing activity:
Navy - SH
(Project 3439-N599)

FSC 3439

DISTRIBUTION STATEMENT A Approved for public release; distribution unlimited

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T11:21Z
Check the source to verify that this is the current version before use.