MILITARY SPECIFICATION

ELECTRODES, WELDING, COVERED, LOW-HYDROGEN, AND IRON-POWDER LOW-HYDROGEN, CHROMIUM-MOLYBDENUM ALLOY STEEL AND CORROSION RESISTING STEEL

This amendment forms a part of Military Specification MIL-E-22200/8B, date 25 June 1981, and is approved for use by all Departments and Agencies of the Department of Defense.

PAGE 4

Table II: Delete and substitute:

"TABLE II. Water content.

Types	Percent by weight maximum	
	Condition A 1/	Condition B 2/ 3/
MIL-80XX	0.10	0.20
MIL-90XX	.10	.20
MIL-410-XX	.60	----
MIL-502-XX	.60	----
MIL-505-XX	.60	----

1/ Condition A - When removed from sealed manufacturer container.
2/ Condition B - After 9 hours exposure at 80 percent relative humidity (RH) and 80 degrees Fahrenheit (°F) in accordance with 4.6 herein.
3/ Required for qualification (QPL) inspection only."

FSC 3439

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T11:23Z
Check the source to verify that this is the current version before use.

PAGE 9

Add as new paragraph 4.5.2.1:

"4.5.2.1 Temperature and humidity environmental exposure pressures. The electrode sample shall be exposed in a blue M environmental chamber model FR 251-1 or equivalent for 9 hours minimum at 80°F minus 0, plus 5°F and 80 percent RH minus 0, plus 5 percent. The chamber shall have a two-pen recorder with the first pen for dry bulb temperature and the second pen for the differential between wet bulb and dry bulb temperatures. The chamber is available in all standard voltages for the various power supplies. The procedure shall be as follows:

(a) The electrode sample in unopened packages shall be heated to a temperature minus 0, plus 10°F above the dew point of the chamber at the time of loading.
(b) The electrode sample shall be loaded into the chamber without delay after the packages are opened.
(c) The electrodes shall be placed in the chamber in a vertical position on 1-inch centers.
(d) Time, temperature and humidity shall be continuously recorded for the period that the electrodes are in the chamber.
(e) Counting of exposure time shall start when the required temperature and humidity in the chamber are established.
(f) At the end of the exposure time, the electrodes shall be removed from the chamber and a sample of the coating taken for moisture determination."

PAGE 11

Table XII, under "Procedures" column, across from "Covering moisture": Delete "4.6.9" and substitute "4.6.9 and 4.5.2.1 herein".

Custodians:
Army - AL
Navy - SH
Air Force - 20

Review activity:
DLA - GS

User activities:
Army - AT, MR
Navy - MC, OS

Preparing activity:
Navy - SH
(Project 3439-0558)

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T11:23Z
Check the source to verify that this is the current version before use.