JAN–G–479

17 JULY 1947

JOINT ARMY-NAVY SPECIFICATION

GLASS, GROUND (For Ordnance Use)

This specification was approved by the War Department and the Navy Department for use of procurement services of the Army and the Navy and supersedes the following specification:

U. S. Army	Navy Department
50-11-23A	-----
12 June 1933	

A. APPLICABLE SPECIFICATIONS AND OTHER PUBLICATION

A-1. *Specifications.*—The following specifications of the issue in effect on date of invitation for bids, form a part of this specification:

U. S. ARMY SPECIFICATIONS

50-0-1—General Specification for Ammunition except Small Arms Ammunition.[1]

100-2 —Standard Specification for Marking Shipments by Contractors.[1]

NAVY DEPARTMENT SPECIFICATION

General Specifications for Inspection of Material.[2]

FEDERAL SPECIFICATION

RR-S-366—Sieves, Standard, Testing.

A-2. *Other publication.*—The following publication, of the issue in effect on the date of invitation for bids, forms a part of this specification:

BUREAU OF SUPPLIES AND ACCOUNTS PUBLICATION

Navy Shipment Marking Handbook.[2]

B. GRADE AND CLASSES

B-1. This specification covers one grade of ground glass, furnished in five classes, A, B, C, D and E according to granulation, as specified in the contract or order. (See par. E-2.)

C. MATERIAL AND WORKMANSHIP

C-1. *Material.*—The material used to produce the ground glass shall be a soft, white, soda-lime glass.

[1] Applicable only to Army purchases.
[2] Applicable only to Navy purchases.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T07:32Z
Check the source to verify that this is the current version before use.

C-2. *Workmanship.*—The glass shall be ground with French burrstones or other mills giving to the particle the shape and edge characteristic of burrstone grinding.

D. GENERAL REQUIREMENTS

D-1. See section E.

E. DETAIL REQUIREMENTS

E-1. *Foreign matter.*—The material shall be free from foreign matter.

E-2. *Particle shape.*—The fracture of the particles shall be conchoidal and there shall be no long needles or round particles due to rumbling.

E-3. *Granulation.*—Ground glass shall conform to the granulation requirements shown in table I using U. S. Standard sieves conforming to Federal Specification RR-S-366.

Table I—Granulation requirements.

	Class A	Class B	Class C	Class D	Class E
	Percent (min.)	Percent (min.)	Percent (min.)	Percent (min.)	Percent (min.)
Through sieve No. 60	100	--	--	--	--
Through sieve No. 100	--	100	--	--	--
Through sieve No. 140	--	--	100	90	--
Through sieve No. 170	--	--	--	--	90
Retained on sieve No. 100	99	--	--	--	--
Retained on sieve No. 170	--	--	--	75	--
Retained on sieve No. 200	--	99	99	--	75

F. METHODS OF SAMPLING, INSPECTION, AND TESTS

F-1. *Size of lot.*—Unless otherwise specified a lot shall consist of not more than 100 pounds of material of one class.

F-2. *Sampling.*—Select at least 10 percent but not more than 10 of the containers comprising the lot. By means of a scoop, remove from each selected container sufficient of the material to form a sample of approximately 2 ounces. Mix these samples thoroughly and quarter until a composite sample of approximately 8 ounces is obtained. Place the composite sample in a rubber-stoppered bottle and label to show the name of the material, class, manufacturer, plant, contract or order number, and number of pounds in the lot. All acceptance tests shall be made on the composite sample representative of the lot.

F-3. *Inspection.*—

F-3a. *Army.*—Inspection shall be made in accordance with the requirements of U. S. Army Specification 50-0-1, and shall be at the point of delivery unless otherwise specified in the contract or order.

F-3b. *Navy.*—Unless otherwise specified in the contract or order, inspection shall be made at the point of delivery.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T07:32Z
Check the source to verify that this is the current version before use.

F-4. *Tests.*—The laboratory tests shall be made in accordance with the following paragraphs. For Navy purchases, tests shall be made at a Government laboratory unless otherwise specified in the contract or order.

F-4a. *Foreign matter.*—Determine by microscopic examination using a low power.

F-4b. *Particle shape.*—Determine by microscopic examination.

F-4c. *Granulation.*—Place an accurately weighed portion of approximately 100 gm. of the sample on the specified nest of sieves properly superimposed and assembled with a bottom pan. Cover and shake 5 minutes by hand, or mechanically with a shaker geared to produce 300±15 gyrations and 150±10 taps of the striker per minute. Weigh the portions retained or passed by the various sieves and calculate the results to a percentage basis as specified in paragraph E-3.

G. PACKAGING, PACKING, AND MARKING FOR SHIPMENT

G-1. *Packing.*—Unless otherwise specified ground glass shall be packed in bags, barrels, or boxes so constructed as to insure acceptance by common or other carrier for safe transportation at the lowest rate to the point of delivery.

G-2. *Marking.*— In addition to any special marking required by the contract or order, shipments for the Army shall be marked in accordance with the requirements of U. S. Army Specification 100-2; for the Navy, in accordance with the requirements of the Navy Shipment Marking Handbook.

H. NOTES

H-1. *Use.*—The material covered by this specification is intended for use as an ingredient in primer compositions.

H-2. Requests, requisitions, schedules, and contracts or orders should contain the following:

(a) Title, number, and date of the specification.
(b) Class of material required. (See par. B-1.)

H-3. Copies of Joint Army-Navy specifications and Federal specifications (required for Army purchases) and U. S. Army specifications may be obtained as indicated in the "Index of United States Army, Joint Army-Navy, and Federal Specifications Used by the War Department." Copies of this Index may be obtained from the Superintendent of Documents, Government Printing Office, Washington 25, D. C. Agencies within the War Department will obtain copies of Joint Army-Navy, U. S. Army, and Federal specifications through established War Department channels. Both the title and identifying symbol number should be stipulated when requesting copies of specifications.

H-4. Copies of Joint Army-Navy specifications and Federal specifications (required for Navy purchases), Navy Department specifications, and the Navy Shipment Marking Handbook may be obtained upon application to the Bureau of Supplies and Accounts, Navy Department, Washington 25, D. C., except that Naval activities should make application to the Supply Officer in Command,

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T07:32Z
Check the source to verify that this is the current version before use.

Naval Supply Depot, Bayonne, N. J. Both the title and identifying symbol number should be stipulated when requesting copies of specifications.

H-3. Copies of this Joint Army-Navy specification (required for Army purchases) may be obtained from the Office, Chief of Ordnance, War Department, Washington 25, D. C.

Notice—When Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the United States Government thereby incurs no responsibility nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications or other data is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use, or sell any patented invention that may in any way be related thereto.

Army: OS.
Navy: OS.

(JAN-C-416)

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T07:32Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

OMB Approval
No. 22-R255

INSTRUCTIONS: The purpose of this form is to solicit beneficial comments which will help achieve procurement of suiteble products at reasonable cost and minimum delay, or will otherwise enhance use of the document. DoD contractors, government activities, or manufacturers/vendors who are prospective suppliers of the product are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity.

DOCUMENT IDENTIFIER AND TITLE

NAME OF ORGANIZATION AND ADDRESS

CONTRACT NUMBER

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY DOCUMENT REQUIREMENT CONSIDERED TOO RIGID

3. IS THE DOCUMENT RESTRICTIVE?

☐ YES ☐ NO *(If "Yes", in what way?)*

4. REMARKS

SUBMITTED BY *(Printed or typed name and address - Optional)*

TELEPHONE NO.

DATE

DD FORM 1 JAN 72 1426

REPLACES EDITION OF 1 JAN 66 WHICH MAY BE USED

S/N 0102-014-1802

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T07:32Z
Check the source to verify that this is the current version before use.

FOLD

POSTAGE AND FEES PAID



OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

Commanding Officer
Naval Ordnance Station
Standardization Division
ATTN: Code 611
Indian Head, MD 20640

OLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T07:32Z
Check the source to verify that this is the current version before use.