MIL-C-483D
AMENDMENT-1
26 June 1978

MILITARY SPECIFICATION

CLOTH, PILE; ALPACA AND WOOL

This amendment forms a part of Military Specification MIL-C-483D, dated 15 March 1974, and is approved for use by all Departments and Agencies of the Department of Defense.

PAGE 1

1.2, under "Classification": Add the following:

"Type X - Cloth, knitted wool pile, polyester back".

2.1: Add the following Military Specification:

"MIL-C-43665 - Cloth Wool: Mothproofing Treatment Of".

PAGE 2

2.1, under MILITARY: Add "MIL-STD-1491 - Glossary of Knitted Imperfections".

3.3, after "Materials": Add "(see 6.8)".

3.3.1.1: Add the following sentence. "The backing yarn for type X shall be spun polyester (see 3.5.3)."

PAGES 2 and 3

3.3.1.2.1 and 3.3.1.2.2: Delete last sentence in both paragraphs.

Add the following new paragraph:

"3.3.1.2.3 Type X. The pile shall be wool. The wool shall not be lower in grade than 56's U.S. Standard."

3.4 Add the following new sentences: 'The color of the pile for type X shall be brown to match the standard sample. The color shall be obtained by blending dyed and undyed wool. The color of the backing yarn shall be natural."

3.4.1, line 2: Delete the words "natural (north sky) daylight or'.

FSC 8305

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T07:33Z
Check the source to verify that this is the current version before use.

PAGE 4

Add the following new paragraph:

"3.5.3 Type X. The cloth shall be a knitted wool pile cloth with a polyester backing (see 6.9). An acrylic type resin applied to the back of the cloth as a bonding or anticurl agent will be permitted. The finished cloth shall conform to the following minimum requirements when tested as specified in 4.5:

Weight	-	13.0 ounces per square yard.
Backing texture	-	11 wales per inch.
	-	17 courses per inch.
Pile height	-	1/2 ± 1/32 inch.
Shearable pile percent (based on finished weight)	-	45."

3.6.1: Add the following sentence: "The pH value for type X shall be no less than 5.5 nor more than 8.5 when tested as specified in 4.5."

3.6.2: Delete in entirety and substitute:

"3.6.2 Mothproofing. The alpaca and wool pile shall be mothproofed in accordance with MIL-C-43665."

PAGE 5

Add the following new paragraph:

"4.1.1 Certificate of compliance. Where certificates of compliance are submitted, the Government reserves the right to check test such items to determine the validity of the certification."

PAGE 6

4.4.3.1, line 4, after type VII. Insert "and X".

PAGE 7

4.4.3.1, under Defect (one class) column opposite "Broken or missing yarns": Delete "Ground warp or filling," and substitute "Ground warp (wales) or filling (courses)".

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T07:33Z
Check the source to verify that this is the current version before use.

PAGE 7 (cont'd)

4.4.3.1, list of defects: Add the following:

"Knitting defects (as defined in MIL-STD-1491) applicable to type X only.	Abrasion, drop stitch, run, float, loose or tight yarn, or crease."

PAGE 9

Table IV: Delete "Fluorin content 3.6.2 4.5.2" and add the following:

"Backing material (type X)	3.5.3	3/
Weight (type X)	3.5.3	3/
Backing texture (type X)	3.5.3	3/
Pile height (type X)	3.5.3	3/
Shearable pile percent (type X)	3.5.3	3/"

Table IV: Add the following footnote:

"3/ Unless otherwise specified, a certificate of compliance shall be submitted and will be acceptable for the stated requirements.

PAGES 10 and 11

4.5.2 through 4.5.2.3: Delete in entirety.

PAGE 12

Add the following new paragraphs:

"6.8 Recycled material. It is encouraged that recycled material be used when practical as long as it meets the requirements of the specification.

6.9 Cloth, knitted pile wool, polyester back. Fabric conforming to Style 519/318 of Draper Brothers Co., Inc., Canton, MA is known to meet the requirements specified in 3.5.3."

Custodians:

Army - GL
Navy - SA
Air Force - 11

Preparing activity:

Army - GL

Project No. 8305-0459

Review activities:

Army - MD
Air Force - 99

User activity:

Navy - AS

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T07:33Z
Check the source to verify that this is the current version before use.