MIL-C-484H
AMENDMENT-1
28 July 1987

MILITARY SPECIFICATION

CLOTH, WIND RESISTANT OXFORD, COTTON, QUARPEL TREATED

This amendment forms a part of Military Specification MIL-C-484H, dated 11 February 1985, and is approved for use by all Departments and Agencies of the Department of Defense.

PAGE 1

1.2, for type IV: Delete "6.2" and substitute "6.7".

PAGE 3

2.3: Delete and substitute:

"2.3 Order of precedence. In the event of a conflict between the text of this document and the references cited herein, the text of this document shall take precedence. Nothing in this document, however, shall supersede applicable laws and regulations unless a specific exemption has been obtained."

3.1, line 2, after "and shall": Add ", unless otherwise indicated (see 3.3.2),".

3.3.2: Delete and substitute:

"3.3.1 Matching. The color of the cloth shall match the standard sample when viewed under filtered tungsten lamps that approximate artificial daylight and that have a correlated color temperature of 7500 ± 200 K, with illumination of 100 ± 20 foot candles, and shall be a good match to the standard sample under incandescent lamplight at 2300 ± 200 K."

3.3.2: Delete and substitute:

"3.3.2 Colorfastness. The dyed and finished cloth shall show fastness to laundering, perspiration, and light equal to or better than the standard sample or equal to or better than the rating of 'good' when tested as specified in 4.2.3. The cloth shall have an AATCC Chromatic Transference Scale rating not lower than 3.5 for all shades except that for wet crocking, black and dark-blue shades shall have an AATCC Chromatic Transference Scale rating not lower than 2.5, when tested as specified in 4.2.3."

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T07:33Z
Check the source to verify that this is the current version before use.

PAGE 4

Table I, for type VI: Delete "6.2" and substitute "6.7".

3.6: Delete the first sentence and substitute "The shrinkage in the warp and in the filling of the finished cloth shall be no greater than 2.5 percent for the individual sample unit and no greater than 2.0 percent for the lot average when tested as specified in 4.2.3."

PAGE 5

3.8, line 1: Delete "5.5" and substitute "5.0".

PAGE 6

Add the following new paragraph:

"4.1.2 Responsibility for compliance. All items must meet all requirements of sections 3 and 5. The inspection set forth in this document shall become part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in the document shall not relieve the contractor of the responsibility of assuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling in quality conformance does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to acceptance of defective material."

PAGE 9

Table III, in "Test method" column, line 3, after "2020": Add "1/".

PAGE 12

Add the following new paragraph:

"6.8 Subject term (key word) listing.

Cloth, wind resistant oxford
Water repellency
Quarpel treated"

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T07:33Z
Check the source to verify that this is the current version before use.

Custodians:

Army - GL
Navy - NU
Air Force - 99

Review activities:

Army - MD
Navy - MC
Air Force - 82
DLA - CT

User activity:

Air Force - 45

Preparing activity:

Army - GL

Project No. 8305-0121

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T07:33Z
Check the source to verify that this is the current version before use.