INCH-POUND

MIL-P-501P
1 March 1991
SUPERSEDING
MIL-P-501N
25 November 1987

MILITARY SPECIFICATION

PIN, TENT, METAL

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers metal tent pins (see 6.1).

1.2 Classification. The tent pins shall be of the following types and classes as specified (see 6.2).

Type I	-	Aluminum, 9-inch
Type II	-	Steel, 12-inch
Class A	-	Arctic soil
Class B	-	Hard soil
Type III	-	Steel, 18-inch

2. APPLICABLE DOCUMENTS

2.1 Government documents.

2.1.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those listed in the issue of the Department of Defense Index of Specifications and Standards (DODISS) and supplement thereto, cited in the solicitation (see 6.2).

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be used in improving this document should be addressed to: U.S. Army Natick Research, Development, and Engineering Center, Natick, MA 01760-5017 by using the Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A

FSC 8340

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T07:36Z
Check the source to verify that this is the current version before use.

SPECIFICATIONS

FEDERAL

QQ-A-250/4	-	Aluminum Alloy 2024, Plate and Sheet
TT-C-490	-	Cleaning Methods for Ferrous Surfaces and Pretreatments for Organic Coatings
TT-E-489	-	Enamel, Alkyd, Gloss, Low Voc Content
TT-L-32	-	Lacquer, Cellulose Nitrate, Gloss for Aircraft Use
PPP-B-621	-	Boxes, Wood, Nailed and Lock-Corner
PPP-B-636	-	Boxes, Shipping, Fiberboard
PPP-B-640	-	Boxes, Fiberboard, Corrugated, Triple-Wall

MILITARY

MIL-L-35078	-	Loads, Unit: Preparation of Semiperishable Subsistence Items; Clothing, Personal Equipment and Equipage; General Specification For

STANDARDS

MILITARY

MIL-STD-105	-	Sampling Procedures and Tables for Inspection by Attributes
MIL-STD-129	-	Marking for Shipment and Storage
MIL-STD-130	-	Identification Marking of U.S. Military Property
MIL-STD-147	-	Palletized Unit Loads

(Unless otherwise indicated, copies of federal and military specifications, standards, and handbooks are available from the Standardization Documents Order Desk, Building 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.)

2.1.2 Other Government documents, drawings, and publications. The following other Government documents, drawings, and publications form a part of this document to the extent specified herein. Unless otherwise specified, the issues are those cited in the solicitation.

DRAWINGS

U.S. ARMY NATICK RESEARCH, DEVELOPMENT, AND ENGINEERING CENTER

5-4-121	-	Pins, Tent, Metal; Type I, Aluminum, 9 inch
5-4-196	-	Pins, Tent, Metal; Steel 18-inch, Type-III, for Temperate Climate Soils
5-4-791	-	Pins, Tent, Metal; Steel 12 inch, Type II, Class A for Arctic Soil and Class B for Hard Soil

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T07:36Z
Check the source to verify that this is the current version before use.

(Copies of drawings are available from the U.S. Army Natick Research, Development, and Engineering Center, ATTN: STRNC-UX, Natick, MA 01760-5017.)

2.2 Non-Government publications. The following documents form a part of this document to the extent specified herein. Unless otherwise specified, the issues of the documents which are DOD adopted are those listed in the issue of the DODISS cited in the solicitation. Unless otherwise specified, the issues of documents not listed in the DODISS are the issues of the documents cited in the solicitation (see 6.2).

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

A 322	-	Steel Bars, Alloy, Standard Grades
A 576	-	Steel Bars, Carbon, Hot-Wrought, Special Quality
B 209	-	Aluminum and Aluminum-Alloy Sheet and Plate
B 449	-	Chromate Treatments On Aluminum
D 3951	-	Standard Practice for Commercial Packaging
E 18	-	Rockwell Hardness and Rockwell Superficial Hardness of Metallic Materials
E 381	-	Microetch Testing, Inspection, and Rating Steel Products, Comprising Bars, Billets, Blooms, and Forgings

(Copies may be obtained from the American Society for Testing and Materials, 1916 Race Street, PA 19103-1187.)

(Non-Government standards and other publications are normally available from the organizations that prepare or distribute the documents. These documents also may be available in or through libraries or other informational services.)

2.3 Order of precedence. In the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 First article. When specified (see 6.2), a sample shall be subjected to first article inspection (see 6.3), in accordance with 4.3.

3.2 Material. The material shall conform to the applicable reference documents specified herein, (see 6.4). It is encouraged that recycled material be used when practical as long as it meets the requirements of this specification.

3.2.1 Aluminum alloy. Aluminum alloy sheet shall conform to alloy 2024-0 of QQ-A-250/4, or ASTM B 209 and heat treated to temper T42 after forming.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T07:36Z
Check the source to verify that this is the current version before use.

3.2.2 Steel alloy bar. Steel alloy bar shall conform to the hot rolled condition (HR), composition 4140 of ASTM A 322 for the type II pin and composition 1040 of ASTM A 576 for the Type III pin.

3.2.3 Lacquer. Lacquer shall conform to either type 1 or 2, International Orange color No. 12197, Insignia Red color No. 11136 or Insignia White color No. 17875, as applicable, of TT-L-32.

3.2.4 Enamel. Enamel shall conform to class A or B, composition G or L, International Orange color Nos. 12197-1 or 12197-2, Red color Nos. 11136 or 11105, or White color Nos. 37875 or 37886, as applicable, of TT-E-489.

3.3 Construction. The construction of the pins shall conform to Drawings 5-4-121, 5-4-196 and 5-4-791, and as specified herein.

3.3.1 Type I pin. The type I pins shall be fabricated of aluminum specified in 3.2.1. After stamping but prior to forming, the blank shall conform to the dimensions shown on Drawing 5-4-121. After forming, the pin shall be heat treated as required by QQ-A-250/4 or ASTM B 209, except that each batch of heat treated pins shall be tested as specified in 4.4.2.3 for a minimum hardness of 61 on the Rockwell 30T scale in lieu of the tensile strength, yield strength, and elongation tests.

3.3.2 Type II pin. The type II pins shall be fabricated of steel specified in 3.2.2. The head portion or the complete type II pin shall be shaped by forging. The type II pin shall be air cooled after forging. The forging shall be free from any crack, seam, or lap when tested as specified in 4.4.5. Forge welding operation shall not be permitted. The center line axis of the finished type II pin shall not bow out of line more than 3/64 inch. After forging and air cooling, the pin shall be heat treated to a Rockwell C40-48 hardness at all depths when tested as specified in 4.4.5.

3.3.3 Type III pins. The type III pins shall be fabricated from steel specified in 3.2.2. The head of the pin or the complete pin shall be shaped by forging. The forging shall be free from any crack, seam or lap when tested as specified in 4.4.5. Parting lines shall be trimmed smooth and resultant flat trim line shall have rounded edges.

3.4 Identification marking. Prior to finishing, pins shall be permanently and legibly marked with the letters "US" and the manufacturer's identification in accordance with MIL-STD-130 in the locations as shown on the applicable drawings referenced in section 2. The type II pin shall also be permanently and legibly marked with the alloy Number "4140" with raised or stamped marking.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T07:36Z
Check the source to verify that this is the current version before use.

Puller pattern not as specified.

3.5 Finish. All grinding, machining, removing of burrs, sharp edges and corners, trimming of forged parting lines, and marking operations shall be completed prior to finishing.

3.5.1 Pretreatment.

3.5.1.1 Type I pin. Prior to lacquering or enameling, the type I pin shall be prepared for painting in accordance with class 1 or 2 requirements of ASTM B 449.

3.5.1.2 Type II and Type III pins. Prior to lacquering or enameling, the type II and type III pins shall be cleaned and treated by any method or type in accordance with TT-C-490, except that the testing for salt spray resistance shall not be required.

3.5.2 Lacquering or enameling. After pretreatment, the pins shall be coated with lacquer or enamel as specified in 3.2.3 or 3.2.4. The coating shall be a smooth, uniform dry film without areas of thin or no film, rust, corrosion, blisters, peels, cracks, sags, or soft runs. The color of the finish shall be orange for type I pin, red for the type II class A and type III pins, or white for the Type II class B pins.

3.6 Workmanship. The finished pins shall not be bent out of shape, twisted, fractured, or malformed. The pins shall be free from cracks and flares. Type I pins shall be free from any die mark, tool mark, and forming mark exceeding 1/32 inch in depth. Type II and type III pins shall be free from loose scale or scale pits exceeding 1/32 inch in depth. The finished pins shall conform to the quality of product established by this specification and the occurrence of defects shall not exceed the applicable acceptable levels.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements (examinations and tests) as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in this specification where such inspections are deemed necessary to ensure supplies and services conform to prescribed requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T07:36Z
Check the source to verify that this is the current version before use.

4.1.1 Responsibility for compliance. All items shall meet all requirements of sections 3 and 5. The inspection set forth in this specification shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in the specification shall not relieve the contractor of the responsibility of ensuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling inspection, as part of manufacturing operations, is an acceptable practice to ascertain conformance to requirements, however, this does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to accept defective material.

4.1.2 Responsibility for dimensional requirements. Unless otherwise specified in the contract or purchase order, the contractor is responsible for ensuring that all specified dimensions have been met. When dimensions cannot be examined on the end item, inspection shall be made at any point, or at all points in the manufacturing process necessary to ensure compliance with all dimensional requirements.

4.2 Classification of inspections. The inspection requirements specified herein are classified as follows:

a. First article inspection (see 4.3)
b. Quality conformance inspection (see 4.4)

4.3 First article inspection. When a first article is required (see 3.1 and 6.2), it shall be examined for the defects specified in 4.4.3 and 4.4.4 and shall be tested for the charactertistics specified in 4.4.5. Any nonconformance shall be cause for rejection of the first article.

4.4 Quality conformance inspection. Unless otherwise specified, sampling for inspection shall be performed in accordance with MIL-STD-105.

4.4.1 Component and material inspection. In accordance with 4.1, components and materials shall be inspected in accordance with all the requirements of referenced documents unless otherwise excluded, amended, modified, or qualified in this specification or applicable purchase document.

4.4.2 In-process inspection. Inspection of subassemblies shall be made to ascertain that construction details which cannot be examined in the finished product are in accordance with specified requirements. The Government reserves the right to exclude from consideration for acceptance, any material or service for which in-process inspection has indicated nonconformance.

4.4.2.1 In-process dimensional examination. An in-process dimensional examination shall be made of type I pin blanks to determine compliance with 3.3.1. Any dimension that is not within the specified requirements shall be

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T07:36Z
Check the source to verify that this is the current version before use.

classified a defect. The lot shall be type I pin blanks. The sample unit shall be one type I pin blank. The inspection level shall be S-2 and the acceptable quality level (AQL), expressed in terms of defects per hundred units, shall be 4.0.

4.4.2.2 In-process examination. Examination shall be made of the fabrication processes in table I to establish conformance with specified requirements. Whenever nonconformance is noted, correction shall be made to the process and all items processed. Items which cannot be corrected shall be removed from production.

TABLE I. In-process examination

Requirement or operation	Requirement reference
Type I pin is heat treated prior to pretreatment	3.3.1
Head portion or complete type II and type III pins shaped by forging	3.3.2 and 3.3.3
Type II pin is air cooled after forging	3.3.2
Forge welding operation shall not be permitted	3.3.2
Type II pin is heat treated prior to pretreatment	3.3.2
Grinding, machining, removing of burrs, sharp edges and corners, trimming of forged parting lines, and marking is completed prior to finishing	3.5
Type I pin is prepared for painting prior to finishing	3.5.1.1
Type II and type III pins are cleaned and treated prior to finishing	3.5.1.2

4.4.2.3 In-process testing. Prior to finishing of the type I pins, testing shall be performed in accordance with ASTM E 18 to determine compliance with 3.3.1. The lot shall be all of the pins in each batch of the heat treated type I pins. The sample unit shall be one pin. The inspection level shall be S-1 and the AQL, expressed in terms of defects per hundred units, shall be 6.5. Three determinations shall be made on each sample unit and the hardness shall be reported as the average of the three readings to the nearest appropriate Rockwell scale value. Any sample failing to meet the minimum of 61 Rockwell hardness on the 30T scale specified in 3.3.1 shall be classified a defect.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T07:36Z
Check the source to verify that this is the current version before use.

4.4.3 End item visual examination. The end items shall be examined for the defects listed in table II. The lot size shall be expressed in units of pins of one type only. The sample unit shall be one completely fabricated pin. The inspection level shall be II and the AQL, expressed in terms of defects per hundred units, shall be 2.5 for major defects and 6.5 for total (major and minor combined) defects.

TABLE II. End item visual defects

Examine	Defect	Classification Major	Minor
Finish	Not lacquered or not enameled	101	
	Color of finish not as specified		201
	Coating is not dry, uniform in appearance		202
	Area of no film; evidence of rust or corrosion		203
	Blister, peel, crack, sag, or soft run		204
Construction:			
Types I, II, and III pins	Pin not fabricated of applicable referenced materials	102	
	Burrs, sharp edges or corners		205
Type I pin	Hole missing or misplaced		206
Type II and III pins	Forge parting lines are not smooth in area indicated on Drawing 5-4-196 or 5-4-791, as applicable	103	
Workmanship:			
Types I, II, and III pins	Pin is bent out of shape, twisted, flared, or malformed		207
	Evidence of crack	104	
Type I pin	Die mark, tool mark, or forming mark exceeding 1/32 inch in depth		208
Types II and III pins	Loose scale or scale pits exceeding 1/32 inch in depth		209

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T07:36Z
Check the source to verify that this is the current version before use.

TABLE II. End item visual defects (cont'd)

Examine	Defect	Classification Major	Minor
Marking:			
Types I, II, and III pins	Missing, illegible, incorrect, incomplete, wrong location, or wrong size		210
Type II pin	Alloy number missing		211

4.4.4 End item dimensional examination. The end items shall be examined for conformance to the dimensions specified on the drawings. Only those dimensions that can be evaluated without damaging or disassembling the end items shall be examined. Any dimension not within the specified tolerance shall be classified as a defect. The lot size shall be expressed in units of pins of one type only. The sample unit shall be one completely fabricated pin. The inspection level shall be S-2 and the AQL, expressed in terms of defects per hundred units, shall be 4.0.

4.4.5 End item testing. The end items shall be tested for the characteristics listed in table III. The lot size shall be expressed in units of pins of one type only. The sample unit shall be one completely fabricated pin. The inspection level shall be S-1 and the AQL, expressed in terms of defects per hundred units, shall be 6.5 except that any test failure shall be cause for rejection of the lot.

TABLE III. End item tests

Characteristics	Requirement paragraph	Test method paragraph	Number of determinations per sample unit	Results reported as
Forging of type II and III pins are free from crack, seam, or lap	3.3.2 3.3.3	4.5.1	1	Pass or fail

Source: https://assist.dla.mil -- Downloaded: 20261O-16T07:36Z
Check the source to verify that this is the current version before use.

TABLE III. End item tests (cont'd)

Characteristics	Requirement paragraph	Test method paragraph	Number of determinations per sample unit	Results reported as
Type II pin				
Hardness:				
Surface	3.3.2	4.5.2 and 4.5.2.1	3	Average of 3 determinations to nearest scale reading
Inner	3.3.2	4.5.2 and 4.5.2.2	4 (2 at each location)	Each individual determination to nearest scale reading

4.4.6 Packaging examination. The fully packaged end items shall be examined for the defects listed below. The lot size shall be expressed in units of shipping containers. The sample unit shall be one shipping container fully packaged. The inspection level shall be S-2 and the AQL, expressed in terms of defects per hundred units, shall be 2.5.

Examine	Defect
Marking (exterior and interior)	Omitted; incorrect; illegible; of improper size, location, sequence, or method of application
Materials	Any component missing, damaged, or not as specified

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T07:36Z
Check the source to verify that this is the current version before use.

Examine	Defect
Workmanship	Inadequate application of components, such as: incomplete sealing or closure of flap, improper taping, loose strapping or inadequate stapling Bulged or distorted container
Content	Number per container is more or less than required

4.4.7 Palletization examination. The fully packaged and palletized end items shall be examined for the defects listed below. The lot size shall be expressed in units of palletized unit loads. The sample unit shall be one palletized unit load, fully packaged. The inspection level shall be S-1 and the AQL, expressed in terms of defects per hundred units, shall be 6.5.

Examine	Defect
Finished dimensions	Length, width, or height exceeds specified maximum requirement
Palletization	Pallet pattern not as specified Interlocking of loads not as specified Load not bonded as specified
Weight	Exceeds maximum load limits
Marking	Omitted; incorrect; illegible; of improper size, location, sequence, or method of application

4.5 Methods of inspection.

4.5.1 Macroetch test. Forgings shall be tested in accordance with ASTM E 381. The pin shall be cut from the driving head end revealing a 2 inch ± 1/4 inch long transverse section through center line of pin projecting portion. Any sample having evidence of crack, seam, or lap shall be classified as a defect.

4.5.2 Rockwell hardness test. Type II pins shall be tested in accordance with ASTM E 18. Any sample failing to meet the Rockwell C40-48 hardness specified in 3.3.2, shall be classified as a defect.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T07:36Z
Check the source to verify that this is the current version before use.

4.5.2.1 Testing of surface hardness. Surface hardness shall be taken at three locations: 1-1/2 inches ± 1/4 inch from tapered point, mid-length ± 1/4 inch of pin, and 2-1/2 inches ± 1/4 inch from driving head end.

4.5.2.2 Testing of inner hardness. Inner hardness shall be taken at two locations: 1/16 inch ± 1/32 inch from the center and 1/16 inch ± 1/32 inch from circumference locations on each of two cross sections obtained by cutting pin perpendicular to the pin axis. The cuts shall be made 2 inches ± 1/4 inch from tapered point and 2 inches ± 1/4 inch from driving head end.

5. PACKAGING

5.1 Preservation. Preservation shall be level A or Commercial as specified (see 6.2).

5.1.1 Level A preservation.

5.1.1.1 Unit pack. Ten type I pins shall be nested and secured around the center with either a notched tapered plastic tie strip or with a plastic or paper covered wire tie to form a compact bundle.

5.1.1.2 Intermediate packs. One hundred type I pins, unit packed as specified in 5.1.1.1, shall be packed in a snug-fitting intermediate fiberboard box conforming to style RSC, type CF, variety SW, or type SF, class domestic, grade 200 of PPP-B-636. The unit packs shall be placed flat in two layers of five each with the unit packs of each layer alternated end for end. The inside dimensions of the box shall approximate 10-1/8 inches in length, 9-1/8 inches in width, and 4-1/2 inches in depth. Approximate dimensions are furnished as a guide only. Closure of the box shall be in accordance with the appendix of PPP-B-636.

5.1.2 Commercial preservation. Type I pins shall be preserved in accordance with ASTM D 3951.

5.2 Packing. Packing shall be level A, B, or Commercial as specified (see 6.2).

5.2.1 Level A packing.

5.2.1.1 Type I pins. Four hundred type I pins, preserved as specified in 5.1, shall be packed in a snug-fitting fiberboard shipping container conforming to style RSC, grade V2s of PPP-B-636. Level A intermediate packs shall be packed flat, two in length, one in width, and two in depth. The inside dimensions of the shipping container shall approximate 19 inches in length, 10-1/2 inches in width, and 9-3/4 inches in depth. Approximate dimensions are furnished as a guide only. Each fiberboard shipping container shall be closed

Source: https://assist.dla.mil -- Downloaded: 202610-16T07:36Z
Check the source to verify that this is the current version before use.

in accordance with method III, waterproofed in accordance with method V, and reinforced in accordance with the appendix of PPP-B-636, except that the inspection shall be in accordance with 4.4.6. Shipping containers shall be arranged in units loads in accordance with MIL-L-35078 for the type and class of load specified (see 6.2). Strapping shall be limited to nonmetallic strapping, except for the type II, class F loads.

5.2.1.2 Type II or type III pins. One hundred type II or type III pins shall be packed in a snug-fitting, nailed wood shipping container conforming to class 2, style 4, type 3 load of PPP-B-621, except that the sides, top, bottom and ends shall be a minimum 3/4 inch thick. The pins shall be placed in the container ten wide and ten deep, with the pins alternated end for end in each layer. Closure and strapping shall be in accordance with the appendix of PPP-B-621.

5.2.2 Level B packing.

5.2.2.1 Type I pins. Four hundred type I pins, preserved as specified in 5.1, shall be packed in a snug-fitting, fiberboard shipping container conforming to style RSC, type CF, variety SW, or type SF, class domestic, grade 275 of PPP-B-636. Level A intermediate packs shall be packed flat, two in length, one in width, and two in depth. The inside dimensions of the shipping container shall approximate 19 inches in length, 10-1/2 inches in width, and 9-3/4 inches in depth. Approximate dimensions are furnished as a guide only. Each container shall be closed in accordance with method II as specified in the appendix of PPP-B-636, except that the inspection shall be in accordance with 4.4.6.

5.2.2.1.1 Weather-resistant fiberboard containers. When specified (see 6.2), the shipping container shall be a grade V3c, V3s, or V4s fiberboard box fabricated in accordance with PPP-B-636 and closed in accordance with method III as specified in the appendix of PPP-B-636, except that the inspection shall be in accordance with 4.4.6.

5.2.2.2 Type II or type III pins. Fifty type II or type III pins shall be packed in a snug fitting double-wall, weather resistant fiberbox, style RSC-L, grade V13c conforming to PPP-B-636. The pins shall be placed in the container ten wide and five deep with the pins alternated end for end in each layer. Closure and strapping shall be in accordance with PPP-B-640. The inside dimensions of the container shall approximate 13-1/2 inches in length, 7-3/4 inches in width, and 3-1/2 inches in depth for the type II pins, and 19-1/2 inches in length, 7-3/4 inches in width, and 3-1/2 inches in depth for type III pins. Approximate dimensions are furnished as a guide only.

5.2.3 Commercial packing. Pins, preserved as specified in 5.1, shall be packed in accordance with ASTM D 3951.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T07:36Z
Check the source to verify that this is the current version before use.

5.3 Palletization. When specified (see 6.2), pins, packed as specified in 5.2.2 and 5.2.3, shall be palletized on a 4-way entry pallet in accordance with load type Ia of MIL-STD-147. Pallet types shall be type I (4-way entry), type IV, or type V in accordance with MIL-STD-147. Each prepared load shall be bonded with straps in accordance with bonding means C and D or film bonding means F or G. Pallet patterns shall be in accordance with the appendix of MIL-STD-147. Interlocking of loads shall be effected by reversing the pattern of each course. If the container is of a size which does not conform to any of the patterns specified in MIL-STD-147, the pallet pattern shall first be approved by the contracting officer.

5.4 Marking. In addition to any special marking required by the contract or purchase order, shipping containers shall be marked in accordance with MIL-STD-129 or ASTM D 3951 as applicable.

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not madatory.)

6.1 Intended use. The tent pins are intended for use as hold-down pins for tents.

Type I	-	In temperate climate soils (temperature above freezing)
Type II	-	In the arctic frozen soils (permafrost) or hard ground
Type III	-	In temperate climate soils (temperature above freezing)

6.2 Acquisition requirements. Acquisition documents must specify the following:

a. Title, number, and date of this specification.
b. Type and class required (see 1.2).
c. Issue of DODISS to be cited in the solicitation, and if required, the specific issue of individual documents referenced (see 2.1.1 and 2.2).
d. When a first article is required (see 3.1, 4.3, and 6.3).
e. Levels of preservation and packing (see 5.1 and 5.2).
f. Type and class of unit load required (see 5.2.1.1).
g. When weather-resistant grade fiberboard shipping containers are required for level B packing (see 5.2.2.1.1).
h. When palletization is required (see 5.3).

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T07:36Z
Check the source to verify that this is the current version before use.

6.3 First article. When a first article is required, it shall be inspected and approved under the appropriate provisions of Federal Acquisition Regulation (FAR) 52.209. The first article should be a preproduction sample. The contracting officer should specify the appropriate type of first article and the number of units to be furnished. The contracting officer should also include specific instructions in acquisition documents regarding arrangements for selection, inspection, and approval of the first article.

6.4 Subject term (key word) listing.

Cylindrical hold-down
Stake
Tentage

6.5 International standardization agreement. Certain provisions of this document are the subject of international standardization agreement as cited in NATO, STANAG NO. 2882, relative to camouflage requirements for tents, shelters and subsidiary components. When amendment, revision, or cancellation of this document is proposed which will affect or violate the international agreement concerned, the preparing activity will take appropriate reconciliation action through international standardization channels including departmental standardization offices, if required.

6.6 Changes from previous issue. Marginal notations are not used in this revision to identify changes with respect to the previous issue due to the extensiveness of the changes.

Custodians:

Army - GL
Navy - NU
Air Force - 99

Review activities:

Army - MD
Air Force - 82
DLA - CT

User activities:

Army - ME
Navy - MC,
Air Force - 45

Preparing activity:

Army - GL

(Project 8340-0539)

Source: https://assist.dla.mil -- Downloaded: 202610-16T07:36Z
Check the source to verify that this is the currentversion before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS

1. The preparing activity must complete blocks 1, 2, 3, and 8. In block 1, both the document number and revision letter should be given.
2. The submitter of this form must complete blocks 4, 5, 6, and 7.
3. The preparing activity must provide a reply within 30 days from receipt of the form.

NOTE: This form may not be used to request copies of documents, nor to request waivers, or clarification of requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

I RECOMMEND A CHANGE:	1. DOCUMENT NUMBER	2. DOCUMENT DATE (YYMMDD)
	MIL-P-501P	1991 March 1

3. DOCUMENT TITLE

PIN, TENT, METAL

4. NATURE OF CHANGE (*Identify paragraph number and include proposed rewrite, if possible. Attach extra sheets as needed.*)

5. REASON FOR RECOMMENDATION

6. SUBMITTER

a. NAME (Last, First, Middle Initial)	b. ORGANIZATION	c. TELEPHONE (Include Area Code)
d. ADDRESS (Include Zip Code)	e. ASSIGNMENT (Check one)	f. DATE SUBMITTED

8. PREPARING ACTIVITY

a. NAME	b. TELEPHONE (Include Area Code) (1) Commercial	(2) AUTOVON
U.S. Army Natick RD&E Center	508-651-4531	256-4531
c. ADDRESS (Include Zip Code)	IF YOU DO NOT RECEIVE A REPLY WITHIN 45 DAYS, CONTACT:	

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T07:36Z
Check the source to verify that this is the current version before use.