FED SUP CLASS
6640

USER ACTIVITIES: ARMY - ME

REVIEWER ACTIVITIES: DoD - MB

This military standard is approved for use by all Departments and Agencies of the Department of Defense. Selection for all new engineering and design applications and for repetitive use shall be made from this document.



PART NUMBER	DIAMETER OF FIBERS* micrometers (in)	PACKAGING	DIMENSIONAL DATA, mm (in)* THICKNESS	WIDTH	LENGTH
MS36095-1	5-8 (0.0002-0.0003)	0.23 kg (1/2 lb) roll	3 (0.12)	250 (10)	1300 (51)
MS36095-2		CANCELED WITHOUT REPLACEMENT			
MS36095-3		CANCELED, REPLACED BY MS36095-1			

* Nominal Dimensions

(LEFT MARGIN - 15)

MATERIAL Glass wool fibers shall be manufactured from borosilicate glass conforming to the requirements for Type I, Class A glass of ASTM E 438.

The glass fibers shall be soft, resilient, and pliable, and shall be practically free from fluorine, alumina, and heavy metals. They shall have a low alkali content to be suitable for use as a filtering medium.

DESIGN: MS36095-1 shall be supplied in the form of rolled sheets.

NOTES
1. Items differing from this Military Standard by minor variations in design or dimensions are considered standard under this document, provided such variations do not affect performance and are not in conflict with the material requirements as specified herein.
2. MS36095-1 is the product of one manufacturer, viz, FSCM 14674.

APPROVED 28 JUN 1961 REVISED (A) 04 JUN 1969 (B) 11 FEB 1988

(B) ENTIRE STANDARD REVISED

P A	EA	INTERNATIONAL INTEREST	TITLE
Other Cost	MS 99		GLASS WOOL, FILTERING

PROCUREMENT SPECIFICATION: NONE | SUPERSEDES:

MILITARY STANDARD
MS 36095
SHEET 1 OF 1

DD FORM 1 MAY 73 672-1 (COORDINATED)

PREVIOUS EDITIONS OF THIS FORM ARE OBSOLETE

PROJECT NUMBER 6640-1467-2
REVISION

DISTRIBUTION STATEMENT A. Approved for public release, distribution is unlimited

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T17:34Z
Check the source to verify that this is the current version before use.