MILITARY SPECIFICATION

FORCEPS, EAR, SERRATED JAWS, HARTMANN

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers one type of ear forceps, of the Hartmann design.

2. APPLICABLE DOCUMENTS

2.1 The following documents of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein:

SPECIFICATIONS

FEDERAL

GG-I-526	- Instruments, Dental and Surgical; General Specifications.
PPP-B-566	- Boxes, Folding, Paperboard.
PPP-B-585	- Boxes, Wood, Wirebound.
PPP-B-601	- Boxes, Wood, Cleated-Plywood.
PPP-B-621	- Boxes, Wood, Nailed and Lock-Corner.
PPP-B-636	- Boxes, Shipping, Fiberboard.
PPP-B-676	- Boxes, Set-up.

MILITARY

MIL-P-116	- Preservation, Methods of.
MIL-L-10547	- Liners, Case, and Sheet Overwrap; Water-Vaporproof or Waterproof, Flexible.

STANDARDS

MILITARY

MIL-STD-105	- Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129	- Marking for Shipment and Storage.

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Hq., Defense Personnel Support Center, ATTN: Directorate of Medical Materiel, Code ATT, 2800 South 20th Street, Philadelphia, PA 19101, by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T10:57Z
Check the source to verify that this is the current version before use.

DRAWING

Defense Personnel Support Center (DPSC) Drawing

No. 20426 FORCEPS, EAR, SERRATED JAWS, HARTMANN

(Copies of specifications, standards, and drawing required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

ASTM E 18 - Rockwell Hardness and Rockwell Superficial Hardness of Metallic Materials.

ASTM E 92 - Vickers Hardness of Metallic Materials, Test for.

ASTM E 140 - Standard Hardness Conversion Tables for Metals.

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

(Technical society and technical association specifications and standards are generally available for reference from libraries. They are also distributed among technical groups and using Federal agencies.)

3. REQUIREMENTS

3.1 General requirements. The forceps shall be in accordance with the applicable requirements of GG-I-526 and as specified herein.

3.2 Material. Shall be fabricated from class 4, type 420 material.

3.3 Hardness. After proper stress relieving, the forceps shall have a Rockwell hardness of C40 to C45 when tested as specified in 4.4.1. The requirements of GG-I-526 shall apply.

3.4 Style, design and dimensions. Shall be an ear forceps, of the Hartmann design, delicate model, having serrated, alligator-type jaws, suitable for removal of foreign bodies from the ear. The jaw serrations of both jaws shall be well defined. The jaws of the forceps shall mesh completely when the forceps are placed in the closed position. The action of the forceps

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T10:57Z
Check the source to verify that this is the current version before use.

shall be easy, not stiff, without drag or binding characteristics. Shanks of the forceps shall be aligned to assure proper action. Forceps shall possess proper lever action, and all surfaces shall be designed to be accessible for sterilization purposes. Forceps utilizing pin design, where the pin is permanently secured for lever action, shall not be acceptable. Forceps shall be in accordance with DPSC Drawing Number 20426.

3.5 Finish. Finish shall be mirror, or mirror and satin.

3.5.1 Passivation. The entire item shall be properly passivated.

3.6 Identification marking. In addition to GG-I-526 requirements, forceps of foreign manufacture shall also be marked "stainless".

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specifications where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Inspection. Shall be in accordance with GG-I-526.

4.1.2 Records. Records of examinations and tests performed by or for the contractor shall be maintained by the contractor and made available to the Government, upon the Government's request, at any time, or from time to time, during the performance of the contract and for a period of 3 years after delivery of the supplies to which such records relate.

4.1.3 Certificates of quality. Certificates of quality, supplied by the manufacturer of the corrosion-resisting steel, may be furnished in lieu of actual performance of such testing by the contractor, provided lot identity has been maintained and can be demonstrated to the Government. The certificate shall include the name of the contractor, the contract number, the name of the manufacturer or supplier, the National Stock Number (NSN), the item identification, the name of the material, the lot number, the lot size, the sample size, the date of testing, the test method, individual test results, and the specification requirements.

4.2 Sampling.

4.2.1 For examination. Sampling for examination shall be conducted in accordance with MIL-STD-105, and as indicated in table I. The unit of product for examination purposes shall be one forceps.

Source: https://assist.dla.mil -- Downloaded: 202640-21T10:57Z
Check the source to verify that this is the currentversion before use.

TABLE I. Sampling criteria for examination.

Type of defect	Inspection level	AQL (percent defective)
Major	II	1.0
Minor	II	2.5

4.2.2 For tests. Sampling for tests shall be conducted in accordance with MIL-STD-105, and as indicated in table II. The unit of product for test purposes shall be one forceps. Where feasible, the same sample unit shall be used for the determination of two or more test characteristics.

TABLE II. Sampling criteria for tests.

Component	Characteristic	Requirement	Test procedure	Inspection level	AQL percent defective
Forceps	Hardness	3.3 & GG-I-526	4.4.1	S-2	1.5
	Dimensions	3.4	-----	S-2	2.5
	Copper sulfate test	GG-I-526	GG-I-526	S-2	1.0
	Boil test	GG-I-526	GG-I-526	S-2	1.0

4.2.3 Raw materials. A sufficient quantity of each lot of metal used in the manufacture of the scissors shall be selected for chemical analysis.

4.3 Examination.

4.3.1 Examination of forceps. The forceps shall be examined to determine compliance with all the requirements contained in this specification. Examination shall be conducted as specified in tables I and III. Examination, however, shall not be restricted to defects listed in table III. Any forceps in the sample containing one or more defects shall be rejected, and if the number of defective forceps in any sample exceeds the acceptance number for the sample, the lot represented by the sample shall be rejected.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T10:57Z
Check the source to verify that this is the current version before use.

TABLE III. Classification of defects

Categories	Defects
Critical	None defined.
Major	
101	Forceps not of the design specified.
102	Both jaws do not possess serrations of equal length and equal depth.
103	Serrations not well defined.
104	Ends of serrations do not possess a well defined chamfer.
105	Jaws do not properly mesh when forceps are placed in the closed position.
106	Action of forceps stiff (opening and closing).
107	All surfaces of forceps not accessible for sterilization and cleaning procedures.
108	Forceps possess pin design for lever action.
109	Finish not as specified.
110	Forceps not free from burrs, cracks, pits, rough areas, scale and corrosion.
Minor	
201	Identification markings not present, not correct, not complete or not legible.

4.3.2 Packaging inspection. The inspection of the preservation-packaging and interior package marking shall be in accordance with the group A and B quality conformance inspection requirements of MIL-P-116. The inspection of the packing and marking for shipment and storage shall be in accordance with the quality assurance provisions of the applicable container specification and the marking requirements of MIL-STD-129.

4.4 Tests. Tests shall be conducted to determine compliance with specification requirements.

4.4.1 Hardness test. Hardness shall be determined in accordance with ASTM Std. Method E 18 or E 92. Conversion of Vickers hardness values to Rockwell values shall be in accordance with ASTM Std. Hardness Conversion Tables E 140.

5. PACKAGING

5.1 Preservation-packaging. Preservation-packaging shall be level A or C as specified (see 6.1).

5.1.1 Level A.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T10:57Z
Check the source to verify that this is the current version before use.

5.1.1.1 Cleaning, drying and preservative. Each forceps shall be thoroughly cleaned and dried in accordance with the applicable method as outlined in MIL-P-116. Preservative shall not be applied.

5.1.1.2 Unit packaging. Each forceps shall be wrapped in neutral tissue or other suitable anticorrosive materials. Each forceps shall be further packaged in accordance with MIL-P-116, method 1C-2.

5.1.1.3 Intermediate packaging. Six (6) forceps shall be packaged in a box of appropriate size and design constructed in accordance with PPP-B-566, PPP-B-676 or PPP-B-636, type CF, class domestic. Closure shall be in accordance with the appendix of the applicable box specification.

5.1.2 Level C. Units shall be packaged in standard commercial containers of the size and kind commonly used, which will afford the degree of protection required for shipment and use of the product for its intended purpose.

5.2 Packing. Packing shall be level A, B or C as specified (see 6.1).

5.2.1 Level A. One hundred forty four (144) forceps shall be packed in a box designed for a type 2 load, and constructed in accordance with PPP-B-585, class 3, style 3; PPP-B-601, overseas type; PPP-B-621, class 2 or PPP-B-636, class weather resistant, grade V3c. Closure and strapping shall be as specified in the appendix of the applicable box specification.

5.2.1.1 Case liner. Each level A wood box shall be lined with a waterproof case liner conforming to MIL-L-10547. Closure and sealing shall conform to applicable paragraphs of appendix thereto. Case liner shall not be required for fiberboard boxes. Fiberboard box shall be waterproof in accordance with the appendix of PPP-B-636.

5.2.2 Level B. One hundred forty four (144) forceps shall be packed in a box designed for a type 2 load, and constructed in accordance with PPP-B-585, class 1, style 3; PPP-B-601, domestic type; PPP-B-621, class 1; or PPP-B-636, type CF, class domestic. Closure shall be as specified in the appendix of the applicable box specification.

5.2.3 Level C. The subject commodity shall be packed in substantial commercial containers of the type, size, and kind commonly used for the purpose, so constructed as to insure acceptance and safe delivery by common or other carriers, at the lowest rate, to point of delivery called for in the contract or purchase order.

5.3 Marking.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T10:57Z
Check the source to verify that this is the current version before use.

5.3.1 Unit, intermediate and exterior container. Each unit, intermediate and exterior container shall be marked in accordance with MIL-STD-129.

6. NOTES

6.1 Ordering data. Procurement documents shall specify the following:

(a) Number, title and date of this specification.
(b) Selection of applicable levels of packaging required (see 5.1 and 5.2).
(c) National Stock Number (NSN).

6.2 This specification covers the following item appearing in the Federal Supply Catalog:

NSN 6515-00-333-5400 FORCEPS, EAR, Serrated Jaws, Hartmann.

Custodians:
Army - MD
Navy - MS
Air Force - 03

Preparing activity:
Defense Supply Agency - DM

Project No. 6515-2015

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T10:57Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

OMB Approval
No. 22-R255

INSTRUCTIONS: The purpose of this form is to solicit beneficial comments which will help achieve procurement of suitable products at reasonable cost and minimum delay, or will otherwise enhance use of the document. *DoD contractors, government activities, or manufacturers/ vendors who are prospective suppliers of the product* are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity.

DOCUMENT IDENTIFIER AND TITLE

MIL-F-37543 FORCEPS, EAR, SERRATED JAWS, HARTMANN

NAME OF ORGANIZATION AND ADDRESS

CONTRACT NUMBER

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY DOCUMENT REQUIREMENT CONSIDERED TOO RIGID

3. IS THE DOCUMENT RESTRICTIVE?

☐ YES ☐ NO *(If "Yes", in what way?)*

4. REMARKS

SUBMITTED BY *(Printed or typed name and address - Optional)*

TELEPHONE NO.

DATE

DD FORM 1 JAN 72 1426

REPLACES EDITION OF 1 JAN 66 WHICH MAY BE USED

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T10:57Z
Check the source to verify that this is the current version before use.