NOT MEASUREMENT SENSITIVE
MIL-P-85856/14
7 December 1988

MILITARY SPECIFICATION SHEET

POWDER MATERIALS FOR FLAME AND PLASMA SPRAYED COATINGS TYPE 316 STAINLESS STEEL, TYPE I, CLASS 2, COMPOSITION M

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The complete requirements for acquiring the powder described herein shall consist of this document and the latest issue of MIL-P-85856.

Chemical Composition

Mo	Cr	Ni	Fe	C	Mn	Si	P	S
2.0 3.0	16.0 18.0	10.0 14.0	Bal	0.1 max.	2.0 max.	3.5 max.	0.04 max.	0.03 max.

Particle Size/Distribution

+140 Mesh (+106 µm)	20.0 max.
-325 Mesh (-45 µm)	20.0 max.

Sprayed Coating Properties

Bond Strength	17.3 MPa (2500 psi) min.
Hardness	Rockwell 15T, 90 min.
Microstructure	See paragraph 4.5.4.1.2 Porosity - 10% max. Unmelted Particles - 5% max.

AMSC N/A FSC 3439

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T11:32Z
Check the source to verify that this is the current version before use.

Deposit Efficiency and Deposition Rate

70% min for N_2/H_2 @ 11.6 lb/hr

Comparable Documents

Powder which meets the requirements specified is qualified under the following specifications.

Rolls-Royce Ltd.	MSRR 9507/26

Custodians:
Air Force - 20
Navy - AS
Army - MR

Review activities:
Air Force - 99, 71
Navy - SH

Preparing activity:
Navy - AS
(Project No. 3439-0663/14)

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T11:32Z
Check the source to verify that this is the current version before use.