NOT MEASUREMENT SENSITIVE
MIL-P-85856/19
7 December 1988

MILITARY SPECIFICATION SHEET

POWDER MATERIALS FOR FLAME AND PLASMA SPRAYED COATINGS COPPER-NICKEL, TYPE I, CLASS 2, COMPOSITION T

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The complete requirements for acquiring the powder described herein shall consist of this document and the latest issue of MIL-P-85856.

Chemical Composition

Ni	Cu	Others	
		Each	Total
37.0 39.0	Bal	-	1.0 max.

Particle Size/Distribution

+200 Mesh (+75 µm)	5.0 max.
-325 Mesh (-45 µm)	5.0 max.

Sprayed Coating Properties

Bond Strength	38.0 MPa (5500 psi) min.
Hardness	Rockwell 15T, 85 min.
Microstructure	See paragraph 4.5.4.1.2 Porosity - 5% max. Unmelted Particles - 10% max.

Deposit Efficiency and Deposition Rate

60% min for N_2/H_2 @ 6.0 lb/hr
60% min for A/H_2 @ 6.0 lb/hr

AMSC N/A FSC 3439

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T11:32Z
Check the source to verify that this is the current version before use.

Comparable Documents

Powder which meets the requirements specified is qualified under the following specifications.

General Electric Company	B50TF42, Class A
Pratt & Whitney Aircraft	PWA 1369

Custodians:
Air Force - 20
Navy - AS
Army - MR

Review activities:
Air Force - 99, 71
Navy - SH

Preparing activity:
Navy - AS
(Project No. 3439-0663/19)

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T11:32Z
Check the source to verify that this is the current version before use.