NOT MEASUREMENT SENSITIVE

MIL-P-85856/20
7 December 1988

MILITARY SPECIFICATION SHEET

POWDER MATERIALS FOR FLAME AND PLASMA SPRAYED COATINGS
NICKEL-CHROMIUM ALLOY, TYPE I, CLASS 1, COMPOSITION U

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The complete requirements for acquiring the powder described herein shall consist of this document and the latest issue of MIL-P-85856.

Chemical Composition

Cr	Ni	Fe	C	Mn	Si
18.0 21.0	76.0 80.0	1.0 max.	0.25 max.	2.5 max.	1.5 max.

Particle Size/Distribution

-270 Mesh (-53 µm)	100.0 min.	
+325 Mesh (+45 µm)	1.0 max.	
-20 µm	75.0 max.	45.0 min.
-5 µm	5.0 max.	

Sprayed Coating Properties

Bond Strength	31.0 MPa (4500 psi) min.
Hardness	Rockwell 15T, 90 min.
Microstructure	See paragraph 4.5.4.1.2 Porosity - 5% max. Unmelted Particles - 5% max.

AMSC N/A FSC 3439

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T11:32Z
Check the source to verify that this is the current version before use.

Deposit Efficiency and Deposition Rate

60% min for N_2/H_2 @ 6.0 lb/hr
45% min for A/H_2 @ 6.0 lb/hr

Comparable Documents

Powder which meets the requirements specified is qualified under the following specifications.

Pratt & Whitney Aircraft	PWA 1319

Custodians:
Air Force - 20
Navy - AS
Army - MR

Review activities:
Air Force - 99, 71
Navy - SH

Preparing activity:
Navy - AS
(Project No. 3439-0663/20)

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T11:32Z
Check the source to verify that this is the current version before use.