NOT MEASUREMENT SENSITIVE

MIL-P-85856/30
7 December 1988

MILITARY SPECIFICATION SHEET

POWDER MATERIALS FOR FLAME AND PLASMA SPRAYED COATINGS
TUNGSTEN CARBIDE-COBALT,
TYPE II, CLASS 1, COMPOSITION A

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The complete requirements for acquiring the powder described herein shall consist of this document and the latest issue of MIL-P-85856.

Chemical Composition

Fe	C	Co	W	Others	
				Each	Total
2.0 max.	3.6 4.3	10.0 13.0	80.0 min.	0.5 max.	-

Particle Size/Distribution

-200 Mesh (75 µm)	100.0 min.
+325 Mesh (+45 µm)	0.5 max.
-20 µm	70.0 min.
-5 µm	10.0 max.

Sprayed Coating Properties

Bond Strength	45.0 MPa (6500 psi) min.
Hardness	Rockwell 15N, 86 min.
Microstructure	See paragraph 4.5.4.1.2 Porosity - 3% max. Unmelted Particles - 1% max.

AMSC N/A FSC 3439

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T11:32Z
Check the source to verify that this is the current version before use.

Deposit Efficiency and Deposition Rate

50% min for A/H_2 @ 8.0 lb/hr

Comparable Documents

Powder which meets the requirements specified is qualified under the following specifications.

General Electric Company	B50TF175, Class A
Pratt & Whitney Aircraft	AMS 7879

Custodians:
Air Force - 20
Navy - AS
Army - MR

Review activities:
Air Force - 99, 71
Navy - SH

Preparing activity:
Navy - AS
(Project No. 3439-0663/30)

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T11:32Z
Check the source to verify that this is the current version before use.