MILITARY SPECIFICATION SHEET

POWDER MATERIALS FOR FLAME AND PLASMA SPRAYED COATINGS ALUMINUM-BRONZE, TYPE I, CLASS 1, COMPOSITION F

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The complete requirements for acquiring the powder described herein shall consist of this document and the latest issue of MIL-P-85856.

Chemical Composition

Fe	Al	Cu	Others	
			Each	Total
0.7 2.0	8.0 11.0	Bal	-	1.0 max.

Particle Size/Distribution

-270 Mesh (53 µm)	90.0 min.
+325 Mesh (45 µm)	25.0 max.
-325 Mesh (45 µm)	70.0 min.

Sprayed Coating Properties

Bond Strength	13.8 MPa (2000 psi) min.
Hardness	Rockwell 15T, 85 min.
Microstructure	See paragraph 4.5.4.1.2 Porosity - 5% max. Unmelted Particles - 5% max.

Deposit Efficiency and Deposition Rate

70% min for N_2/H_2 @ 8.0 lb/hr
45%min for A/H_2 @ 7.0 lb/hr

AMSC N/A FSC 3439

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T11:31Z
Check the source to verify that this is the current version before use.

Comparable Documents

Powder which meets the requirements specified is qualified under the following specifications.

General Electric Company	B50TF161, Class B
Rolls-Royce Ltd.	MSRR 9507/29

Custodians:
Air Force - 20
Navy - AS
Army - MR

Review activities:
Air Force - 99, 71
Navy - SH

Preparing activity:
Navy - AS
(Project No. 3439-0663/03)

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T11:31Z
Check the source to verify that this is the current version before use.