NOT MEASUREMENT SENSITIVE

MIL-P-85856/44

7 December 1988

MILITARY SPECIFICATION SHEET

POWDER MATERIALS FOR FLAME AND PLASMA SPRAYED COATINGS, MAGNESIUM ZIRCONATE PLUS NICKEL CHROMIUM ALLOY, TYPE III, COMPOSITION R

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The complete requirements for acquiring the powder described herein shall consist of this document and the latest issue of MIL-P-85856.

Chemical Composition

Percent by Weight		Components
Min.	Max.	
34.0	36.0	Type I, Composition B, Class 1
64.0	66.0	Type II, Composition G, Class 1

Sprayed Coating Properties

Bond Strength	20.7 MPa (3000 psi) min.
Hardness	Rockwell 15N, 70 min.
Microstructure	See paragraph 4.5.4.1.2 Porosity - 15% max. Unmelted Particles - 10% max.

Deposit Efficiency and Deposition Rate

55% min for N_2/H_2 @ 8.0 lb/hr
55% min for A/H_2 @ 6.0 lb/hr

AMSC N/A FSC 3439

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T11:33Z
Check the source to verify that this is the current version before use.

Comparable Documents

Powder which meets the requirements specified is qualified under the following specifications.

Pratt & Whitney Aircraft	PWA 1346
Rolls-Royce, Ltd.	MSRR 9507/28

Custodians:
Air Force - 20
Navy - AS
Army - MR

Review activities:
Air Force - 99, 71
Navy - SH

Preparing activity:
Navy - AS
(Project No. 3439-0663/44)

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T11:33Z
Check the source to verify that this is the current version before use.