NOT MEASUREMENT SENSITIVE

MIL-P-85856/45
7 December 1988

MILITARY SPECIFICATION SHEET

POWDER MATERIALS FOR FLAME AND PLASMA SPRAYED COATINGS, COMPOSITE BLEND, TYPE III, COMPOSITION S

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The complete requirements for acquiring the powder described herein shall consist of this document and the latest issue of MIL-P-85856.

Chemical Composition

Percent by Weight		Components
Min.	Max.	
69.0	71.0	Type I, Composition DD, Class 2
Remainder		Type I, Composition FF, Class 2

Sprayed Coating Properties

Bond Strength	34.5 MPa (5000 psi) min.
Hardness	Rockwell 15T, 85 min.
Microstructure	See paragraph 4.5.4.1.2 Porosity - 5% max. Unmelted Particles - 5% max.

AMSC N/A FSC 3439

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T11:33Z
Check the source to verify that this is the current version before use.

Deposit Efficiency and Deposition Rate

55% min for A/H_2 @ 25.0 lb/hr

Custodians:
Air Force - 20
Navy - AS
Army - MR

Review activities:
Air Force - 99, 71
Navy - SH

Preparing activity:
Navy - AS
(Project No. 3439-0663/45)

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T11:33Z
Check the source to verify that this is the current version before use.