[METRIC]
A-A-2946
September 29, 1995

COMMERCIAL ITEM DESCRIPTION

PAPER, TRACING

The General Services Administration has authorized the use of this commercial item description for all Federal Agencies. When this commercial item description replaces, Federal Specification UU-P-561 which is cancelled.

1. Scope. This commercial item description covers tracing paper for use in the tracing of drawings, development of original drawings, and for other purposes requiring high grade tracing papers.

1.1. Classification.

Type I - White, rag, medium strength, natural tracing paper, permanent quality
Type II- White, chemical wood, untreated, good translucency, non-permanent quality
Type III- White or tinted blue, rag, high translucency, permanent quality
Type IV- White or tinted blue, rag, medium translucency, permanent quality.

2. Salient Characteristics.

2.1. Material. Tracing paper shall be made from fibrous, cellulosic material and shall conform to the requirements of Table 1.

2.2. Physical Requirements

2.2.1. Color. Types I and II shall be white. Types III and IV shall be white or tinted blue. The color shall not change on aging.

2.2.2. Exposure to ultra-violet radiation. Types III and IV shall develop no change in color or character of sufficient amount to increase the printing time when used for either the diazo or blueprinting process of reproduction.

2.2.3. Finish. All tracing papers shall be of uniform texture with slightly grained surface.

2.2.4. Curl. Types III and IV shall be flat when removed from the package and shall develop no curl during printing.

Beneficial comments, recommendations, additions, deletions, clarifications, etc. and any data which may improve this document should be sent to General Services Administration Federal Supply Service, Engineering Branch, 26 Federal Plaza New York, N.Y. 10278.

FSC 7530

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:27Z
Check the source to verify that this is the current version before use.

Table 1

Type	Basis Weight 17x22-500 | g/m^2	Cotton Fiber %	Min. Folding Endurance MD:CD avg. each dir. MIT	Schopper	Min. Folding Endurance after aging[3] MIT	Schopper	Min. Tearing Strength MD:CD avg. (grams)	Max. Opacity %[2]	Max. Opacity % after aging[3]
I	7.5-8.5 | 28-32	100	200	200	100	100	20	55	3
	9.5-11.0 | 36-41	100	300	300	150	150	28	62	3
	12.5-15.0 | 47-56	100	400	400	200	200	34	70	3
II	13.3-18.4 | 50-69	0[1]	150	150	75	75	15	28	9
	18.5-23.7 | 70-89	0[1]	200	200	100	100	23	30	9
	23.8-31.7 | 90-119	0[1]	250	250	125	125	28	34	9
	31.8-41.0 | 120-154	0[1]	300	300	150	150	45	38	9
	41.1-50.3 | 155-189	0[1]	350	350	175	175	54	40	9
	>50.4 | >190	0[1]	400	350	200	175	65	44	9
III	12.5-15.4 | 47-58	100	300	300	150	150	20	38	5
	15.5-18.4 | 59-69	100	450	400	225	200	30	47	5
	18.5-22.4 | 70-84	100	600	500	300	250	40	55	5
IV	12.5-15.4 | 47-58	100	450	400	225	200	20	47	7
	15.5-18.4 | 59-69	100	600	500	300	250	30	53	7
	18.5-22.4 | 70-84	100	750	600	375	300	40	60	7
	22.5-25.5 | 85-96	100	900	700	450	350	50	63	7
TAPPI	T410	T401	T511	T423	T511	T423	T414	T425	T425

[1]Type II - 95%, min. Bleached chemical wood pulp

[2]Variations between individual readings shall be no more than 4% points.

[3]Use Tappi T544 for aging samples

Source: https://assistdocs.mil --- Downloaded: 20241026T08:27Z
Check the source to verify that this is the current version before use.

2.2.5. Surface. All tracing papers shall be suitable for pencil and ink lines, yielding solid lines without skipping, feathering, spreading or smudging. Types III and IV shall not show surface cracks or abrasion with normal usage, and shall have a non-greasy surface suitable for printing with offset inks. The printed copy shall yield solid, sharp impressions which cannot be easily erased with a soft, non-gritty eraser. The prepared finish shall be such that when passing through a reproduction machine at peak temperature, the finished surface will not lift, flake or peel from the paper.

2.2.6. Form. The tracing paper shall be furnished in rolls, sheets, or pads as specified in the ordering description.

2.2.6.1. Sheets. Sheet paper shall be cut square on four sides, and cut to the sizes specified in the ordering description. Sheets shall be not less than the ordered size, and not more than +/- 0.2 cm (+/- 1/16") over size in either dimension for sizes 20.3 x 26.7 cm (8"x10 1/2") through 38.1 x 45.7 cm (15"x18") and not more than +0.3 cm (+1/8") oversize in either dimension for sheets larger than 38.1 x 45.7 cm (15x18"). Any flat paper with a long dimension 81.3 cm (32") or less will be considered square-cut if the variation of the diagonals does not exceed 0.8 mm (1/32"); over 81.3 cm (32"), 0.2 cm (1/16").

2.2.6.2. Rolls. Rolls shall be furnished in widths and lengths specified in the ordering description. Tolerance on roll width shall be +0.6, -0 cm (+1/4, -0"). The paper shall be uniformly and smoothly wound with an even tension on a fiberboard core having an inside diameter of 4.8 +/- 0.6 cm (1-7/8",+/- 1/4") and shall be suitable restrained to prevent unwinding. The length of the core shall be equal to the width of the roll material with a tolerance of -0, +0.3 cm (-0, +1/8").

2.2.6.3. Pads. Pads shall be furnished in widths and lengths as specified in the ordering description with a tolerance of +/- 0.3 cm (+/- 1/8"). The number of sheets per pad shall be as specified in the ordering description. Pads shall be securely padded at the top and the sheets bound together with glue or other commercially accepted method. Backs of pads shall be chipboard or other suitable material.

2.2.7. Drafting quality. Types III and IV shall allow a pencil line to be erased without causing ghosting, smudging, linting or appreciable change of color of the erased surface. Inked lines shall show no appreciable spreading, feathering, ragged edges or skips when drawn over a fresh or an erased area. There shall be no signs of oil leakage. All tracing paper shall be free of any tendency for sheets to adhere to each other.

2.3. Workmanship. Paper shall be uniform throughout and be free from holes, tears, spots, wrinkles, dirt, foreign matter, or other defects which might affect appearance or serviceability.

3. Bleaching. To obtain an acceptable brightness a chemical bleaching process may be used. When specified in the ordering data, the bleaching process shall not include the use of chlorine, chlorine dioxide, hypochlorite, or other chlorine containing compound. Certification of compliance shall be made available upon request by the Government.

Source: https://assist.dla.mil -- Downloaded: 2026l0-26T08:27Z
Check the source to verify that this is the currentversion before use.

4. Regulatory Requirements. The contractor shall certify that the minimum content standard shall be no less than 50% recovered materials including 20% postconsumer materials in accordance with Executive Order 12873, section 504 (b), dated October 20, 1993 (See definition of postconsumer materials and recovered materials in sections 203 and 205). As an alternative to meeting the standards of section 504(b) for all printing and writing papers, the minimum content standard shall be no less than 50% recovered materials that are a waste material byproduct of a finished product other than a paper or textile product which would otherwise be disposed of in a landfill, as determined by the State in which the facility is located, in accordance with Executive Order 12873, section 504 (c), dated October 20, 1993. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

4.1. Labeling. The recycled content shall be marked on the product or unit pack.

5. Quality Assurance Provisions.

5.1. Contractor Certification. The contractor shall certify and maintain substantiating evidence that the product offered meets the salient characteristics of this Commercial Item Description, and that the product conforms to the producer's own drawings, specifications, standards, and quality assurance practices. The government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

5.1.1. Suppliers are encouraged to use quality control (QC) techniques that exhibit control over their processes (e.g. SPC techniques). These techniques shall ensure quality levels equal to, or greater than, those cited in the applicable technical document or, herein. For those product characteristics which are controlled by such a method, requirements for end item inspection or test may be considered to have been met. End item inspection/testing may be used by the offeror, or the Government representative, as a means to determine the effectiveness of the in-process quality controls. In-process controls shall not be substituted for end item performance testing, unless it can be demonstrated that there exists a direct correlation between the process control and product performance, such that end item performance testing is obviated.

5.1.2 For those characteristics for which there are no such controls, or for end item performance test, lot by lot sampling for inspection/test shall be required.

Sampling for Tappi tests shall be in accordance with Tappi T400. Sampling for all other tests shall be in accordance with The American National Standards Institute (ANSI)/ American Society for Quality Control (ASQC) Z1.4-1933, Sampling Procedures and Tables for Inspection by Attributes. The inspection level shall be S-3 with an AQL of 4 percent defective.

6. Packaging, Packing, and Marking. Packaging, packing and marking shall be as specified in the contract or order.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:27Z
Check the source to verify that this is the current version before use.

7. Applicable Documents and Document Sources. The following documents form a part of the Commercial Item Description to the extent specified herein. Unless otherwise indicated, the issue in effect on the date of invitation for bids or request for proposal shall apply:

(1) Tappi Standards are available from the Technical Association of the Pulp and Paper Industry, P.O. Box 105113, Atlanta, GA 30348.
(2) The American National Standards Institute (ANSI)/ American Society for Quality Control (ASQC) Z1.4-1933, Sampling Procedures and Tables for Inspection by Attributes. American Society for Quality Control, P.O. Box 3005, 611 E. Wisconsin Avenue, Milwaukee, Wi 53201-4606.
(3) Executive Order 12873 is available from The White House Publications Office, New Executive Office Building, White House, Att: Publications, Washington, D.C. 20500. Phone (202) 395-7332.
(4) Copies of Commercial Item Descriptions, federal standards or specifications are available from: Federal Supply Service Bureau, Specification Section (3FPB-W), Suite 8100, 470 East L'Enfant Plaza, SW, Washington, DC 20407.

8. Ordering Data. Purchasers should select the preferred options permitted herein, and include the following information in procurement documents:
1. Title, number and date of the Commercial Item Description
2. Type and weight
3. Color
4. Form, size of sheets, length and width of rolls and pads
5. Number of sheets per pad
6. If non-chlorine bleaching is required
10. Packaging, packing and marking

8.1 Part Identification Number (PIN). The following part identification numbering procedure is for government purposes and does not constitute a requirement for the contractor.

This example describes a white, rag, medium strength tracing paper

AA2946- 1 Example of reference part number:
AA2946 -1

1- Type I- White, rag, medium strength
2- Type II - White, chemical wood
3- Type III- White or tinted blue, rag, high translucency
4- Type IV - White or tinted blue, rag, medium translucency

MILITARY INTEREST:

Army - GL

PREPARING ACTIVITY:

GSA-FSS

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:27Z
Check the source to verify that this is the current version before use.