MIL-M-24325(SHIPS)
AMENDMENT-2
30 January 1974
SUPERSEDING 1/
Amendment-1
13 November 1973

MILITARY SPECIFICATION

MOLDING MATERIAL, PLASTIC, EPOXY COMPOUNDS

THERMOSETTING

This amendment forms a part of Military Specification MIL-M-24325(SHIPS), 7 June 1968, and is approved for use by all Department and Agencies of the Department of Defense.

Page 1

1.2: Add the following type:

"Type GEI-250 - Glass fiber filler, impact resistant, impact strength 25.0 foot-pounds per inch notch."

Pages 2 and 3

Table I: Add the following column for type GEI-250:

PROPERTY TO BE TESTED		TYPE GEI-250
ARC RESISTANCE		120
COMPRESSIVE STRENGTH (ENDWISE)		26000
DIELECTRIC CONSTANT		
1 KILOHERTZ	DRY	6.3
	WET	6.6
1 MEGAHERTZ	DRY	6.0
	WET	6.3
DISSIPATION FACTOR		
1 KILOHERTZ	DRY	0.025
	WET	.030
1 MEGAHERTZ	DRY	.020
	WET	.025
DIELECTRIC STRENGTH		
SHORT TIME	DRY	300
STEP BY STEP		300
SHORT TIME	WET	275
STEP BY STEP		275
DIELECTRIC BREAKDOWN		
SHORT TIME	DRY	40
STEP BY STEP		35
SHORT TIME	WET	40
STEP BY STEP		35

1/ THE MARGINS OF THIS SPECIFICATION ARE MARKED "#" TO INDICATE WHERE CHANGES (ADDITIONS, MODIFICATIONS, CORRECTIONS, DELETIONS) FROM THE PREVIOUS ISSUE HAVE BEEN MADE. THIS WAS DONE AS A CONVENIENCE ONLY AND THE GOVERNMENT ASSUMES NO LIABILITY WHATSOEVER FOR ANY INACCURACIES IN THESE NOTATIONS. BIDDERS AND CONTRACTORS ARE CAUTIONED TO EVALUATE THE REQUIREMENTS OF THIS DOCUMENT BASED ON THE ENTIRE CONTENT IRRESPECTIVE OF THE MARGINAL NOTATIONS AND RELATIONSHIP TO THE LAST PREVIOUS ISSUE.

FSC 9330

Source: https://assist.dla.mil -- Downloaded: 20260-19T21:24Z
Check the source to verify that this is the current version before use.

Pages 2 and 3 (cont'd)

Table I: Add the following column for type GEI-250 (cont'd):

PROPERTY TO BE TESTED	TYPE GEI-250
FLAME RESISTANCE	
IGNITION TIME	90
BURNING TIME	250
FLEXURAL STRENGTH (FACE)	35000
HEAT DISTORTION TEMP. (SIDE)	200
IMPACT STRENGTH, FT-LB/IN. NOTCH	
FACE	25.0
SIDE	25.0
TENSILE STRENGTH	15000
WATER ABSORPTION	0.25
HEAT RESISTANCE	25
DIMENSIONAL STABILITY (HIGH TEMP.)	0.2
VOLUME RESISTANCE	1000
SURFACE RESISTANCE	1000

Page 6

Table III: Add the following column for type GEI-250:

"Property to be tested	Type GEI-250
Arc resistance	120
Dielectric constant at 1 megahertz, wet	6.3
Dissipation factor at 1 megahertz, wet	0.25
Dielectric strength Step-by-step, wet	275
Flexural strength, face	35000
Impact strength, side	25
Water absorption	0.25 "

Page 10

Add new paragraph 6.1.8:

"6.1.8 Type GEI-250. This type is a glass-filled compound of high impact strength and high heat resistance."

6.3 and 6.4: Delete and substitute:

"6.3 With respect to products requiring qualification, awards will be made only for products which are at the time set for opening of bids, qualified for inclusion in applicable Qualified Products List QPL 24325, whether or not such products have actually been so listed by that date. The attention of the suppliers is called to this requirement, and manufacturers are urged to arrange to have the products that they propose to offer to the Federal Government tested for qualification in order that they may be eligible to be awarded contracts or orders for the products covered by this specification. The activity responsible for the Qualified Products List is the Naval Ship Engineering Center, Prince George's Center, Center Building, Hyattsville, Maryland 20782, and information pertaining to qualification of products may be obtained from that activity. Application for Qualification tests shall be made in accordance with "Provisions Governing Qualification SD-6" (see 6.4).

Source: https://assist.dla.mil -- Downloaded: 20260-19T21:24Z
Check the source to verify that this is the current version before use.

6.4 Copies of "Provisions Governing Qualification SD-6" may be obtained upon application to Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, Pennsylvania 19120."

6.5: Delete first two sentences and substitute:

"6.5 Toxicity when heated. It is desired that the following maximum concentrations of the toxic gases not be exceeded when the materials are tested in accordance with the methods of National Technical Information Services Report AD297457. Copies are available from the Department of Commerce, National Technical Information Service, 5285 Port Royal Road, Springfield, Virginia 22151."

6.6: Delete and substitute:

"6.6 Color chips. Color chips may be obtained from Specification Sales (Code 3FRSBS), Building 197, Washington Navy Yard, General Services Administration, Washington, D.C. 20407.)"

Add new paragraph 6.7:

"6.7 International interest. Certain provisions of this specification are the subject of international standardization agreement (ABC-NAVY-STD-17). When amendment, revision, or cancellation of this specification is proposed which affects or violates the international agreement concerned, the preparing activity will take appropriate reconciliation action through international standardization channels including departmental standardization offices, if required."

Preparing activity:
Navy - SH
(Project 9330-N641)

International standardization (see 6.7)

Source: https://assist.dla.mil -- Downloaded: 20261O-19T21:24Z
Check the source to verify that this is the current version before use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T21:24Z
Check the source to verify that this is the current version before use.