The documentation and process conversion measures necessary to comply with this document shall be completed by 23 April 2020.

INCH-POUND

MIL-PRF-19500/768D
23 January 2020
SUPERSEDING
MIL-PRF-19500/768C
13 July 2019

PERFORMANCE SPECIFICATION SHEET

SEMICONDUCTOR DEVICE, DIODE, SILICON, ULTRAFAST RECOVERY, POWER RECTIFIER, TYPES 1N7066, 1N7067, 1N7068, AXIAL LEADED AND SURFACE MOUNT PACKAGES, QUALITY LEVELS JAN, JANTX, JANTXV, AND JANS

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specification sheet and MIL-PRF-19500.

1. SCOPE

1.1 Scope. This specification covers the performance requirements for silicon, ultra fast recovery, power rectifier diodes. Four levels of product assurance (JAN, JANTX, JANTXV and JANS) are provided for each encapsulated device type as specified in MIL-PRF-19500.

1.2 Package outlines. The device package outlines are as follows: An axial leaded package in accordance with figure 1 and square end-cap surface mount package (US) in accordance with figure 2.

1.3 Maximum ratings. Unless otherwise specified, T_A = +25°C.

1.3.1 Ratings applicable to all Part or Identifying Numbers (PIN). $T_{STG} = T_{J(max)}$ = −65°C to +175°C.

* 1.3.2 Ratings applicable to individual types.

Col. 1	Col. 2	Col. 3	Col. 4	Col. 5	Col. 6	Col. 7
Types	V_{RWM}	I_O $T_L \leq$ +55°C L = .125 inch (3.175 mm) or T_{EC} < +100°C (1) (2)	I_{FSM} at T_A = +25°C operating at I_O t_p = 8.3 ms	t_{rr}	$R_{\theta JL}$ at L = .125 inch (3.175 mm)	$R_{\theta JEC}$
		A	A(pk)	ns	°C/W	°C/W
1N7066, US	100	10	250	30	8	4.5
1N7067, US	150	10	250	30	8	4.5
1N7068, US	200	10	250	30	8	4.5

(1) Axial lead, derate at 83.3 mA/°C above rated T_L.
(2) Surface mount, derate at 133.3 mA/ºC above rated T_{EC}.

Comments, suggestions, or questions on this document should be addressed to DLA Land and Maritime, VAC, P.O. Box 3990, Columbus, OH 43218-3990, or emailed to Semiconductor@dla.mil. Since contact information can change, you may want to verify the currency of this address information using the ASSIST Online database at https://assist.dla.mil.

AMSC N/A

FSC 5961

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T05:52Z
Check the source to verify that this is the current version before use.

1.4 Primary electrical characteristics. Unless otherwise specified, T_A = +25°C.

Types	V_{BR} at 100 µA, pulse ≤ 20 ms	I_{R1} at $V_R = V_{RWM}$ T_A = +25°C, pulsed V_R ≤ 20 ms	I_{R2} at $V_R = V_{RWM}$ T_A = +125°C, pulsed V_R ≤ 20 ms
	Volts	µA	µA
1N7066, US	110	1.0	100
1N7067, US	165	1.0	100
1N7068, US	220	1.0	100

1.5 PIN. The PIN is in accordance with MIL-PRF-19500, and as specified herein. See 6.4 for PIN construction example and 6.5 for a list of available PINs.

1.5.1 JAN certification mark and quality level. The quality level designators for encapsulated devices that are applicable for this specification sheet from the lowest to the highest level are as follows: "JAN", "JANTX", "JANTXV" and "JANS".

1.5.2 Device type. The designation system for the devices covered by this specification sheet is as follows.

1.5.2.1 First number and first letter symbols. The devices of this specification sheet use the first number and letter symbols "1N".

1.5.2.2 Second number symbols. The second number symbols for the devices covered by this specification sheet are as follows: "7066", "7067", and "7068".

1.5.3 Suffix symbols. The following suffix symbol(s) are incorporated into the PINs for this specification sheet.

	A blank suffix symbol identifies that the package is an axial leaded device.
US	A "US" designators identifies that the device is in a SMD package configuration.

1.5.4 Lead finish. The lead finishes applicable to this specification sheet are listed on QPDSIS-19500.

2. APPLICABLE DOCUMENTS

2.1 General. The documents listed in this section are specified in sections 3 and 4 of this specification. This section does not include documents cited in other sections of this specification or recommended for additional information or as examples. While every effort has been made to ensure the completeness of this list, document users are cautioned that they must meet all specified requirements of documents cited in sections 3 and 4 of this specification, whether or not they are listed.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T05:52Z
Check the source to verify that this is the current version before use.

2.2 Government documents.

2.2.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those cited in the solicitation or contract.

DEPARTMENT OF DEFENSE SPECIFICATIONS


MIL-PRF-19500 - Semiconductor Devices, General Specification for.

DEPARTMENT OF DEFENSE STANDARDS

MIL-STD-750 - Test Methods for Semiconductor Devices.

(Copies of these documents are available online at https://quicksearch.dla.mil.)

2.3 Order of precedence. Unless otherwise noted herein or in the contract, in the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.




LTR	Dimensions				Notes
	Inches		Millimeters		
	Min	Max	Min	Max	
BD	.135	.165	3.43	4.19	2
BL	.135	.155	3.43	3.94	3
LD	.036	.042	0.91	1.07	3
LL	.900	1.30	22.86	33.02	

NOTES:
1. Dimensions are in inches. Millimeters are given for general information only.
2. Dimension BD shall be measured at the largest diameter.
3. Dimension BL shall include the entire body including slugs and sections of the lead over which the diameter is uncontrolled. This uncontrolled area is defined as the zone between the edge of the diode body and extending .050 inch (1.27 mm) maximum onto the leads.
4. In accordance with ASME Y14.5M, diameters are equivalent to ϕx symbology.

FIGURE 1. Physical dimensions of axial leaded package.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T05:52Z
Check the source to verify that this is the current version before use.



LTR	Dimensions				Notes
	Inches		Millimeters		
	Min	Max	Min	Max	
BD	.172	.180	4.37	4.57	
BL	.180	.220	4.57	5.58	
ECT	.020	.028	0.51	0.71	
S	.002		0.05		3

NOTES:
1. Dimensions are in inches. Millimeters are given for general information only.
2. Dimensions are pre-solder dip.
3. Minimum clearance of diode body to mounting surface on all orientations.
4. Cathode marking to be either in color band or a color dot on the face of the end tab.
5. Color dots will be .020 inch (0.51 mm) diameter minimum and shall not lie within .020 inch (0.51 mm) of the mounting surface.
6. In accordance with ASME Y14.5M, diameters are equivalent to ϕx symbology.

FIGURE 2. Physical dimensions of US surface mount package.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T05:52Z
Check the source to verify that this is the current version before use.

3. REQUIREMENTS

3.1 General. The individual item requirements shall be as specified in MIL-PRF-19500 and as modified herein.

3.2 Qualification. Devices furnished under this specification shall be products that are manufactured by a manufacturer authorized by the qualifying activity for listing on the applicable qualified manufacturer's list (QML) before contract award (see 4.2 and 6.3).

3.3 Abbreviations, symbols, and definitions. Abbreviations, symbols, and definitions used herein shall be as specified in MIL-PRF-19500 and as follows:

EC	End-cap.
$I_{(BR)}$	Current for testing breakdown voltage.
V_{fr}	Forward recovery voltage.

3.4 Interface and physical dimensions. The interface and physical dimensions shall be as specified in MIL-PRF-19500, and figures 1 and 2 herein.

3.4.1 Diode construction. These devices shall be constructed utilizing high temperature metallurgical bonding between both sides of the silicon die and terminal pins. Metallurgical bond shall be in accordance with the requirements of category I, appendix A of MIL-PRF-19500. No point contacts are permitted. Silver button dumet design is prohibited. US version devices shall be structurally identical to the non-surface mount devices except for lead terminations.

3.4.2 Lead finish. Unless otherwise specified, lead or end-cap finish shall be solderable in accordance with MIL-PRF-19500, MIL-STD-750, and herein. Where a choice of finish is desired, it shall be specified in the acquisition document (see 6.2).

3.4.3 Lead material. Unless otherwise specified, lead or end-cap material shall be in accordance with appendix H of MIL-PRF-19500, and herein. Where a choice of material is desired, it shall be specified in the acquisition document (see 6.2).

3.5 Marking. Devices shall be marked as specified in MIL-PRF-19500.

3.5.1 Marking of US versions. For US versions only, all marking may be omitted from the device except for the cathode marking. All marking which is omitted from the body of the devices shall appear on the label of the initial container.

3.5.2 Polarity. The polarity shall be indicated with a contrasting color band to denote the cathode end. Alternately, for surface mount (US) devices, a minimum of three evenly spaced contrasting color dots around the periphery of the cathode end may be used. No color coding will be permitted.

3.6 Electrical performance characteristics. Unless otherwise specified herein, the electrical performance characteristics are as specified in 1.3, 1.4, and table I herein.

3.7 Electrical test requirements. The electrical test requirements shall be the subgroups specified in table I herein.

3.8 Workmanship. Semiconductor devices shall be processed in such a manner as to be uniform in quality and shall be free from other defects that will affect life, serviceability, or appearance.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T05:52Z
Check the source to verify that this is the current version before use.

4. VERIFICATION

4.1 Classification of inspections. The inspection requirements specified herein are classified as follows:

a. Qualification inspection (see 4.2).

b. Screening (see 4.3).

c. Conformance inspection (see 4.4 and tables I, II, and III).

4.2 Qualification inspection. Qualification inspection shall be in accordance with MIL-PRF-19500 and as specified herein.

4.2.2 Group E qualification. Group E inspection shall be performed for qualification or re-qualification only. In case qualification was awarded to a prior revision of the specification sheet that did not request the performance of table III tests, the tests specified in table III herein that were not performed in the prior revision shall be performed on the first inspection lot of this revision to maintain qualification.

4.3 Screening (quality levels JANS, JANTXV and JANTX only). Screening shall be in accordance with table E-IV of MIL-PRF-19500 and as specified herein. The following measurements shall be made in accordance with table I herein. Devices that exceed the limits of table I herein shall not be acceptable.

Screen	Measurements	
	JANS level	JANTXV and JANTX level
(1) 3c	Thermal impedance (see 4.3.1)	Thermal impedance (see 4.3.1)
5	Not applicable	Not applicable
6	Not applicable	Not applicable
9	Group A, subgroup 2	Not required
10	Method 1038 of MIL-STD-750, condition A, T_A = 150°C, t = 48 hours	Method 1038 of MIL-STD-750, condition A, T_A = 150°C, t = 48 hours
11	Group A, subgroup 2, delta limits in accordance with table III herein	Group A, subgroup 2, delta limits in accordance with table III herein
12	Burn-In (see 4.3.2), t = 240 hours min	Burn-In (see 4.3.2), t = 96 hours min
13	Table I, subgroup 2 and 3, delta limits in accordance with table III herein, scope display evaluation (see 4.5.2)	Table I, subgroup 2, delta limits in accordance with table III herein, scope display evaluation (see 4.5.2).
14a	Not applicable	Not applicable
14b	Opaque glass diodes may use method 2068 in lieu of hermeticity testing.	Opaque glass diodes may use method 2068 in lieu of hermeticity testing.

(1) Shall be performed anytime after temperature cycling, screen 3a; JANTX and JANTXV levels do not need to be repeated in screening requirements.

4.3.1 Thermal impedance. The thermal impedance measurements shall be performed in accordance with method 3101 of MIL-STD-750 using the guidelines in that method for determining I_M, I_H, t_H, t_{MD} and K factor where appropriate. The limits will be statistically derived. See table E-IX, subgroup 4 of MIL-PRF-19500 and table II, subgroup 4 herein.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T05:52Z
Check the source to verify that this is the current version before use.

4.3.2 Free air power burn-in conditions. Power burn-in shall be in accordance with condition B of method 1038 of MIL-STD-750. The details of 4.5.3 and those that follow shall apply: $I_{O(min)}$ = 3A, $V_{r(pk)}$ = rated V_{RWM}, T_A = 55°C maximum. Adjust I_O or T_A to achieve the required T_J. T_J = 135°C minimum.

4.4 Conformance inspection. Conformance inspection shall be in accordance with MIL-PRF-19500 and as specified herein.

4.4.1 Group A inspection. Group A inspection shall be conducted in accordance with MIL-PRF-19500 and table I herein. The $Z_{\theta JX}$ end-point shall be derived by the supplier and approved by the qualifying activity. This $Z_{\theta JX}$ end-point shall also be documented in the qualification report. End-points shall include delta limits in accordance with table III herein when applicable.

4.4.2 Group B inspection. Group B inspection shall be conducted in accordance with the tests and conditions specified for subgroup testing in table E-VIA (JANS) and table E-VIB (JAN, JANTX, and JANTXV) of MIL-PRF-19500 and herein. End-points shall include delta limits in accordance with table III herein when applicable.

4.4.2.1 Quality level JANS.

	Subgroup	Method	Condition
*	B3	4066	Condition A, I_{FSM} = 250 A; ten surges of 8.3 ms each at 1 minute intervals, superimposed on I_O = 10A, V_{RWM} = rated, see column 2 of 1.3.2. T_A = 25°C.
	B3	1071	Fine leak not required. Opaque glass diodes may use method 2068 in lieu of hermeticity.
	B4	1037	I_O = 5 A minimum (see 1.3.2); V_R = rated V_{RWM} (see 1.3.2); 2,000 cycles. End-points shall include delta limits in accordance with table III herein.
	B4	1071	Fine leak not required. Opaque glass diodes may use method 2068 in lieu of hermeticity.
	B5	1027	I_O = 3 A minimum, t = 1,000 hours, V_{Rpk} = 80 percent minimum of rated V_{RWM} (see column 2 of 1.3.2) adjust I_O or T_A to achieve T_J = 175°C minimum; f = 50 - 60 Hz. T_A = 55°C max. For irradiated devices, include t_{rr} as an end-point measurement. End-points shall include delta limits in accordance with table III herein.
	B8	4065	Peak reverse power, P_{RM} ≥ 636 W square wave. Test shall be performed on each sublot; sampling plan: n = 10, c = 0, electrical end-points, see table I, subgroup 2 herein.

4.4.2.2 Quality levels JAN, JANTX, and JANTXV.

Subgroup	Method	Condition
B2	1071	Fine leak not required. Opaque glass diodes may use method 2068 in lieu of hermeticity.
B3	1037	I_O = 5 A minimum (see 1.3.2); V_R = rated V_{RWM} (see 1.3.2); 2,000 cycles. End-points shall include delta limits in accordance with table III herein.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T05:52Z
Check the source to verify that this is the current version before use.

4.4.3 Group C inspection. Group C inspection shall be conducted in accordance with the conditions specified for subgroup testing in table E-VII of MIL-PRF-19500. End-points shall include delta limits in accordance with table III herein when applicable.

Subgroup	Method	Condition
C2	2036	Condition A, 12 pounds (5.44 kg)(silver leads) 20 pounds (9.07 kg) (copper leads), t = 15 seconds. Condition E, 2 pounds (0.91 kg). (Lead fatigue not applicable to US device.)
C2	2038	Condition B, US devices: 20 pounds (9.07 kg) (copper tabs), t = 15 seconds.
C2	1071	Fine leak not required. Opaque glass diodes may use method 2068 in lieu of hermeticity.
C5	4081	$R_{\theta JL}/R_{\theta JEC}$ in accordance with 1.3.2 herein.
C6	1037	I_O = 5 A minimum (see 1.3.2); V_R = rated V_{RWM} (see 1.3.2); 6,000 cycles total, may continue from Group B. End-points shall include delta limits in accordance with table III herein.

4.4.4 Group E inspection. Group E inspection shall be conducted in accordance with the conditions specified for subgroup testing in table E-IX of MIL-PRF-19500 and as specified herein. End-points shall include delta limits in accordance with table III herein when applicable.

4.5 Methods of inspection. Methods of inspection shall be as specified in the appropriate tables as follows.

4.5.1 Pulse measurements. Conditions for pulse measurement shall be as specified in section 4 of MIL-STD-750.

4.5.2 Scope display evaluation. Scope display evaluation shall be stable in accordance with method 4023 of MIL-STD-750, condition A, max lift = 20 µA. Scope display may be performed on ATE (automatic test equipment) for screening only with the approval of the qualifying activity. Scope display in table I, subgroup 4 shall be performed on a curve tracer. The reverse current (I_{BR}) shall be 100 µA peak.

4.5.3 Burn-in and life tests. These tests shall be conducted with a half-sine waveform of the specified peak voltage impressed across the diode in the reverse direction followed by a half-sine waveform of the specified average rectified current. The forward conduction angle of the rectified current shall be neither greater than 180 degrees nor less than 150 degrees.

4.5.3.1 Junction temperature measurements. Use method 3100 of MIL-STD-750 to measure T_J. The use of a current limiting or ballast resistor is permitted provided that each DUT still sees the I_O and that the required voltage, where applicable, is maintained through-out the burn-in period.

4.5.3.2 Mounting conditions. At the option of the manufacturer, any clips or heat sink mounting configurations may be utilized provided that I_O is increased such that the junction temperature of each diode is maintained at +135°C minimum for screening, +150°C minimum for life test, and that the minimum required voltage V_{RWM} is maintained throughout the burn-in period.

4.5.4 Thermal resistance. Thermal resistance measurement shall be performed in accordance with method 4081 of MIL-STD-750 using the guidelines in that method for determining I_M, I_H, t_{MD} and t_H. See subgroup 4 of table E-IX of MIL-PRF-19500 and figure 3 herein. Forced moving air or draft shall not be permitted across the devices during test.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T05:52Z
Check the source to verify that this is the current version before use.

TABLE I. Group A inspection.

Inspection 1/	MIL-STD-750		Symbol	Limit		Unit
	Method	Conditions		Min	Max	
Subgroup 1						
Visual and mechanical examination	2071					
Subgroup 2						
Thermal impedance 2/	3101	See 4.3.1	$Z_{\theta JX}$			°C/W
Forward voltage	4011	Condition B; pulsed (see 4.5.1) I_{FM} = 6.0 A I_{FM} = 10 A I_{FM} = 20 A	 V_{FM1} V_{FM2} V_{FM3}		 0.900 0.950 1.050	 V V V
Reverse current	4016	DC method; V_R = rated (1.3.2, column 2); pulsed (see 4.5.1)	I_{R1}		1	µA
Breakdown voltage	4021	$I_{(BR)}$ = 100 µA, pulse ≤ 20 ms	$V_{(BR)1}$			
1N7066 1N7067 1N7068				110 160 210		V V V
Subgroup 3						
High temperature operation:		T_A = +125°C				
Reverse current	4016	DC method; V_R = rated (1.3.2, column 2); pulsed (see 4.5.1)	I_{R2}		100	µA
Forward voltage	4011	Condition B; I_{FM} = 6.0 A; pulsed (see 4.5.1)	V_{FM4}		0.850	V
High temperature operation:		T_A = +150°C				
Reverse current	4016	DC method; V_R = rated (1.3.2, column 2); pulsed (see 4.5.1)	I_{R3}		500	µA
Forward voltage	4011	Condition B; I_{FM} = 6.0 A; pulsed (see 4.5.1)	V_{FM5}		0.780	V

See footnotes at end of table.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T05:52Z
Check the source to verify that this is the current version before use.

TABLE I. Group A inspection - Continued.

Inspection 1/	MIL-STD-750		Symbol	Limit		Unit
	Method	Conditions		Min	Max	
Subgroup 3 - continued.						
Low-temperature operation:		T_A = −55°C				
Forward voltage	4011	Condition B; I_{FM} = 6.0 A; pulsed (see 4.5.1)	V_{FM6}		1.050	V
Subgroup 4						
Reverse recovery time	4031	Condition B; $I_F = I_{RM}$ = 1.0 A $i_{(REC)}$ = 0.1 A; di/dt = 100 A/µs (min)	t_{rr}		30	ns
Capacitance	4001	V_R = 10 V; f = 1 MHz; V_{sig} = 50 mV (p-p)	C_J		80	pF
Scope display evaluation	4023	See 4.5.2, n = 116, c = 0				
Subgroup 5						
Not applicable						
Subgroup 6						
* Forward surge	4066	Condition A, ten surges of 8.3 ms each at 1 minute intervals superimposed on I_O = 10 A; V_{RWM} = rated (see 1.3.2); T_A = +25°C	I_{FSM}	250		A(pk)
Electrical measurements		See table I, subgroup 2 except $Z_{\theta JX}$				
Subgroup 7						
Not applicable						

1/ For sampling plan, see MIL-PRF-19500.
2/ For end-point measurements, this test is required for the following subgroups:
Group B, subgroups 2 and 3 (JAN, JANTX, JANTXV).
Group B, subgroups 3 and 4 (JANS).
Group C, subgroups 2 and 6.
Group E, subgroup 1.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T05:52Z
Check the source to verify that this is the current version before use.

TABLE II. Group E inspection (all quality levels) for qualification and requalification only.

Inspection	MIL-STD-750		Sampling plan
	Method	Conditions	
Subgroup 1			45 devices c = 0
Thermal shock (liquid to liquid)	1056	20 cycles, condition D except low temperature shall be −195°C (achieved using liquid nitrogen). After the test, perform a visual examination for cracked glass.	
Temperature cycling (air to air)	1051	−65°C to +175°C, 500 cycles.	
Hermetic seal 1/	1071	Fine leak not required. Opaque glass diodes may use method 2068 in lieu of hermeticity.	
Electrical measurement		See table I, subgroup 2 and table III, steps 1 and 2.	
Subgroup 2			45 devices c = 0
Steady-state dc blocking life	1048	t = 1,000 hours; T_A = +150°C; V_R dc = 80 - 85 percent rated V_{RWM} (see 1.3.2).	
Electrical measurement		See table I, subgroup 2 herein, except $Z_{\theta JX}$ need not to be performed, and table III, steps 1 and 2 herein. For irradiated devices, include t_{rr} as an end-point measurement.	
Subgroup 4			Sample size N/A
Thermal impedance curves		See MIL-PRF-19500.	
Subgroup 5			
Not applicable			
Subgroup 6			
ESD	1020		
Subgroup 7			
Resistance to soldering heat	2031	Conditions A, B, and C	3 devices
Hermetic seal 1/	1071	Fine leak not required. Opaque glass diodes may use method 2068 in lieu of hermeticity.	

See footnotes at end of table.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T05:52Z
Check the source to verify that this is the current version before use.

TABLE II. Group E inspection (all quality levels) for qualification and requalification only – Continued.

Inspection	MIL-STD-750		Sampling plan
	Method	Conditions	
Subgroup 8			n = 45
Peak reverse power	4065	Peak reverse power, (P_{RM}) = 636 W. The test shall be performed on each sublot.	
Electrical measurement		During the P_{RM} test, the voltage (V_{BR}) shall be monitored to verify it has not collapsed. Any collapse in V_{BR} during or after the P_{RM} test, or rise in leakage current (I_R) after the test exceeds I_R in table I, shall be considered a failure. Progressively higher levels of P_{RM} shall be applied until failure occurs on all devices within the chosen sample size, or 1,000 W is obtained.	
Subgroup 9			n = 45
Resistance to glass cracking	1057	Step stress to destruction by increasing cycles or up to a maximum of 25 cycles.	
Subgroup 10			22 devices c = 0
Forward surge	4066	Condition A, I_{FSM} = rated (see 1.3.2); ten surges of 8.3 ms each at 1 minute intervals superimposed on $I_O = I_{O1}$ rated (see 1.3.2); V_{RWM} = rated (see 1.3.2); T_A = + 25°C.	
Electrical measurement		See table I, subgroup 2.	


1/ Opaque glass non-cavity axial lead diodes may use test method 2068 in lieu of test method1071 of MIL-STD-750.

TABLE III. Group A, B, C, and E delta electrical measurements. 1/

Step	Inspection	MIL-STD-750		Symbol	Limit	Unit
		Method	Conditions			
1.	Forward voltage	4011	Condition B; I_{FM} = 6.0 A(pk); pulsed (see 4.5.1)	ΔV_{FM1}	±50 mV dc change from initial value.	
2.	Reverse current	4016	DC method; V_R = rated (1.3.2, column 2)	ΔI_{R1}	±100 percent or ±200 nA dc change from initial reading, whichever is greater.	

1/ Devices which exceed the table I limits for this test shall not be accepted.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T05:52Z
Check the source to verify that this is the current version before use.



NOTE: $Z_{\theta JX}$ = 2.0 °C/W max at 65 ms.

FIGURE 3. Thermal impedance curves.

5. PACKAGING

5.1 Packaging. For acquisition purposes, the packaging requirements shall be as specified in the contract or order (see 6.2). When packaging of materiel is to be performed by DoD or in-house contractor personnel, these personnel need to contact the responsible packaging activity to ascertain packaging requirements. Packaging requirements are maintained by the Inventory Control Point's packaging activities within the Military Service or Defense Agency, or within the Military Service's system commands. Packaging data retrieval is available from the managing Military Department's or Defense Agency's automated packaging files, CD-ROM products, or by contacting the responsible packaging activity.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T05:52Z
Check the source to verify that this is the current version before use.

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory. The notes specified in MIL-PRF-19500 are applicable to this specification.)

6.1 Intended use. Semiconductors conforming to this specification are intended for original equipment design applications and logistic support of existing equipment.

6.2 Acquisition requirements. Acquisition documents should specify the following:

a. Title, number, and date of this specification.

b. Packaging requirements (see 5.1).


c. Lead finish (see 3.4.2).

d. The complete PIN, see 1.5 and 6.4.

e. Lead material (see 3.4.3).

6.3 Qualification. With respect to products requiring qualification, awards will be made only for products which are, at the time of award of contract, qualified for inclusion in Qualified Manufacturers List (QML 19500) whether or not such products have actually been so listed by that date. The attention of the contractors is called to these requirements, and manufacturers are urged to arrange to have the products that they propose to offer to the Federal Government tested for qualification in order that they may be eligible to be awarded contracts or orders for the products covered by this specification. Information pertaining to qualification of products may be obtained from DLA Land and Maritime, ATTN: VQE, P.O. Box 3990, Columbus, OH 43218-3990 or e-mail vqe.chief@dla.mil. An online listing of products qualified to this specification may be found in the Qualified Products Database (QPD) at https://qpldocs.dla.mil.

6.4 PIN construction example. The PINs are constructed using the following form.



6.5 List of PINs. The following is a list of possible PINs available for encapsulated devices covered by this specification sheet.

Quality level JAN	JAN1N7066	JAN1N7067	JAN1N7068
Quality level JANTX	JANTX1N7066	JANTX1N7067	JANTX1N7068
Quality level JANTXV	JANTXV1N7066	JANTXV1N7067	JANTXV1N7068

6.6 Request for new types and configurations. Requests for new device types or configurations for inclusions in this specification sheet should be submitted to: DLA Land and Maritime, ATTN: VAC, Post Office Box 3990, Columbus, OH 43218-3990 or by electronic mail at Semiconductor@dla.mil or by facsimile (614) 693-1642 or DSN 850-6939.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T05:52Z
Check the source to verify that this is the current version before use.

6.7 Changes from previous issue. Marginal notations are not used in this revision to identify changes with respect to the previous issue due to the extent of the changes.

Custodians:
Army - CR
Navy - EC
Air Force - 85
NASA - NA
DLA - CC

Review activities:
Army - AR, AV, MI, SM
Navy - AS, MC
Air Force - 19, 71

Preparing activity:
DLA - CC

(Project 5961-2020-002)

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at https://assist.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T05:52Z
Check the source to verify that this is the current version before use.