The documentation and process conversion measures necessary to comply with this revision shall be completed by 25 May 2026.

INCH-POUND

MIL-PRF-19500/795
w/AMENDMENT 1
25 February 2026
SUPERSEDING
MIL-PRF-19500/795
16 May 2025

PERFORMANCE SPECIFICATION SHEET

TRANSISTOR, FIELD EFFECT RADIATION HARDENED, N-CHANNEL, SILICON, TYPES 2N7645, QUALITY LEVELS JANTXV AND JANS

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specification sheet and MIL-PRF-19500.

1. SCOPE

1.1 Scope. This specification covers the performance requirements for an N-channel, enhancement-mode, MOSFET, radiation hardened (total dose and single event effects (SEE)), power transistor. Two levels of product assurance (JANTXV and JANS) are provided for each encapsulated device. Provisions for radiation hardness assurance (RHA) to two radiation levels ("R" and "F") are provided for JANTXV and JANS product assurance level.

* 1.2 Package outlines. The device package outlines are as follows: surface mount SMD-0.2, U8C (ceramic lid) suffix in accordance with figure 1, surface mount SMD-0.2, U8CE (ceramic lid) suffix in accordance with figure 2, for all encapsulated device types.

* 1.3 Maximum ratings. Unless otherwise specified T_A = +25°C

Type	P_T (1) T_C = +25°C	P_T T_A = +25°C	$R_{\theta JC}$ (2)	V_{DS}	V_{DG}	V_{GS}	I_{D1} (3) (4) T_C = +25°C	I_{D2} T_C = +100°C	I_S	I_{DM} (5)	T_J and T_{STG}
	W	W	°C/W	V dc	V dc	V dc	A dc	A dc	A dc	A (pk)	°C
2N7645U8C, U8CE	36	1.0	3.5	20	20	±12	17	17	17	68	-55 to +150

(1) Derate linearly by 0.3 W/°C for T_C > +25°C.
(2) See figure 3, thermal impedance curves.
(3) The following formula derives the maximum theoretical I_D limit. I_D is limited by package and internal wires and may be limited by pin diameter:

$$I_D = \sqrt{\frac{T_{JM} - T_C}{(R_{\theta JC}) \times (R_{DS}(on) \text{ at } T_{JM})}}$$

(4) See figure 4, maximum drain current graph.
(5) I_{DM} = 4 X I_{D1}; I_{D1} as calculated by footnote (3).

Comments, suggestions, or questions on this document should be addressed to DLA Weapons Support, ATTN: VAC, P.O. Box 3990, Columbus, OH 43218-3990, or emailed to Semiconductor@dla.mil. Since contact information can change, you may want to verify the currency of this address information using the ASSIST Online database at https://assist.dla.mil/.

AMSC N/A
FSC 5961

DISTRIBUTION STATEMENT A. Approved for public release. Distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T06:05Z
Check the source to verify that this is the current version before use.

* 1.4 Primary electrical characteristics. Unless otherwise specified T_C = +25°C.

Type	Min $V_{(BR)DSS}$ V_{GS} = 0 I_D = 250 µA dc	$V_{GS(TH)1}$ $V_{DS} \geq V_{GS}$ I_D = 250 µA dc	Max I_{DSS1} V_{GS} = 0 V_{DS} = 80% of rated V_D	Max $r_{DS(on)}$ (1) V_{GS} = 12V, I_D = I_{D2}		E_{AS}
				T_J = +25°C	T_J = +150°C	
	V dc	V dc Min Max	µA dc	Ω	Ω	mJ
2N7645U8C, U8CE	20	1.0 2.3	1.0	0.015	0.023	37

(1) Pulsed (see 4.5.1).

1.5 Part or Identifying Number (PIN). The PIN is in accordance with MIL-PRF-19500, and as specified herein. See 6.5 for PIN construction example and 6.6 for a list of available PINs.

1.5.1 JAN certification mark and quality level. The only quality level designators for encapsulated devices that are applicable for this specification sheet are the quality levels "JANTXV" and "JANS".

1.5.2 Radiation hardness assurance (RHA) designator. The RHA levels that are applicable for this specification sheet from lowest to highest are as follows: "R" and "F".

1.5.3 Device type. The designation system for the device types of transistors covered by this specification sheet are as follows.

1.5.3.1 First number and first letter symbols. The transistors of this specification sheet use the first number and letter symbols "2N".

1.5.3.2 Second number symbols. The second number symbols for the transistors covered by this specification sheet are as follows: "7645".

* 1.5.4 Suffix letters. The following suffix letters are incorporated in the PIN for this specification sheet:

U8C	Indicates a ceramic lidded 3 pad surface mount package (SMD-0.2) (see figure 1).
U8CE	Indicates a ceramic lidded 3 pad surface mount package with enhanced PCB mount features, similar to a SMD-0.2 (see figure 2)

1.5.5 Lead finish. The lead finishes applicable to this specification sheet are listed on QPDSIS-19500.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T06:05Z
Check the source to verify that this is the current version before use.

* 1.6 Radiation features:

Maximum total ionizing dose (TID) available (Dose rate = 50-300 rad(Si)/s)):

For device type 2N7645U8C, U8CE: ..... 300 krad(Si) 1/


Heavy Ion Single Event Effect (SEE) SEB and SEGR test:

For device type 2N7645U8C, U8CE:
No SEB and SEGR were observed at surface LET (see table IV) ..... ≤ 93.2 MeV·cm^2/mg 2/
(In-situ Bias V_{DS} = 17 V and V_{GS} = 0 V)
(In-situ Bias V_{DS} = 16 V and V_{GS} = -1 V)
(In-situ Bias V_{DS} = 16 V and V_{GS} = -2 V)
(In-situ Bias V_{DS} = 14 V and V_{GS} = -3 V)
(In-situ Bias V_{DS} = 10 V and V_{GS} = -4 V)
(In-situ Bias V_{DS} = 8 V and V_{GS} = -5 V)

1/ Manufacturer supplying device types 2N7645U8C, U8CE has performed characterization testing in accordance with MIL-STD-750, method 1019, condition A (dose rate = 50 - 300 rad(Si)/s). The radiation end point limits are guaranteed only for the conditions as specified in MIL-STD-750, method 1019, condition A to a maximum total ionizing dose level of 300 krad(Si).

2/ Manufacturer also performed heavy ion SEB and SEGR test at TAMU Radiation Effects Facility for the MOSFET technology devices in accordance with TM1080 of MIL-STD-750. Limits are characterized at initial qualification and after any design or process changes which may affect the SEE (SEB/SEGR) characteristics. For more information on SEE (SEB/SEGR) test results, customers are requested to contact the manufacturer.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T06:05Z
Check the source to verify that this is the current version before use.




Symbol	Dimensions			
	Inches		Millimeters	
	Min	Max	Min	Max
BL	.305	.321	7.75	8.15
BW	.200	.226	5.08	5.74
CH		.106		2.69
LW1	.193	.203	4.90	5.16
LW2	.076	.086	1.93	2.18
LL1	.174	.184	4.42	4.67
LL2	.074	.084	1.88	2.13
Q1	.030	.040	0.76	1.02
Q2	.030	.040	0.76	1.02
Q3	.01 REF		0.25 REF	
Q4	.01 REF		0.25 REF	
TERM 1	Drain			
TERM 2	Gate			
TERM 3	Source			

NOTES:
1. Dimensions are in inches.
2. Millimeters are given for general information only.
3. Lid is isolated.

FIGURE 1. Dimensions and configuration (SMD-0.2), with ceramic lid (U8C).

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T06:05Z
Check the source to verify that this is the current version before use.



Symbol	Dimensions			
	Inches		Millimeters	
	Min	Max	Min	Max
BL	.300	.310	7.62	7.87
BW	.205	.215	5.21	5.46
CH		.097		2.46
LH	.010	.020	0.25	0.51
LW1	.180	.190	4.57	4.83
LW2	.068	.078	1.73	1.98
LL1	.161	.171	4.09	4.34
LL2	.068	.078	1.73	1.98
LS1	.121 BSC		3.07 BSC	
LS2	.061 BSC		1.55 BSC	
LS3	.044 BSC		1.12 BSC	
LS4	.167 BSC		4.24 BSC	
Q1	.030		0.76	
Q2	.030		0.76	
TERM 1	Drain			
TERM 2	Gate			
TERM 3	Source			

NOTES:
1. Dimensions are in inches.
2. Millimeters are given for general information only.
3. Lid is isolated.

* FIGURE 2. Dimensions and configuration (Similar to SMD-0.2), with ceramic lid (U8CE).

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T06:05Z
Check the source to verify that this is the current version before use.

2. APPLICABLE DOCUMENTS

2.1 General. The documents listed in this section are specified in sections 3 and 4 of this specification. This section does not include documents cited in other sections of this specification or recommended for additional information or as examples. While every effort has been made to ensure the completeness of this list, document users are cautioned that they must meet all specified requirements of documents cited in sections 3 and 4 of this specification, whether or not they are listed.

2.2 Government documents.

2.2.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those cited in the solicitation or contract.

DEPARTMENT OF DEFENSE SPECIFICATIONS

MIL-PRF-19500 - Semiconductor Devices, General Specification for.

DEPARTMENT OF DEFENSE STANDARDS

MIL-STD-750 - Test Methods for Semiconductor Devices.
MIL-STD-883 - Test Method Standard Microcircuits

(Copies of these documents are available online at https://quicksearch.dla.mil/).

2.3 Order of precedence. Unless otherwise noted herein or in the contract, in the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 General. The individual item requirements shall be as specified in MIL-PRF-19500 and as modified herein.

3.2 Qualification. Devices furnished under this specification shall be products that are manufactured by a manufacturer authorized by the qualifying activity for listing on the applicable qualified manufacturer's list (QML) before contract award (see 4.2 and 6.3).

3.3 Abbreviations, symbols, and definitions. Abbreviations, symbols, and definitions used herein shall be as specified in MIL-PRF-19500.

* 3.4 Interface and physical dimensions. Interface and physical dimensions shall be as specified in MIL-PRF-19500, and on figure 1 (SMD-0.2, U8C), and figure 2 (Similar to SMD-0.2, U8CE) herein.

3.4.1 Lead finish. Lead finish shall be solderable in accordance with MIL-PRF-19500, MIL-STD-750, and herein. Where a choice of lead finish is desired, it shall be specified in the acquisition document (see 6.2).

3.4.2 Multiple chip construction. Multiple chip construction is not permitted to meet the requirements of this specification.

3.4.3 Silicone die coating. The use of a silicone die coat requires a successful completion method 5011 of MIL-STD-883, on each lot of silicone die coating for its intended applications.

3.5 Marking. Marking shall be in accordance with MIL-PRF-19500.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T06:05Z
Check the source to verify that this is the current version before use.

3.6 Electrical performance characteristics. Unless otherwise specified herein, the electrical performance characteristics are as specified in 1.3, 1.4, and table I.

3.7 Electrostatic discharge sensitive (ESDS). The devices covered by this specification sheet have been classified as ESDS. The devices shall be handled in accordance with the ESD program established to comply with the requirements of MIL-PRF-19500 to avoid damage due to the accumulation of static charge. The following handling practices shall be followed:

a. Devices should be handled on benches with conductive handling devices.

b. Ground test equipment, tools, and personnel handling devices.

c. Do not handle devices by the leads.

d. Store devices in conductive foam or carriers.

e. Avoid use of plastic, rubber, or silk in MOS areas.

f. Maintain relative humidity above 50 percent if practical.

g. Care should be exercised during test and troubleshooting to apply not more than maximum rated voltage to any lead.

h. Gate shall be terminated to source, R ≤ 100 kΩ, whenever bias voltage is to be applied drain to source.

3.8 Workmanship. Semiconductor devices shall be processed in such a manner as to be uniform in quality and shall be free from other defects that will affect life, serviceability, or appearance.

4. VERIFICATION

4.1 Classification of inspections. The inspection requirements specified herein are classified as follows:

a. Qualification inspection (see 4.2).

b. Screening (see 4.3).

c. Conformance inspection (see 4.4 and tables I and II).

4.2 Qualification inspection. Qualification inspection shall be in accordance with MIL-PRF-19500 and as specified herein.

4.2.1 Group E qualification. Group E inspection shall be performed for qualification or re-qualification only. In case qualification was awarded to a prior revision of the specification sheet that did not request the performance of table III tests, the tests specified in table III herein that were not performed in the prior revision shall be performed on the first inspection lot of this revision to maintain qualification.

4.2.1.1 Single event effects (SEE). SEE (SEB/SEGR) shall be performed in accordance with TM1080 of MIL-STD-750 at initial qualification and after process or design changes which may affect radiation hardness (see table III and table IV). Upon qualification, manufacturers shall provide the verification test conditions from section 5 of method 1080 of MIL-STD-750 that were used to qualify the device for inclusion into section 6 of the slash sheet. End-point measurements shall be in accordance with table II. SEE (SEB/SEGR) characterization data shall be made available upon request of the qualifying or acquiring activity.

4.2.2 Silicone die coating. When silicone die coating is used, method 5011 of MIL-STD-883 shall be performed on that coating in the full MIL-PRF-19500 qualification process.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T06:05Z
Check the source to verify that this is the current version before use.

4.3 Screening of encapsulated devices. Screening of packaged devices shall be in accordance with table E-IV of MIL-PRF-19500, and as specified herein. The following measurements shall be made in accordance with table I herein. Devices that exceed the limits of table I herein shall not be acceptable.

Screen (1) (2)	Measurements for JANS	Measurements for JANTXV
(3)	Gate stress test (see 4.3.1)	Gate stress test (see 4.3.1)
(3)	Method 3470 of MIL-STD-750, E_{AS} (see 4.3.2)	Method 3470 of MIL-STD-750, E_{AS} (see 4.3.2)
(3) 3c	Method 3161 of MIL-STD-750, thermal impedance, (see 4.3.3)	Method 3161 of MIL-STD-750, thermal impedance, (see 4.3.3)
5	Method 2052 of MIL-STD-750, PIND (see MIL-PRF-19500 and 4.3.4)	Not applicable
9	Subgroup 2 of table I herein	Not applicable
10	Method 1042 of MIL-STD-750, test condition B	Method 1042 of MIL-STD-750, test condition B
11	Subgroup 2 of table I herein. ΔI_{GSSF1} = ±20 nA dc or ±100 percent of initial value, whichever is greater. ΔI_{GSSR1} = ±20 nA dc or ±100 percent of initial value, whichever is greater. ΔI_{DSS1} = ± 500 nA dc or ±100 percent of initial value, whichever is greater.	Subgroup 2 of table I herein.
12	Method 1042 of MIL-STD-750, test condition A	Method 1042 of MIL-STD-750, test condition A
13	Subgroups 2 and 3 of table I herein ΔI_{GSSF1} = ±20 nA dc or ±100 percent of initial value, whichever is greater. ΔI_{GSSR1} = ±20 nA dc or ±100 percent of initial value, whichever is greater. ΔI_{DSS1} = ± 500 nA dc or ±100 percent of initial value, whichever is greater. $\Delta r_{DS(ON)1}$ = ±20 percent of initial value. $\Delta V_{GS(TH)1}$ = ±20 percent of initial value.	Subgroup 2 of table I herein ΔI_{GSSF1} = ±20 nA dc or ±100 percent of initial value, whichever is greater. ΔI_{GSSR1} = ±20 nA dc or ±100 percent of initial value, whichever is greater. ΔI_{DSS1} = ± 500 nA dc or ±100 percent of initial value, whichever is greater. $\Delta r_{DS(ON)1}$ = ±20 percent of initial value. $\Delta V_{GS(TH)1}$ = ±20 percent of initial value.

(1) At the end of the test program, I_{GSSF1}, I_{GSSR1}, and I_{DSS1} are measured.
(2) An out-of-family program to characterize I_{GSSF1}, I_{GSSR1}, I_{DSS1} and $V_{GS(th)1}$ shall be invoked
(3) Shall be performed anytime after temperature cycling, screen 3a; JANTXV does not need to be repeated in screening requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T06:05Z
Check the source to verify that this is the current version before use.

4.3.1 Gate stress test. Apply V_{GS} = ±14 V minimum for t = 250 µs minimum.

4.3.2 Single pulse avalanche energy (E_{AS}).

a. Peak current ..... $I_{AS} = I_{D2}$.

b. Inductance: ..... $\left[\frac{2E_{AS}}{(I_{D2})^2}\right]\left[\frac{V_{BR} - V_{DD}}{V_{BR}}\right]$ mH minimum.

c. Gate to source resistor (R_{GS})..... 25 ≤ R_{GS} ≤ 200 Ω.

d. Supply voltage (V_{DD})..... V_{DD} = 20 V dc, up to rated V_{DS}.

e. Peak gate voltage (V_{GS}) ..... 12 V, up to maximum rated V_{GS}.

f. Initial case temperature ..... T_C = +25°C +10°C, -5°C.

g. Number of pulses to be applied..... 1 pulse minimum.

4.3.3 Thermal impedance. The thermal impedance measurements shall be performed in accordance with method 3161 of MIL-STD-750 using the guidelines in that method for determining I_M, I_H, t_H, t_{MD}, t_{SW}, (and V_H where appropriate). See table III, group E, subgroup 4 herein.

4.3.4 PIND. Not applicable in screening when devices are processed using alternative method and flow requirements approved by the qualifying activity, that includes incorporating the use of certified clean processing and silicone die coat. Instead, the PIND test performance shall be performed in group B3 and group C3, on a lot sample basis. PIND failures detected in group B or C will represent lot jeopardy and shall be evaluated for root cause and lot integrity.

4.4 Conformance inspection. Conformance inspection shall be in accordance with MIL-PRF-19500.

4.4.1 Group A inspection. Group A inspection shall be conducted in accordance with table E-V of MIL-PRF-19500 and table I herein.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T06:05Z
Check the source to verify that this is the current version before use.

4.4.2 Group B inspection. Group B inspection shall be conducted in accordance with the conditions specified for subgroup testing in table E-VIA (JANS) and table E-VIB (JANTXV) of MIL-PRF-19500, and as follows.

4.4.2.1 Quality level JANS (table E-VIA of MIL-PRF-19500).

Subgroup	Method	Condition
B3	1051	Test condition G, 100 cycles.
B3	2077	Scanning electron microscope (SEM).
B3	2052	PIND, required if not performed in screening. (22 devices, c = 0 for large lots, 12 devices, c = 0 for small lots).
B4	1042	Intermittent operation life, condition D, t_{on} = 30 seconds minimum.
B5	1042	Accelerated steady-state gate bias, condition B, V_{GS} = rated; T_A = +175°C, t = 24 hours minimum; or T_A = +150°C, t = 48 hours minimum.
B5	1042	Accelerated steady-state reverse bias, condition A, V_{DS} = rated; T_A = +175°C, t = 120 hours minimum; or T_A = +150°C, t = 240 hours minimum.
B5	2037	Test condition D.

4.4.2.2 Quality level JANTXV (table E-VIB of MIL-PRF-19500).

Subgroup	Method	Condition
B2	1051	Test condition G, 25 cycles.
B3	1042	Intermittent operation life, condition D, t_{on} = 30 seconds minimum.

4.4.3 Group C inspection. Group C inspection shall be conducted in accordance with the conditions specified for subgroup testing in table E-VII of MIL-PRF-19500 and as follows.

Subgroup	Method	Condition
C2	2036	Terminal strength is not applicable.
C3	2052	PIND, required if not performed in screening. (22 devices, c = 0 for large lots, 12 devices, c = 0 for small lots).
C5	3161	See 4.3.3, $R_{\theta JC}$ = 3.5 °C/W.
C6	1042	Intermittent operation life, condition D, t_{on} = 30 seconds minimum.

4.4.4 Group D inspection. Group D inspection shall be conducted in accordance with table E-VIII of MIL-PRF-19500 and table II herein.

4.4.5 Group E inspection. Group E inspection shall be conducted in accordance with the conditions specified for subgroup testing in table E-IX of MIL-PRF-19500 and as specified in table III herein.

4.5 Methods of inspection. Methods of inspection shall be as specified in the appropriate tables and as follows.

4.5.1 Pulse measurements. Conditions for pulse measurement shall be as specified in section 4 of MIL-STD-750.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T06:05Z
Check the source to verify that this is the current version before use.

TABLE I. Group A inspection.

	Inspection 1/	MIL-STD-750		Symbol	Limits	Limits	Unit
		Method	Condition		Min	Max	
	Subgroup 1						
	Visual and mechanical inspection	2071					
	Subgroup 2						
	Thermal impedance 2/	3161	See 4.3.3	$Z_{\theta JC}$			°C/W
*	Breakdown voltage drain to source 2N7645U8C, U8CE	3407	Bias condition C, V_{GS} = 0 V, I_D = 250 µA dc	$V_{(BR)DSS}$	20		V dc
	Gate to source voltage (threshold)	3403	$V_{DS} \geq V_{GS}$, I_D = 250 µA dc	$V_{GS(TH)1}$	1.0	2.3	V dc
	Gate current	3411	V_{GS} = +12 V dc, bias condition C, V_{DS} = 0 V	I_{GSSF1}		+100	nA dc
	Gate current	3411	V_{GS} = -12 V dc, bias condition C, V_{DS} = 0 V	I_{GSSR1}		-100	nA dc
	Drain current	3413	V_{GS} = 0 V dc, bias condition C, V_{DS} = 80 percent of rated V_{DS},	I_{DSS1}		1.0	µA dc
*	Static drain to source on-state resistance 2N7645U8C, U8CE	3421	V_{GS} = 12 V dc, condition A, pulsed (see 4.5.1), I_D = I_{D2}	$r_{DS(ON)1}$		0.015	Ω
	Forward voltage	4011	V_{GS} = 0 V dc, condition A, I_D = I_{D1}	V_{SD}		1.0	V dc

See footnotes at end of table.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T06:05Z
Check the source to verify that this is the current version before use.

TABLE I. Group A inspection - Continued.

	Inspection 1/	MIL-STD-750		Symbol	Limits	Limits	Unit
		Method	Condition		Min	Max	
	Subgroup 3						
	High temperature operation		$T_C = T_J = +125°C$				
	Gate current	3411	$V_{GS} = \pm 20$ V dc, bias condition C, $V_{DS} = 0$ V	I_{GSS2}		±200	nA dc
	Drain current	3413	$V_{GS} = 0$ V dc, bias condition C, V_{DS} = 80 percent of rated V_{DS}	I_{DSS2}		10	µA dc
*	Static drain to source on-state resistance 2N7645U8C, U8CE	3421	V_{GS} = 12 V dc, condition A, pulsed (see 4.5.1), $I_D = I_{D2}$	$r_{DS(ON)3}$		0.022	Ω
	Gate to source voltage (threshold)	3403	$V_{DS} \geq V_{GS}$, I_D = 250 µA dc	$V_{GS(TH)2}$	0.7		V dc
	Low temperature operation		$T_C = T_J = -55°C$				
	Gate to source voltage (threshold)	3403	$V_{DS} \geq V_{GS(TH)3}$, I_D = 250 µA dc	$V_{GS(TH)3}$		2.5	V dc
	Subgroup 4						
*	Forward transconductance 2N7645U8C, U8CE	3475	$I_D = I_{D2}$, V_{DD} = 15 V dc (see 4.5.1)	g_{FS}	20		S
	Switching Time Tests	3472	$I_D = I_{D1}$, V_{GS} = 5.5 V dc, R_G = 2.35 Ω, V_{DD} = 50 percent rated V_{DS}				
*	Turn-On Delay Time 2N7645U8C, U8CE			td(on)		24	ns
*	Rise Time 2N7645U8C, U8CE			tr		150	ns
*	Turn-Off Delay Time 2N7645U8C, U8CE			td(off)		32	ns
*	Fall Time 2N7645U8C, U8CE			tf		18	ns

See footnotes at end of table.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T06:05Z
Check the source to verify that this is the current version before use.

TABLE I. Group A inspection - Continued.

	Inspection 1/	MIL-STD-750		Symbol	Limits	Limits	Unit
		Method	Condition		Min	Max	
	Subgroup 5						
	Safe operating area test	3474	See figure 5, tp = 10 ms min. V_{DS} = 80 percent of max. rated V_{DS}				
	Electrical measurements		See table I, subgroup 2				
	Subgroup 6						
	Not applicable						
	Subgroup 7						
	Gate charge	3471	Condition B, $I_D = I_{D1}$, V_{GS} = 5.5 V dc V_{DD} = 50 percent of rated V_{DS}				
	On-state gate charge and turn-off gate charge			Q_G			
*	2N7645U8C, U8CE					26	nC
	Gate to source charge (turn-on and turn-off)			Q_{GS}			
*	2N7645U8C, U8CE					8	nC
	Gate to drain charge (turn-on and turn-off)			Q_{GD}			
*	2N7645U8C, U8CE					8	nC
	Reverse recovery time	3473	Condition A, di/dt = -100 A/µs, $V_{DD} \leq 25$ V, $I_D = I_{D1}$	t_{rr}			
*	2N7645U8C, U8CE					41	ns

1/ For sampling plan, see MIL-PRF-19500.
2/ For end-point measurements, this test is required for the following subgroups:
Group B, subgroups 2 and 3 (JANTXV).
Group B, subgroups 3 and 4 (JANS).
Group C, subgroup 2 and 6.
Group E, subgroup 1.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T06:05Z
Check the source to verify that this is the current version before use.

TABLE II. Group D inspection.

	Inspection 1/ 2/ 3/	MIL-STD-750		Symbol	Pre-irradiation limits		Post-irradiation limits		Unit
		Method	Conditions		R and F		R and F		
					Min	Max	Min	Max	
	Subgroup 1 Not applicable								
	Subgroup 2		T_C = + 25°C						
	Steady-state total dose irradiation (V_{GS} bias) 4/	1019	Condition A, V_{GS} = 12 V; V_{DS} = 0						
	Steady-state total dose irradiation (V_{DS} bias) 4/	1019	Condition A, V_{GS} = 0; V_{DS} = 80 percent of rated V_{DS}(pre-irradiation)						
	End-point electricals:								
	Breakdown voltage, drain to source	3407	Bias condition C, V_{GS} = 0; I_D = 250 µA	$V_{(BR)DSS}$					
*	2N7645U8C, U8CE				20		20		V dc
	Gate to source voltage (threshold)	3403	$V_{DS} \geq V_{GS}$, I_D = 250 µA	$V_{GS(th)1}$	1.0	2.3	1.0	2.3	V dc
	Gate current	3411	Bias condition C, V_{GS} = +12 V; V_{DS} = 0	I_{GSSF1}		100		100	nA dc
	Gate current	3411	Bias condition C, V_{GS} = -12 V; V_{DS} = 0	I_{GSSR1}		-100		-100	nA dc
	Drain current	3413	Bias condition C, V_{GS} = 0 V_{DS} = 80 percent of rated V_{DS} (pre-irradiation)	I_{DSS}		1.0		1.0	µA dc
	Static drain to source on-state voltage	3405	V_{GS} = 4.5 V; I_D = I_{D2} condition A, pulsed (see 4.5.1)	$V_{DS(on)}$					
*	2N7645U8C, U8CE 5/					0.255		0.255	V dc
	Forward voltage source drain diode	4011	Bias condition A, V_{GS} = 0; I_D = I_{D1}	V_{SD}		1.0		1.0	V dc

1/ For sampling plan, see MIL-PRF-19500.
2/ Group D qualification may be performed prior to lot formation. Wafers qualified to these group D QCI requirements may be used for any other specification sheets utilizing the same die design.
3/ At the manufacturer's option, group D samples need not be subjected to the screening tests, and may be assembled in its qualified package or in any qualified package that the manufacturer has data to correlate the performance to the designated package.
4/ Separate samples shall be pulled for each bias. Devices supplied to this specification sheet have been characterized through levels R and F of irradiation. Pre and Post irradiation values are identical unless otherwise specified in Table II. When performing post irradiation electrical measurements for any RHA level, TA = +25°C (see 1.6 herein).
5/ Group D samples are built and tested in TO-3 packages. The equivalent pre-radiation and post radiation limit for $V_{DS(on)}$ in the TO-3 package is 0.255 Vdc for the 2N7645.


Source: https://assist.dla.mil -- Downloaded: 2026-10-19T06:05Z
Check the source to verify that this is the current version before use.

TABLE III. Group E inspection (all quality levels) for qualification or re-qualification only.

Inspection	MIL-STD-750		Sample plan
	Method	Conditions	
Subgroup 1			45 devices c = 0
Temperature cycling	1051	-55°C to +150°C, 500 cycles	
Hermetic seal Fine leak Gross leak	1071	As applicable.	
Electrical measurements		See table I, subgroup 2 herein.	
Subgroup 2 1/			45 devices c = 0
Steady-state gate bias	1042	Condition B, 1,000 hours.	
Electrical measurements		See table I, subgroup 2 herein.	
Steady-state reverse bias	1042	Condition A, 1,000 hours.	
Electrical measurements		See table I, subgroup 2 herein.	
Subgroup 3			
Not applicable			
Subgroup 4			Sample size N/A
Thermal impedance curves		See MIL-PRF-19500.	
Subgroup 5			
Not applicable			
Subgroup 10			22 devices c = 0
Commutating diode for safe operating area test procedure for measuring dv/dt during reverse recovery of power MOSFET transistors or insulated gate bipolar transistors	3476		
Subgroup 11			3 devices
SEE 2/ 3/	1080	See MIL-STD-750 method 1080 and 6.2.	

1/ A separate sample for each test shall be pulled.
2/ Group E qualification of SEE testing may be performed prior to lot formation. Qualification may be extended to other specification sheets utilizing the same structurally identical die design.
3/ Device qualification to a higher level linear energy transfer (LET) is sufficient to qualify all lower level LETs.


Source: https://assist.dla.mil -- Downloaded: 2026-10-19T06:05Z
Check the source to verify that this is the current version before use.



2N7645U8C, U8CE

FIGURE 3. Thermal response curve


Maximum Current Rating



2N7645U8C, U8CE

FIGURE 4. Maximum drain current versus case temperature graphs.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T06:05Z
Check the source to verify that this is the current version before use.



2N7645U8C, U8CE

FIGURE 5. Safe operating area graph.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T06:05Z
Check the source to verify that this is the current version before use.

5. PACKAGING

5.1 Packaging. For acquisition purposes, the packaging requirements shall be as specified in the contract or order (see 6.2). When packaging of materiel is to be performed by DoD or in-house contractor personnel, these personnel need to contact the responsible packaging activity to ascertain packaging requirements. Packaging requirements are maintained by the Inventory Control Point's packaging activities within the Military Service or Defense Agency, or within the Military Service's system commands. Packaging data retrieval is available from the managing Military Department's or Defense Agency's automated packaging files, CD-ROM products, or by contacting the responsible packaging activity.

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory. The notes specified in MIL-PRF-19500 are applicable to this specification.)

6.1 Intended use. Semiconductors conforming to this specification are intended for original equipment design applications and logistic support of existing equipment.

6.2 Acquisition requirements. Acquisition documents should specify the following:

a. Title, number, and date of this specification.

b. Packaging requirements (see 5.1).

c. Lead finish (see 3.4.1).

d. The complete PIN, see 1.5 and 6.6.

e. For acquisition of RHA designated devices, table II, subgroup 1 testing of group D herein is optional. If subgroup 1 is desired, it should be specified in the contract or order.

f. If SEE testing data is desired, it should be specified in the contract or order (see 4.2.1.1).

g. If specific SEE characterization conditions are desired (see section 6.7 and table IV), manufacturer's cage code should be specified in the contract or order.


* 6.3 Qualification. With respect to products requiring qualification, awards will be made only for products which are, at the time of award of contract, qualified for inclusion in Qualified Manufacturers List (QML 19500) whether or not such products have actually been so listed by that date. The attention of the contractors is called to these requirements, and manufacturers are urged to arrange to have the products that they propose to offer to the Federal Government tested for qualification in order that they may be eligible to be awarded contracts or orders for the products covered by this specification. Information pertaining to qualification of products may be obtained from DLA Weapons Support, ATTN: VQE, P.O. Box 3990, Columbus, OH 43218-3990 or e-mail vqe.chief@dla.mil. An online listing of products qualified to this specification may be found in the Qualified Products Database (QPD) at https://qpldocs.dla.mil.

6.4 Substitution information. Devices covered by this specification are substitutable for the manufacturer's and user's Part or Identifying Number (PIN) (without JAN and RHA prefix). This information in no way implies that manufacturer's PINs are substitutable for the military PIN.

Preferred types military PIN	Commercial PIN
2N7645U8C	IRHNMC87Y20
2N7645U8CE	

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T06:05Z
Check the source to verify that this is the current version before use.

6.5 PIN construction example. The PINs for encapsulated devices are constructed using the following form.



* 6.6 List of PINs. The following is a list of possible PINs available on this specification sheet.

PINs for devices of the "TXV" quality level	PINs for devices of the "S" quality level with RHA
JANTXVR2N7645U8C	JANSR2N7645U8C
JANTXVF2N7645U8C	JANSF2N7645U8C
JANTXVR2N7645U8CE	JANSR2N7645U8CE
JANTXVF2N7645U8CE	JANSF2N7645U8CE

1/ The PIN is also available without an RHA designator.

6.7 Application data.

6.7.1 Manufacturer specific irradiation data. Each manufacturer qualified to this specification sheet has characterized its devices to the requirements of MIL-STD-750 method 1080 and as specified herein. Since each manufacturer's characterization conditions can be different and can vary by the version of method 1080 qualified to, the MIL-STD-750 method 1080 revision version date and conditions used by each manufacturer for characterization have been listed here (see table IV) for information only. SEE (SEB and SEGR) conditions and figures listed in section 6 are current of the date of this specification sheet, please contact the manufacturer for the most recent conditions.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T06:05Z
Check the source to verify that this is the current version before use.

TABLE IV. Manufacturers characterization conditions.

	Manufacturers CAGE	Inspection	MIL-STD-750		Sample plan
			Method	Conditions	
	69210	SEE 1/	1080	See MIL-STD-750 method 1080 and figure 6.	3 devices
		Pre SEB/SEGR Electrical measurements		I_{GSSF1}, I_{GSSR1}, and I_{DSS1} in accordance with table I, subgroup 2	
		SEE irradiation		Fluence = 3E5 ±20 percent ions/cm^2 Flux = 4E3 to 4E4 ions/cm^2/sec	
*		2N7645U8C, U8CE		Surface LET = 40 MeV-cm2/mg ±5%, range = 40.1 µm ±5%, Kr ion beam energy = 312 MeV ±5%. In-situ bias conditions: V_{DS} = 18 V and V_{GS} = -3 V V_{DS} = 17 V and V_{GS} = -4 V V_{DS} = 15 V and V_{GS} = -5 V (Typical 3.72 MeV/Nucleon at Texas A & M Cyclotron)	
		Post SEB/SEGR Electrical measurements		I_{GSSF1}, I_{GSSR1}, and I_{DSS1} in accordance with table I, subgroup 2	
		SEE 1/	1080	See MIL-STD-750 method 1080 and figure 6.	3 devices
		Pre SEB/SEGR Electrical measurements		I_{GSSF1}, I_{GSSR1}, and I_{DSS1} in accordance with table I, subgroup 2	
		SEE irradiation		Fluence = 3E5 ±20 percent ions/cm^2 Flux = 4E3 to 4E4 ions/cm^2/sec, temperature = 25 ±5°C	
*		2N7645U8C, U8CE		Surface LET = 67.9 MeV-cm2/mg ±5%, range = 52.5 µm ±5%, Xe ion beam energy= 675 MeV ±5%. In-situ bias conditions: V_{DS} = 17 V and V_{GS} = -3 V; V_{DS} = 14 V and V_{GS} = -4 V V_{DS} = 12 V and V_{GS} = -5 V (Typical 5.24 MeV/Nucleon at Texas A & M Cyclotron)	
		Post SEB/SEGR Electrical measurements		I_{GSSF1}, I_{GSSR1}, and I_{DSS1} in accordance with table I, subgroup 2	

See footnote at end of table.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T06:05Z
Check the source to verify that this is the current version before use.

TABLE IV. Manufacturers characterization conditions - continued.


Manufacturers CAGE	Inspection	MIL-STD-750		Sample plan
		Method	Conditions	
69210	SEE 1/	1080	See MIL-STD-750 method 1080 and figure 6.	3 devices
	Pre SEB/SEGR Electrical measurements		I_{GSSF1}, I_{GSSR1}, and I_{DSS1} in accordance with table I, subgroup 2	
	SEE irradiation		Fluence = 3E5 ions/cm^2 Flux = 4E3 to 4E4 ions/cm^2/sec, temperature = 25 ±5°C	
*	2N7645U8C, U8CE		Surface LET = 93.2 MeV-cm2/mg ±5%, range = 65.1 µm ±5% Au ion beam energy= 1105 MeV ±5%.	
			In-situ bias conditions: V_{DS} = 17 V and V_{GS} = 0 V V_{DS} = 16 V and V_{GS} = -1 V V_{DS} = 16 V and V_{GS} = -2 V V_{DS} = 14 V and V_{GS} = -3 V V_{DS} = 10 V and V_{GS} = -4 V V_{DS} = 8 V and V_{GS} = -5 V	
			(Typical 5.61 MeV/Nucleon at Texas A & M Cyclotron)	
	Post SEB/SEGR Electrical measurements		I_{GSSF1}, I_{GSSR1}, and I_{DSS1} in accordance with table I, subgroup 2	
Upon qualification, all manufacturers will provide the verification test conditions to be added to this table.				

1/ I_{GSSF1}, I_{GSSR1}, and I_{DSS1} parameters were examined before and following SEB/SEGR heavy ion irradiation to determine acceptability for each bias conditions. Other test conditions in accordance with table I, subgroup 2, may be performed at the manufacturer's option.

2/ Manufacturer performed heavy ion SEE(SEB/SEGR) test at TAMU Radiation Effects Facility for the MOSFET technology devices in accordance with TM1080 of MIL-STD-750. No single event burnout (SEB) and Single event gate rupture(SEGR) were observed to surface LET as stated above table IV and safe operating area (see figure 6). Limits are characterized at initial qualification and after any design or process changes which may affect the SEE(SEB/SEGR) characteristics. For more information on SEE (SEB/SEGR) test results, customers are requested to contact the manufacturer.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T06:05Z
Check the source to verify that this is the current version before use.

Worst-Case SEE Response



2N7645U8C, U8CE

FIGURE 6. SEB/SEGR safe operating area graph.

6.8 Request for new types and configurations. Requests for new device types or configurations for inclusions in this specification sheet should be submitted to: DLA Weapons Support, ATTN: VAC, Post Office Box 3990, Columbus, OH 43218-3990 or by electronic mail at Semiconductor@dla.mil.

* 6.9 Amendment notations. The margins of this specification are marked with asterisks to indicate modifications generated by this amendment. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous issue.

Custodians:
Army - CR
Navy - SH
Air Force - 85
NASA - NA
DLA - CC

Review activity:
Army - AV, MI
Air force - 19

Preparing activity:
DLA - CC

(Project 5961-2026-019)

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at https://assist.dla.mil/.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T06:05Z
Check the source to verify that this is the current version before use.