INCH-POUND

MIL-B-52489E
AMENDMENT 1
26 May 1995

MILITARY SPECIFICATION

BARBED TAPE, CONCERTINA

This amendment forms a part of Military Specification MIL-B-52489E, dated 26 March 1987, and is approved for use by all Departments and Agencies of the Department of Defense.

PAGE 1

2.1.1.: Under SPECIFICATIONS, FEDERAL, delete:
"QQ-S-781 - Strapping, Steel, and Seals
QQ-W-461 - Wire, Steel, Carbon, (Round, Bare and Coated)"

Beneficial comments, delete in its entirety and substitute the following:

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Commander, US Army Aviation and Troop Command, ATTN: AMSAT-R-EDS, 4300 Goodfellow Boulevard, St Louis, MO 63120-1798 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

PAGE 2

2.1.1: Under SPECIFICATIONS, MILITARY, delete: "MILITARY" and "MIL-T-704 - Treatment and Painting of Materiel."

2.1.1: Under STANDARDS, FEDERAL, delete: "FEDERAL" and "MIL-STD-595 - Colors."

DISTRIBUTION STATEMENT A. Approved for public release, distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 202610-22T21:20Z
Check the source to verify that this is the current version before use.

PAGE 2

2.2.: Under AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM),
delete: "ASTM D 522 - Elongation of Attached Organic Coatings with Conical Mandrel Apparatus
ASTM D 523 - Specular Gloss
ASTM D 2092- Preparation of Zinc-Coated Steel Surfaces for Painting
ASTM D 3359- Measuring Adhesion by Test Tape"

add: "ASTM A 641 - Zinc-Coated (Galvanized) Carbon Steel Wire
ASTM A 777 - Galvanized Round Steel Tying Wire
ASTM B 633 - Standard Specification for Electrodeposited Coatings of Zinc on Iron and Steel"

PAGE 3

3.3.1.1, lines 4 thru 9, delete: "The barbed tape shall be phosphatized in accordance with commercially available phosphatizing processes for zinc phosphate conversion coatings and shall be compatible with galvanized surfaces. The treatment for conversion to zinc phosphate coatings shall be in accordance with ASTM D 2092. The minimum zinc phosphate coating weight shall be 150 mg/sq ft for spray processes and 300 mg/sq ft for immersion processes."
lines 9 and 10, change to "Coat may be applied before all machining, brazing, and forming."

3.3.1.2, lines 3 thru 8, delete: "The clips or strips shall be phosphatized in accordance with commercially available phosphatizing processes for zinc phosphate conversion coatings. The treatment for conversion to zinc phosphate coatings shall be in accordance with ASTM D 2092. The minimum zinc phosphate coating weight shall be 150 mg/sq ft for spray processes and 300 mg/sq ft for immersion processes", and substitute: "The clips or strips shall be zinc coated 0.0002 inch minimum each side and shall then have a supplementary chromate treatment complying with ASTM B633, Type III, with applicable test thereof."

PAGE 4

3.3.1.3, delete in its entirety.

3.3.3.1 and 3.3.3.2, line 2, delete: "QQ-W-461, steel no. 1010, finish 5, soft, class 1", and substitute: "ASTM A 641, class 1 coating, soft temper."

PAGE 5

3.5 thru 3.5.2, delete in its entirety.

Source: https://assist.dla.mil - Downloaded: 2026-10-22T21:20Z
Check the source to verify that this is the current version before use.

PAGE 6

3.5.3 thru 3.5.3.5, delete in its entirety.

PAGE 7

4.4.1.3, line 1, delete: "Sampling" and substitute "Sample size".

4.4.2.3, delete last sentence and substitute: "Presence of one or more defects shall be cause for rejection".

PAGE 8

4.4.3.2, delete in its entirety.

PAGE 9

4.5.1.3, under Major, delete: "120. Color not as specified" and "121. Treatment and painting not as specified".

4.5.1.3.1, 4.5.2.2, 4.5.2.3, and 4.5.2.4, delete in its entirety.

PAGE 10

4.5.2.5., delete in its entirety.

4.5.2.6, change to: "Salt spray. Using a specimen not less than 6 inches long, taken from the barbed tape concertina, subject the specimen to continuous salt spray test in accordance with ASTM B117, for not less than 120 hours. The specimen shall show no blistering nor white corrosion or base metal corrosion products. The appearance of corrosion products visible to the unaided eye at normal reading distance shall be cause for rejection, except those white corrosion products at the edge of the specimens shall not constitute failure."

4.6.2.3, line 2, delete: "The AQL shall be 1.0 percent defective" and substitute: "Presence of one or more defects shall be cause for rejection".

5.2, line 3, delete: "QQ-S-781, class 2, type V, finish B, size 9", and substitute "ASTM A 777, class II, size 9 (0.148 inch nominal diameter), regular coating."

Custodian:
Army - AV

Review Activity:
DLA - CS

Preparing activity:
Army - AV

Agent:
DLA - CS

(Project 5660-0098)

Source: https://assist.dla.mil - Downloaded: 2026-10-22T21:20Z
Check the source to verify that this is the current version before use.