MIL-C-50447A (PA)
14 May 1975
SUPERSEDING
MIL-C-50447 (MU)
9 July 1969

MILITARY SPECIFICATION

CASE CARTRIDGE, 40MM, M118 and M195; PLUG, BASE FOR

This specification Is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 This specification covers one type of base plug for use in Case Cartridge , 40MM, M118 and M195.

2* APPLICABLE DOCUMENTS

2.1 The following documents of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

SPECIFICATIONS

MILITARY

MIL-A-8625 - Anodic Coatings for Aluminum and Aluminum Alloys
MIL-A-48078 - Ammunition, Standard Quality Assurance Provisions, General Specification For

STANDARDS

MILITARY"

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes (ABC-STD-105)

FSC : 1310

Source: https://assist.dla.mil -- Downloaded: 2026l0-22T20:25Z
Check the source to verify that this is the current version before use.

MIL-STD-n69 - Packaging, Packing and Marking for Shipment of Inert Ammunition Components

DRAWINGS

PICATINNY ARSENAL

PRODUCT AND PACKAGING DRAWINGS

8844611 - Plug, Base

INSPECTION EQUIPMENT DRAWINGS

9202532 - Gage, Automatic
8841561 - Gage, Concentricity

2.2 Other publications.-The following documents form a part of this specification to the extent specified herein. Unless otherwise-indicated, the issue in effect on the date of invitation-for bids or request for proposal shall apply.

AMERICAN SOCIETY FOR TESTING AND MATERIALS

ASTM-B-117-73 - Standard Method of Salt Spray (Fog) Testing

(Application for copies should be addressed to: American Society for Testing and Materials, 1916 Race Street, Philadelphia, Pa. 19103).

3* REQUIREMENTS

3.1 Material.-Materials shall be in accordance with the applicable drawings and specifications.

3.2 Part.-The part shall comply with all requirements specified on Drawing (Dwg.) 8844611, all associated drawings, and with all requirements specified in applicable specifications.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:25Z
Check the source to verify that this is the current version before use.

I

3.3 Workmanship.-All parts and assemblies shall be fabricated and finished in a thorough, workmanlike manner. They shall be free of burrs, chips, sharp edges, cracks, unblended radii, surface defects, dirt, grease, rust, corrosion products, and other foreign matter. The cleaning method used shall not be injurious to any parts, nor shall the parts be contaminated by the cleaning agents. All marking and stamping shall be neat and sharply defined.

3.4 Submission of results of contractor-conducted examinations and tests.-The contractor shall forward copies of the results of any of his examinations or tests to the designated address as required by the contract. (See 6.4).

3.5 First Article Inspection. -This specification contains technical provisions for first article inspection. Requirements for the submission of first article samples by the contractor shall be as specified in the contract.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection and Standard Quality Assurance Provisions.-unless otherwise specified herein or in the contract, the provisions of MIL-A-48078 shall apply and are hereby made a part of this detail specification.

4.2 Classification of Inspections.-The following types of inspection shall be conducted on this item:

a. First Article Inspection
b. Quality Conformance Inspection “

4.3 First Article Inspection.-

4.3.1 Submission.-The contractor shall submit a first article as designated by the Contracting Officer for evaluation. in accordance with the provisions of 4.3.2. The first article sample shall consist of the following items In sample quantities as indicated.

Source: https://assist.dla.mil -- Downloaded: 202610-22T20:25Z
Check the source to verify that this is the current version before use.

Part Description	Drawings	Quantity
Base Plug	8844611	50

4.3.2 Inspections to be Performed .-See MIL-A-48078 (PA) and Table 1 here in.

4.3.3 Rejection .-See MIL-A-48078 (PA).

4.4 Quality Conformance Inspection

4.4.1 Inspection Lot Formation.-Inspection lots shall comply with the lot formation provisions of MIL-A-48078 (PA).

4.4.2 Examination. -See MIL-A-48078 (PA).

a. Sampling Plans.-Unless otherwise specified in the Classification of Defects and Test Tables, sampling plans for major and minor defects shall be in accordance with MIL-STD-105, Inspection Level II.

Source: https://assist.dla.mil -- Downloaded: 202610-22T20:25Z
Check the source to verify that this is the current version before use.

TABLE 1 - FIRST ARTICLE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

MIL-C-50447A (PA)

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER
	Base Plug				SEE BELOW
					NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
	Base Plug (Dwg. 8844611)				
	Examination for Defects	50	-	3.2	4.4.2.1
	Salt Spray	10	-	3.2	4.5.1

NOTES:

SARPA-C[illegible] FORM 2567 FEB 74

Source: https://assist.dla.mil -- Downloaded: 202610-22T20:25Z
Check the source to verify that this is the current version before use.

4.4.3 Testing. -

4.4.3.1 Process control inspection of bath temperature for anodic coating (Dwg. 8844611), Major Defect.-Continuing monitoring inspection shall be conducted for the bath temperature requirement specified on the drawing. If the bath temperature for a batch of parts does not comply with the drawing requirement, the batch shall be suitably identified, classed defective and removed from the lot.

4.4.4 Inspection Equipment. -The inspection equipment required to perform the examinations and tests prescribed herein is described in the Paragraph Refernece/Inspection Method column in the tables starting with Paragraph 4.4.2.1. The contractor shall submit for approval inspection equipment designs in accordance with the terms of the contract. See Section 6 of MIL-A-48078 and 6.3 herein.

4.5 Test methods and procedures.-

4.5.1 Salt Spray.-The base plug shall be subjected to the salt spray test in accordance with ASTM-B-117-73. This test shall be conducted for 240 hours. Salt solution shall be 5 percent. This test is a destructive test. Parts so tested shall not be returned to the lot.

5. PREPARATION FOR DELIVERY

5.1 Preservation and packaging.-

5.1.1 Level C.-See 5.2.1.

5.2 Packing.-

5.2.1 Level C.-The base plug shall be packed for shipment in acco-with MIL-STD-1169.

5.3 Marking.-Marking of the carton shall comply with. MIL-STD-1169.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:25Z
Check the source to verify that this is the current version before use.

5.4 Shipping.-When components from more than one lot are shipped as a carload, each lot shall be kept separate, and the division between lots clearly indicated to prevent mixing of the lots in transit.

6. NOTES

6.1 Intended Use.-The component covered by this specification is intended for use in Case Cartridge, 40MM, M118 and M195.

6.2 Ordering Data.-See MIL-A-48078 (PA).

6.3 Submission of Inspection Equipment Designs for Approval.-See MIL-A-48078 (PA). Submit equipment designs as required to Commander, Attn: SARPA-QA-T, Picatinny Arsenal,. Dover, NJ 07801.

6 4 Submission of results of contractor conducted m ns and tests Unless otherwise specified by the Contracting Officer the contractor shall forward requested records of examinations or tests to Commanders Picatinny Arsenal, Attn: SARPA-QA-A-S.

Custodian:
Army-PA

Preparing, Activity:
Army-PA

Project Number: 1310-A077

Source: https://assist.dla.mil -- Downloaded: 202610-22T20:25Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

MIL-C-50447A (PA)

PARAGRAPH	TITLE		SHEET 1 OF 2		DRAWING NUMBER 8844611
4.4.2.1	Base Plug				NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Critical					
1	Depth of primer cavity		100%	3.2	Automatic Gage (9202532)
Special	None defined				
Major A					
101	Salt Spray	(a)	(a)	3.2	4.5.1
Major B					
131	Largest outside diameter		0.40%	3.2	Gage
132	Concentricity of smallest outside diameter with largest outside diameter		0.40%	3.2	8841561
133	Concentricity of primer cavity diameter with largest outside diameter		0.40%	3.2	8841561
134	Smallest outside diameter		0.40%	3.2	Gage
135	Diameter of primer cavity		0.40%	3.2	Gage
136	Length of primer end to shoulder including angle		0.40%	3.2	Gage
137	Total length		0.40%	3.2	Gage
138	Diameter of flash hole		0.40%	3.2	Gage
139	Radius of intersection of primer cavity missing		0.40%	3.2	Visual

NOTES:

(a) Sampling and rejection shall be in accordance with MIL-A-8625.

SARPA-QA FORM 2567 FEB 74

Source: https://assist.dla.mil -- Downloaded: 202610-22T20:25Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS MIL-C-50447A (PA)

PARAGRAPH	TITLE	SHEET 2 OF 2	DRAWING NUMBER
4.4.2.1	Base Plug		8844611
			NEXT HIGHER ASSEMBLY

CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Minor					
201	Second largest outside diameter		0.65%	3.2	Gage
202	Length from primer end to far side of shoulder		0.65%	3.2	Gage
203	Protective coating with bare spot except anode rack marks		0.65%	3.2	Visual
204	Finish improper		0.65%	3.2	Visual
205	Color incorrect		0.65%	3.2	Visual
206	Evidence of poor workmanship		0.65%	3.3	Visual

NOTES:

SARPA-QA FORM 2567 FEB 74

Source: https://assist.dla.mil -- Downloaded: 202610-22T20:25Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

OMB Approval
No. 22-R255

INSTRUCTIONS: The purpose of this form is to solicit beneficial comments which will help achieve procurement of suitable products at reasonable cost and minimum delay, or will otherwise enhance use of the document. DoD contractors, government activities, or manufacturers/ vendors who are prospective suppliers of the product are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity.

DOCUMENT IDENTIFIER AND TITLE

NAME OF ORGANIZATION AND ADDRESS

CONTRACT NUMBER

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?
   A. GIVE PARAGRAPH NUMBER AND WORDING.

   B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY DOCUMENT REQUIREMENT CONSIDERED TOO RIGID

3. IS THE DOCUMENT RESTRICTIVE?

   ☐ YES ☐ NO *(If "Yes", in what way?)*

4. REMARKS

SUBMITTED BY *(Printed or typed name and address - Optional)*

TELEPHONE NO.

DATE

DD FORM 1 JAN 72 1426 REPLACES EDITION OF 1 JAN 66 WHICH MAY BE USED

Source: https://assist.dla.mil -- Downloaded: 20260-22T20:252
Check the source to verify that this is the current version before use.