INCH-POUND

MIL-C-63292 (AR)
AMENDMENT 4
23 June 1989
SUPERSEDING
AMENDMENT 3
13 May 1988

MILITARY SPECIFICATION

CASE, CARTRIDGE, 105MM, M148A1B1

This amendment forms a part of Military Specification MIL-C-63292 (AR) dated 8 February 1980 and is approved for use within the U.S. Army Armament Munitions and Chemical Command and is available for use by all Departments and Agencies of the Department of Defense.

PAGE 1

2.1 STANDARDS MILITARY:

Add: "MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes".

PAGE 4

3.8.4 Delete: "No cartridge case shall have a burr." and substitute: "Burrs shall be limited to those described in 105mm Cartridge Case 'Visual Defect Standards'."

PAGE 5

4.3.1: Change "254*" to "262".

Delete the following sentence in its entirely: "*All samples must meet the requirements for thermal treatment and high stress expansion test as performed in the uncoated state."

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:35Z
Check the source to verify that this is the current version before use.

PAGE 6

Table I - First Article Inspection:

Cartridge Case - Prior to Coating: Delete in its entirety.

Cartridge Case - After Coating:

Change "254" to "262"

Add:	"Tension Test (info Only)	4	3.3	4.5.4
	Macro Examination	4	3.8.2	4.5.5
	Hardness	20	3.3	4.5.3"

PAGE 8

4.4.2.1: Delete in its entirety and substitute new paragraph 4.4.2.1 (included as page 3).

PAGE 10

* 4.4.2.2: Delete in its entirety and substitute new paragraph 4.4.2.2 (included as pages 4, 5, and 6).

4.4.2.3: Major Defect, delete "None defined."

Add Major Defect 101:

"101 Cracks and other metal defects (cartridge cases) just prior to packing into carton	100%	3.8.1	Visual"

PAGE 15

Delete this paragraph in its entirety and substitute:

"4.5.4 Tension test (Information Only). Four cartridge cases from each lot shall be subjected to this test. The test specimens shall be taken from each cartridge case in accordance with the standard position and size of the tensile specimen chart described in Figure 1. The yield strength, tensile strength and elongation shall be determined in accordance with the procedures prescribed by ASTM-E8. The results shall be recorded for information only."

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:35Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER
4.4.2.1	Case, Cartridge - Prior to Coating				10522799
					NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Critical	None defined.				
Major 101	High stress expansion test		100% (a)	3.1	4.5.2

NOTES:
(a) All non-compliance units must be removed from the lot. Evidence of cracks in any portion of the case shall be cause for rejection.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:35Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE	SHEET	DRAWING NUMBER
4.4.2.2	Case, Cartridge - After Coating	1 OF 3	10522799
			NEXT HIGHER ASSEMBLY

CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Critical	None defined.				
Major					
101	Cracks		100% (a)	3.8.1	4.5.7
102	Metal defective		100% (a)	3.8.1	4.5.7
103	Thickness of coating	(See 4.5.6)		3.4	4.5.6.1
104	Salt spray	(See 4.5.6)		3.1	4.5.6.2
105	Maximum profile and alignment		100% (a)	3.5	4.5.8
106	Excess pressure ballistic test	(See 4.4.3.1.2)		3.6	4.5.9.2.1
107	True position of pitch diameter of thread with body (10)		0.40%	3.1	Gage
108	True position of primer hole counterbore with pitch diameter of thread.		0.40%	3.1	Gage
109	True position of primer hole thread relief with pitch diameter of thread		0.40%	3.1	Gage
110	Pitch diameter of thread, max.		0.40%	3.1	Gage
111	Minor diameter of thread, max.		0.40%	3.1	Gage
112	Length total, max.		0.40%	3.1	Gage
113	Diameter of primer hole counterbore		0.40%	3.1	Gage
114	Depth of primer hole counterbore, min.		0.40%	3.1	Gage
115	Length from flange to bottom of primer hole counterbore, max.		0.40%	3.1	Gage
116	Depth of thread relief		0.40%	3.1	Gage
117	Protective coating defective		0.40%	3.4	Visual

NOTES:
(a) All non-compliance units must be removed form the lot.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:35Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE		SHEET 2 OF 3		DRAWING NUMBER
* 4.4.2.2	Case, Cartridge - After Coating				10522799
					NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
(10a)					
119	Hardness	4	(b)	3.3	4.5.3
120	Macro-Examination	4	(b)	3.8.2	4.5.5
121	Diameter of flange, min.		0.40%	3.1	Gage
122	Diameter of mouth		0.40%	3.1	Gage
123	(Deleted)				
124	Thickness of flange, min.		0.40%	3.1	Gage
125	Thickness of base, min.		0.40%	3.1	Gage
126	Wall thickness at first datum from base		0.40%	3.1	Gage
127	Wall thickness at second datum from base		0.40%	3.1	Gage
128	Wall thickness at third datum from base		0.40%	3.1	Gage
129	Wall thickness at mouth		0.40%	3.1	Gage
130	Contour of inside of base and sidewall not smooth		0.40%	3.1	Visual
Minor					
201	Pitch diameter of thread, min		0.65%	3.1	Gage
202	Diameter of primer hole thread relief		0.65%	3.1	Gage
203	Thread damaged or not full		0.65%	3.8.3	Visual
204	Body dented or damaged		0.65%	3.1	Visual
205	Marking missing, incorrect or illegible		0.65%	3.1	Visual

NOTES:
(b) Reject on one defect.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:35Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE		SHEET 3 OF 3		DRAWING NUMBER 10522799
4.4.2.2	Case, Cartridge - After Coating				NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
206	Wax coating missing		0.65%	3.1	Visual
207	Evidence of poor workmanship		0.65%	3.8.4 & 3.8.5	Visual
208	Diameter of body under flange, min.		0.65%	3.1	Gage
209	Location of first basic diameter from flange, min.		0.65%	3.1	Gage
210	Location of second basic diameter from flange, min.		0.65%	3.1	Gage
211	Location of third basic diameter from flange, min.		0.65%	3.1	Gage
212	Location of fourth basic diameter from flange, min.		0.65%	3.1	Gage
213	Radii or chamfers,missing or incorrect		0.65%	3.1	Visual
214	Surface finish, improper		0.65%	3.1	Visual
215	Length total, min.		0.65%	3.1	Gage
Special					
301	Tension Test (Information Only)	(c)		3.3	4.5.4

NOTES:
(c) Samples used for the hardness test shall be used in the tension test (see 4.5.4).

Source: https://assist.dla.mil -- (21 of 35)
Downloaded: 2026-10-23T02:35Z
Check the source to verify that this is the current version before use.

PAGE 16

4.5.6.1 Last sentence, delete: "...rejection of the lot." and substitute: "...testing additional samples in accordance with MIL-STD-105, Inspection Level II, 0.40% AQL."

4.5.8 First sentence, delete: "...8663760..." and substitute: "...8647040...".

PAGE 17

4.5.9.1.3 Second sentence, delete: "...product..." and substitute: "...produce...".

Between "(498.49 MPa)" and "74,200 psi", add: "...to...".

NOTE: The margins of this amendment are marked with an asterisk to indicate where changes (additions, modifications, corrections, deletions) from the previous amendment were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous amendment.

Custodian:
Army-AR

Preparing Activity:
Army-AR

(Project 1315-AB71)

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:35Z
Check the source to verify that this is the current version before use.