MIL-T-81736(AS)
AMENDMENT 3
30 December 1977
SUPERSEDING
AMENDMENT 2
2 April 1973

MILITARY SPECIFICATION

TAPE, TEXTILE, NYLON, LANDBASED ARRESTING GEAR, 8 INCH

This amendment forms a part of Military Specification MIL-T-81736(AS), dated 14 August 1969

PAGE 1

1.1, delete in its entirety and substitute the following:

"1.1 This specification covers the requirements of an 8-inch nylon tape having a breaking strength of not less than 150,000 pounds."

* 2.1, SPECIFICATIONS (Military):

Delete:

| | |
|---|---|
| "MIL-B-13239 | Barrier Material, Waterproofed, Flexible, All Temperature |
| MIL-B-81374 | Barrier Material, Greaseproof, Waterproof, Flexible, High Strength" |

Add:

| | |
|---|---|
| "MIL-B-131 | Barrier Material, Watervaporproof, Flexible, Heat Sealable" |

2.1, STANDARDS (Military):

Add:

| | |
|---|---|
| "MIL-STD-1480 | Color Codes for Webbing, Textile; Manufacturers' Identification" |

PAGE 2

2.2, delete the following: "U.S. Air Force Specification Bulletin No. 90 Color Codes Manufacturers' Identification, Nylon Webbing.

(Application for copies should be addressed to the procuring activity or as directed by the contracting officer)."

FSC 8315

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T06:02Z
Check the source to verify that this is the current version before use.

PAGE 4

Table I: After "Breaking strength" characteristic delete the requirement "130,000 1/" and substitute "150,000 1/".

At the bottom of the page delete footnote 1/ in its entirety and substitute the following:

"1/ A failure at or above 150,000 pounds tension or a jawbreak at or above 150,000 pounds will be considered acceptable. A failure below 150,000 pounds tension or a jawbreak below 150,000 pounds will be considered unacceptable."

PAGE 5

3.6.1, delete in its entirety and substitute the following:

"3.6.1 Manufacturer's identification. Each manufacturer shall incorporate, as part of the binder warp at the center of the tape, two ends dyed to match the shade assigned to that manufacturer in accordance with MIL-STD-1480. A producer not listed in MIL-STD-1480 shall apply to the Commander, US Army Natick Research and Development Command, Natick, Massachusetts 01760, for assignment of color coding. The colorfastness of this yarn shall be rated as "Fair" or "Good" when tested as specified in 4.7."

4.1, delete and substitute:

* "4.1 Responsibility for inspection. Unless otherwise specified in the contract, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements."

PAGE 6

* 4.6.4.1, delete (a) and (b) and substitute:

"(a) Yard-by-yard. A one yard unit of each production tape shall be inspected as specified in 4.7.4.1 and 4.7.4.1.1 at intervals of approximately 40 feet.

(b) Overall. Each production tape length shall be examined for the defects specified in 4.7.4.2."



Source: https://assist.dla.mil -- Downloaded: 2026-10-23T06:02Z
Check the source to verify that this is the current version before use.

PAGE 8

TABLE II: Under "OTHER" column and opposite "Melting point" and "Denier" tests insert "4.7.3."

At bottom of page after footnote 5/ notation insert "(See 4.7.3)".

PAGE 9

4.7.2.1, line 2: delete "130,000 pounds" and substitute "150,000 pounds".

PAGE 10

Line 1: After "production" and before "are" insert "tapes."

PAGE 11

4.7.3, delete in its entirety and substitute the following:

"4.7.3 Type of nylon, melting point, denier, and filament count A certificate of compliance shall be submitted from the yarn manufacturer and will be accepted as proof that requirements for type of nylon, melting point, denier, filament count, and bright, high tenacity, light and heat resistant nylon yarn are met. The certification shall contain verifiable actual test data. If the approximate melting point of the specimens is not known before testing, it shall be determined by a trial run."

PAGE 16

5.1.2, lines 2 and 3: delete "MIL-B-81374 or MIL-B-13239, Type B-2, Class 1, Grade A" and substitute "MIL-B-131, Class 1."

NOTE: The margins of this amendment are marked with an asterisk to indicate where changes from the previous amendment were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous amendment.

Preparing Activity:
Navy - AS
(Project No. 8315-N267)

☆ U.S. GOVERNMENT PRINTING OFFICE: 1977 — 703-122/549



Source: https://assist.dla.mil -- Downloaded: 2026-10-23T06:02Z
Check the source to verify that this is the current version before use.