MIL-C-12836A(MU)
19 November 1965
SUPERSEDING
MIL-C-12836(CmlC)
25 June 1953

MILITARY SPECIFICATION
CLOTH, KNITTED, COTTON

1. SCOPE

1.1 This specification covers one type of jersey knit cotton cloth.

2. APPLICABLE DOCUMENTS

2.1 Government documents. The following documents of the issue in effect on date of invitation for bids or request for proposal form a part of this specification to the extent specified herein:

SPECIFICATIONS

FEDERAL

CCC-T-191	-	Textile Test Methods.

STANDARDS

MILITARY

MIL-STD-105	-	Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129	-	Marking for Shipment and Storage.

(Copies of specifications, standards, drawings, and publications required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following document forms a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.

FSC 8305

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T23:25Z
Check the source to verify that this is the current version before use.

UNIFORM CLASSIFICATION COMMITTEE

Uniform Freight Classification Ratings, Rules and Regulations.

(Application for copies of these freight classification rules should be addressed to the Uniform Classification Committee, 202 Union Station, Chicago, Illinois 60606.)

3. REQUIREMENTS

3.1 Material. The cloth shall be manufactured from cotton of suitable grade and staple to comply with this specification.

3.1.1 Construction. The cloth shall be jersey knit, well napped on one side, and furnished in tubular form.

3.2 Physical requirements.

3.2.1 Weight. The cloth shall weigh a minimum of 10.5 ounces per square yard when tested as specified in 4.6.1.

3.2.2 Count. The cloth shall have a minimum of 19 wales and 22 courses per inch when tested as specified in 4.6.1.

3.2.3 Dimensions.

3.2.3.1 Length. The cloth shall be furnished in rolls having a minimum length of 25 yards when tested as specified in 4.6.1.

3.2.3.2 Width. The tubing, when laid flat on a horizontal surface, shall be 32 ± 1 inches in width when tested as specified in 4.6.1.

3.2.4 Bursting strength. The bursting strength of the fabric shall be no less than 90 pounds when tested as specified in 4.6.1.

3.3 Air permeability. The air permeability of the finished cloth shall be between 85 and 100 cubic feet per minute per square foot of cloth when tested as specified in 4.6.1.

3.4 Color. The color shall be Olive Drab, Shade No. 7 (see 6.3).

3.4.1 Sulfur dye. The cloth shall not show the presence of sulfur when tested as specified in 4.6.2.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T23:25Z
Check the source to verify that this is the current version before use.

3.4.2 Color fastness. The material shall show good color fastness in water when tested as specified in 4.6.1.

3.5 Preproduction. When specified in the contract or order, a preproduction sample shall be produced for examination and test. The preproduction sample shall be manufactured using the same materials, methods and equipment as will be used during regular production (see 6.2).

3.6 Workmanship. The finished cloth shall be clean, evenly knitted, free from holes, drop stitches, or any other defects which may affect appearance or serviceability.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specifications where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.2 Special provisions.

4.2.1 Alternative inspection. The supplier may utilize any alternative inspection procedure which will provide equal or better assurance of quality by submitting a written proposal with justification and obtaining a written approval from the Government prior to instituting the procedure. In case of dispute, the procedures of the specification will govern.

4.2.2 Objective evidence. The supplier shall provide objective evidence acceptable to the contracting officer that the requirements of 3.1, 3.1.1, 3.4 and section 5 for which specific inspection has not been provided in this specification have been satisfied.

4.3 Lotting. A lot shall consist of the cotton cloth produced by one manufacturer, at one plant, using the same materials and processes, under essentially the same manufacturing conditions.

4.4 Sampling.

4.4.1 For examination. Sampling shall be conducted in accordance with MIL-STD-105 and table I.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T23:25Z
Check the source to verify that this is the current version before use.

4.4.2 For tests. A sample of 2 continuous yards, full width of the finished cloth, shall be taken from each sample roll selected in accordance with table I.

Table I. Sample size.

Lot size (yards)	Sample size in rolls*
Up to 400	3
401 to 800	5
801 and up	7

*If a lot contains fewer than 3 rolls, each roll in the lot shall be examined.

4.5 Inspection provisions.

4.5.1 Yard by yard examination. The required yardage of each roll shall be examined on both sides and visual defects classified as listed in table II. All defects found shall be counted regardless of their proximity to each other, except where two or more defects represent a single local condition of the cloth, in which case only the more serious defect shall be counted. A continuous defect shall be counted as one defect for each wale-wise yard or fraction thereof in which is occurs. The unit of product for this examination shall be one lineat yard. The Acceptable Quality Level (AQL) shall be 10.0 defects per hundred units. An approximate equal number of yards shall be examined in each roll of the sample.

Table II. Yard by yard examination.

Defects
Hole, cut or tear.
Abrasion mark resulting in a weak area.
Shade bar or streak, stains, or spots, clearly visible*, caused by yarn of different weight, twist, thickness, or other physical difference from adjacent yarns.
Oversized knot extending above surface of cloth.
Any run or dropped stitch.
Slubs or heavy yarns, more than twice the normal thickness.
Any mend clearly visible* which may affect serviceability.
Heavy or light areas.
Ends cut or frayed.
Embedded crease or wrinkle.

*Clearly visible at normal inspection distance (three to six feet)

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T23:25Z
Check the source to verify that this is the current version before use.

4.5.2 Overall examination. Each defect listed in table III shall be counted no more than once in each roll examined. The unit of product shall be one roll. The number of rolls to be examined (sample size) shall be in accordance with table I; the acceptance number shall be 0.

Table III. Overall examination.

Defects
Uneven knitting throughout the roll Unevenly napped

4.5.3 For tests. The sample cloth shall be tested in accordance with 4.6. The lot shall be rejected if one or more samples fail to meet any of the specified tests.

4.6 Tests. Tests shall be conducted as follows:

4.6.1 Physical requirements. The sample cotton cloth shall be tested in accordance with the methods of testing specified in CCC-T-191 and as listed in table IV.

Table IV. Instructions for testing.

Characteristic	Requirement	Test method
Weight	3.2.1	5041
Count, wales and courses	3.2.2	5070
Length	3.2.3.1	5010.1
Width	3.2.3.2	5020
Bursting strength	3.2.4	5120
Air permeability	3.3	5450
Sulfur dye	3.4.1	4.6.2
Color fastness	3.4.2	5630

4.6.2 Detection of sulfur dyes. Analytical reagent grade chemicals and distilled water shall be used throughout the test. Place a 1-inch square piece of cloth, taken from the unit of product, in a test tube and cover it with a solution containing 1-gram of stannous chloride for every 2 milliliters of 6N hydrochloric acid. Cover the mouth of the test tube with a piece of filter paper which has been

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T23:25Z
Check the source to verify that this is the current version before use.

moistened with a few drops of 0.5N solution of lead acetate. Boil the solution in the test tube. The appearance of a black stain on the filter paper indicates the presence of a sulfur dye.

5. PREPARATION FOR DELIVERY

5.1 *Packaging, level C.* The cloth shall be packaged to afford adequate protection from the supply source to the first receiving activity for immediate use.

5.2 Packing, level C. The cloth, packaged as specified in 5.1, shall be packed to insure carrier acceptance and safe delivery to the first domestic destination. Containers shall comply with the Uniform Freight Classification rules or regulations of other carriers applicable to the mode of transportation.

5.3 Marking. In addition to any special marking required by the contract or order, unit packages and shipping containers shall be marked in accordance with MIL-STD-129.

6. NOTES

6.1 Intended use. The cotton cloth covered by this specification is intended for use as a filter material in dust respirators.

6.2 Ordering data. Procurement documents should specify the following:

(a) The title, number and date of this specification.
(b) Whether a preproduction sample is required.
    (1) Quantity required.
    (2) Time allowed for supplier submission of samples for Government test and evaluation after award of contract.
    (3) Name and address of test facilities and shipping instructions when testing is performed by the Government.
    (4) Time required for the Government to notify the supplier whether or not to proceed with production.

6.3 Color standard. The color shall be in accordance with the US Army Standard Color Card, issued by the Textile Color Card Association of the United States, Inc.

6.4 International interest. Certain provisions of this specification are the subject of international standardization agreement. When amendment, revision, or cancellation of this specification is proposed, the departmental custodians will inform their respective Departmental Standardization Office so that appropriate action may be taken respecting the International Agreement concerned.

Custodian:
Army - MU

Preparing activity:
Army - MU(EA)

Review activity:
Army - GL

Project No. 8305-A324

International interest (see section 6).

Source: https://assist.dla.mil -- Downloaded: 2026-10-17 20:25:57
Check the source to verify that this is the current version before use.