METRIC


MIL-PRF-49291/10
27 August 2009

PERFORMANCE SPECIFICATION SHEET

FIBER, OPTICAL, TYPE I, CLASS I, SIZE IV, COMPOSITION A, WAVELENGTH B, RADIATION RESISTANT, ENHANCED PERFORMANCE CHARACTERISTICS (METRIC)

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specification sheet and MIL-PRF-49291.




PIN	Dimensions		
	A (µm)	B (µm)	C (µm)
M49291/10-01 M49291/10-01A	62.5 ± 2.5	1/	125 ± 1 2/
M49291/10-02 M49291/10-02A	62.5 ± 2.5	125 ± 1	245 ± 10 3/

1/ Cladding diameter remains unspecified with condition that optical fiber must meet specified requirements.
2/ Overall dimension includes a non-strippable coating (or surface treatment). Cladding along with this coating shall conform to C diameter. Use C dimension in lieu of cladding to determine cladding ovality, core-to-cladding offset and cladding dimensions.
3/ Integrated fiber and cable manufacturing process may exceed this diameter. When this condition occurs, then this configuration shall conform to cabling specification in addition to this specification sheet.

FIGURE 1. Dimensions and configuration of optical fiber construction.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:01Z
Check the source to verify that this is the current version before use.



Circle (solid)	Diameter (µm)
Inner	60.0
Second	65.0
Third	124.0
Fourth	126.0

FIGURE 2. Tolerance fields.

Part or identifying number (PIN). (See figure 1 and table II):

M49291/10-01
M49291/10-01A
M49291/10-02
M49291/10-02A

REQUIREMENTS:

Test samples for qualification: Reels of optical fiber produced for initial qualification and quality conformance shall be from at least two different preforms (see MIL-PRF-49291 paragraph 4.5.1).

Dimensions and configuration:

Diameter: See figure 1 and figure 2. (Diameter requirements are based on selecting fibers with end-point tolerances of 125 ± 1 µm from production with a 125 ± 2 µm tolerance.)

Ovality:
Core: ≤ 5 percent.
Cladding: ≤ 1 percent.

Offset:

Core-to-cladding: ≤ 2 µm

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:01Z
Check the source to verify that this is the current version before use.

Fiber-to-coating:
Coating-cladding concentricity error: $\leq$ 10.5 µm
Overall coating concentricity ratio (OCCR or coating noncircularity): $\geq$0.75 for a 250 µm diameter coating.

Fiber curl: Not applicable.

Splices within the optical fiber: Splices within the optical fiber are not allowed.

Proof test: 1.38 GPa (200 kpsi).

Fiber mass/unit length: 0.1 kg/km maximum.

Optical parameters:

Change in optical transmittance: Measurements to be made at 850 nm ± 20 nm.

Maximum attenuation rate: Spectral attenuation shall be performed at a sufficient number of wavelengths to cover the applicable optical transmission windows and sources for attenuation. Sufficient coverage includes the optical transmission windows (850 nm, 1,300 nm), ultraviolet absorption band (600 nm to 870 nm), Rayleigh scattering losses (800 nm to 1,200 nm), OH impurity absorption peaks (945 nm, 1,249 nm, and 1,383 nm). Use of a source and power meter to perform this measurement is not acceptable. Attenuation rate for wavelengths of operation shall not exceed the maximum values listed below.

Maximum attenuation rate over the wavelength range from 800 nm to 1600 nm shall be less than 4.5 dB/km. Attenuation rate for wavelengths of operation shall not exceed 3.0 dB/km at 850 nm ± 20 nm and 0.7 dB/km at 1,300 nm ± 20 nm.

Numerical aperture: 0.275 ± 0.015 at 850 nm ± 25 nm.

Overfill bandwidth: ≥ 300 MHz-km at 850 nm ± 20 nm and ≥ 600 MHz-km at 1,300 nm ± 20 nm

RML/EMB_c bandwidth: ≥ 385 MHz-km at 850 nm ± 20 nm and ≥ 700 MHz-km at 1,300 nm ± 20 nm

Chromatic dispersion: Zero dispersion wavelength shall be 1,343 nm ± 23 nm. The value of the slope at the zero dispersion wavelength shall be not greater than 0.11 ps/nm^2-km for a zero dispersion wavelength between 1,320 nm to 1,348 nm and shall not be greater than 0.001 (1,458-zero dispersion wavelength) ps/nm^2-km for a zero dispersion wavelength between 1,348 nm to 1,366 nm.

Transient attenuation: Transient attenuation shall be ≤ 1.5 dB at 1,300 nm when tested in accordance with TIA-455-78.

Attenuation uniformity. Applicable except perform at 850 nm and 1,300 nm. There shall be no discontinuities in attenuation along the length greater than 0.2 dB.

Macrobend attenuation: Applicable except test shall be performed in accordance with TIA/EIA-455-62, method B, with optical power measurements obtained for each row of parameters in table I.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:01Z
Check the source to verify that this is the current version before use.

TABLE I. Macrobend attenuation test parameters.

Mandrel diameter mm (Inch)	Number of turns around mandrel	Measurement wavelength (nm)	Macrobend attenuation (dB)
76 ± 1 (3.0 ±.04)	100	1300 ± 20	0.5
76 ± 1 (3.0 ±.04)	100	850 ± 25	0.5
30 ± 1 (1.2 ± .04)	10	1,300 ± 20	1.5
30 ± 1 (1.2 ± .04)	10	850 ± 25	1.5
20 ± 1 (.79 ± .04)	1	1300 ± 20	2.5
20 ± 1 (.79 ± .04)	1	850 ± 25	2.5
15 ± .5 (.59 ± .02)	1	1,300 ± 20	3.5
15 ± .5 (.59 ± .02)	1	850 ± 25	3.5

Polarization mode dispersion: Not applicable.

ENVIRONMENTAL:

Temperature range: See table II.

TABLE II. Temperature range. 1/

PIN	Operating ^{o}C (^{o}F)	Nonoperating ^{o}C (^{o}F)	Storage ^{o}C (^{o}F)
M49291/10-01 M49291/10-02 2/	-55 to +165 (-67 to 329)	-40 to + 85 (-40 to 185)	-40 to +85 (-40 to 185)
M49291/10-01A M49291/10-02A 3/	-46 to +85 (-51 to 185)	-55 to +85 (-67 to 185)	-55 to +85 (-67 to 185)

1/ Temperatures are specified in degrees Centigrade, Fahrenheit equivalent are specified in parenthesis.
2/ Temperature ranges in row 2 conform to those specified for other MIL-SPEC fiber optic cabling components for aircraft applications.
3/ Temperature ranges in row 3 conform to those specified for other MIL-SPEC fiber optic cabling components for standard applications (such as the telecommunication industry).

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:01Z
Check the source to verify that this is the current version before use.

Fluid immersion aging: Not applicable.

Mechanical strippability: Applicable with the following diameter and residue requirements and test methods:

Diameter requirement. Requirement that the stripped optical fiber complies with diameter B in figure 1 shall be verified by successful insertion and removal of each optical fiber stripped end into a ring gauge/die/ferrule with a hole diameter of 125 +1/-0 micron. It is in the interest of the implementer to choose a gauge closer to 126 micron versus 125 microns.

Residual requirement. Requirement that no residual coating material remains on fiber shall be verified by the performance of a fiber pullout test. The end of each stripped length of optical fiber shall be terminated onto the end of a MIL-PRF-29504 terminus (or other suitable fiber optic connector if approved by the Qualifying Activity prior to test sample fabrication). Fabrication shall be performed as specified in NAVSEA Drawing 8283255. A copy of this document can be obtained at web site: https://fiberoptics.nswc.navy.mil/ in the NAVSEA Drawing section under Component Information. The fiber pull out force shall be tested by applying a 14.0 N (3.1 pounds) axial tensile load between the optical fiber and the terminus for a minimum duration of one minute. At the completion of the test, the optical fiber shall be visually examined and length measured to verify that no fiber pull out occurred.

Splicing compatibility. Nine 10 meter lengths of optical fiber conforming to the requirements of this specification sheet shall be fusion spliced, mechanically spliced and connectorized (using MIL-PRF-29504/4 and MIL-PRF-29504/5 termini) to optical fiber conforming to MIL-PRF-49291/6. Three sample lengths are to be used for each type splice or connector. An insertion loss measurement shall be performed in accordance with method B of TIA/EIA-455-34. The insertion loss shall not exceed 0.2 dB per splice and 0.5 dB per connector mated pair when performed at a wavelength of 1,300 nm.

Thermal shock.

Applicable as specified for M49291/10-01A and M49291/10-02A.

Applicable for M49291/10-01 and M49291/10-02, except that the temperatures of -55°C +0/-5°C and 165°C +5/-0°C shall be used for the low and high soak temperatures, respectively. Test shall be performed in accordance with TIA/EIA-455-71, schedule C-0 (5 cycles). The change in optical transmittance shall be measured during (towards the end of each soak temperature) and after the test.

Temperature cycling:

Applicable as specified for M49291/10-01A and M49291/10-02A.

Applicable for M49291/10-01 and M49291/10-02 except for the optical fiber with a -55°C to 165°C temperature range, perform the following in lieu of the specified temperature cycling test. Optical fiber shall be tested in accordance with EIA/TIA-455-3 using the number of cycles, test condition schedule and soak times in accordance with the table III. The change in optical transmittance shall be measured during and after the test. At a minimum for the “during test” measurements, an optical transmittance measurement shall be performed towards the end of each soak period (maintain step in table III) after every cycle. A post test visual examination of the test specimens shall reveal no surface impairment or any damage detrimental to the operation of the test specimens. The operating temperature range shall be as specified herein. Test fixtures, if used must be of minimum mass and approved by the qualifying activity. No other mass (item that causes significant thermal lag) shall be added inside the chamber. This test shall be performed both after temperature-humidity cycling and after temperature life (for M49291/10-01 and M49291/10-02).

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:01Z
Check the source to verify that this is the current version before use.

TABLE III Temperature cycling steps.

Step	Cycle	Action	Temperature °C (°F)	Duration 1/
1	1	Maintain	25 ±-2 (77 ± 4)	4 hours (minimum)
2		Ramp to	-55 +0/-3 (-67 +0/-5)	7.5 minutes
3		Maintain	-55 +0/-3 (-67 +0/-5)	15 minutes (minimum)
4		Ramp to	165 +3/-0 (329 +5/-0)	22 minutes
5		Maintain	165 +3/-0 (329 +5/-0)	15 minutes (minimum)
6	2	Ramp to	-55 +0/-3 (-67 +0/-5)	22 minutes
7		Maintain	-55 +0/-3 (-67 +0/-5)	15 minutes (minimum)
8		Ramp to	165 +3/-0 (329 +5/-0)	22 minutes
9		Maintain	165 +3/-0 (329 +5/-0)	15 minutes (minimum)
10	3-10	Repeat steps 6 thru 9, 8 additional times, for a total of 10 cycles.		
11	Post 10	Ramp to	25 ± 2 (77 ± 4)	6 minutes
12		Maintain	25 ± 2 (77 ± 4)	4 hours (minimum)

1/ Ramp rate is 10°C per minute or faster, soak time (maintain step) is 15 minutes.

Life aging (temperature life).

Applicable as specified for M49291/10-01A and M49291/10-02A.

Applicable for M49291/10-01 and M49291/10-02 except that the high exposure temperature shall be 165°C +5°C, -0°C. Test samples shall be tested in accordance with TIA/EIA-455-4 for the duration of 1,000 hours at the high exposure temperature. The change in optical transmittance shall be measured after the test. The optical fiber shall be visually examined after the test to the extent feasible. Optical fiber shall not be damaged, and there shall be no distortion, cracking of coating or other damage detrimental to the operation of the optical fiber. The requirement for the change in optical transmittance shall be met after the test. Performance of a cable/fiber retention test is not required as part of the final inspection for this test.

Nuclear radiation resistance: Nuclear radiation resistance requirements and test conditions shall be as shown below and in table IV and table V:

Light launch conditions: In accordance with EIA-455-50.

Wavelength: 1,300 nm ± 25 nm.

Source type: LED with FWHM spectral width ≤ 160 nm.

TABLE IV. Steady state gamma radiation test conditions.

Test temperature (^{o}C)	Dose rate	Total dose (rad Si))
-28 ± 2 25 ± 2 85 ± 2	50 +0, -20 rad (Si)/sec	Classified

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:01Z
Check the source to verify that this is the current version before use.

(Some nuclear radiation resistance characteristics of this optical fiber are classified and shall be obtained from the qualifying activity. Application to receive these requirements must be made through the Department of the Navy, Naval Surface Warfare Center, Dahlgren Division, ATTN: Code B35, 17320 Dahlgren Road, Dahlgren, VA 22448-5100. Information concerning security clearance classification and "need to know" must be detailed in the request.)

TABLE V. Steady state gamma radiation test requirements.

Maximum induced attenuation (dB/km)	Attenuation at specified recovery time (dB/km)	Specified recovery time (sec)
≤ 50 1/	≤ 15 at -28°C 1/ ≤ 5 at 25°C ≤ 5 at 85°C	1,000

1/ The radiation induced loss for a given threat. The total dose associate with the threat is classified and not necessarily equal to the test total dose.

QUALITY CONFORMANCE:

In group A testing length may be measured using mechanical methods.

In group C testing the mechanical strippability test may be omitted if the optical fiber coatings have not changed from when the mechanical strippability test was last performed. The manufacturer shall provide a certificate of compliance for mechanical strippability in the group C test report.

Qualification by similarity:

Change in glass.

Manufacturers who are qualified under this specification sheet and whose optical fiber with a change in the glass (composition or profile) passes the tests specified in table VI are qualified under this specification sheet for the optical fiber with changed glass.

TABLE VI. Change in glass.

Visual and mechanical
Fiber length
Attenuation uniformity
Attenuation rate
Numerical aperture
Core diameter
Transient attenuation
Macrobend attenuation
Bandwidth
Chromatic dispersion
Temperature cycling
Nuclear radiation resistance

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:01Z
Check the source to verify that this is the current version before use.

Change in coating.

Manufacturers who are qualified under this specification sheet and whose optical fiber with a change in the coating (composition or thickness) passes the tests specified in table VII, are qualified under this specification sheet for the optical fiber with changed coating.

TABLE VII. Change in coating.

Visual and mechanical
Fiber length
Attenuation rate
Transient attenuation
Macrobend attenuation
Coating diameter
Coating noncircularity
Mechanical strippability
Dynamic tensile strength
Thermal shock
Storage temperature
Temperature humidity cycling
Temperature cycling
Life aging
Fungus resistance

Referenced documents. In addition to MIL-PRF-49291, this specification sheet references the following documents:

MIL-PRF-29504/4	EIA/TIA-455-3	TIA/EIA-455-62
MIL-PRF-29504/5	EIA-455-50	TIA/EIA-455-71
MIL-PRF-49291/6	TIA/EIA-455-4	TIA-455-78
NAVSEA Dwg 8283255	TIA/EIA-455-34	

Custodians:
Army - CR
Navy - AS
Air Force – 85
NASA - NA

Preparing activity:
DLA - CC

(Project 6010-2008-010)

Review activities:
Navy - SH
Air Force – 02, 13, 19, 33, 93, 99
DIA - DI
DLA – CC

NOTE: The activities listed above were interested in this document on the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at http://assist.daps.dla.mil

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:01Z
Check the source to verify that this is the current version before use.