MIL-T-12919F
31 March 1986
SUPERSEDING
MIL-T-12919E
31 May 1972

MILITARY SPECIFICATION

TENT LINER, GENERAL PURPOSE, MEDIUM

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This document covers a tent liner for use with medium general purpose tents. Permanently attached screen side walls are provided with the liner (see 6.1). A cover is provided with each tent liner for protection during transport.

2. APPLICABLE DOCUMENTS

* 2.1 Government documents. Unless otherwise specified, the following documents of the issue in effect on date of invitation for bids or request for proposal form a part of this document to the extent specified herein.

SPECIFICATIONS

FEDERAL

L-S-125	- Screening, Insect, Nonmetallic
T-T-871	- Twine, Cotton, Wrapping
T-T-911	- Twine, Fibrous, Jute
V-T-285	- Thread, Polyester

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to U.S. Army Natick Research, Development, and Engineering Center, Natick, MA 01760-5014, by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 8340

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 202610-17T23:40Z
Check the source to verify that this is the current version before use.

CCC-C-429	- Cloth, Osnaburg, Cotton
CCC-C-467	- Cloth, Burlap, Jute (or Kenaf)
DDD-L-20	- Label: For Clothing, Equipage, and Tentage, (General Use)
PPP-B-601	- Boxes, Wood, Cleated-Plywood
PPP-B-636	- Boxes, Shipping, Fiberboard

MILITARY

MIL-W-530	- Webbing, Textile, Cotton, General Purpose, Natural or in Colors
MIL-L-1709	- Lines, Tent
MIL-C-2399	- Cement, Liquid, Tent Patching
MIL-R-3390	- Rings, Dee
MIL-C-10859	- Cloth, Oxford, Cotton, (Permeable)
MIL-G-16491	- Grommet, Metallic
MIL-L-35078	- Load, Unit: Preparation of Semiperishable Subsistence Items; General Specification For
MIL-T-40625	- Tubing, Bias Sewn (Burlap or Osnaburg), Cloth
MIL-T-43566	- Tape, Textile, Cotton, General Purpose, Natural or in Colors
MIL-C-43627	- Cloth, Duck, Cotton, Plied Yarns, Fire, Water, Weather and Mildew Resistant Treated, Lightdry Finish
MIL-W-43638	- Webbing, Textile, Woven, for Tent Framing
MIL-W-44049	- Webbing, Textile and Type, Textile, Polypropylene

STANDARDS

FEDERAL

FED-STD-751	- Stitches, Seams, and Stitchings

MILITARY

MIL-STD-105	- Sampling Procedures and Tables for Inspection by Attributes
MIL-STD-129	- Marking for Shipment and Storage
MIL-STD-147	- Palletized Unit Loads
MIL-STD-731	- Quality of Wood Members for Containers and Pallets

DRAWINGS

U.S. ARMY NATICK RESEARCH, DEVELOPMENT, AND ENGINEERING CENTER

5-4-370	- Tent Liner, General Purpose, Medium; Illustration
5-4-371	- Inside View at Corner and Sections

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T23:40Z
Check the source to verify that this is the current version before use.

5-4-372	- Body Assembly
5-4-373	- Liner End Details
5-4-374	- Side Wall Screen Assembly
5-4-375	- Details
5-4-376	- Cover
5-4-418	- Erection Instructions
5-4-419	- Care and Maintenance Instructions
5-4-495	- Packaging Procedure

(Copies of documents required by contractors in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting activity.)

OTHER GOVERNMENT DOCUMENTS

Department of the Army Field Manual FM 10-16 -
General Repair for Tents, Canvas, and Webbing

(Application for copies should be addressed to the Superintendent of Documents, U.S. Government Printing Office, Washington, D.C. 20402.)

* 2.2 Other publications. Unless otherwise specified, the following document of the issue in effect on the date of invitation for bids or request for proposal forms a part of this document to the extent specified herein.

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

D 3951 - Standard Practice for Commercial Packaging

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

(Technical society and technical association documents are generally available for reference from libraries. They are also distributed among technical groups and using Federal agencies.)

2.3 Order of precedence. In the event of conflict between the text of this document and the references cited herein, the text of this document shall take precedence.

3. REQUIREMENTS

3.1 First article. When specified in the contract or purchase order, a sample shall be subjected to first article inspection (see 4.3, 6.2, and 6.3).

Source: https://assist.dla.mil -- Downloaded: 2026l0-17T23:40Z
Check the source to verify that this is the currentversion before use.

3.2 Materials and components.

3.2.1 Cloth, oxford, cotton. The cloth for the liner shall conform to type I, class 2 of MIL-C-10859.

3.2.2 Cloth, duck, cotton. The cloth for the cover shall conform to MIL-C-43627 and shall be dyed Olive Drab 7.

* 3.2.3 Tape, textile, cotton. The tape for the binding and the tie tapes shall conform to type I, class 1b, 3/4 inch width of MIL-T-43566. Alternatively, the tape shall be polypropylene conforming to type I, class 1 of MIL-W-44049.

* 3.2.4 Webbing, textile, cotton. The eave reinforcement webbing and ridge grommet reinforcement webbing shall conform to type II, class 1b, 1 1/2 inch width of MIL-W-530. Alternatively, the webbing shall be polypropylene conforming to type II, class 1 of MIL-W-44049.

3.2.5 Webbing, textile, low elongation. The roof and side wall screen reinforcement webbing shall conform to type I, 1-inch width of MIL-W-43638.

3.2.6 Thread, polyester. The thread for the liner shall be type I or II, class 1 and the thread for the cover shall be type I, class 1, subclass B conforming to V-T-285 as listed in table I.

TABLE I. Thread types

Location	Size of thread
For all stitching on liner except stitching indicated by "Z" on drawings	Size E for needle and bobbin
For stitching on liner indicated by "Z" on drawings	Size E for needle Size B for looper
For all stitching on cover except stitching indicated by "Z" on drawings	Size F for needle and bobbin
For stitching on cover indicated by "Z" on drawings	Size F for needle Size E for looper

Source: https://assist.dla.mil -- Downloaded: 202610-17T23:40Z
Check the source to verify that this is the currentversion before use.

3.2.6.1 Color. The thread for the liner shall be natural and the thread for the cover shall be dyed Olive Drab S-1 (C.A. 66022). The dyed thread shall show fastness to weathering equal to or better than the standard shade sample (see 6.4). If no standard sample is available, the thread shall show good fastness to weathering.

3.2.7 Screening, nonmetallic. The screening shall conform to type III, class 1 or 2, size 18 x 18 of L-S-125, and the color shall be Green.

3.2.8 Lines, tent. The tent lines shall conform to MIL-L-1709 in the types specified in table II.

TABLE II. Types of tent lines

Type	Use
I	Footstop
L (except that the finished length of lines shall be 34 inches)	Eave, ridge, and lantern suspension lines
XXI	Cover tie line

3.2.9 Grommet, metallic. The metallic grommets shall conform to type III, class 3, size No. 4 of MIL-G-16491.

3.2.10 Ring, dee. The dee rings shall conform to class 1 or 2, configuration K, size 1 x 3/4, class 1 or 2 of MIL-R-3390.

3.3 Construction. The construction shall conform to the Drawings 5-4-370 through 5-4-376 and as specified herein.

3.3.1 Stitches, seams, and stitchings.

3.3.1.1 Types of stitching. Stitching, except bartacking, shall conform to FED-STD-751 as listed in table III.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T23:40Z
Check the source to verify that this is the current version before use.

TABLE III. Stitching types

Location	Type
For all stitching, except overedge stitching and stitching indicated by "Z" on drawings	Type 301 - 6 to 8 stitches per inch on liner; 5 to 7 stitches per inch on cover
For overedge stitching	Type 304 - 14 to 16 stitches per inch; type 503, 504 or 505 - 10 to 12 stitches per inch
For stitching indicated by "Z" on drawings	Type 401 - 6 to 8 stitches per inch on liner; 5 to 7 stitches per inch on cover. The chain portion of the stitching shall not appear on the outside of the liner or cover
For bartacking	Bartacks shall be 1/2 inch long with 1/8-inch bight and shall contain 28 stitches. Bartacking shall be free of thread breaks and shall contain no loose stitching

3.3.1.2 Thread breaks. Thread breaks in stitching shall be overstitched, on each side of break, not less than 1 inch at each break on stitch type 301; not less than 3/4 inch at each break on stitch type 304, 503, 504, or 505; and not less than 1 1/2 inches at each break on stitch type 401. Thread breaks on type 401 stitching may be overstitched with type 301 stitching. Bartacking shall be free of thread breaks.

3.3.1.3 Stitching ends, type 301. The ends of type 301 stitching shall be overstitched not less than 1 inch, except where ends are turned under in a hem or held down by other stitching. Where stitching is performed automatically on stitch patterns such as box, box with cross-stitch, "W" stitching or straight line tacking, 3 or more tying, overlapping, or back stitches shall be used to secure the ends.

Source: https://assist.dla.mil -- Downloaded: 202610-17T23:40Z
Check the source to verify that this is the currentversion before use.

3.3.1.4 Skipped stitches. Two or more consecutively skipped stitches occurring in type 301 stitching shall be overstitched not less than 1 inch on each side of skips. Any skipped stitch in type 401 stitching shall be overstitched not less than 1 1/2 inches on each side of skip. Skipped stitches in 401 stitching may be overstitched with type 301 stitching.

3.3.1.5 Lubrication. The addition of any lubricant to the polyester thread prior to or during the sewing operation is prohibited.

* 3.3.1.6 Stitch margins. Unless otherwise specified, all stitch margins shall be 1/8 ± 1/16 inch.

3.3.2 Setting of grommets. Holes punched to receive the grommets shall be smaller than the outside diameter of the grommet barrel so that the barrel must be forced through the hole. The grommets shall be securely clinched without cutting the materials.

* 3.3.3 Repairs. Any necessary repairs shall be effected in accordance with Department of the Army Field Manual FM 10-16, except that patches other than as specified herein will not be acceptable. Cemented patches on holes, cuts, or tears not more than 1 inch in diameter or length, using cement specified in MIL-C-2399, shall be permitted. The patch shall be large enough to overlap the damaged area with a margin of at least 3/4 inch on all sides. Cemented patches shall not be applied over seams or hardware areas. A maximum of three cemented patches per tent liner shall be allowed without prior authorization. All other repairs shall require authorization by the contracting officer.

3.4 Marking. All marking and labels shall conform to DDD-L-20.

* 3.4.1 Identification label. Identification labels shall conform to type VI, class 6 and shall be 3 1/2 inches by 5 1/2 inches minimum with a blank space of at least 1 1/4 inches provided on the bottom of the label for the Department of Defense inspector's stamp. Identification labels shall be stitched to the tent liner and cover in the locations shown on Drawings 5-4-418 and 5-4-419.

* 3.4.2 Instruction labels. Labels for instruction in erection and care and maintenance shall conform to type VI, class 7 and shall be stitched to the tent liner and cover in the locations shown on Drawings 5-4-418 and 5-4-419. The labels shall be proportionate copies of the drawings, as reproduced from the glossy prints of the drawings furnished by the contracting activity. The size of the labels shall be, borderline to borderline, 16 inches ± 1/4 inch in the longer dimension with a minimum 1/2-inch margin outside of the borderline on all sides.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T23:40Z
Check the source to verify that this is the current version before use.

3.4.3 Special markings. The letters "US" on the tent liner and cover and the special markings on the cover shall conform to type IV, class 9, in the size characters and in the locations shown on the drawings. Class 9 markings shall be clearly legible after subjection to accelerated weathering.

* 3.5 Workmanship. Cloth components shall be clean and free of holes, cuts, tears, or cloth defects such as multiple floats or broken or missing yarns. Webbing and tape shall not have frayed or scalloped edges, and rope components shall be free of cuts or breaks. Thread tension shall be maintained so that there will be no loose stitching, and seam allowances shall be maintained so that no run-offs, twists, pleats, or open seams result. Care shall be taken in sewing to see that there shall be no needle chews. All thread ends shall be trimmed to 1/2 inch or less. Metal components shall be free of burrs, sharp edges, or corroded areas and shall not be broken or malformed. Reinforcement bands may be spliced as shown on applicable drawings.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the document where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

* 4.1.1 Responsibility for compliance. All items must meet all requirements of sections 3 and 5. The inspection set forth in this document shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in the document shall not relieve the contractor of the responsibility of assuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling in quality conformance does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to acceptance of defective material.

4.2 Classification of inspection. The inspection requirements specified herein are classified as follows:

a. First article inspection (see 4.3).
b. Quality conformance inspection (see 4.4).

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T23:40Z
Check the source to verify that this is the current version before use.

4.3 First article inspection. When a first article is required (see 6.2), it shall be examined for defects listed in tables IV and V. The presence of any visual defect or any dimension not within the specified requirements shall be cause for rejection of the first article.

4.4 Quality conformance inspection. Unless otherwise specified, sampling for inspection shall be performed in accordance with MIL-STD-105.

4.4.1 Component and material inspection. In accordance with 4.1, components and materials shall be inspected and tested in accordance with all the requirements of referenced documents unless otherwise excluded, amended, modified, or qualified in this document or applicable purchase document.

4.4.2 In-process examination. Examination shall be made to determine that the following are as specified:

a. There shall be no lubrication of polyester thread prior to or during sewing operations for compliance with 3.3.1.5.

b. Holes punched to receive grommets are in compliance with 3.3.2.

Whenever nonconformance is noted, correction shall be made to the affected items and to the process.

4.4.3 End item inspection. The tent liners shall be examined for visual and dimensional defects. The lot size shall be all completely fabricated tent liners with covers or covers only, as applicable, offered for inspection at one time. The sample unit shall be one completely fabricated tent liner with cover or cover only.

* 4.4.3.1 End item visual examination. The completely fabricated tent liner with cover shall be examined for the applicable visual defects in table IV. The inspection level shall be I, and the acceptable quality level (AQL), expressed in terms of defects per hundred units, shall be 25.0 for major defects and 150.0 for total combined major and minor defects. The completely fabricated cover only (when purchased separately) shall be examined for applicable defects in table IV. The inspection level shall be S-3, and the AQL shall be 10.0 for major defects and 40.0 for total combined major and minor defects.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T23:40Z
Check the source to verify that this is the current version before use.

TABLE IV. Classification of visual defects

Examine	Defect	Classification	
		Major	Minor
Fabric	Cut, tear, or hole:		
	-greater than 1/4 inch in length or diameter	X	
	-greater than 1/8 inch but not greater than 1/4 inch in length or diameter		X
	-more than 5 holes 1/8 inch or less in length or diameter		X
	Broken or missing yarns, multiple floats clearly visible at normal inspection distance (approximately 3 feet)		X
	NOTE: Any open place larger than 1/8 inch shall be classified under cut, tear, or hole.		
Screening	Cut or tear more than 1/4 inch in length or diameter	X	
Tape and webbing	Edge frayed or scalloped		X
Rope components	Any cut; any break		X
	Eye splice omitted or not as specified		X
	Line not spliced through eave chape, pole opening loops, or ridge suspension lines		X
	Free end not finished as specified		X
Hardware	Broken	X	
	Malformed:		
	-fails to perform intended function	X	
	-but will perform intended function		X
	Corroded area		X

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T23:40Z
Check the source to verify that this is the current version before use.

TABLE IV. Classification of visual defects - Continued

Examine	Defect	Classification	
		Major	Minor
Hardware (continued)	Burr or sharp edge that may cause injury in handling or damage to fabric	X	
Grommets	Improperly set; two or more teeth exposed (except where grommet is set as specified but is in an area of uneven thickness that prevents uniform clinching)		X
	Clinched loosely, allowing grommet to rotate in hole		X
	Clinched excessively tight, cutting fabric:		
	-on liner	X	
	-on cover		X
	Insecurely clinched (i.e., grommet or washer becomes disengaged):		
	-on liner	X	
	-on cover		X
	End grommet on screen wall set with rim extending beyond folded edge of sod cloth		X
	Ridge grommet set with rim extending beyond edges of grommet reinforcement webbing		X
Seams and stitching	Open seam on stitch type 301:		
	-for more than 1 inch	X	
	-for more than 1/4 inch but not more than 1 inch		X
	Open seam on stitch type 401:		
	-both rows of stitching open (not necessarily at the same location)	X	
	-one row of stitching open		X

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T23:40Z
Check the source to verify that this is the current version before use.

TABLE IV. Classification of visual defects - Continued

Examine	Defect	Classification	
		Major	Minor
Seams and stitching (continued)	NOTE: A seam shall be classified as open when one or more stitches joining a seam are broken, or when one or more skipped or runoff stitches occur.		
	Raw edges caught in stitching: -more than 1 inch		X
	Pleated seams		X
	Thread breaks, skipped stitches: -overstitched less than 1 inch on stitch type 301		X
	-overstitched less than 3/4 inch on stitch type 304, 503, 504, or 505		X
	-overstitched less than 1 1/2 inches on stitch type 401		X
	NOTE: Thread breaks or skipped stitches not overstitched shall be classified as open seams.		
	Needle chews resulting in cut, tear, or hole (See Fabric; cut, tear, or hole)		
	One or more required rows of stitching omitted (except on boxstitching)	X	
Boxstitching	Incomplete: -two or more rows of stitching omitted	X	
	-one row of stitching omitted		X
Bartacking	Less than specified length		X
Seam type	Wrong seam type	X	

Source: https://assist.dla.mil -- Downloaded: 202610-17T23:40Z
Check the source to verify that this is the current version before use.

TABLE IV. Classification of visual defects - Continued

Examine	Defect	Classification	
		Major	Minor
Seams and stitching (continued)			
Stitch tension	Loose, resulting in exposed bobbin or top thread for more than 6 inches		X
	Tight, as evidenced by puckering of seam for more than 6 inches		X
Stitches per inch	Less than minimum specified		X
	NOTE: Variation in the number of stitches per inch caused by the operator speeding up the machine in order to sew over heavy places or heavy seams or in turning corners shall be no defect if only one stitch is varied and a minor defect if two or more stitches are varied.		
Stitching gage	Not as specified		X
Stitching margin	Larger than specified for more than 2 inches in length		X
	Less than specified for more than 2 inches in length		X
Stitching ends	Overstitched less than 1 inch on stitch type 301 (except where ends are held down by other stitching, where ends are turned under in a hem, or where stitching is performed automatically)		X
	Secured with less than 3 tying, overlapping, or back stitches when automatic stitching is performed		X

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T23:40Z
Check the source to verify that this is the current version before use.

TABLE IV. Classification of visual defects - Continued

Examine	Defect	Classification	
		Major	Minor
Seams and stitching (continued)			
Stitching indicated by "Z" on drawings	Chain portion of stitching shows on outside of liner or cover		X
Mends, darns, or patches	Repairs not in accordance with Department of the Army Field Manual FM 10-16 and not authorized by the contracting officer (see 3.3.3)	X	
Components and assembly	Any component not fabricated of applicable referenced material	X	
	Any component or operation omitted unless otherwise referenced herein	X	
Construction details			
Hems	Constructed with partial turnunder when double turnunder is required		X
	Twisted or pleated		X
Reinforcements	Improperly applied, causing excessive fullness on reinforcement or reinforced parts		X
	Incorrect splicing of reinforcement bands		X
Binding	Improperly or loosely applied		X
	Ends not finished as specified		X
Panel splicing	More than 1 splice per panel		X
	Adjacent panels spliced at same location		X

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T23:40Z
Check the source to verify that this is the current version before use.

TABLE IV. Classification of visual defects - Continued

Examine	Defect	Classification	
		Major	Minor
Construction details (continued)			
Screen wall	Sod cloth set on outside	X	
	Ends of sod cloth caught in stitching attaching screen sidewall to end wall		X
	Top edge of screen or top end of screen reinforcement webbing not caught in both rows of stitching attaching eave reinforcement webbing to body eave		X
	Reinforcement webbing set on inside of wall instead of outside		X
Corner lugs	Top or bottom of lug stitched together failing to provide clearance for side walls		X
	Any part of lugs single ply		X
Roof and ridge, inside	End of ridge reinforcement webbing not looped at pole opening		X
	Folded edge of end roof reinforcement webbings not looped at ridge end pole opening		X
	End of side roof reinforcement webbing not caught in binding around pole opening or in eave reinforcement		X
Tie tapes	Two or more missing per body or end section	X	
	One missing per body or end section		X
General	Any other construction detail not performed as specified		X

Source: https://assist.dla.mil -- Downloaded: 202610-17T23:40Z
Check the source to verify that this is the current version before use.

TABLE IV. Classification of visual defects - Continued

Examine	Defect	Classification	
		Major	Minor
Labels	Omitted, incorrect, illegible, or misplaced		X
Marking; "US" and nomenclature	Omitted, incorrect, illegible, or misplaced		X
Cleanness	Grease or oil stains		X
	Thread ends not trimmed throughout to 1/2 inch or less.		X

* 4.4.3.2 End item dimensional examination. The completely fabricated tent liner with cover shall be examined for the applicable dimensional defects in table V. The inspection level shall be S-4, and the AQL, expressed in terms of defects per hundred units, shall be 6.5 for major defects and 40.0 for total combined major and minor defects. The completely fabricated cover only (when purchased separately) shall be examined for the applicable dimensional defects in table V. The inspection level shall be S-2, and the AQL shall be 2.5 for major defects and 25.0 for total combined major and minor defects.

Source: https://assist.dla.mil -- Downloaded: 202610-17T23:40Z
Check the source to verify that this is the current version before use.

TABLE V. Classification of dimensional defects

Examine	Defect	Classification	
		Major	Minor
Overall dimensions of liner	Smaller than specified dimensions less applicable minus tolerance indicated on drawings	X	
	Larger than specified dimensions and applicable tolerance indicated on drawings		X
Overall dimensions of cover; location and component dimensions (unless otherwise specified)	Smaller than specified dimensions less applicable minus tolerance indicated on drawing, but not smaller than specified dimensions less twice the applicable minus tolerance	X	
	Larger than specified dimensions and applicable plus tolerance indicated on drawing (except cover)		X
Liner openings	Larger or smaller than specified dimensions by more than 1/2 inch (unless otherwise specified)		X
Tie tapes	Finished length less than specified by more than 1 inch		X
Webbing	Turnunder at ends or ridge webbing forming loops at pole opening less than specified by more than 1/2 inch		X
Rope components	Eye less than specified by more than 1/2 inch		X
	Finished length less than specified by more than 2 inches		X

Source: https://assist.dla.mil -- Downloaded: 202610-17T23:40Z
Check the source to verify that this is the current version before use.

TABLE V. Classification of dimensional defects - Continued

Examine	Defect	Classification	
		Major	Minor
Reinforcements	Finished dimensions less than specified by more than 1/2 inch		X
	Edges of webbing reinforcements of door, ventilator, or stovepipe openings misplaced by more than 1/8 inch		X
Sod cloth	Finished width less than specified by more than 1 inch		X
Screen wall	Center line of vertical webbing out of alignment with eave grommets by more than 1/2 inch		X
Stovepipe opening	Any stovepipe opening less than 15 1/2 by 15 1/2 inches or more than 17 by 17 inches		X
Hems	If required to finish less than 3/4 inch in width, less than specified		X
	If required to finish 3/4 inch or more in width, less than specified by more than 1/4 inch		X
Grommets	Grommets on bottom of screen walls at location of vertical reinforcement webbing set off center of reinforcement webbing by more than 1/2 inch		X
	Intermediate grommets on bottom of screen wall unequally spaced by more than 2 inches		X
	Any eave grommet set out of alignment with roof webbing reinforcement by more than 1/2 inch		X

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T23:40Z
Check the source to verify that this is the current version before use.

TABLE V. Classification of dimensional defects - Continued

Examine	Defect	Classification	
		Major	Minor
Grommets (continued)	Ridge grommet set less than 3/4 inch or more than 1 3/4 inches from ridge line		X
	Cover grommet set less than 1 inch from corners or off center of hem by more than 1/2 inch		X

4.4.4 Packaging inspection. An examination shall be made to determine that preservation, packing, and marking comply with section 5 requirements. Defects shall be scored in accordance with table VI. The lot shall be the number of completely packed tent liners with covers or covers only offered for inspection at one time. The sample unit shall be one completely packed tent liner with cover, or ten covers only, fully packaged. The inspection level shall be S-2, and the AQL, expressed in terms of defects per hundred units, shall be 2.5.

TABLE VI. Packaging inspection

Examine	Defect
Marking	Omitted; incorrect; illegible; of improper size, location, sequence, or method of application
Materials	Any component missing Any component damaged
Workmanship	Inadequate application of components, such as incomplete closure of cloth wrapping or loose stitching

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T23:40Z
Check the source to verify that this is the current version before use.

4.4.5 Palletization examination. The fully packaged and palletized end items shall be examined for the defects in table VII. The lot size shall be expressed in units of palletized unit loads. The sample unit shall be one palletized unit load fully packaged. The inspection level shall be S-1, and the AQL, expressed in terms of defects per hundred units, shall be 6.5.

Table VII. Palletization examination

Examine	Defect
Finished dimensions	Length, width, or height exceeds specified maximum requirement
Palletization	Pallet pattern not as specified Interlocking of loads not as specified Load not bonded with required straps as specified
Weight	Exceeds maximum load limits
Marking	Omitted; incorrect; illegible; of improper size, location, sequence, or method of application

5. PACKAGING

5.1 Preservation. Preservation shall be level A or Commercial, as specified (see 6.2).

5.1.1 Level A.

5.1.1.1 Tent liner with cover. Each tent liner shall be folded and unit packed within the cover provided, as shown on Drawing 5-4-495.

5.1.1.2 Tent liner covers. Each tent liner cover shall be compactly folded so that the identification markings are clearly visible. The folded cover shall measure approximately 18 by 24 inches. All tie lines shall be placed within the folds. Five folded covers shall be stacked and cross-tied with cotton tape or twine.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T23:40Z
Check the source to verify that this is the current version before use.

* 5.1.2 Commercial. Tent liners in covers, or five folded, stacked, and tied covers only, shall be preserved in accordance with ASTM D 3951.

5.2 Packing. Packing shall be level A, B, or Commercial, as specified (see 6.2).

5.2.1 Level A packing.

5.2.1.1 Tent liners with covers. Tent liners in covers, preserved as specified in 5.1, shall be packed in a close-fitting cleated-plywood box conforming to overseas type, style A of PPP-B-601. Boxes and skids shall be fabricated in accordance with type of load and gross weight requirements in the box document. Each shipping container shall be closed and reinforced with steel strapping in accordance with the appendix of PPP-B-601.

5.2.1.2 Tent liner covers. Ten tent liner covers, preserved as specified in 5.1, shall be packed in a snug-fitting container conforming to style RSC-L, V2s of PPP-B-636. The inside of each container shall be fitted with a liner conforming to V3c of PPP-B-636. Each shipping container shall be closed, waterproofed, and reinforced with flat strapping or tape banding in accordance with the appendix of PPP-B-636. Shipping containers shall be arranged in unit loads in accordance with MIL-L-35078 for the type and class of load specified (see 6.2). Strapping shall be limited to nonmetallic strapping, except for type II, class F loads.

5.2.2 Level B packing. Each tent liner with cover, or ten tent liner covers only, preserved as specified in 5.1, shall be wrapped and sewn in cotton osnaburg cloth conforming to class 2 of CCC-C-429 or burlap cloth conforming to class 3 of CCC-C-467. The cloth wrapping shall be securely hand sewn with type I or II, 16-ply cotton twine conforming to T-T-871, or type I, size No. 2 jute twine conforming to T-T-911, with approximately one stitch to the inch and every third stitch overhand knotted. Alternatively, the bottom and side may be machine-sewn. A minimum of 5 inches of wrapping material shall be gathered together on each of the four corners and securely hand-sewn into ears for handles. In place of the sewn wrapping indicated above, bias-sewn tubing (or bag presewn one end) conforming to MIL-T-40625 may be used. One end of the tubing may be machine-sewn. The formation of handles shall be effected by hand sewing in conformance with the method as described above. Wherever machine sewing is used, the thread type, stitch type, and number of stitches per inch shall conform to the requirements specified in MIL-T-40625. However, the polyester sewing thread used in manufacturing the end items may be used for effecting the machine-sewn closure of the wrapping or tubing.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T23:40Z
Check the source to verify that this is the current version before use.

* 5.2.3 Commercial packing. Tent liners with covers, or ten tent liner covers only, preserved as specified in 5.1, shall be packed in accordance with ASTM D 3951.

* 5.3 Palletization. When specified (see 6.2), tent liner covers, packed as specified in 5.2, shall be palletized on a 4-way entry pallet in accordance with load type Ia of MIL-STD-147. Pallet type shall be type I (4-way entry), type IV or type V in accordance with MIL-STD-147. Pallets shall be fabricated from wood groups I, II, III, or IV of MIL-STD-731. Each prepared load shall be bonded with primary and secondary straps in accordance with bonding means K and L or film bonding means O or P. Pallet patterns shall be in accordance with appendix of MIL-STD-147. Interlocking of loads shall be effected by reversing the pattern of each course.

5.4 Marking. In addition to any special marking required by the contract or purchase order, shipments shall be marked in accordance with MIL-STD-129 or ASTM D 3951, as applicable.

5.4.1 Additional marking. The following shall be stenciled or imprinted on each shipping container in characters not less than 3/4 inch high:

"SEE ERECTION INSTRUCTIONS STITCHED TO INSIDE OF TENT COVER"

6. NOTES

6.1 Intended use. The tent liner is designed to be used with Tent, General Purpose, Medium in either cold, temperate, or tropical areas. In cold weather, the liner provides insulation. In hot weather, the tent and liner side walls can be rolled up to expose the attached screen side walls of the liner, thus providing increased ventilation of the tent.

* 6.2 Ordering data. Acquisition documents should specify the following:

a. Title, number, and date of this document.
b. When first article is required (see 3.1, 4.3, and 6.3).
c. Selection of applicable levels of preservation and packing (see 5.1 and 5.2).
d. Type and class of unit load required (see 5.2.1).
e. When palletization is required (see 5.3).

* 6.3 First article. When a first article is required, it shall be inspected and approved under appropriate provisions of FAR 52.209. The first article should be a preproduction sample consisting of one unit. The contracting officer should include specific instructions in all acquisition instruments regarding arrangements for inspection and approval of the first article.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T23:40Z
Check the source to verify that this is the current version before use.

6.4 Standard sample. For access to standard shade sample of thread, address the contracting activity issuing the invitation for bids.

* 6.5 International standardization agreements. Certain provisions of this document are the subject of international standardization agreement as cited in NATO, STANAG No. 2882, relative to camouflage requirements for tents, shelters, and subsidiary components. When amendment, revision, or cancellation of this document is proposed that will affect or violate the international agreement concerned, the preparing activity will take appropriate reconciliation action through international standardization channels including departmental standardization offices, if required.

6.6 Changes from previous issue. The margins of this document are marked with an asterisk to indicate where changes (additions, modifications, corrections, deletions) from the previous issue were made. This was done as a convenience only, and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous issue.

Custodians:

Army - GL
Navy - NU
Air Force - 99

Review activities:

Air Force - 82
DLA - CT

User activities:

Navy - MC, YD

Preparing activity:

Army - GL

Project No. 8340-0472

Source: https://assist.dla.mil -- Downloaded: 202640-17T23:40Z
Check the source to verify that this is the current version before use.

NSTRUCTIONS: In a continuing effort to make our standardization documents better, the DoD provides this form for use in ubmitting comments and suggestions for improvements. All users of military standardization documents are invited to provide uggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and nailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was oo rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the roblems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an cknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being onsidered.

VOTE: This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of pecification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization o waive any portion of the referenced document*(s)* or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

EPARTMENT OF THE ARMY
ay Natick Research and Development Center
Natick, Massachusetts 01760

NO POSTAGE NECESSARY IF MAILED IN THE UNITED STATES

FFICIAL BUSINESS
ENALTY FOR PRIVATE USE $300
STRNC-ES

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO. 12062 WASHINGTON D. C.
POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE ARMY

Commander
US Army Natick Research and Development Center
ATTN: STRNC-ES
Natick, MA 01760

Source: https://assist.dla.mil -- Downloaded: 202610-17T23:40Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE
MIL-T-12919F	TENT LINER, GENERAL PURPOSE, MEDIUM

3a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION *(Mark on* ☐ VENDOR ☐ USER ☐ MANUFACTURER ☐ OTHER *(Specify)*:
b. ADDRESS *(Street, City, State, ZIP Code)*	

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Inclu* *Code)* – Optional *ta*
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

DD FORM 82 MAR 1426 PREVIOUS EDITION IS OBSOLETE.

Source: https://assist.dla.mil - Downloaded: 2025-11-27T16:40Z
Check the source to verify that this is the current version before use.