MIL-G-1057H
14 April 1988
SUPERSEDING
MIL-G-1057G
27 December 1983

# MILITARY SPECIFICATION

## GLOVES, CLOTH, COTTON, SPECIAL, OG-109

This specification is approved for use by all Departments and Agencies of the Department of Defense.

### 1. SCOPE

* 1.1 Scope. This document covers a dyed cotton glove (intended for subsequent antivesicant treatment).

1.2 Classification. The gloves shall be of one type in the following sizes as specified (see 6.2).

Schedule of sizes

Small
Medium
Large

### 2. APPLICABLE DOCUMENTS

* 2.1 Government documents.

* 2.1.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this specification to the extent specified herein. Unless otherwise specified, the issues of these documents shall be those listed in the issue of the Department of Defense Index of Specifications and Standards (DODISS) and supplement thereto, cited in the solicitation.

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be used in improving this document should be addressed to: U.S. Army Natick Research, Development, and Engineering Center, Natick, MA 01760-5014 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 8415

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 202610-16T12:38Z
Check the source to verify that this is the currentversion before use.

SPECIFICATIONS

FEDERAL

| | | |
|---|---|---|
| A-A-203 | - | Paper, Kraft, Untreated |
| V-T-276 | - | Thread, Cotton |
| DDD-L-20 | - | Label: For Clothing, Equipage, and Tentage, (General Use) |
| PPP-B-636 | - | Boxes, Shipping, Fiberboard |

MILITARY

| | | |
|---|---|---|
| MIL-L-35078 | - | Loads, Unit: Preparation of Semiperishable Subsistence Items; Clothing, Personal Equipment and Equipage; General Specification For |

STANDARDS

FEDERAL

| | | |
|---|---|---|
| FED-STD-191 | - | Textile Test Methods |
| FED-STD-751 | - | Stitches, Seams, and Stitchings |

MILITARY

| | | |
|---|---|---|
| MIL-STD-105 | - | Sampling Procedures and Tables for Inspection by Attributes |
| MIL-STD-129 | - | Marking for Shipment and Storage |
| MIL-STD-147 | - | Palletized Unit Loads |
| MIL-STD-731 | - | Quality of Wood Members for Containers and Pallets |

* (Copies of specifications, standards, and handbooks required by contractors in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting activity.)

* 2.1.2 Other Government documents, drawings, and publications. The following other Government documents, drawings, and publications form a part of this specification to the extent specified herein. Unless otherwise specified, the issues shall be those in effect on the date of the solicitation.

AMERICAN ASSOCIATION OF TEXTILE CHEMISTS AND COLORISTS (AATCC)

Chromatic Transference Scale

(Application for copies should be addressed to the American Association of Textile Chemists and Colorists, P.O. Box 12215, Research Triangle Park, NC 27709-2215.)



Source: https://assist.dla.mil -- Downloaded: 202610-16T12:38Z
Check the source to verify that this is the current version before use.

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

D 3951 - Standard Practice for Commercial Packaging

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

* (Nongovernment standards and other publications are normally available from the organizations which prepare or which distribute the documents. These documents also may be available in or through libraries or other informational services.)

* 2.3 Order of precedence. In the event of a conflict between the text of this specification and the references cited herein, the text of this specification shall take precedence. Nothing in this specification, however, shall supersede applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 Samples.

3.1.1 Guide samples. Guide samples, when furnished, are solely for guidance and information to the contractor (see 6.3). Variation from this document may appear in the sample, in which case this document shall govern.

3.1.2 Standard sample. The finished dyed glove shall match the standard sample for shade and finish appearance and shall be equal to or better than the standard sample with respect to all characteristics for which the standard sample is referenced (see 6.3).

* 3.2 First article. When specified in the contract or purchase order, a sample shall be subjected to first article inspection (see 4.3, 6.2, and 6.5).

3.3 Material.

3.3.1 Cotton jersey knit fabric. The fabric for the hand portion and welt shall be dyed, cotton, plain (jersey) knit. The fabric shall be napped (fleeced) on the back and shall conform to the requirements listed in table I when tested as specified in 4.4.1.1.

TABLE I. Physical requirements for jersey knit fabric

| | |
|---|---|
| Ounces per yard (minimum) | 10.5 |
| Wales per inch (minimum) | 19 |
| Courses per inch (minimum) | 22 |
| Bursting strength, pounds (minimum) | 75 |



Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:38Z
Check the source to verify that this is the current version before use.

3.3.2 Cotton rib knit fabric. The fabric for the cuff shall be 1 by 1 rib knit, seamless, dyed, cotton tubing. The tubing shall conform to the requirements specified in table II when tested as specified in 4.4.1.1.

TABLE II. Physical requirements for rib knit fabric

| | |
|---|---|
| Yards per pound: | |
| Minimum | 8.0 |
| Maximum | 12.0 |
| Wales per inch (minimum) | 16 |
| Courses per inch (minimum) | 20 |
| Flat width, inches (minimum) | 3 |

3.3.3 Color. The color of the knitted fabrics shall be Olive Green 109 and shall match the standard sample. The use of sulfur dyes and dyes containing elementary sulfur or compounds capable of oxidation to sulfuric acid is prohibited. The dyed fabrics shall show no more labile sulfur than shown by the standard sample, when tested as specified in 4.4.1.1.

3.3.3.1 Matching. The color of the finished cloth shall match the standard sample when viewed under filtered tungsten lamps that approximate artificial daylight and that have a correlated color temperature of 7500 $\pm$ 200 K, with illumination of 100 $\pm$ 20 foot candles, and shall be a good match to the standard sample under incandescent lamplight at 2300 $\pm$ 200 K.

3.3.3.2 Colorfastness. The finished cloth shall show fastness to laundering, bleaching, and perspiration equal to or better than the standard sample or equal to or better than a rating of "good". The finished cloth shall show fastness to crocking equal to or better than the standard sample or shall have an AATCC Chromatic Transference Scale rating of 3.5. Testing shall be as specified in 4.4.1.1.

3.3.4 pH. The pH of the water extracted from the finished fabric shall be not less than 5.0 and not more than 7.0 when tested as specified in 4.4.1.1.

3.3.5 Non-fibrous material. The starch and protein content including chloroform-soluble and water-soluble material in the finished fabric shall not exceed 3.0 percent when tested as specified in 4.4.1.1.

3.3.6 Thread. The dyed cotton thread for seaming and stitching shall conform to type IA3, ticket No. 30, 3-ply and ticket No. 50, 3-ply or V-T-276. The color of the thread shall be Olive Drab S-1, C.A. 66022. The dyed thread shall show colorfastness to laundering, chlorine bleaching, and perspiration, equal to or better than the standard sample. When no standard sample is available, the dyed thread shall show colorfastness to laundering, chlorine bleaching, and perspiration.



Source: https://assist.dla.mil -- Downloaded: 202610-16T12:38Z
Check the source to verify that this is the current version before use.

3.4 Labeling. Each glove shall be marked with a combination identification and size label conforming to type IV, class 4 of DDD-L-20, except that the marking medium shall be an approved black ink (see 6.4). The legend and size of characters shall be as follows:

| Legend | Minimum size of characters |
|---|---|
| Glove, Cloth, Cotton Special Olive Green 109 | 3/8 inch |
| Contract No. | 3/8 inch |
| Stock No. | 3/8 inch |
| Size - SMALL, MEDIUM or LARGE 1/ | 3/4 inch |

1/ As an alternate, size may be marked S, M, or L.

The marking shall also include the information required by the applicable products labeling act. The label shall show good fastness to laundering as specified in DDD-L-20.

3.5 Design. The design shall be a full inseamed, slip-on, seamless palm, Gunn style glove. The seam at the base of the fingers shall be provided with a reinforcement welt turned up to cover the stitching. A long knitted wristlet is inseam sewn to top of hand portion of glove. The napped surface of the cotton jersey knit fabric shall be on the inside of the glove.

3.6 Figure. Figure 1 is furnished for information purposes only. If there are any inconsistencies between the written document and the figure, the written document shall govern.

3.7 Patterns. Standard patterns will be furnished by the Government. The standard patterns shall not be altered in any way and shall be used only as a guide for making the dies. The dies for cutting the gloves shall conform to the standard patterns, with the exception that either outward notches or chisel marks may be used as the guide markers during the closing operations.

3.8 Construction.

3.8.1 Manufacturing operations requirements. The gloves shall be manufactured by and with the use of all operations specified in table III. The contractor is not required to follow the exact sequence of operations.

3.8.2 Stitches, seams, and stitchings. The stitch, seam, and stitching types specified in table III shall conform to FED-STD-751. When two or more methods, seam, or stitch types are given for the same operation, any one of them may be used. The minimum and maximum number of stitches per inch shall be as specified in table III.



Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:38Z
Check the source to verify that this is the current version before use.

3.8.2.1 Type 301 stitching. Unless otherwise indicated, ends of seams and stitching produced with 301 stitch type. when not caught in other seams or stitching, shall be backstitched not less than 1/2 inch. Thread tension shall be maintained so that there will be no loose stitching resulting in loose bobbin or top thread and no excessively tight stitching resulting in puckering of the materials sewn.

3.8.2.1.1 Repairs of type 301 stitching. Repairs of type 301 stitching shall be as follows:

a. When thread breaks or bobbin run-outs occur during sewing, the stitching shall be repaired by restarting the stitching a minimum of 1/2 inch back of the end of the stitching.

b. Thread breaks or two or more consecutive skipped or run-off stitches noted during inspection of the item (in-process or end item) shall be repaired by overstitching. The stitching shall start a minimum of 1/2 inch back of the defective area, continue over the defective area, and continue a minimum of 1/2 inch beyond the defective area onto the existing stitching. Loose or tight stitching shall be repaired by removing the defective stitching without damaging the material and restitching in the required manner. 1/

1/ When making the above repairs, the ends of the stitching are not required to be backstitched.

3.8.2.2 Type 401 stitching. Thread tension shall be maintained so that there will be no loose stitching and the looper thread shall be on the inside of the gloves. Both ends of all seams or stitching produced with 401 stitch type, when not caught in other seams or stitching shall have a 1/2 to 3/4 inch chain extending beyond each end. All repairs shall be in accordance with 3.8.2.1.1a. and 3.8.2.1.1b.



Source: https://assist.dla.mil -- Downloaded: 202610-16T12:38Z
Check the source to verify that this is the currentversion before use.

| NO. | TABLE III. MANUFACTURING OPERATIONS REQUIREMENTS | STITCH TYPE | SEAM AND STITCHING TYPE | STITCHES PER INCH | THREAD | | |
|---|---|---|---|---|---|---|---|
| | | | | | NEEDLE | BOBBIN/ LOOPER | COVER |
| 1. | Cutting.<br><br>The gloves shall be cut in accordance with the patterns (see 3.7).<br><br>a. Hand portion. The hand portion of the gloves shall be cut from knitted napped fabric specified in 3.3.1 and shall be cut in accordance with dies made from the standard patterns. All component parts shall be cut from the same piece of material with the length of the components running in the wale direction indicated on the standard patterns.<br><br>The components for the hand portions of each glove shall consist of the following four sections:<br><br>1. Back of hand, fingers, and front of thumb.<br>2. Back of thumb, front of hand, and index and small finger.<br>3. Front of middle and ring fingers.<br>4. Fourchette welt.<br><br>b. Cuff. The cuff shall be cut from rib knit tubing specified in 3.3.2 in sufficient length to permit the wristlet to be formed with a double thickness by folding over to meet the required finished length. (No patterns provided.) | | | | | | |
| 2. | Replacement of defective components.<br><br>During the spreading, cutting, and manufacturing process, components having material defects or damages that are classified as defects in 4.4.2 and 4.4.3 shall be removed from production and replaced with non-defective and properly matched components. | | | | | | |





Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:38Z
Check the source to verify that this is the current version before use.

TABLE III. (cont'd)

| NO. | MANUFACTURING OPERATIONS REQUIREMENTS | STITCH TYPE | SEAM AND STITCHING TYPE | STITCHES PER INCH | THREAD | | |
|---|---|---|---|---|---|---|---|
| | | | | | NEEDLE | BOBBIN/ LOOPER | COVER |
| 3. | Join fourchettes to palm. | | | | | | |
| | Join fourchettes to palm with inserted 1/2 inch welt and inseam with one row of stitching 1/8 to 3/16 inch from cut edge. The welt strap shall be so placed on the palm, unnapped to unnapped surface, to permit the welt strap to be turned back to cover and protect the base of the fingers. Ends of welt shall be turned down, nap to unnapped fourchette and caught in the closing seams. | 301 | SSa-1 | 10-14 | 30-3 | 30-3 | |
| | | or 401 | SSa-1 | 10-14 | 30-3 | 30-3 | |
| 4. | Closing. | | | | | | |
| | Join front and back together by inseaming with one row of stitches 1/8 to 3/16 inch from cut edge. | 301 | SSa-1 | 10-14 | 30-3 | 30-3 | |
| | | or 401 | SSa-1 | 10-14 | 30-3 | 50-3 | |
| 5. | Attach cuff. | | | | | | |
| | Join cut ends of double thickness wrist tubing to hand inseaming with one row of stitching 3/16 to 1/4 inch from cut edge completely around and continuing the stitching by at least 1 inch beyond the beginning and leaving 1/2 to 3/4 inch chain at point of run-off. Ends of closing stitches of hand wrist shall be caught in cuff stitching. | 401 | SSa-1 | 10-14 | 30-3 | 30-3 | |
| 6. | Labeling. | | | | | | |
| | The combination identification and size label shall be applied outside on the back of the base of the glove 1/4 to 1 inch from the wristlet seam. As an alternate position, the label may be applied on back of knitted cuff. | | | | | | |

NATICK Form 903
1 Dec 76 EDITION OF 1 OCT 76 WILL BE USED UNTIL EXHAUSTED.



Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:38Z
Check the source to verify that this is the current version before use.

| NO. | TABLE III. (cont'd)<br>MANUFACTURING OPERATIONS REQUIREMENTS | STITCH TYPE | SEAM AND STITCHING TYPE | STITCHES PER INCH | THREAD | | |
|---|---|---|---|---|---|---|---|
| | | | | | NEEDLE | BOBBIN/ LOOPER | COVER |
| 7. | Forming.<br><br>The gloves shall be laid off on forms and all seams worked out. | | | | | | |
| 8. | Cleaning.<br><br>Remove all spots, stains, and loose ends. Trim thread ends. | | | | | | |
| 9. | Match and pair gloves.<br><br>Tack each pair of gloves together, approximately 1/2 inch down on the front of the wristlet opening with not less than two stitches using a cord thread which will permit the pair to be pulled apart without tearing fabric. | | | | | | |

NATICK Form 903
1 Dec 76 EDITION OF 1 OCT 76 WILL BE USED UNTIL EXHAUSTED.



Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:38Z
Check the source to verify that this is the current version before use.

3.9 Measurements. The measurements of the finished gloves shall conform to table IV. The measurements shall be made with the glove laid out flat under no tension.

TABLE IV. Glove measurements

| | Fig. 1 reference | Measurements (inches) S | M | L | Tolerance plus or minus (inches) |
|---|---|---|---|---|---|
| Total length | A | 16-3/4 | 17-1/4 | 17-3/4 | 1/2 |
| Hand width | B | 4-1/8 | 4-3/8 | 4-5/8 | 1/4 |
| Hand length | C | 10 | 10-1/4 | 10-1/2 | 1/4 |
| Cuff width | D | 3-1/4 | 3-1/4 | 3-1/4 | 1/4 |
| Cuff length | E | 6-3/4 | 7 | 7-1/4 | 1/4 |
| Thumb length | F | 2-1/2 | 2-3/4 | 3 | 1/4 |
| Middle finger length | G | 3-1/4 | 3-1/2 | 3-3/4 | 1/4 |

* 3.10 Workmanship. The finished gloves shall conform to the quality of product established by this document. The occurrence of defects shall not exceed the applicable acceptable quality levels.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in this document where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

* 4.1.1 Responsibility for compliance. All items must meet all requirements of sections 3 and 5. The inspection set forth in this document shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in the document shall not relieve the contractor of the responsibility of assuring that all products or supplies



Source: https://assist.dla.mil -- Downloaded: 202610-16T12:38Z
Check the source to verify that this is the currentversion before use.

submitted to the Government for acceptance comply with all requirements of the contract. Sampling in quality conformance does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to acceptance of defective material.

* 4.1.2 Responsibility for dimensional requirements. Unless otherwise specified in the contract or purchase order, the contractor is responsible for assuring that all specified dimensions have been met. When dimensions cannot be examined on the end item, inspection shall be made at any point or at all points in the manufacturing process necessary to assure compliance with all dimensional requirements.

* 4.1.3 Certificates of compliance. Where certificates of compliance are submitted the Government reserves the right to inspect such items to determine the validity of the certification.

4.2 Classification of inspection. The inspection requirements specified herein are classified as follows:

a. First article inspection (see 4.3).
b. Quality conformance inspection (see 4.4).

4.3 First article inspection. When a first article is required (see 6.2), it shall be examined for the defects specified 4.4.2 and 4.4.3. The presence of any defect shall be cause for rejection of the first article.

4.4 Quality conformance inspection. Unless otherwise specified, sampling for inspection shall be in accordance with MIL-STD-105.

4.4.1 Component and material inspection. In accordance with 4.1, components and materials shall be inspected in accordance with all the requirements of referenced documents unless otherwise excluded, amended, modified, or qualified in this document or applicable purchase document.

* 4.4.1.1 Component testing. Testing shall be performed on the components listed in table V for the characteristics shown. The test methods listed in table V shall be in accordance with FED-STD-191. The lot size shall be expressed in units of 1 yard. The sample unit shall be 1-1/2 continuous yards full width of each cloth. The sample size shall be as shown below and the lot shall be unacceptable if one or more sample units fail to meet any requirement specified. All test reports shall contain the individual values utilized in expressing the final result.

| Lot size (yards) | Sample size (sample units) |
|---|---|
| 800 or less | 2 |
| 801 up to and including 22,000 | 3 |
| 22,001 and over | 5 |



Source: https://assist.dla.mil -- Downloaded: 202610-16T12:38Z
Check the source to verify that this is the current version before use.

TABLE V. Component tests

| Component | Characteristic | Requirement reference | Test method |
|---|---|---|---|
| Cotton jersey knit (hand fabric) and cotton rib knit (cuff fabric) | Material identification | 3.3.1 and 3.3.2 | 1200 1/ |
| | Type of knit | 3.3.1 and 3.3.2 | Visual 2/ |
| | Weight (ounces per sq. yd.) | 3.3.1 | 5041 3/ |
| | Yards per pound | 3.3.2 | 5041 4/ |
| | Wales per inch | 3.3.1 and 3.3.2 | 5070 |
| | Courses per inch | 3.3.1 and 3.3.2 | 5070 |
| | Bursting strength | 3.3.1 | 5120 3/ |
| | Width (flat) | 3.3.2 | 5020 4/ |
| | Presence of sulfur | 3.3.3 | 2020 1/ |
| | Colorfastness to: | | |
| | Laundering | 3.3.3.2 | 5610 |
| | Bleaching | 3.3.3.2 | 5600 |
| | Perspiration | 3.3.3.2 | 5680 |
| | Crocking | 3.3.3.2 | 5651 |
| | pH | 3.3.4 | 2811 |
| | Non-fibrous material | 3.3.5 | 2611 |

1/ Unless otherwise specified, a certificate of compliance shall be submitted and will be acceptable for the stated requirement.

2/ For this examination, one determination shall be made per sample unit and the result reported as pass or fail.

3/ Applies only to jersey knit fabric.

4/ Applies only to rib knit fabric.

* 4.4.2 End item visual examination. The end item shall be examined for the defects listed in table VI. The lot size shall be expressed in units of gloves. The sample unit shall be one glove and the selection shall be by pairs. Defects for pairing shall be classified as a single defect. The inspection level shall be II and the acceptable quality level (AQL), expressed in terms of defects per hundred units, shall be 2.5 for major defects and 6.5 for total (major and minor combined) defects.



Source: https://assist.dla.mil -- Downloaded: 202640-16T12:38Z
Check the source to verify that this is the currenversion before use.

TABLE VI. End item visual defects

| Examine | Defect | Classification Major | Minor |
|---|---|---|---|
| Material defects and damages | Any hole, cut, or tear | X | |
| | Run or dropped stitch, end out | X | |
| | Any mend, abrasion mark | X | |
| | Needle chew | X | |
| | Slubs, burrs, or shives | | X |
| | Knots, tight twist yarn | | X |
| Cleanliness | Spot, stain, or streak of an obvious permanent nature | X | |
| | Removable spot, stain, or streak clearly noticeable | | X |
| | Thread ends not trimmed or threads not removed | | X |
| | Surplus material on seams not trimmed throughout glove | | X |
| Color | Not specified color, color not uniform, or shaded parts clearly noticeable | | X |
| Component and assembly | Any component part or required operation omitted (unless otherwise classified herein) | X | |
| | Jersey knit fabric not properly napped | X | |
| | Rib knit fabric not seamless | X | |
| Cutting | Any component part not cut with the length in the wale direction | X | |
| | Any component part not cut in accordance with standard patterns | X | |
| Finishing | Poorly shaped | | X |
| | Laying-off omitted | | X |
| Seams and stitching (general) | Seams twisted, puckered, or pleated | | X |
| | End of seam or stitching (stitch type 301) when not caught in other seam or stitching, backtacked or backstitched less than 1/2 inch | | X |
| | End of seam produced with 401 stitch type when not caught in other seam or stitching, having chain extending less than 1/2 inch or more than 3/4 inch beyond each end | | X |



Source: https://assist.dla.mil -- Downloaded: 202610-16T12:38Z
Check the source to verify that this is the current version before use.

TABLE VI. End item visual defects (cont'd)

| Examine | Defect | Classification Major | Minor |
|---|---|---|---|
| Seams and stitching (general) (cont'd) | End of seam produced with 401 stitch type when not caught in other seam or stitching not having chain extend beyond each end | X | |
| | Any part of glove caught in unrelated operation | | X |
| | Gage of stitching, irregular or not as specified | | X |
| Open seams | Any open seam | X | |
| | Open seam repaired but not repaired as specified | | X |
| | NOTE: A seam shall be classified as open when one or more stitches joining a seam are broken or when two or more consecutive skipped or run-off stitches occur. | | |
| Raw edge | Any raw edge on outside of glove except welt | X | |
| Seam and stitch type | Wrong seam type | | X |
| | Wrong stitch type | | X |
| Stitch tension | Loose tension resulting in a loose seam | X | |
| | Tight tension, i.e., stitches break when normal strain is applied to the seam or stitching (Score in accordance with open seam classification) | | |
| | NOTE: Puckering is evidence of tight tension. When puckering is evident, the seams shall be tested by exerting pull on the lengthwise direction of the seam. | | |
| Stitches per inch (to be scored only when the condition exists on a major portion of the seam) | Less than specified minimum by: | | |
| | 1 or 2 stitches | | X |
| | 3 or more stitches | X | |
| | More than the specified maximum | | X |



Source: https://assist.dla.mil -- Downloaded: 202610-16T12:38Z
Check the source to verify that this is the current version before use.

TABLE VI. End item visual defects (cont'd)

| Examine | Defect | Classification Major | Minor |
|---|---|---|---|
| Fingers and thumb | Fingers and thumb not formed as specified | | X |
| | Twisted | | X |
| Fourchette | Fourchette welting not caught in specified seam | X | |
| | Fourchette welt is too short or finished width is insufficient to remain turned back over the row of stitching that is intended to be protected | | X |
| Cuff | Spliced (not tubular) | X | |
| | Not constructed of double thickness | | X |
| Pairing | Not properly mated, i.e., not right and left of same size, two gloves for same hand | X | |
| | Tacking omitted or not as specified | | X |
| Label | Missing, incomplete, incorrect, not legible, not specified type, or not in specified location | | X |

* 4.4.3 End item dimensional examination. The end item shall be examined for the measurements listed in 3.9. Any measurement not within the specified tolerance shall be classified as a defect. The lot size shall be expressed in units of gloves. The sample unit shall be one glove. The inspection level shall be S-3 and the AQL, expressed in terms of defects per hundred units, shall be 4.0.

* 4.4.4 Packaging examination. The fully packaged end items shall be examined for the defects listed below. The lot size shall be expressed in units of shipping containers. The sample unit shall be one shipping container fully packaged. The inspection level shall be S-2 and the AQL, expressed in terms of defects per hundred units, shall be 2.5.

| Examine | Defect |
|---|---|
| Marking (exterior and interior) | Omitted; incorrect; illegible; of improper size, location, sequence, or method of application. |
| Materials | Any component missing, damaged, or not as specified. |



Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:38Z
Check the source to verify that this is the current version before use.

| Examine | Defect |
|---|---|
| Workmanship | Inadequate application of components such as: incomplete closure of container flap, improper taping, loose strapping, or inadequate stapling.<br>Bulged or distorted container. |
| Content | Number of bundles per container is more or less than required.<br>Number of pairs of gloves per bundle is more or less than required. 1/ |

1/ For this defect, three bundles shall be examined from each shipping container in the sample.

4.4.5 Palletization examination. The fully packaged and palletized end items shall be examined for the defects listed below. The lot size shall be expressed in units of palletized unit loads. The sample unit shall be one palletized unit load fully packaged. The inspection level shall be S-1 and the AQL, expressed in terms of defects per hundred units, shall be 6.5.

| Examine | Defect |
|---|---|
| Finished dimensions | Length, width, or height exceeds specified maximum requirements. |
| Palletization | Pallet pattern not as specified.<br>Interlocking of loads not as specified.<br>Load not bonded with required straps as specified. |
| Weight | Exceeds maximum load limits. |
| Marking | Omitted; incorrect; illegible; of improper size, location, sequence, or method of application. |

5. PACKAGING

5.1 Preservation. Preservation shall be level A or Commercial, as specified (see 6.2).

5.1.1 Level A. Each pair of gloves shall be adjusted to approximately 13 inches in length by folding over the cuffs. Five pairs of folded gloves of one size only, with each pair alternated end for end, shall be neatly stacked and staggered in a bundle measuring 15 inches in length. Each bundle shall be securely tied with cotton tape or twine approximately three inches in from each end.



Source: https://assist.dla.mil -- Downloaded: 202610-16T12:38Z
Check the source to verify that this is the current version before use.

5.1.2 Commercial packaging. The gloves shall be preserved in accordance with ASTM D 3951.

5.2 Packing. Packing shall be level A, B, or Commercial as specified (see 6.2).

* 5.2.1 Level A packing. One hundred and twenty pairs of gloves of one size only, preserved as specified in 5.1, shall be packed in a snug-fitting fiberboard shipping container conforming to style RSC-L, grade V2s of PPP-B-636. The inside of each shipping container shall be fitted with a box liner conforming to type CF, class weather-resistant, variety DW, grade V15c of PPP-B-636. Level A unit bundles shall be packed six in length, one in width, and four in depth within a shipping container. Inside dimensions of each container shall approximate 23-1/2 inches in length, 15 inches in width, and 15 inches in depth. Approximate dimensions are furnished as a guide only. Each container shall have the contents completely covered on the top and bottom with a sheet of 30-pound minimum basis weight kraft paper conforming to A-A-203. Each shipping container shall be closed in accordance with method III, waterproofed in accordance with method V, and reinforced as specified in the appendix of PPP-B-636, except that the inspection shall be in accordance with 4.4.4. Shipping containers shall be arranged in unit loads in accordance with MIL-L-35078 for the type and class of load specified (see 6.2). Strapping shall be limited to nonmetallic strapping, except for type II, class F loads.

5.2.2 Level B packing. One hundred and twenty pairs of gloves of one size only, preserved as specified in 5.1, shall be packed in a snug-fitting fiberboard shipping container conforming to style RSC-L, type CF (variety SW) or SF, class domestic, grade 275 of PPP-B-636. The inside of each shipping container shall be fitted with a box liner conforming to type CF, class domestic, variety DW, grade 275 of PPP-B-636. Level A bundles shall be packed six in length, one in width, and four in depth within a shipping container. Inside dimensions of each container shall approximate 23-1/2 inches in length, 15 inches in width, abd 15 inches in depth. Approximate dimensions are furnished as a guide only. Each container shall have the contents completely covered on the top and bottom with a sheet of 30-pound minimum basis weight kraft paper conforming to A-A-203. Each shipping container shall be closed in accordance with method II as specified in the appendix of PPP-B-636, except that the inspection shall be in accordance with 4.4.4.

5.2.2.1 Weather-resistant fiberboard containers. When specified (see 6.2), the shipping container shall be a grade V3c, V3s, or V4s fiberboard box fabricated in accordance with PPP-B-636 and closed in accordance with method III as specified in the appendix of PPP-B-636, except that the inspection shall be in accordance with 4.4.4.



Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:38Z
Check the source to verify that this is the current version before use.

5.2.3 Commercial packing. Gloves, preserved as specified in 5.1, shall be packed in accordance with ASTM D 3951.

* 5.3 Palletization. When specified (see 6.2), gloves packed as specified in 5.2.2 and 5.2.3 shall be palletized on a 4-way entry pallet in accordance with load type 1a of MIL-STD-147. Pallet types shall be type I (4-way entry), type IV, or type V in accordance with MIL-STD-147. Pallets shall be fabricated from wood groups I, II, III, or IV of MIL-STD-731. Each prepared load shall be bonded with primary and secondary straps in accordance with bonding means K and L or film bonding means O or P. Pallet pattern shall be number 3 in accordance with the appendix of MIL-STD-147. Interlocking of loads shall be effected by reversing the pattern of each course.

* 5.4 Marking. In addition to any special marking required by the contract or purchase order, shipping containers and palletized unit loads shall be marked in accordance with MIL-STD-129 or ASTM D 3951, as applicable.

6. NOTES

6.1 Intended use. The gloves, following impregnation with antivesicant material, are to protect the hands and wrists from vesicants.

* 6.2 Ordering data. Acquisition documents should specify the following:

a. Title, number, and date of this document
b. Sizes required (see 1.2)
c. When a first article is required (See 3.2, 4.3, and 6.5).
d. Selection of applicable levels of preservation and packing (see 5.1 and 5.2)
e. Type and class of unit load required (See 5.2.1).
f. When weather-resistant grade fiberboard shipping containers are required for level B packing (see 5.2.2.1)
g. When palletization is required (see 5.3).

6.3 Samples. For access to samples, address the contracting activity issuing the invitation for bids.

6.4 Marking inks. Only those marking inks, approved by the U.S. Army Natick Research, Development, and Engineering Center, Natick, MA 01760-5014, and so listed in the invitation for bids or request for proposal, shall be considered acceptable for the related procurement.



Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:38Z
Check the source to verify that this is the current version before use.

* 6.5 First article. When a first article is required, it shall be inspected and approved under the appropriate provisions of FAR 52.209. The first article should be a preproduction sample. The contracting officer should specify the appropriate type of first article and the number of units to be furnished. The contracting offer should include specific instructions in all acquisition instruments regarding arrangements for selection, inspection, and approval of the first article.

* 6.6 Subject terms (key word) listing.

Gloves
Impregnated
Vesicant protective

6.7 Changes from previous issue. The margins of this document are marked with an asterisk to indicate where changes (additions, modifications, corrections, deletions) from the previous issue were made. This was done as a convenience only and the government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous issue.

Custodians:

Army - GL
Navy - NU
Air Force - 99

Preparing activity:

Army - GL

Project No. 8415-0624

Review activities:

Army - MD
Air Force - 11, 82
DLA - CT

User activities:

Navy - MC, YD
Air Force - 45



Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:38Z
Check the source to verify that this is the current version before use.

**INSTRUCTIONS:** In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

*NOTE:* This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document*(s)* or to amend contractual requirements.

*(Fold along this line)*

*(Fold along this line)*

DEPARTMENT OF THE ARMY

U.S. ARMY NATICK RESEARCH, DEVELOPMENT
and ENGINEERING CENTER
ATTN: STRNC-ES
Natick, MA 01760-5014

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

NO POSTAGE
NECESSARY
IF MAILED
IN THE
UNITED STATES

**BUSINESS REPLY MAIL**
FIRST CLASS PERMIT NO. 12062 WASHINGTON D. C.
POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE ARMY

Commander
U.S. Army Natick Research, Development
and Engineering Center
ATTN: STRNC-ES
Natick, MA 01760-5014

Source: https://assist.dla.mil -- Downloaded: 202610-16T12:38Z
Check the source to verify that this is the current version before use.

# STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

*(See Instructions – Reverse Side)*

| 1. DOCUMENT NUMBER | 2. DOCUMENT TITLE |
|---|---|
| MIL-G-1057H | Gloves, Cloth, Cotton, Special, OG-109 |

| 3a. NAME OF SUBMITTING ORGANIZATION | 4. TYPE OF ORGANIZATION *(Mark one)* |
|---|---|
| | ☐ VENDOR<br>☐ USER<br>☐ MANUFACTURER<br>☐ OTHER *(Specify)*: _____ |
| b. ADDRESS *(Street, City, State, ZIP Code)* | |

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

| 7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional | b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional |
|---|---|
| c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional | 8. DATE OF SUBMISSION *(YYMMDD)* |

DD FORM 82 MAR 1426 PREVIOUS EDITION IS OBSOLETE. NATICK OP-1, Feb 86

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:38Z
Check the source to verify that this is the current version before use.