16 November 1966

MILITARY SPECIFICATION

ADHESIVE, MODIFIED EPOXY RESIN WITH POLYAMINE CURING AGENT

This amendment forms a part of Military Specification MIL-A-81253(OS), 1 March 1965, and has been approved by the Naval Ordnance Systems Command, Department of the Navy.

By this amendment the basic Specification MIL-A-81253(WP) is designated as MIL-A-81253(OS).

Page 1, paragraph 1.1 Add to end of paragraph "adhesive."

Page 2, paragraph 3.1, lines 6 and 7· Delete "technical requirements of the contract." and substitute "requirements of this specification."

Page 3, paragraph 3.3. Delete and substitute

"3.3 Material The adhesive shall be made from a low-viscosity modified epoxy resin and triethylenetetramine."

Page 3, paragraph 3.6 Delete and substitute·

"3.6 Tensile shear The tensile shear value of the cured resin shall be no less than 3250 pounds per square inch (psi) for each test specimen."

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T05:07Z
Check the source to verify that this is the current version before use.