MIL-L-17507F
27 February 1978
SUPERSEDING
MIL-L-17507E
21 September 1972

MILITARY SPECIFICATION

LACE, ORNAMENTAL

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers the requirements for woven and braided gold lace.

* 1.2 Classification. The gold lace shall be of the following types, classes, styles, substyles, and color patterns (see 6.2):

Type I - Lace gold wire
Type II - Lace gold thread

Class 1- Silver base wire
Class 2- White metal base wire
Class 3- Metallic silver plastic film
Class 4- Metallic aluminum plastic film
Class 5- Metallic, aluminum gold yarn

Style A- Plain
Style B- Interwoven Stripe
Substyle B1- Warpwise (Army)
Substyle B2- Fillingwise (Navy)

2. APPLICABLE DOCUMENTS

* 2.1 Issues of documents. The following documents of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein:

Beneficial comments recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Officer in Charge, Navy Clothing and Textile Research Facility, 21 Strathmore Road, Natick, MA 01760 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

FSC 8315

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T10:13Z
Check the source to verify that this is the current version before use.

SPECIFICATIONS

FEDERAL

P-D-680 - Dry Cleaning Solvent
PPP-B-636 - Boxes, Shipping, Fiberboard

MILITARY

MIL-E-17568 - Embroidery Materials, Metallic and Synthetic Metallic

STANDARDS

FEDERAL

FED-STD-191 - Textile Test Methods

MILITARY

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes
MIL-STD-129 - Marking for Shipment and Storage

(Copies of specifications, standards, drawings, and publications required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

LAWS AND REGULATIONS

U.S. POSTAL SERVICE MANUAL

(Copies of the manual may be obtained from the Superintendent of Documents, U.S. Government Printing Office, Washington, D.C. 20402).

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply:

NATIONAL MOTOR FREIGHT TRAFFIC ASSOCIATION, INC., AGENT

National Motor Freight Classification

(Application for copies should be addressed to American Trucking Associations, ATTN: Tariff Order Section, 1616 P Street, N.W., Washington, DC 20036.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T10:13Z
Check the source to verify that this is the current version before use.

UNIFORM CLASSIFICATION COMMITTEE, AGENT

Uniform Freight Classification

(Application for copies should be addressed to the Uniform Classification Committee, Room 1106, 222 South Riverside Plaza, Chicago, Illinois 60606.)

COLOR ASSOCIATION OF THE UNITED STATES, INC.

United States Army Standard Color Card for Official Colors for Arms and Services (Application for copies shall be addressed to Color Association of the United States, 200 Madison Avenue, New York, New York 10016.)

3. REQUIREMENTS

3.1 Guide sample. Guide samples, when furnished, are solely for guidance and information to the contractor (see 6.3). Variations from this specification may appear in the sample, in which case this specification shall govern.

3.2 Standard sample. The finished gold lace shall match the standard sample for shade, and shall be equal to or better than the standard sample with respect to all characteristics for which the standard sample is referenced (see 6.3).

3.3 First article approval. The requirement for first article will be as specified by the procuring activity (see 6.2).

3.4 Materials.

3.4.1 Lace gold wire. The gold wire used to form the covering of the type I gold lace, shall be either a Class 1 - Silver base wire or a Class 2 - White metal base wire, conforming to the respective requirements specified in 3.4.4.1 and 3.4.4.2.

3.4.2 Lace gold thread. The gold thread used to form the covering of the type II gold lace, shall consist of a flattened wire or an imitation gold ribbon, conforming to the requirements specified in 3.4.2.1 and 3.4.2.2.

3.4.2.1 Flattened wire. The gold wire shall conform to the requirements of either the Class 1 - Silver base wire (see 3.4.4.1) or a Class 2 - White metal base wire (see 3.4.4.2), except that the wire shall be flattened. The wire shall be wound evenly and uniformly around a core of yarn conforming to the requirements specified in 3.4.3.1.

* 3.4.2.2 Imitation gold ribbon. The imitation gold ribbon shall conform to the requirements of either the Class 3 - Metallic silver plastic film (see 3.4.4.3) or Class 4 - Metallic aluminum plastic film (see 3.4.4.4) or Class 5 - Metallic aluminum gold yarn (see 3.4.4.5). The ribbon shall be wound evenly and uniformly around a core of yarn conforming to the requirements specified in 3.4.3.1.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T10:13Z
Check the source to verify that this is the current version before use.

3.4.3 Yarns.

* 3.4. .1 Core yarn. The core yarn used with the flattened gold wire or imitation gold ribbon coverings shall be 2 or 3 ply nylon, rayon, or mercerized cotton yarn and tested as specified in 4.4.1. The color of the core yarn shall be yellow or gold.

3.4.3.2 Warp (stuffer and binder) yarns. The warp (stuffer and binder) yarns used in types I and II woven gold lace shall be 2 or 3 ply nylon, rayon, or mercerized cotton yarn and tested as specified in 4.4.1. The yarns shall be gold in color and match cable no. 65002 (see 2.2).

3.4.3.3 Filler yarn. The filler yarn used in types I and II braided gold lace shall be 2 or 3 ply nylon, rayon, or mercerized cotton yarn and tested as specified in 4.4.1. The yarn shall be gold in color and match cable no. 65002 (see 2.2).

3.4.3.4 Interwoven stripe yarn. The interwoven stripe yarn used in types I and II, style B gold lace shall be 2 or 3 ply nylon, rayon, or mercerized cotton yarn and tested as specified in 4.4.1. The color of the yarn shall be as specified in table II (Army) and table III (Navy).

3.4.3.5 Labile sulfur. The use of dyes and compounds containing elementary sulfur capable of oxidation to sulfuric acid is prohibited. The dyestuff shall be chosen and applied so that the dyed and finished yarn shall contain no more labile sulfur than shown by the standard sample when tested as specified in 4.4.1. When a standard sample is not available, the dyed and finished yarn shall show no more than a slight trace of labile sulfur as defined in the test method specified in 4.3.1.

3.4.3.6 Colorfastness of dyed yarns. The dyed yarn shall show a minimum of "good" fastness to light and wet-dry cleaning when tested as specified in 4.4.1.

3.4.4 Coverings.

3.4.4.1 Class 1 - Silver base wire. When Class 1 wire is specified (see 6.2), the base wire shall be made of silver, rounded in shape. The base wire shall assay not less than 990 fine silver, and shall be evenly and thoroughly electroplated with not less than 2 percent 24 Karat gold when tested as specified in 4.4.1.

3.4.4.2 Class 2 - White metal base wire. When Class 2 wire is specified (see 6.2), the base wire shall be a white metal rounded in shape evenly and thoroughly electroplated with not less than 2 percent 24 karat gold. The metal content of the white metal (taken on a basis of parts per thousand) before electroplating shall assay as follows (see 4.4.1).

Source: https://assist.dla.mil -- Downloaded: 202610-18T10:13Z
Check the source to verify that this is the current version before use.

as applicable.

Silver - 22.5 (min)	Zinc - 19.5 (min)
Nickel - 48.0 (min)	Copper - Remainder

3.4.4.3 Class 3 - metallic silver plastic film. When class 3 metallic silver plastic film is specified (see 6.2), the imitation gold ribbon shall finish .014 to .016 inch (0.35 to 0.40 mm) wide by 0.00070 to 0.00080 inch (0.019 to 0.020 mm) thick. The ribbon shall consist of a gold colorant sandwiched between a 0.0005 inch (0.013 mm) clear polyester film and a metallic silver surface produced by the vacuum evaporation or deposition technique. The silver surface shall be backed with a substrate material suitable for the purpose intended. The gold color shall be of a luster and color to provide a match in the finished lace form to the approved standard, and meet the requirements specified herein (see 4.4.1).

3.4.4.4 Class 4 - metallic aluminum plastic film. When Class 4 metallic aluminum plastic film is specified (see 6.2), the imitation gold ribbon shall finish approximately 0.016 inch (0.40mm) wide by 0.0015 inch (0.038mm) thick. The ribbon shall be of either one, two, or three plies of clear polyester film of which the inner ply shall have a metallic aluminum surface produced by the vacuum evaporation or deposition technique (aluminum foil of the appropriate thickness can be substituted) on either one side or both sides (back to back) laminated with a polyester-cross linking adhesive (if applicable) to form a single composite sheet. The gold color shall be of a luster and shade to provide a match between the finished lace and the approved standard sample and meet the requirements specified herein (see 4.4.1).

* 3.4.4.5 Class 5 - Metallic, aluminum (gold) yarn. The class 5 synthetic metallic aluminum (gold) yarn shall conform to the requirements of Type III, Class 11 of MIL-E-17568.

3.4.5 Finish. The types I and II, classes 1 and 2, gold lace shall be evenly and thoroughly lacquered with a clear synthetic lacquer. The use of pigmented lacquers are prohibited. The dry lacquer film shall be continuous, level, adherent, and essentially free from lint, dust, and other foreign inclusions (see 4.4.1).

3.5 Construction.

3.5.1 Style A (Plain) gold wire lace. When specified (see 6.2), the style A (Plain) gold wire lace shall conform to the physical requirements listed in table I when tested as specified in 4.5.

3.5.2 Style B (Interwoven) gold thread lace. When specified (see 6.2), the style B (Interwoven) gold thread lace shall conform to the physical requirements listed in tables II and III when tested as specified in 4.5.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T10:13Z
Check the source to verify that this is the current version before use.

* Table I - Physical requirements for

Types I and II, Classes 1 through 5, style A (Plain)

Type	Width, inches 1/ (min.)	No. of Vellum	Weight of metal per Yard (0.9M) of lace, grams (min.) 3/		Picks per inch (25.4mm) min				
			Class 1	Class 2	Class 1	Class 2	Class 3	Class 4	Class 5
I	1/8 braid 2/	2	4.60	3.70	250	250	-	-	-
I	1/4	2	4.80	3.74	280	280	-	-	-
I	1/2	2	9.90	7.75	280	280	-	-	-
I	3/4	2	13.70	10.99	260	260	-	-	-
I	1	2	18.70	15.00	260	260	-	-	-
I	1 1/2	2	28.50	22.30	260	260	-	-	-
I	2	2	38.00	30.00	260	260	-	-	-
II	1/8	1	1.85	1.45	270	270	230	200	188
II	1/8	2	1.85	1.45	270	270	-	-	188
II	1/4	2	3.15	2.47	270	270	230	200	188
II	1/4	1	-	-	-	-	230	200	188
II	3/8 braid	2	-	-	-	-	36 4/	36 4/	-
II	3/8	2	4.40	3.45	270	270	230	200	188
II	3/8	1	4.40	3.45	270	270	230	200	188
II	1/2	2	5.80	4.55	270	270	230	200	188
II	1/2 braid	2	-	-	-	-	32 5/	32 5/	-
II	3/4	2	8.48	6.60	270	270	-	-	188
II	1	2	10.80	8.50	270	270	-	-	188
II	1 1/2	2	16.50	13.00	270	270	230	200	188
II	1 3/4	2	20.20	15.75	270	270	-	-	188
II	2	2	23.50	18.30	270	270	230	200	188

1/ To convert to metric system multiply inch measurement by 25.4 to find millimeters.

2/ Denotes 18 carriers (min) and 10 warp ends (min), to be used.

3/ For classes 3 and 4, these requirements are not applicable.

4/ The braid shall be of the flat type and constructed as follows:

1/16 inch (1.6mm) wide selvedge, 2 lines of plain braid, 3 cotton filler ends per line.
Vellum, braided cotton filler
Plain braid
Vellum, braided cotton filler
1/16 inch (1.6mm) wide selvedge, 2 lines of plain braid, 3 cotton filler ends per line.

with

Carriers - 33(min.), Ends per carrier - 2(min), Warp ends - 66(min)

Source: https://assist.dla.mil -- Downloaded: 20261O-18T10:13Z
Check the source to verify that this is the current version before use.

5/ The braid shall be of the flat type and constructed as follows:

5/64 inch (2.0mm) wide selvedge, 2 lines of plain braid, 1 cotton filler end per line.
Vellum, braided cotton filler
Plain braid
Vellum, braided cotton filler
5/64 inch (2.0mm) wide selvedge, 2 lines of plain braid, 1 cotton filler end per line.
with
Carriers - 48(min), Ends per carrier - 2(min), Warp ends - 38(min).

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T10:13Z
Check the source to verify that this is the current version before use.

Table II - Physical requirements for Type I,
Classes 1 and 2, Style B (Interwoven stripe) Substyle B1 (Army)

*

Width inch 1/	No. of Vellum	Weight of metal Per yard (0.9M) of lace grams (min.)		Picks per inch (25.4MM)Min	Appli-cation	Color Pattern Repeat Inch 1/			Ribs per inch(25.4mm) (silk stripe)
		Class 1	Class 2			(Outside) Gold	(Center) As specified	(Outside) Gold	
3/4	4	13.00	10.15	270	Sleeve	1/4	1/4 2/	1/4	27
1-3/4	4	33.00	26.00	270	Cap	1/2	- 3/	1/2	27

1/ To convert to metric system multiply inch measurement by 25.4 to find millimeters.

2/ Only one color is required for center stripe. When two Army service colors are listed only the first named color shall be used.

3/ Army service colors having one color shall be 3/4 inch wide. When two Army service colors are listed the first named color shall be 1/2 inch wide in the middle and the second named color 1/8 inch wide on each side of middle color (see 2.2 and 6.4).

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T10:13Z
Check the source to verify that this is the current version before use.

Table III - Physical Requirements for Type II,
Classes 1 thru 5, Style B (Interwoven stripe) Substyle B2 (Navy)

Width Inch 1/ (min.)	No. of Vellum	Weight of metal 2/ Per yard (0.9m) of lace, grams (min)		Picks per inch (25.4 mm) min.					Application 4/	Color Pattern Repeat Inches 1/ (Outside) Gold	(Center) Blue 3/	(Outside) Gold
		Class 1	Class 2	Class 1	Class 2	Class 3	Class 4	Class 5				
1/2	2	4.90	3.90	270	270	230	200	188	1 Shoulder	2 11/16	1/2	2 11/16
1/2	2	2.90	2.26	270	270	230	200	188	2 Shoulder	1/2	1/2	1/2
1/4	2	1.60	1.24	270	270	230	200	188	3 Shoulder	1/2	1/2	1/2
1/2	2	5.60	4.32	270	270	230	200	188	4 Sleeve	15	1/2	15
1/2	2	4.60	3.60	270	270	230	200	188	5 Sleeve	2	1/2	2
1/4	2	2.52	1.97	270	270	230	200	188	6 Sleeve	2	1/2	2

1/ To convert to metric system multiply inch measurement by 25.4 to find millimeters.

2/ For classes 3, 4, and 5 these requirements are not applicable.

3/ The color blue shall match Ultramine Blue, Cable No. 65010 (see 2.2)

4/ 1. and 4. - Commissioned Warrant Officer (W-4) - 2. and 5. Commissioned Warrant Officer (W-3 and W-2)
3. and 6. - Warrant Officer (W-1)

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T10:13Z
Check the source to verify that this is the current version before use.

* 3.6 Colorfastness. Type II gold lace, classes 3, 4, and 5 shall show fastness to dry cleaning; salt water and soap; dry and wet heat; light; weathering; crocking; perspiration; and chlorine bleaching equal to or better than the standard sample. When no standard sample is available, the gold lace shall show a minimum of "good" fastness to dry cleaning; salt water and soap; dry and wet heat; light; perspiration; and chlorine bleaching; a minimum of "fair" fastness to "weathering"; and a Munsell Value for crocking not lower than 8.5. Tests shall be performed as specified in 4.5.

* 3.7 Durability of color. Type II gold lace, classes 3, 4, and 5 shall not discolor when tested as specified in 4.5.1.

* 3.8 Tackiness. Type II gold lace, classes 3, 4, and 5 shall not become tacky when tested as specified in 4.5.2.

3.9 Corrosion Resistance. Types I and II gold lace, class 1 shall show no signs of corrosion when tested as specified in 4.5.3.

3.10 Length. Unless otherwise specified (see 6.2), the gold lace shall be put on rolls of not less than 25 continuous yards.

3.11 Workmanship. The finished gold lace shall conform to the quality of product established by this specification. The occurrence of defects shall not exceed the applicable acceptable quality levels.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspection set forth in specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Certificate of compliance. Where certificates of compliance are submitted, the Government reserves the right to check test such items to determine the validity of the certification.

4.2 Classification of inspections. The inspection requirements specified herein are classified as follows:

a. First article inspection (see 4.3).
b. Quality conformance inspection (see 4.4).

4.3 First article inspection. When required (see 6.2), the first article submitted in accordance with 3.3 shall be visually inspected as specified in 4.4.2 for compliance with design, construction, workmanship, and dimensional requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T10:13Z
Check the source to verify that this is the current version before use.

4.4 Quality conformance inspection. Sampling for inspection shall be performed in accordance with MIL-STD-105, except where otherwise indicated hereinafter.

* 4.4.1 Component and material inspection. In accordance with 4.1, components and materials shall be inspected and tested in accordance with all the requirements of referenced specifications, drawings, and standards unless otherwise excluded, amended, modified, or qualified in this specification or applicable purchase document. A certificate of compliance shall be submitted and will be acceptable for the:

- yarn identification and ply requirements of 3.4.3.1 thru 3.4.3.4
- metal content requirements of 3.4.4.2
- plastic film requirements of 3.4.4.3 and 3.4.4.4
- metallic yarn requirements of 3.4.4.5 and
- lacquer requirements of 3.4.5
- anti-tarnish tissue paper requirement of 5.1.1

In addition, materials listed in Table IV shall be tested for the characteristics specified and in accordance with referenced test methods of FED-STD-191. All test reports shall contain the individual values utilized in expressing the final results. The sample unit for the base wire shall be 75 continuous yards (meters) and the lot size shall be expressed in yards (meters): The sample unit for the yarn (each type used), shall be a cone spool or a sufficient number of bobbins to total a minimum of 360 yards (meters). The lot size shall be expressed in units of yards (meters). The lot shall be unacceptable if one or more sample units fail to meet any of the test requirements specified. The sample size shall be as follows:

Lot size (units)	Sample size
800 or less	2
801 thru 22,000	3
22,001 and over	5

Table IV - Material testing

*

Material	Characteristic	Requirement paragraph	Test Method
Yarns			
Core, Warp (Stuffer and binder), filler, and interwoven stripe			
	Labile sulfur	3.4.3.5	2020 1/
	Colorfastness to:		
	Light 2/	3.4.3.6	5660 1/
	Wet-dry cleaning	3.4.3.6	5622 1/
Base wire			
Class 1	Silver assay	3.4.4.1	4.4.1.1 3/
	Gold assay	3.4.4.1	4.4.1.1 3/
Class 2	Gold assay	3.4.4.2	4.4.1.1 3/

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T10:13Z
Check the source to verify that this is the current version before use.

1/ One determination shall be performed per sample unit, and the results reported as "pass" or "fail".
2/ Test specimens shall be exposed for a minimum of 40 standard fading hours in which no appreciable change in color shall be evident before the first 20 hours. After first 20 hours an appreciable, but not objectionable, shade change shall be permitted.
3/ One determination shall be performed per sample unit, and the results reported to the nearest 0.01 percent.

4.4.1.1 Quantity of gold and silver. The quantities of gold and silver may be determined by standard commercial methods of assay using at lease two samples of one yard (meter) each. However, in case of dispute, the following methods shall be used:

4.4.1.1.1 Gold content. Boil 1 gram of alloy (accurately weighed) with 60 ml. 1:1 nitric acid (HNO3) in a 400 ml. beaker using a small flame or hot plate. Continue boiling until all metals except the gold are in solution. Dilute to 200ml. with hot water. Filter through a rapid ashless filter paper and wash several times with hot water. Take the filter paper with the gold (cutting off any excess filter paper), wrap in a 2 x 2 inch (5.0 x 5.0 cm) piece of silver free lead foil and roll into a ball. Place the ball in the hollow of a bone ash cupel, and add lead shot around the ball. Place cupel in a muffle furnace for one hour at 1000°C. Remove from the furnace and examine hollow for flakes of gold impurities and discolored gold bead. If any are noticed, add additional lead shot and return cupel to the muffle furnace for one hour. Otherwise, cool the gold bead and weigh. The gold content shall be calculated as follows:

$$\text{Gold content} = \frac{W\ (AU) \times 100}{WS} = P\ (AU)$$

Whereas:
W (AU) = Weight of gold
WS = Weight of sample
P (AU) = Percent of gold

4.4.1.1.2 Silver content. Dilute the filtrate, from 4.4.1.1.1 to a 1,000 ml. volumetric flask, and dilute to the mark. Pipette a 200 ml. aliquot from the flask into a 400 ml. beaker. Heat to boiling, and add HCL (3:100) drop by drop from a pipette until precipitation is complete (1 ml. of HCL solution precipitates about 0.038 grams of silver). When solution has cooled and precipitate has settled, determine whether precipitation is complete by adding a few drops of the HCL (3:100). If solution remains clear, filter on a weighed porcelain Gooch crucible. Wash the precipitate several times with HNO3 (1:200) and finally with cold water. Protect the silver chloride from the light: dry in an oven for not less than two hours, cool and weigh. The silver content shall be calculated as follows:

Source: https://assist.dla.mil -- Downloaded: 20261O-18T10:13Z
Check the source to verify that this is the currentversion before use.

4.4.1.1.2 Silver content (Cont'd)

$$\text{Silver content} = \frac{W(AGCL) \times 752.63 \times 5}{WS}$$

Whereas: W(AGCL) = Weight of silver chloride
WS = Weight of sample minus weight of gold

4.4.1.1.3 Alloy. Ascertain by difference.

* 4.4.2 Examination of the end item. The required yardage of each roll shall be inspected and visual defects classified in accordance with the defects listed below. All defects found shall be counted regardless of their proximity one to another, except where two or more defects represent a single local condition of the lace, in which case only the more serious defect shall be counted. A continuous defect shall be counted as one defect for each linear yard (meter) or fraction thereof in which it occurs. The unit of product for this examination shall be one linear yard (meter). The sample size shall be in accordance with level II of MIL-STD-105. The acceptable quality levels shall be 2.5 major and 6.5 total per 100 units (yards or meters). The lot size shall be expressed in units of one linear yard (meter). An approximate equal number of yards (meters) shall be examined from each roll selected.

4.4.2.1 Visual examination.

Examine	Defect	Classification Major	Minor
General (when applicable)	Abrasion mark	X	
	Any cut, hole, or tear	X	
	Gold plating chipped, not continuous, peeled, blistered, or tarnished (types I and II, classes 1 and 2)	X	
	Any delamination or separation of film (type II, classes 3, 4 and 5)	X	
	Broken or missing yarn	X	
	Uneven tension, resulting in thick and thin places	X	
	Tight or loose yarn, causing distortion or loopiness	X	
	Broken or missing end or pick	X	
	Tight picks		X
	Course or heavy picks		X
	Fine or light picks		X
	Knots, slubs		X

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T10:13Z
Check the source to verify that this is the current version before use.

4.4.2.1 Visual examination (Cont'd)

Examine	Defect	Classification Major	Classification Minor
Cleanness	Any spot or stain		X
Color	Not as specified	X	
	Variation of shade in same roll		X
Design	Not as specified	X	
	Number of vellum stripes other than specified	X	
	Width less than specified, including color pattern stripes when applicable	X	
	Vellum stripes not round or full		X
Construction			
	Selvages curled, folded, or rolled	X	
	More than one splice		X
Finishing	Lacquer coating tacky, flakey, missing, or uneven (types I and II, classes 1 and 2)	X	

* 4.4.2.2 Length examination. The rolls shall be examined for gross length. Any gross length found to be less than the specified minimum length or any gross length found to be more than one yard (meter) below the gross length marked on the roll ticket shall be considered a defect with respect to length. The unit of product for this examination shall be one roll. The lot size shall be the number of rolls in the end item inspection lot. The inspection level shall be S-3 and the acceptable quality level (AQL) shall be 4.0 defects per one hundred units.

4.4.2.3 Examination for total yardage in sample. The lot shall be unnaceptable if the total of the actual gross lengths of rolls in the sample is less than the total of the gross lengths marked on the roll tickets.

4.4.3 Examination of packaging requirements. An examination shall be made to determine that the packaging, packing, and marking complies with Section 5 requirements. Defects shall be scored in accordance with the list below. The sample unit shall be one shipping container fully prepared for delivery, except that it need not be closed. Defects of closure listed below shall be examined on shipping containers fully prepared for delivery. The lot size shall be the number of shipping containers in the end item inspection lot. The inspection level shall be S-2 and the AQL 2.5 defects per 100 units.

Source: https://assist.dla.mil -- Downloaded: 202640-18T10:13Z
Check the source to verify that this is the currentversion before use.

Examine	Defect
Marking (exterior and interior)	Omitted, incorrect, illegible, or improper size, location, sequence, or method of application.
Materials	Any component missing, damaged, or not as specified.
Workmanship	Inadequate application of components such as: Incomplete closure of container flaps, loose strapping, inadequate stapling, improper taping, or open seams in polyethylene bag.
Content	Bulged or distorted container Number of rolls per exterior shipping containers is more or less than required.

4.5 Testing of the end item. The finished gold lace shall be tested for characteristics shown in table V. The sample unit for test purposes shall be three continuous yards (meters). The lot size shall be expressed in units of one yard (meters) each. All test reports shall contain the individual values used in expressing the final results. The lot shall be unacceptable if one or more sample units fail to meet any requirements specified. The sample size for each characteristic shall be as follows:

Lot size in yards (meters)	Sample units for testing
800 or less	2
801 thru 22,000	3
22,001 and over	5

Table V - End Item Testing

Characteristic	Requirement paragraph	Test method
Lace, braided		
No. of carriers	Table I	1/
Ends per carrier	Table I	1/
No. of warp ends	Table I	1/
Type of braid	Table I	1/
Weight of metal	Table I	1/
Picks per inch	Table I	1/
Lace, woven		
Weight of metal	Tables I, II, and III	1/
Picks per inch	Tables I, II, and III	1/
Ribs per inch	Table II	1/
Colorfastness to:		
Dry-cleaning	3.6	5621 2/
Salt water and soap	3.6	5632 2/
Dry & wet heat (175° to 190°C)	3.6	5640 2/
Light (40 hours)	3.6	5660 2/
Weathering (40 hours)	3.6	5671 2/

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T10:13Z
Check the source to verify that this is the current version before use.

Table V - End Item Testing (Cont'd)

Characteristic	Requirement paragraph	Test method
Crocking	3.6	5651 2/
Perspiration	3.6	5680 2/
Chlorine Bleaching	3.6	5600 2/
Durability of color	3.7	4.5.1 2/
Tackiness	3.8	4.5.2 2/
Corrosion Resistance	3.9	4.5.3 3/

1/ Unless otherwise specified, a certificate of compliance shall be accepted for this characteristic.
2/ Test applicable to type II, classes 3, 4, and 5 only.
3/ Test applicable to types I and II, class 1, only.

4.5.1 Durability of color. A cloth saturated with methyl ethyl ketone solvent shall be lightly rubbed once back and forth along a 3 inch specimen of the gold lace. Any evidence of discoloration shall be cause for failure. One determination shall be performed per sample unit, and the result reported as "pass" or "fail".

4.5.2 Tackiness. A cloth saturated with type I (Stoddard) solvent of P-D-680, shall be lightly rubbed once back and forth along a 3 inch specimen of the gold lace. Any evidence of tackiness shall be cause for failure. One determination shall be performed per sample unit, and the result reported as "pass" or "fail".

4.5.3 Corrosion resistance. The gold lace shall be equal to the standard sample after exposure to a salt spray of 3 percent salt solution for 12 hours. In the event of the unavailability of a standard sample, there shall be no appreciable change in the color, or no more than a slight evidence of corrosion. One determination shall be performed per sample unit, and the result reported as "pass" or "fail".

5. PACKAGING

5.1 Preservation-packaging. Preservation-packaging shall be level A or C, as specified (see 6.2).

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T10:13Z
Check the source to verify that this is the current version before use.

* 5.1.1 Level A. Each roll of lace shall be completely wrapped with two thicknesses of anti-tarnish tissue paper (see 4.4.1). The ends of the tissue wrap shall be folded back to prevent unwrapping. Each wrapped roll shall be inserted into a snug-fitting clear polyethylene film bag of 0.002 inch (0.05mm) thickness (±20) percent tolerance. The polyethylene bag shall be formed with heat sealed seams. The final closure of the bag shall be heat sealed with the seal made as close as possible to the open end. Prior to, or during the heat sealing operation, excess air shall be expelled to the extent necessary to insure that the bagged rolls of gold lace will fit into the interior box. Each bagged roll shall then be placed in a snug-fitting, two piece full telescope style, folding or set-up type box. Any grade of boxboard strong enough to prevent crushing of the lace may be used for the interior box. Each box shall be secured with gummed paper tape, 1 inch minimum width.

5.1.2 Level C (Commercial packaging) Gold lace shall be packaged to afford adequate protection against physical damage during shipment from the supply source to the first receiving activity. The contractor may use his standard practice when it meets this requirement.

5.2 Packing. Packing shall be level A, B or C as specified (see 6.2).

* 5.2.1 Level A. Gold lace of one type, class, style, substyle and width packaged as specified in 5.1, shall be packed in a snug-fitting fiberboard shipping container conforming to type SF, class weather-resistant, grade V2s, style RSC of PPP-B-636. The maximum weight of box and contents shall not exceed 65 pounds. Exact dimensions of the container shall be determined by the contractor in order to insure that the contents fit snugly. Each shipping container shall be closed, waterproofed, and reinforced in accordance with methods III and IV as specified in the appendix of PPP-B-636.

5.2.2 Level B. Gold lace of one type, class, style, substyle, and width packaged as specified in 5.1; shall be packed in a snug-fitting fiberboard shipping container conforming to Type CF or SF class domestic, style RSC, (variety SW for type CF) grade 275 of PPP-B-636. Exact dimensions of the container shall be determined by the contractor in order to insure that the contents fit snugly. The maximum weight of the box and contents shall not exceed 65 pounds. Each shipping container shall be closed in accordance with method III as specified in the appendix of PPP-B-636.

5.2.2.1 Weather-resistant fiberboard container. When specified (see 6.2), the shipping container shall be grade V3c, V3s or V4s fiberboard box fabricated in accordance with PPP-B-636 and closed in accordance with the appendix of the box specification.

5.2.3 Level C (Commercial packing). Gold Lace; packaged as specified in 5.1, shall be packed in a manner to insure carrier acceptance and safe delivery at destination at the lowest transportation rate for such supplies. The quantity per shipping container shall be the same as that normally used by the contractor for retail distribution. Containers shall comply with the US Postal Service Manual, Uniform Freight Classification Rules or National Motor Freight Classification Rules, as applicable.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T10:13Z
Check the source to verify that this is the current version before use.

5.3 Marking. In addition to any special marking required by the contract or order, interior packages and shipping containers shall be marked in accordance with the requirements of MIL-STD-129.

6. NOTES

6.1 Intended use. The gold lace covered by this specification is intended to be used by authorized military personnel of the Department of Defense.

6.2 Ordering data. Procurement documents should specify the following:

a. Title, number, and date of this specification.
b. Type, class, style, and substyle (see 1.2).
c. Color pattern and shade designation when style B lace is specified (see 1.2 and 3.5.2).
d. Whether first article sample is required (see 3.3)
e. Widths required (see tables I, II, or III).
f. Length required (see 3.10).
g. Selection of the applicable levels of packaging and packing required (see 5.1 and 5.2).
h. When weather resistant grade fiberboard shipping containers are required for level B packing (see 5.2.2.1).

6.3 Samples. For access to samples, address the procuring office issuing the invitation for bids.

6.4 Army service colors. The authorized Army Branch of Service Colors (see 3.5) are as follows:

Adjutant General's Corps	Dark Blue (Cable No. 65012) and Scarlet (Cable No. 65006)
Armor	Yellow (Cable No. 65002)
Artillery	Scarlet (Cable No. 65006)
Chaplains	Black (Cable No. 65018)
Chemical Corps	Cobalt Blue (Cable No. 65011) and Golden Yellow (Cable No. 65001)
Corps of Engineers	Scarlet (Cable No. 65006) and White (Cable No. 65005)
Finance Corps	Silver Gray (Cable No. 65008) and Golden Yellow (Cable No. 65001)
Infantry	Light Blue (Cable No. 65014)
Inspector General	Dark Blue (Cable No. 65012) and Light Blue (Cable No. 65014)
Judge Advocate General's Corps	Dark Blue (Cable No. 65013) and White (Cable No. 65005)
Army Medical Service Corps	Maroon (Cable No. 65017) and White (Cable No.65005)
Military Intelligence Reserve	Golden Yellow (Cable No. 65001) and Purple (Cable No. 65009)
Military Police Corps	Green (Cable No. 65007) and Yellow (Cable No. 65002)

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T10:13Z
Check the source to verify that this is the current version before use.

National Guard Bureau	Dark Blue (Cable No. 65012)
Ordnance Corps	Crimson (Cable No. 65013) and Yellow (Cable No. 65002)
Permanent Professors of the United States Military Academy	Scarlet (Cable No. 65006) and Silver Gray (Cable No. 65008)
Quartermasters Corps	Buff (Cable No. 65015)
Signal Corps	Orange (Cable No. 65004) and White (Cable No. 65005)
Staff Specialists Reserve	Green (Cable No. 65007)
Transportation Corps	Brick Red (Cable No. 65020) and Golden Yellow (Cable No. 65001)
Unassigned to Branch	Teal Blue (Cable No. 65024) and White (Cable No. 65005)
Warrant Officers	Brown (Cable No. 65016)
Women's Army Corps	Mosstone Green (Cable No. 65022) and Old Gold (Cable No. 65021)

6.5 Changes from previous issue. The margins of this specification are marked with an asterisk to indicate where changes (additions, modifications, corrections, deletions) from the previous issue were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous issue.

Custodians:

Army - GL
Navy - SA
Air Force - 11

Review Activity:

Air Force - 99

User Activity:

Navy - CG

Preparing Activity:

Navy - SA

Project number:

8315-0235

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T10:13Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS: This form is provided to solicit beneficial comments which may improve this document and enhance its use. DoD contractors, government activities, manufacturers, vendors, or other prospective users of the document are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity. A response will be provided to the submitter, when name and address is provided, within 30 days indicating that the 1426 was received and when any appropriate action on it will be completed.
NOTE: This form shall not be used to submit requests for waivers, deviations or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

DOCUMENT IDENTIFIER *(Number)* AND TITLE
MIL-L-17507F LACE, ORNAMENTAL

NAME OF ORGANIZATION AND ADDRESS OF SUBMITTER

☐ VENDOR ☐ USER ☐ MANUFACTURER

1. ☐ HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE? ☐ IS ANY PART OF IT TOO RIGID, RESTRICTIVE, LOOSE OR AMBIGUOUS? PLEASE EXPLAIN BELOW.

A. GIVE PARAGRAPH NUMBER AND WORDING

B. RECOMMENDED WORDING CHANGE

C. REASON FOR RECOMMENDED CHANGE(S)

2. REMARKS

SUBMITTED BY *(Printed or typed name and address — Optional)*

TELEPHONE NO.

DATE

DD FORM 1426
1 OCT 76

Replaces edition of 1 Jan 72 which may be used.

S/N 0102-LF-001-4260

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T10:13Z
Check the source to verify that this is the current version before use.

FOLD

OFFICER IN CHARGE
NAVY CLOTHING & TEXTILE RESEARCH FACILITY
21 STRATHMORE ROAD
NATICK, MA 01760

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

POSTAGE AND FEES PAID
DEPARTMENT OF THE NAVY
DoD-316

U.S.MAIL

OFFICER IN CHARGE
NAVY CLOTHING & TEXTILE RESEARCH FACILITY
21 STRATHMORE ROAD
NATICK, MA 01760

FOLD

Source: https://assist.dla.mil -- Downloaded: 2026l0-18T10:13Z
Check the source to verify that this is the currentversion before use.